<Review>

(Accepted for publication : October 18, 2001)

Applications of Surface Analysis Techniques in Surface Characterization of Polymer Surfaces and Interfaces

Chi-Ming Chan^{*†}, Lu-Tao Weng^{**} and Lin Li^{***}

Abstract

The surface properties of polymers, copolymers, and polymer blends are very important to many industrial applications. Especially, the surface properties of copolymers and polymer blends can be very different from those of bulk. X-ray photoelectron spectroscopy (XPS) and time-of-flight secondary mass spectrometry (ToF-SIMS) have been the two of the key surface analysis techniques that are widely used to characterize these surfaces. This review provides a brief introduction to the principles of XPS and ToF-SIMS and their applications to study of the surfaces and interface of copolymers and polymer blends.

1. Introduction

The surface properties of polymers are important for many applications such as adhesion, biomaterials, protective coatings, friction and wear, composites, microelectronics devices, and thin-film technology. In general, special surface properties such as chemical composition, hydrophilicity, roughness, crystallinity, conductivity, lubricity, and cross-linking density are required for the success of these applications. The surface properties of polymers are in general different from their bulk. In particular,

the surface chemical and physical properties of polymer blends can be significantly different from those predicted by their bulk compositions. To determine the physical and chemical properties of surfaces and interfaces of copolymer and polymer blends, surface analysis techniques such as X-ray photoelectron spectroscopy (XPS), static secondary ion mass spectrometry (SSIMS), atomic force microscopy (AFM), scanning electron microscopy (SEM), attenuated internal

Dr. Chi-Ming CHAN

Profile : Dr. Chi-Ming CHAN is Professor in the Department of Chemical Engineering at the Hong Kong University of Science and Technology. Professor Chan graduated from the University of Minnesota with a B.S. in chemical engineering before going on to earn his MS and PhD in the same subject at the California Institute of Technology. His major research interest is in polymer composites and surface and interfacial properties of materials. In addition to over ninety papers published in leading journals, he has written a book on polymer entitled *Polymer Surface Modification* and he is a co-author of another book entitled *Low Energy Electron Diffraction: Theory and Experiment*. His research work is protected by 15 US patents and 4 European patents.

† To whom correspondence should be addressed.

* Department of Chemical Engineering

** Materials Characterization and Preparation Facility
The Hong Kong University of Science and Technology
Clear Water Bay Hong Kong

*** State Key Laboratory of Polymer Physics and Chemistry
Center for Molecular Science, Institute of Chemistry
Chinese Academy of Sciences
Beijing 100080 China

(日本接着学会第39回年次大会特別講演)

Table 1 Characteristics of XPS and SSIMS

	XPS	SSIMS
Information		
Elemental	From He	All
Isotope	No	All
Chemical state	Yes	Possible
Molecular information	Little	Yes (high)
Structural information	No	Yes
*Saturation/unsaturation	Yes (difficult)	Yes
*Branching	Yes (difficult)	Yes
*Conformation (tacticity)	No	Yes
*Sequence distribution		
Sampling depth*	2.0 nm at $\theta = 15^\circ$ 5.3 nm at $\theta = 45^\circ$ 7.5 nm at $\theta = 90^\circ$	<1.0 nm for molecular ions
Detection limit	0.1% to 1%	ppm - ppb
Imaging/microscopy		
-Spatial resolution	5-10 μm	0.2 μm
-Elemental imaging	Yes	Yes
-Molecular imaging	No	Yes
Quantification	Yes	Difficult
Database	Rich	Limited
Sample damage	No	No/Very small
Samples	All	All

*The attenuation length is assumed to be 2.5 nm.

reflection infrared spectroscopy (ATR-IR), and dynamic contact angle measurements are essential. In this article, we are going to focus on two of the most powerful surface analysis techniques - XPS and SSIMS - which have been used extensively to

characterize surface properties of copolymers and polymer blends. The main characteristics of XPS and SSIMS are summarized in Table 1.

2. X-ray photoelectron spectroscopy

X-ray photoelectron spectroscopy, which is also known as electron spectroscopy for chemical analysis (ESCA), is probably the most widely used technique in the surface characterization of polymers [1-6]. This technique that is based on the photoelectric effect was initially developed by Professor Kai Siegbahn at the University of Uppsala. A sample is irradiated by a beam of X-rays. The interaction between an X-ray photon and the core level electron of an atom causes a complete transfer of the photon energy to the electron. The electron then has

enough energy to escape from the surface of the sample. This electron is referred to as the photoelectron. The basic principle of XPS is schematically shown in Fig. 1. For an electrically conductive solid, the binding energy of the core level electron (E_b) can be calculated using the following equation:

$$E_b = h\nu - E_k - \phi \quad (1)$$

where $h\nu$ is the X-ray photon energy, E_k is the kinetic energy of the photoelectron and is the work function of the spectrometer which is about 4-5 eV. The photon energy is known from the X-ray source employed (1486.6 eV for Al K α and 1253.6 eV for Mg K α , the two most commonly used sources) and E_k can be measured by the XPS spectrometer. For insulating materials such as polymers, however, surface charging has to be considered and Eq. 1 should be rewritten as:

$$E_b = h\nu - E_k - \phi - C \quad (2)$$

where C is a charge constant which is unknown and varies from sample to sample. Therefore, for

Fig. 1 Schematic diagram showing the basic principle of XPS.

insulating materials, the electron binding energy is usually determined by using an internal reference peak. For example, the C 1s peak of aliphatic carbon at 285.0 eV [4] is often used as the internal reference for polymers.

Elements have unique electron binding energies. Therefore, knowing the electron binding energy allows the identification of various elements. XPS is thus able to detect all elements except hydrogen. Furthermore, the electron binding energy is also sensitive to the electronic environment of the atom. When an atom is bonded to another atom of an element having a different electronegativity, the electron binding energy may increase or decrease. This change in binding energy is called the chemical shift, which can be used to provide structural information of a molecule.

Although X-rays penetrate deeply into the sample, the photoelectrons can only escape from a region near the surface. The sampling depth is given by the following equation:

$$d = 3\lambda \sin \theta \quad (3)$$

where λ is the attenuation length of the photoelectron and θ (take-off angle) is the angle between the sample surface and the analyzer. By changing the take-off angle, the chemical information at various depths can be obtained. Angle-dependent analyses have been widely used to investigate surface segregation phenomena in polymer blends.

XPS is also a quantitative technique. The XPS peak intensities after normalization by the sensitivity factors can be used to calculate the surface chemical composition by using the following equation:

$$C_i = \frac{A_i/S_i}{\sum_i^m A_i/S_i} \quad (4)$$

where C_i is the concentration of an element i , m is the number of elements in the sample, A_i and S_i are the peak area and the sensitivity factor of the element i , respectively.

In the past decades, significant developments have been made in XPS instrumentation. These developments include focussed and monochromatic X-ray sources, high transmission electron spectrometers, large collection lens, high efficiency detectors and more reliable charge compensation systems. These

developments result in a considerable increase both in sensitivity and in energy resolution, allowing small-area XPS ($<100 \mu\text{m}$) or XPS imaging with spatial resolution $<10 \mu\text{m}$ to be performed routinely. For polymers, perhaps, the most significant achievement is the new charge compensation systems [7,8], that can very effectively control the surface potential of insulating samples and consequently enhance the energy resolution considerably. All these advances have been highlighted by some recent applications of XPS in obtaining valence band spectra of polymers. These spectra have been shown to be fairly sensitive to the molecular structure and consequently can be used to distinguish some polymers that are not distinguishable using XPS core level spectra [9, 10].

3. Static Secondary Ion Mass Spectrometry (SSIMS)

Static secondary ion mass spectrometry has been shown to be a valuable technique to provide molecular information of polymers [2, 6, 11-17]. It complements XPS because SSIMS can differentiate among polymers that have similar XPS spectra. SSIMS was first introduced by Benninghoven in 1969 [18] and was used by Gardella and Hercules [19] and Briggs [11] in the 80s to study polymer surfaces. The capabilities of the technique have been expanded significantly during the last decades thanks to the development of high performance time-of-flight mass spectrometers.

The basic principle of SIMS is described in Fig. 2. In a SIMS experiment, a sample is bombarded with a primary ion beam of kinetic energy of 1-25 keV. Upon bombardment, the kinetic energy and momentum of the impinging ions are transferred to the sample via a collision cascade process. When the transferred recoil energy is higher than the surface binding energy, secondary particles are emitted from the surface. A very small fraction ($<1\%$) of these particles consists of both positive and negative ions. The collection of these positive or negative ions by a mass spectrometer constitutes the basis of SIMS. In SSIMS analyses, the total ion density is kept below $10^{12} \text{ ions/cm}^2$ (static condition). In this case, only one per thousand of the surface atoms is directly

Fig. 2 The basic principle of SIMS.

bombarded by the primary ion (assuming a surface atom density of 10^{15} atoms/cm $^2 \approx 1$ monolayer). The surface damage is negligible and the emitted secondary ions would contain the molecular information of the polymer surface.

The sampling depth of SSIMS is smaller than that of XPS. Experimental results acquired during recent years on Langmuir-Blodgett layers or thin polymer films have shown that molecular ions are emitted from the outermost monolayer [20, 21]. Therefore, the sampling depth of SSIMS is normally considered to be less than 1 nm when molecular ions are analyzed. However, the sampling depth of the atomic ions may be greater due to their higher internal energies. Experimental results have indicated that atomic ions can escape from several monolayers deep.

SSIMS images can be obtained either in the microscope or microprobe mode. The microscope mode is only possible for ToF spectrometers equipped with the TRIFT^{TM} system that has stigmatic optics for imaging secondary ions [22]. In this mode, the surface area is irradiated by a focused ion beam and the images are directly recorded using a position-sensitive detector (e.g. resistive anode encoder). The spatial resolution of the microscope mode is typically a few mm. In the microprobe mode, a finely focused ion beam (e.g. 25 kV Ga⁺ with a spot size < 0.2 μ m) is rastered point by point over a given area and the secondary ions are synchronously detected. Usually, two modes of operation are used in the image acquisition. In the case where the secondary ions to be mapped are known prior to the imaging experiment,

only the intensities of these selected ions are acquired at each point (or pixel). In the other case, the full SIMS spectrum at each pixel is acquired and stored in a complete raw data stream from which the images can be created retrospectively. This is called the "retrospective analysis" and represents a major advantage of ToF-SIMS imaging analysis [23].

For polymer samples, sub-micron spatial resolution is now possible using microprobe imaging. For high ion yield materials, the spatial resolution of the microprobe mode is mainly determined by the primary beam size. However, for polymer samples, the ion yield and sample charge stabilization control are also important factors determining the spatial resolution. Using a Ga gun, the yield of the molecular ions is often too low to provide images at sub-micron resolution [6]. In this case, retrospective analysis can be applied because the yield of the molecular ions, although too low for imaging, is still high enough for spectral analysis. Indium (^{119}In) liquid metal ion gun is most likely a potential new gun for molecular imaging because the yield of molecular ions can be dramatically enhanced by using an ^{119}In gun compared to a Ga gun [24].

SSIMS analysis is, in essence, not quantitative. The difficulty in SSIMS quantitative analysis is due to the fact that the mechanisms of the formation and emission of the secondary ions are not well understood. In particular, the matrix effects, i.e. that secondary ion yields are strongly dependent on the matrix, are the main obstacle for quantitative analysis. However, the experimental results acquired during the recent years have shown that the situation has been improved for polymer materials. Indeed, it has been shown that for many copolymers or polymer blend systems [25-32], if the secondary fragments are correctly selected, matrix effects can be negligible. In this case, the intensity of a fragment of a copolymer or polymer blend is a linear addition of the intensities of the fragment from different components:

$$I_i = \sum k_{ji} x_j \quad (5)$$

where I_i is the intensity of the fragment i of a copolymer or polymer blend, k_{ji} is the sensitivity factor of fragment i of component j , and x_j is the

molar fraction of the component j . The sensitivity factor, which is independent of the copolymer or polymer blend composition, can be obtained from the intensity of the fragment i of the pure component j . In a binary system (a copolymer with repeat units A and B or a polymer blend with components A and B), if the fragments m and n are contributed only by A and B, respectively and the matrix effects are negligible, Eq. 5 then becomes:

$$\frac{I_m}{I_n} = \frac{k_{A,m}x_A}{k_{B,n}x_B} \quad (8)$$

Therefore, the intensity ratio I_m/I_n is proportional to the molar ratio x_A/x_B with a slope of $k_{A,m}/k_{B,n}$. This relation has been used to perform quantitative analyses for some copolymers and polymer blend systems [25, 27]. It has been shown that the validity of Eq. 6 depends strongly on the selection of appropriate fragments; however, no general guidelines are available.

4. Polymers with a well defined segment length

Surface properties of block copolymers are usually quite different from that of the bulk [33-54]. The difference in the surface free energy between the block components is a major reason that the blocks of lower surface free energy preferentially segregate to the surface. Other factors, such as the relative length of the blocks, their sequence length distribution and the concentration of the constituents may also play an important role in determining the surface composition of copolymers.

In one of our recent works, the effects of the sequence distribution of poly(acrylonitrile-butadiene) rubbers (NBRs), determined by ^{13}C -NMR, on the surface chemical composition, determined by XPS and dynamic contact angle (DCA) measurements, were studied [50]. The results of XPS and ^{13}C -NMR analyses suggest that surface segregation of the lower surface energy segment (BD) of the NBR copolymers occurs only when the BD segment length is at least equal to the length of the BBB segment and the BBB intensity is above a certain value. In order to investigate the effects of the sequence length on the surface composition of polymers, two series of

polyethers with a well-defined segment length were prepared, the relationship between the structure of the secondary ion fragments and the surface chemical structure was studied. The synthesis is described as in Scheme 1 [55]:

Scheme 1 The preparation of the BA and 6FBA polyethers.

Thin films of the BA and 6FBA polymers were prepared by solution spin casting on silicon wafers. The solvents used for the BA and 6FBA polymers were chloroform and tetrahydrofuran, respectively.

The influence of segmental length on the surface chemical composition

The number of the CH_2 groups, n_s , determined by the C-to-O atomic ratios of the BA and 6FBA polymers, as a function of n in bulk, is shown in Fig. 3. The value of n_s of the 6FBA polymers exhibits a linear relationship with the value of n for $n = 4$ to 18.

Fig. 3 n_s determined by XPS n of the BA-Cn and 6FBA-Cn polymers [56]

However, for the BA polymers n_s determined by XPS is much larger than n when $n > 14$. This suggests that the flexible segments segregate onto the surface of the BA polymers when the length of the flexible segment is long enough ($n > 14$, segment length $\sim 17 \text{ \AA}$). Repeated measurements yielded similar results. A comparison of the XPS results between the BA and 6FBA polymers indicates that the effects of the flexible segment length on the surface composition are different even for the sequential polymers with a very similar structure. The difference in the surface free energy between the rigid and flexible segments is the driving force for the segregation of the low surface component to the surface. Because the BA and 6FBA polymers have a different side group (CH_3 and CF_3), the surface energy difference between the rigid and flexible segments is not identical for these two polymers. The length of the flexible segment plays an important role in determining the surface composition of the polyethers. In the BA polymers, the flexible segment obviously has a lower surface energy than the rigid segment. When the length of the flexible segment increases, the mobility of the segment also increases. As a result, surface excess of the flexible segments occurs. But for the 6FBA polymers, the surface energy difference between the rigid and flexible segments may not be significant. Therefore, no significant surface excess of the flexible segments is observed even at $n = 18$.

The influence of the segmental length on the SIMS intensities

The influence of the flexible segment length on the normalized intensity, I_i^N , of the positive aliphatic hydrocarbon ions and the aromatic ions was investigated [57]. The normalized intensity of the characteristic fragments of the flexible aliphatic segments and rigid segments is defined by the following equation:

$$I_i^N = \frac{I_i/I_t}{I_t/I_t(n=4)} \quad (7)$$

where I_t is the total ion intensity, $I_t/I_t(n=4)$ is chosen as the reference and all normalized peak intensities of 6FBA polymers, $(I_i/I_t(n=4)) = 1$. For example, I_i^N of the 6FBA polymers vs. n is plotted in Fig. 4. A series of positive aliphatic ion fragments, such as C_4H_2^+ , C_4H_3^+ , C_4H_4^+ , C_4H_5^+ , C_4H_6^+ , C_4H_7^+ , C_4H_8^+ , and C_4H_9^+ , at $m/z = 50, 51, 52, 53, 54, 55, 56$, and 57 were used and the variation of I_i^N can be seen in Fig. 4a. When the flexible segment length increases, the intensity of the highly unsaturated aliphatic ion fragments, such as C_4H_2^+ and C_4H_3^+ at $m/z=50$ and 51 decreases. However, the intensity of the saturated aliphatic ion, C_4H_9^+ , at $m/z=57$ increases as the flexible segment length increases. This can be explained by the structure of the 6FBA polymers, as shown in Scheme 1. The highly unsaturated aliphatic ions are mainly emitted from the rigid segment and their intensity decreases as the number of the CH_2 group increases. The other unsaturated ions, such as C_4H_4^+ ,

Fig. 4 The influence of the flexible segment length on the intensity of the characteristic positive hydrocarbon ions n of the 6FBA polymers. (a) aliphatic secondary ions and (b) aromatic secondary ions [56]

$C_4H_5^+$, $C_4H_6^+$, $C_4H_7^+$ and $C_4H_8^+$, are emitted from both the rigid and flexible segments.

The variation of I_i^n of the aromatic ion fragments of the 6FBA polymers, such as $C_6H_5^+$, $C_7H_7^+$, $C_9H_7^+$ and $C_{13}H_9^+$ at $m/z=77$, 91, 115 and 165, is shown in Figure 4b. The aromatic ions such as $C_6H_5^+$ and $C_7H_7^+$ can also be emitted from the aliphatic flexible segments. Therefore, they cannot be used as the characteristic positive ions of the rigid segments. However, the larger aromatic fragments, such as $C_9H_7^+$ and $C_{13}H_9^+$, are mainly emitted from the rigid segments; therefore, it is possible to use the intensity of these ions to determine the surface composition of the 6FBA polymers.

In order to simplify the analysis of the ToF-SIMS results, the characteristic ion fragments of the BA and 6FBA polymers are summarized in three series. (1) Flexible fragments, F_i , are mainly emitted from the flexible segment, such as CH_2^+ , $C_2H_5^+$, $C_3H_7^+$, and $C_4H_9^+$, at $m/z=14$, 29, 43, and 57, respectively. (2) Rigid fragments, R_j , are mainly emitted from the rigid segment, such as $C_7H_{11}O^+$ and $C_{14}H_{13}O_2^+$ at $m/z=135$, and 213, respectively, for the BA polymers and $C_9F_6H_5O^+$, $C_{14}F_3H_{10}O_2^+$, $C_9F_5H_4O^+$ and $C_4F_3H_8O_2^+$ at $m/z=243$, 267, 223 and 265, respectively, for the 6FBA polymers. The chemical structures of these ion fragments were reported previously. (3) Molecular fragments, AB_n , are directly related to the structure of the repeat units of the BA and 6FBA polymers, such as $[M-H]^+$ at $m/z=281$, 309, 337, ... with $n=4, 6, 8, \dots$ of the BA polymers. If the matrix effects can be neglected, the ratios of the absolute intensities, $I(F_i)/I(R_j)$, of the flexible fragments to the rigid fragments are related to the number of the CH_2 groups at the surface, n_s , as shown in Eq. 8:

$$\begin{aligned} \frac{I(F_i)}{I(R_j)} &= \frac{S_i \cdot C(F)}{S_j \cdot C(R)} \propto K(ij) \cdot n_s \\ (8) \end{aligned}$$

where $I(F_i)$ and $I(R_j)$ are the absolute intensities of the flexible and rigid segments,

respectively. S_i and S_j are related to the sensitive factors of the ion fragments i and j , respectively. $C(R)$ and $C(F)$ are the molar concentrations of the flexible and rigid segments, respectively. K_{ij} is a parameter related to the yield of fragments i and j .

To verify Eq. 8, the SIMS results of the BA and 6FBA polymers were analyzed. The intensities of the positive saturated aliphatic ions, such as $C_2H_5^+$, $C_3H_7^+$ and $C_4H_9^+$ at $m/z=29$, 43, and 57, $I(F_{29})$, $I(F_{43})$, and $I(F_{57})$, were used for the flexible segments of the polymers. For the rigid segments of the BA polymers, the intensities of the characteristic positive ions of the BA polymers $C_7H_{11}O^+$ and $C_{14}H_{13}O_2^+$ at $m/z=135$ and 213, $I(R_{135})$ and $I(R_{213})$, were adopted, while for the 6FBA polymers the intensities of the characteristic positive ions of the 6FBA polymers $C_9F_6H_5O^+$ and $C_{14}F_3H_{10}O_2^+$ at $m/z=243$ and 267, $I(R_{243})$ and $I(R_{267})$, were adopted. As an example, the intensity ratios of the ions for the BA polymers, $I(F_{57})/I(R_{135})$ ($C_4H_9^+/C_7H_{11}O^+$) and $I(F_{57})/I(R_{213})$ ($C_4H_9^+/C_{14}H_{13}O_2^+$), are plotted vs n , as shown in Fig. 5. The intensity ratios, $I(F_{57})/I(R_{135})$ and $I(F_{57})/I(R_{213})$, increase monotonically with n , as shown in Fig. 5a. It is obvious that the ratios do not increase linearly with n . However, the intensity ratios, $I(F_{57})/I(R_{135})$ and $I(F_{57})/I(R_{213})$, increase fairly linearly with n_s as shown in Fig. 5b. The intensity ratios of 6FBA polymers, $I(F_{57})/I(R_{243})$ ($C_4H_9^+/C_9F_6H_5O^+$), and $I(F_{57})/I(R_{267})$ ($C_4H_9^+/C_{14}F_3H_{10}O_2^+$), increase linearly with n . The other intensity ratios, $I(F_{29})/I(R_j)$ and $I(F_{43})/I(R_j)$, show similar results. These results further reflect the fact that the ratios of the ionic intensities are directly related to the surface concentra-

Fig. 5 Intensity ratios of positive ions $I(F_{57})/I(R_{135})$ and $I(F_{57})/I(R_{213})$ for the BA polymers as function of (a) n and (b) n_s [56]

tion of the flexible segments and can be used for quantitatively analyzing the surface compositions of these polymers.

The distribution of end groups at the surface

The structure and the characteristic negative ions of the BA-C8 polymer are shown in scheme 2.

In the negative ToF-SIMS spectra of the BA-C8 polymer, the characteristic fragments of the end-

Scheme 2 Some characteristic negative ions of the BA-C8 polymer.

groups are $^{-79}\text{Br}^-$ at $m/z=79$ amu and $^{-81}\text{Br}^-$ at $m/z=81$ amu. The characteristic fragments of the rigid segment are O^- at $m/z=16$ amu; OH^- at $m/z=17$ amu; C_2H^- at $m/z=25$ amu; C_4H^- at $m/z=49$ amu; and the characteristic fragment for the flexible segment is CH_2^- at $m/z=14$ amu, as shown in scheme 2 and Fig. 6. There are no distinguishable differences in the high-mass-resolution spectra between the amorphous and semi-crystalline polymer films except for the intensities of the end-groups: $^{-79}\text{Br}^-$ and $^{-81}\text{Br}^-$. In order to semi-quantitatively analyze the difference in chemical composition between the semi-crystalline and amorphous films of the BA-C8 polymer, the normalized intensity ratios, I_n , of the semi-crystalline and amorphous BA-C8 samples are compared. I_n is defined as

$$I_n = \left(\frac{I_i^c}{I_t^c} \right) / \left(\frac{I_i^a}{I_t^a} \right) \quad (8)$$

where, I_i^c and I_t^c are, respectively, the intensity of the peak at $m/z=i$ amu and the total intensity of the mass range $m/z=2-500$ amu for the semi-crystalline BA-C8 films. I_i^a and I_t^a are the same as I_i^c and I_t^c but for the amorphous BA-C8 films. The values of I_n are very close to 1 for the positive secondary ions, as shown in Fig. 7a. For the negative ions, the values of I_n at $m/z=79$ and 80 amu ($^{-79}\text{Br}^-$ and $^{-81}\text{Br}^-$) increase by a factor greater than 15. However, the values of I_n for the other negative ions show almost no change, as shown in Fig. 7b. These results show the end-groups can segregate to the surface during crystallization.

The surface topography of the amorphous and semi-crystalline BA-C8 thin films are determined using atomic force microscopy (AFM), as

Fig. 6 ToF-SIMS spectra of the BA-C8 polymer: (a) negative spectrum of a BA-C8 amorphous film; (b) positive spectrum of a BA-C8 amorphous film; (c) negative spectrum of a BA-C8 semi-crystalline film; and, (d) positive spectrum of a BA-C8 semi-crystalline film [57].

Fig. 7 A comparison of surface compositions between the crystalline and amorphous BA-C8 polymer films: (a) ratios of the positive ToF-SIMS peaks and (b) ratios of the negative ToF-SIMS peaks [57].

shown in Fig. 8a-c. The chemical images of the BA-C8 films obtained by mapping the characteristic fragments of the end-groups, the $^{-79}\text{Br}^-$ and $^{-81}\text{Br}^-$ peaks at $m/z = 79$ and 81 amu, are shown in Fig. 8d-f. Initially, the polymer chains in a freshly prepared BA-C8 film exist as random coils. The sample surface is very smooth, as shown in Fig. 8a and the ToF-SIMS chemical image shows a homogeneous distribution of Br, as shown in Fig. 8d. After about 10 hours at 25°C a spherulite of $\sim 10 \mu\text{m}$ in diameter is observed in the AFM image (c.f., Fig. 8b). The relative height change of the BA-C8 film, which is due to the material constriction as a result of crystallization, is about 100 nm. A comparison between the AFM topographic image (c.f., Fig. 8b) and the ToF-SIMS chemical image (c.f., Fig. 8e) reveals the size of the spherulite to be similar to the sizes of the ToF-SIMS images showing higher Br concentrations. The surface of a BA-C8 polymer film which has been isothermally crystallized at room temperature for one week, shows a relative height change of the surface

of $\sim 200 \text{ nm}$, as shown in Fig. 8c. The areas at the edges of the spherulites and the eyes at the centers of the spherulites are higher than other areas. The ToF-SIMS chemical image, as shown in Fig. 8f, indicates the aggregation of the bromine end-groups at the boundaries and the eyes of the spherulites.

The aggregation and rearrangement of the bromine end-groups at the surface of the semi-crystalline BA-C8 polymer film can be caused by thermodynamic as well as kinetic factors. Crystallization induces the migration and rearrangement of the chain segments and end-groups on the surface of the BA-C8 polymer film. It is known that the free energy of a crystalline surface, γ_c , and the free energy of an amorphous surface, γ_a , are related by the following equation

$$\gamma_c = (\rho_c/\rho_a)^\beta \gamma_a \quad (10)$$

where ρ_c and ρ_a are the densities of the crystalline and the amorphous components, respectively. Usually, $\beta = 3.0 - 4.5$ and $\rho_c > \rho_a$, hence the free energy of a crystalline surface can be much higher than that of an amorphous surface. Crystallization increases the free energy of the surface and hence will promote the migration of the end-groups to the surface.

5. Polymer blend Processing

Segregation of one of the components of a blend or an additive in a homopolymer to the interface between the melt and the die-wall surface has also gained importance in polymer processing. Reduction in the apparent viscosity of poly(vinyl chloride) with an increase in the concentration of an additive was detected [58]. The reduction was attributed to a film of lubricant generated between the surface of a steel die and the polymer melt during extrusion. The lubricant layer was suspected to cause wall slip of the polymer. However, no direct measurement was made to determine the surface concentration of the additive. The migration of one of the components to the interface between the melt and the die wall during extrusion of an incompatible blend presents a very interesting rheological phenomenon [59-69]. Shih [59] studied the melt flows and the melt viscosities of an incompatible blend of an ethylene-propylene-1,4,-

Surface morphology of BA-C8 polymer film by AFM

End group, Br⁻, distributions on the surface by ToF-SIMS

Fig. 8 Surface morphology and end-group distributions of the BA-C8 polymer films: (a) and (d) freshly prepared films; (b) and (e) after isothermal crystallization at 25°C for approximately 10 hours; (c) and (f) after isothermal crystallization at 25°C for approximately one week [57].

hexadiene terpolymer and a copolymer of vinylidene fluoride and hexafluoropropylene. A marked reduction in the melt viscosity of either component was observed when a small amount of the other component was present. It was speculated that the die was coated with the minor component of the blend. The reduction of the viscosities was attributed to a slippage between the polymer and coated capillary. However, it is possible that the die wall was actually coated with the low-energy component, and the reduction of the viscosity was not related to the concentration of the components. In a study of the viscosity of blends of polyethylene (PE) and poly(bis(2,2,2-trifluoroethoxy) phosphazene) (PPH), it was found that the viscosity of the blend which contained 10% of PPH and 90% PE was much lower than that of pure PE [60]. The effect was much more pronounced

for the blend containing 30% PPH. Electron microscopic analysis on the surface of the extrudates showed a high concentration of PPH, which acts as a low-viscosity lubricant.

Chan et al. [61-63, 69] found that the viscosity reduction of polymer blends can involve either cohesive failure in the lubricant layer or adhesive failure at the interface between the lubricant layer and the extrudate. The polymer blend of interest typically consists of a low surface energy component (a fluoropolymer or fluoroelastomer present in a low concentration) and a thermoplastic. Viscosity reduction is generally observed when the viscosity of the low surface energy component is lower or similar to that of the thermoplastic. Figs. 9 and 10 illustrate the concept of cohesive failure and adhesive failure, respectively, during extrusion of a polymer blend.

Fig. 9 Cohesive failure in the lubricant layer which adheres to the die wall surface [62].

Fig. 10 Adhesive failure at the interface between the lubricant layer and extrudate and adhesive failure at the interface between the lubricant layer and the die wall surface [62].

These models assume that a lubricant layer, which comprises mainly the low surface energy component of the blend, is formed on the die wall surface due to the migration of the low surface energy component to the interface. Figure 9 shows that cohesive failure

occurs in the lubricant layer. Figure 10 shows that adhesive failure can occur at the interface between the extrudate and the lubricant layer or at the interface between the lubricant layer and the die wall.

In order to differentiate the different modes of failure as described in Figs. 9 and 10, we have to use an analytical technique, which can detect the lubricant layer on the extrudate surface providing that the lubricant (the lubricant is a minor component of a binary polymer blend) has a chemical composition different from the major component of the blend. But if the thickness of the lubricant layer on the extrudate is very small (i.e., 10 nm or less), then the correct mode of failure can be determined only by a surface sensitive technique such as XPS or SIMS because the sampling depths for SIMS and XPS are typically 0.5 and 3 nm, respectively [1]. Therefore, these techniques can be applied to differentiate different modes of failure as described in Figures 9 and 10, even if the lubricant layer is monolayer thick.

Chan et al. [61] have combined rheological and surface analyses to unravel the mechanism which governs the gradual reduction in the viscosity of incompatible blends of poly(ether ether ketone) and polytetrafluoroethylene (PTFE) during an extrusion. Figure 11 shows the apparent viscosity of the 5%-PTFE sample at various shear rates, normalized with respect to the viscosity of the control at the same rates. It is clear that the viscosity of the 5%-PTFE sample is lower than that of the control at the rates examined, and the rate of reduction of viscosity is higher at the higher shear rates. The apparent values at the end of these runs (about 30 minutes for the lower rates and 20 minutes for the 500 s⁻¹) are plotted in Figure 12 along with the flow curves for the control, pure PTFE, and the 5%-PTFE blend. From Figure 12, it appears that there is no critical rate at which the viscosity changes dramatically from the value of the control. At all rates, the viscosity of the 5%-PTFE sample is lower than that of the control, and progressively decreases with an increase in the shear rate. This points to a lubrication effect rather than a wall-slip effect on the viscosity. Similar to the steady-state value curve, the flow curve for the 5%-PTFE sample does not show any critical shear rate.

Fig. 11 The effect of apparent shear rate on apparent viscosity for the 5%-PTFE sample. Normalized viscosities were used (ϕ = the viscosity of the 5%-PTFE sample/the viscosity of the pure PEEK at the same shear rate). Each discontinuity corresponds to a filling of the reservoir [61].

Fig. 12 The apparent viscosity of pure PEEK, pure PTFE and 5%-PTFE sample as a function of apparent shear rate and the "steady-state" apparent viscosity for the 5%-PTFE sample at different shear rates obtained from Figure 11: ○, pure PEEK; ■, 5%-PTFE sample; ●, pure PTFE; ▲, the "steady-state" apparent viscosity for the 5%-PTFE sample at different shear rates [61].

In Table 2, a comparison of the amount of fluorine detected on the extrudate surface appears to confirm this argument. As the apparent shear rate increases from 50 to 500 s⁻¹ for the 5%-PTFE sample, the steady-state surface fluorine concentration also increases (from 37.9 atomic % at 50 s⁻¹ to 46.3 atomic % at 500 s⁻¹). If there is no accumulation of

PTFE at the surface, the amount of fluorine for the 5%-PTFE sample should equal its bulk value, or about 2.0 atomic %. The actual values measured for the extrudates indicate that substantial surface migration of PTFE has occurred for the 5%-PTFE sample.

If reduction in viscosity of samples is related to accumulation of PTFE at the die surface, then the surface of the extrudate should show a gradual increase in the PTFE concentration. The surface chemical compositions of the extrudates obtained from the first, second, and third runs of the 5%-PTFE sample at the apparent shear rate of 500 s⁻¹ were calculated, with results summarized in Table 2. If there is no migration of PTFE to the surface, the surface concentration of fluorine of the 1%-PTFE and 5%-PTFE samples should be approximately 0.4 and 2.0 atomic percent, respectively. The fluorine concentration of the surface of the 1%-PTFE extrudate from the first run was 18.5 atomic percent, which is substantially higher than that of the bulk. For the 5%-PTFE sample, the fluorine concentration of the extrudate surface increased from 19.2 to 49.4 atomic percent in going from the first to the second run. During the second and the third runs of the 5%-PTFE sample, the surface of extrudates was heavily populated with PTFE, resulting in a dramatic reduction in viscosity (in a pure PTFE surface, the carbon and fluorine concentrations are 33.3 and 66.7 atomic percent, respectively).

This definitely supports the postulate that reduction in viscosity of samples is related to accumulation of PTFE at the die surface.

As shown in Table 2, at the shear rate of 500 s⁻¹, the surface concentration of fluorine of the 5%-PTFE sample increases significantly from the first

Table 2 Surface chemical composition of extrudates determined by XPS [61].

Sample	run	Apparent shear rate s^{-1}	Surface chemical composition Atomic percent		
			C	O	F
1%-PTFE (bulk composition)			86.1	13.5	0.4
5%-PTFE (bulk composition)			84.9	13.1	2.0
pure PTFE			33.6		66.7
5%-PTFE (region A in Fig. 11)		50	55.6	6.5	37.9
5%-PTFE (region B in Fig. 11)		50	60.6	7.3	32.1
5%-PTFE (region C in Fig. 11)		100	49.1	15.2	35.7
1%-PTFE	first	500	71.4	10.1	18.5
	second	500	69.4	9.7	20.9
5%-PTFE	first	500	70.1	10.7	19.2
	second	500	46.9	3.7	49.4
	third	500	49.6	4.1	46.3
Control after the 5%-PTFE run	first	500	65.0	9.2	25.8
	second	500	81.1	12.9	6.0
	third	500	82.9	12.8	4.3

to the second filling of the barrel of the capillary rheometer and reaches more or less a steady-state value in the third filling. These results point to the fact that an increase in the PTFE concentration at the surface decreases the viscosity of the blend. However, the PTFE surface concentration for the extrudate obtained at $500 s^{-1}$ (at the end of the first filling) is lower than those obtained at 50 and $100 s^{-1}$ and yet the viscosity at $500 s^{-1}$ is the lowest (cf., Table 2). This apparent discrepancy can be resolved by examining the flow curve of pure PTFE as shown in Figure 12, which indicates that the apparent viscosity of pure PTFE is a strong function of the apparent shear rate. As a result, the apparent viscosity of the 5%-PTFE blend measured at $500 s^{-1}$ is lower than those measured at 50 and $100 s^{-1}$ even though the surface PTFE concentration of the extrudate obtained at $500 s^{-1}$ at the end of the first filling is lower than those of the extrudates obtained at 50 and $100 s^{-1}$.

To confirm the fact that the die wall was coated with PTFE, a control sample was run after a run with the 5%-PTFE sample. Figure 13 shows the viscosity of the control as a function of time. The viscosity of pure PEEK at the initial time was much lower than that of the pure sample obtained from a clean

Fig. 13 The apparent viscosity of control sample as a function of time. This experiment was performed after a run with a 5%-PTFE sample for 20 minutes at $500 s^{-1}$ [61].

die and was very similar to that of 5%-PTFE sample at the end of the third run. This observation agrees well with the postulate that the die wall is coated with PTFE and the lubricating effect of PTFE lowers the viscosity of the control sample. As the experiment progressed, the amount of PTFE at the die surface was depleted slowly; hence, the viscosity of the control sample increased gradually. Finally, when all PTFE was depleted from the die wall, the measured viscosity reached the same value as the viscosity of the control sample obtained from a clean die. The surface chemical compositions of extrudates at

Fig. 14 A plot of the normalized apparent viscosity of the 2.5% Dynamar /HHM 5502 blend as a function of time [62].

various regions were calculated and are summarized in Table 2. The surface concentration of fluorine, which is directly related to the PTFE concentration of the extrudate surface, gradually decreased as a function of time. The extrudate from the third run had a very small amount of fluorine, suggesting that the amount of PTFE at the die wall had been almost depleted. The surface chemical composition and viscosity data provide a very convincing argument for the PTFE-coated die-wall theory.

During extrusion of blends of high-density polyethylene (HHM 5502, Philips Petroleum Ltd.) and Dynamar FX-9613 (a copolymer of vinylidene fluoride and hexafluoropropylene obtained from Dyneon-A 3M-Hoechst company), the viscosity of the blends was found to be time-dependent and significantly lower than that of HHM 5502 [62,63]. The viscosity of the blends decreased with time and reached a steady-state value on a time scale depending on the shear rate. Fig. 14 shows the apparent viscosity of Dynamar FX-9613 and HHM 5502 as well as the steady-state apparent viscosity of three Dynamar /HHM 5502 blends at different shear rates and 200 °C. The steady-state apparent viscosity has to be used because the viscosity of the Dynamar/HHM 5502 blends changes at the onset of the experiments. The apparent viscosity of blends is lower than that of HHM 5502 and of Dynamar.

The results of the XPS analyses of extrudates of the 0.5 and 2.5% blends are shown in Tables 3 and 4, respectively. Positions A and B represent the

Table 3 Summary of the surface chemical composition of the extrudates of the 0.5% Dynamar/HHM 5502 blend and the pure Dynamar extrudate [62].

Run	Position#	Apparent shear rate (s ⁻¹)	Surface chemical composition (atomic %)			
			C	N	O	F
1	B	10	98.93	0.00	0.44	0.62
1	A	100	99.09	0.00	0.38	0.53
1	B	100	97.97	0.00	0.69	1.33
1	A	250	99.37	0.00	0.33	0.30
2	B	250	97.48	0.00	0.44	2.06
1	A	500	99.16	0.17	0.43	0.23
3	B	500	96.74	0.00	1.36	1.90
1	A	750	99.51	0.00	0.38	0.11
3	B	750	97.35	0.00	0.84	1.81
1	B	1500	98.70	0.00	0.25	1.06
Dynamar extrudate			38.8		0.4	60.8

#Positions A and B represent the samples obtained in the unsteady- and steady-state apparent viscosity regions, respectively.

Table 4 Summary of the surface chemical composition of the extrudates of the 2.5% Dynamar/HHM 5502 blend [62].

Run	Position#	Apparent shear rate (s ⁻¹)	Surface chemical composition (atomic %)			
			C	N	O	F
1	B	10	97.21	0.00	0.32	2.46
1	A	100	95.41	0.69	2.87	1.03
1	B	100	92.44	0.87	4.22	2.48
1	B	250	93.05	0.35	2.73	3.88
1	A	500	94.99	0.11	0.89	4.02
3	B	500	92.67	0.12	0.94	6.27
1	B	750	86.96	0.00	1.31	11.72
1	B	1500	96.51	0.00	0.22	3.27
Dynamar extrudate			38.8		0.4	60.8

#Positions A and B represent the samples obtained in the unsteady- and steady-state apparent viscosity regions, respectively.

samples obtained in the unsteady- and steady-state apparent viscosity regions, respectively. The fluorine concentrations on the extrudate surfaces are fairly low. These results also differ from those observed

for the PEEK/PTFE blends by Chan et al. [61] who found that a larger viscosity reduction produced a higher fluorine concentration on the extrudate surface. If we assume that the fluoroelastomer, being a low surface energy component of the blend, has a stronger tendency to migrate to the die wall surface, then, the low fluorine concentrations, especially observed for the extrudates of the 0.5% blends, suggest that adhesive failure did occur at the interface between the HDPE extrudate and that a layer of fluoroelastomer formed on the die wall surface.

Fig. 15 Normalized apparent viscosity of the control sample as a function of time. The experiment was performed without cleaning the die after the third run with the 0.5% (a) and 2.5% (b) Dynamar/HHM 5502 blends at a shear rate of 500 s⁻¹ [62].

To confirm that the reduction in viscosity is caused by a Dynamar lubricant layer formed on the die wall surface, neat HHM 5502 was run after the third run for the 0.5 and 2.5% blends without cleaning the die. Fig. 15 a and b show the normalized apparent viscosity for the blends and the neat HDPE as a function of time. The apparent viscosity of neat HHM 5502, obtained with the "unclean" die is only slightly higher than that of the blends and much lower than that of neat HHM 5502 obtained with a clean die. These results reveal that during the extrusion of the blend, Dynamar migrated from the melt to the interface and adhered to the die wall surface. The viscosity reduction was achieved by the HDPE slipping over the fluoroelastomer layer. When neat HHM 5502 was used, the Dynamar layer that had been formed during the extrusion of the blend still functioned as a lubricant layer which is responsible for observed viscosity reduction of the HDPE. In addition, the viscosity of the HDPE obtained with the "unclean" die is relatively constant even after 1200 seconds of shearing, indicating that the Dynamar layer is strongly adhered to the die wall surface and has relatively good cohesive strength.

The presence of the Dynamar layer on the die wall surface is further confirmed by XPS analyses (cf. Table 5) of the extrudates of the HDPE. There is a

Table 5 Summary of the surface chemical composition of the extrudates of pure HDPE HHM 5502 after the extrusion of the 0.5% and 2.5% Dynamar/HHM 5502 blends [62].

Run	Position#	Apparent shear rate (s ⁻¹)	Surface chemical composition (atomic %)			
			C	N	O	F
Control runs after the extrusion of the 0.5% blend						
1	A	500	97.59	0.00	0.34	2.08
2	B	500	99.06	0.00	0.18	0.77
Control runs after the extrusion of the 2.5% blend						
1	A	500	88.33	1.21	6.49	3.97
2	B	500	97.68	0.03	1.09	1.20
3	C	500	93.41	0.93	4.25	1.40

#Position A represents the samples obtained in the unsteady-state apparent viscosity region. Positions B and C (B and C obtained in the second and third runs, respectively) represent the samples obtained in the steady-state apparent viscosity regions.

Fig. 16 Schematic diagram showing a specially designed slit die block

small amount of fluorine on the surface of the HDPE extrudate even at the third run and the fluorine concentration decreases as the run time increases. In fact, the XPS results of the HDPE extrudates obtained with the "fluoroelastomer-coated" die are very similar to the XPS results of the extrudates of the blends. In both cases, the fluorine concentrations are very small suggesting adhesive failure at the interface between the HDPE melt and the fluoroelastomer layer formed on the die wall surface.

To confirm the above hypothesis, a specially made slit die block containing two pieces of insert was used (c.f., Fig. 16) [69]. The inserts which could be taken out from the slit die block at the end of the measurement were separated from the polymer block by acid etching. The polymer block contained the information about the lubricant layer formed between the extrudate and the die wall. The first polymer block sample was obtained from the slit inserts after a batch of blend containing 0.5 wt% Dynamar was run through the slit capillary at a shear rate of 250 s^{-1} . The inserts that were removed from the capillary block after the viscosity measurement were placed in dilute hydrochloric acid for

chemical etching. Afterwards, the remnant polymer block was detached from the inner surfaces of the metal inserts. A careful inspection of the polymer block revealed that the two major fractured surfaces of the polymer block were not the same: one side was smooth while another was rough. In addition, it was found that the metal surface in contact with the rough side of the polymer block was covered with a very thin transparent layer. XPS was then performed on the inner fractured surfaces of both metal inserts as well as the smooth fractured surface of the polymer block. Since our aim was to verify the presence of a Dynamar layer at the interface between the extrudate and the metal insert, we also needed the composition of pure Dynamar for reference. Their elemental compositions are shown in Table 6, from which we can deduce that Dynamar contains a fluoropolymer and some silicon dioxide and magnesium oxide as fillers.

On the smooth fractured surface of the polymer block, a high concentration of silicon and oxygen was detected. From the ratio of silicon to oxygen concentrations (2:1), silicon dioxide was thus present there. The metal surface in contact with that polymer surface consisted mainly of iron, carbon and oxygen, which are typical constituents for stainless steel, and only a small amount of SiO_2 . From these results, we can conclude that when the polymer block was detached from the insert, for this pair of fractured surfaces, the locus of failure occurred in the immediate vicinity of the metal surface. It implies that immediately adjacent to the metal surface there is a layer mainly consisting of SiO_2 .

On the other hand, for the metal surface fractured from the rough polymer surface, a high concentra-

Table 6 Chemical composition of Dynamar and surface chemical compositions of fractured surfaces as determined by XPS.

Element (atomic %)	Pure Dynamar	Polymer Surface (smooth)	Metal Surface contacting the "smooth" surface	Metal Surface contacting the "rough" surface
F	22.5	1.4	0.0	35.1
O	32.2	60.2	54.7	9.3
C	26.5	8.9	14.2	47.9
Si	16.0	29.5	4.6	3.1
Others	2.8 (Mg)	0.0	26.5 (Fe)	4.6 (Fe)

tion of fluorine and only a low concentration of silicon were detected. Such seemingly inconsistent XPS results for the two fractured sides can be resolved by viewing that the loci of failure in these two cases are different, but both represent a different portion of the inferred interfacial lubricant layer. The locus of failure for this pair of rough fractured surfaces, accordingly, should be located in a fluoropolymer-rich region at some distance away from the metal surface. It is interesting to note that a superposition of the XPS spectrum of smooth fractured polymer surface (with a high concentration of Si and O) and that of the rough fractured metal surface (with a high concentration of F and C) almost reproduces the spectrum of pure Dynamar, as shown in Fig. 17. Therefore, an overall migration of Dynamar towards the metal surface took place during the extrusion. From the XPS results, a schematic diagram depicting the chemical profile of the lubricant layer, is shown in Fig. 18. The positions of two loci of failure for this sample are also shown.

Fig. 17 A comparison of the XPS spectra of (a) the "smooth" fractured surface of the polymer block (b) the "rough" fractured surface of the metal (c) pure Dynamar [69].

Fig. 18. Schematic diagram showing the chemical structure of the lubricant layer [69].

It must be stressed that the phenomenon of asymmetric failure for this polymer block was an isolated and incidental case. In other etched samples, we had, almost without exception, obtained smooth and symmetrical fractured surfaces at the silicon dioxide layer/metal interface. Yet this very incidence has left us with an enriched picture of the lubricant structure. As shown in Fig. 18, a layer containing a high concentration of silicon dioxide is found in the region in contact with the metal surface of the inserts. Between the extrudate and the silicon dioxide layer there is a fluoropolymer layer - the layer responsible for the viscosity reduction phenomenon. Thus now it is confirmed that a Dynamar layer is formed at the polymer melt/metal interface during extrusion of the HDPE/Dynamar blends.

A full characterization of the lubricant layer included not only the analyses of the chemical composition and profile, but also the measurement of its thickness. Hence the next step was to perform a SSIMS analysis on the cross-sections of the polymer block samples. These samples with flat surfaces were prepared by cryo-microtome with 45°-edged sharp glass knives at a set temperature of -100°C. This was to guarantee that the fluoropolymer-dominated lubricant layer was sectioned at a temperature below its glass transition temperature, for a brittle fracture of the lubricant layer to take place, thus avoiding its deformation under the shear of sectioning.

An overall SSIMS micrograph as well as

Fig. 19 SSIMS micrographs of the cross-section of the polymer block obtained after the extrusion of 5.0 wt% Dynamar blend at shear rate of 250 s^{-1} [69]

individual SSIMS micrographs of the cross-section of the polymer block obtained after the extrusion of 5.0 wt% Dynamar blend at 250 s^{-1} , are shown in Fig. 19. The CH^- , O^- and F^- micrographs reveal the spatial distributions of HDPE, silicon dioxide and fluoropolymer on the surface of the sample. It is easy to observe that while both the O^- and F^- species concentrate in the region at the edge of the block, there is comparatively low concentration of CH^- there. This again directly points to the presence of a lubricant layer. From these micrographs, however, we cannot observe obvious dividing border between an SiO_2 -rich sub-layer and an fluoropolymer-rich sub-layer, as displayed in Fig. 18.

To explain that, the schematic diagram, as shown in Fig. 18, can be understood in the following way. Throughout the whole lubricant layer, silicon dioxide is generally present. However, there is also a large region within the lubricant layer that contains the fluoropolymer. This region, located at some distance away from the metal surface, is referred to as the fluoropolymer-rich layer as shown in Fig. 18. This layer is basically a mixture of silicon dioxide and fluoropolymer, as shown by the overlapping of

the regions of high concentrations of O and F at the edge of the polymer block, as shown in Fig. 19. Under closer inspection, however, it is observed that the region of high concentration of silicon dioxide is a bit wider than that of the fluoropolymer. The non-overlapped region, in which fluoropolymer is almost absent, is the silicon-dioxide-rich layer immediately in contact with the metal surface. This region is very thin. In other words, while the thicker fluoropolymer-rich layer contains significant amounts both of silicon dioxide and fluoropolymer, the thin silicon-dioxide-rich layer is almost pure silicon dioxide. To determine the thickness of the lubricant layer, a fluorine line scan, as shown in Fig. 20, showing the concentration of fluorine across the cross-section of the poly-

mer block mentioned above was obtained using the F^- micrograph shown in Fig. 19. This scan clearly reveals a region of high fluorine concentration and the width of this region is assigned to as the thickness

Fig. 20 A fluorine linescan across the lubricant layer in the F^- micrograph shown in Fig. 19 [69]

of the lubricant layer. It was estimated to be about 10 μm .

We can conclude that the viscosity reduction in these blends is caused by adhesive failure between the HDPE extrudate and the fluoropolymer layer which forms on the die wall surface during extrusion.

The above examples show that XPS and SSIMS can be a very powerful tool to provide information, which will advance our understanding of fundamental mechanisms in polymer processing.

Conclusions

We have described some applications of XPS and SSIMS in the surface characterization of polymer blends and copolymers. With further improvement in the spatial resolution of XPS and better grasp of the fundamentals of the SIMS process, these two important techniques will contribute significantly to the understanding of the surfaces and interfaces of polymer blends and copolymers in the years to come.

Acknowledgment

This work was supported by the Hong Kong Government Research Grants Council under Grant No. HKUST 9123/97P.

References

- Chan, C. M. *Polymer Surface Modification and Characterization*, Hanser, New York, (1994), Ch. 3.
- Garbassi, F., Morra, M., and Occhiello, E. *Polymer Surfaces From Physics to Technology*, New York, John Wiley & sons, (1998), Ch. 3.
- Andrade, J. D. in *Surface and Interfacial Aspects of Biomedical Polymers*, J. D. Andrade (Ed.), New York, Plenum Press, (1985), Ch. 5.
- Beamson, G. and Briggs, D. *High Resolution XPS of Organic Polymers. The Science ESCA300 Database*, New York, John Wiley & Sons, (1992).
- Briggs, D. in *Practical Surface Analysis, Vol. 1, Auger and X-ray Photoelectron Spectroscopy*, D. Briggs and M. P. Seah (Eds.), New York, John Wiley, (1990).
- Briggs, D. *Surface analysis of polymers by XPS and static SIMS*, Cambridge University Press, (1998).
- Larson, P. E. and Kelly, M. A. *J. Vac. Sci. Technol. A* **16**, 3463 (1998).
- Metsn, J. B. *Surface Interface Anal.* **27**, 1069 (1999).
- Galuska, A. and Halverson, B. *Surf. Interface Anal.* **26**, 425 (1998).
- Thomas, E. A. and Fulghum, J. E. *J. Vac. Sci. Technol. A* **16**, 1106 (1998).
- Briggs, D. in *Practical Surface Analysis, Vol. 2 Ion and Neutral Spectroscopy*, Briggs, D. and Seah, M. P. (Eds.), New York, John Wiley, (1990).
- Chan, C. M. *Polymer Surface Modification and Characterization*, Hanser, New York, (1994), Ch. 4.
- Vickerman, J. C., Brown, A. and Reed, N. M. *Secondary Ion Mass Spectrometry, Principle and Applications*, Internat. Ser. Monographs on Chemistry, No. 17, Oxford, Oxford Science Publ. (1989).
- Czanderna, A. W. and Hercules, D. H. (Eds.), *Ion Spectroscopy for Surface Analysis*, New York, Plenum Press, (1991).
- Vickerman, J. C. *Secondary ion mass spectrometry - the surface mass spectrometry, in Surface Analysis, The Principle Techniques*, J. C. Vickerman, Ed. New York, John Wiley & Sons, (1997), Ch. 5.
- Benninghoven, A., Rudenauer, F. G. and Werner, H. W. *Secondary Ion Mass spectrometry, Basic Concepts Instrumental Aspects Applications and Trends*, New York, John Wiley & Sons, (1987).
- Bertrand, P. and Weng, L. T. in *Surface characterization: A User's Sourcebook*, Brune, D., Hellborg, R., Whitlow, H. J., and Hunderi, O., (Eds.), Wiley-VCH (1997) p. 334.
- Benninghoven, A. *Phys. Status Solidi* **K169**, 34 (1969).
- Gardella, Jr., J. A. and Hercules, D. M. *Anal. Chem.* **52**, 226 (1980).
- Leggett, G. in *The Static SIMS library*, Vickerman, J. C., Briggs, D. and Henderson, A., (Eds.), Surface Spectra, Manchester, (1996).
- (a) Benninghoven, A. *Angew. Chem. Int. Ed. Engl.* **33**, 1023 (1994).
(b) Decorte, A., Bertrand, P., Arys, X., Jonas, A., Wischerhoff, E., Mayer, B. and Laschewsky, A. *Surf. Sci.* **366**, 149 (1996).
- Schueler, B. W. *Microsc. Microanal. Microstruct.* **3**, 119 (1992).
- Reichlmaier, S., Bryan, S. R., and Briggs, D. *J. Vac. Sci. Technol. A* **13**, 1217 (1995).
- Bryan, S. R., Reich, F., Schueler, B. W., and March, G., in *Secondary Ion Mass Spectrometry SIMS X*, Benninghoven, A., Hagenhoff, B., and Werner, H. W., (Eds.), John Wiley & Sons, Chichester (1997), p. 939.
- Lub, J., van Vroonhoven, F. C. B. M., van Leyen D. and Benninghoven, A. *J. Polym. Sci., Part B* **27**, 2071 (1989).
- Briggs, D. and Ratner, B. D. *Polym. Commun.* **29**, 6 (1988).
- Bhatia, Q. S. and Burrell, M. C. *Surf. Interface Anal.* **15**, 388 (1990).
- Thompson, P. M. *Anal. Chem.* **63**, 2447 (1991).
- Weng, L. T., Bertrand, P., Lauer, W., Zimmer, R. and Buseti, S. *Surf. Interface Anal.* **23**, 879 (1995).
- Lhoest, J. -B., Bertrand, P., Weng, L. T. and Dewez, J. -L. *Macromolecules* **28**, 4631 (1995).
- Briggs, D. and Davies, M. C. *Surf. Interface Anal.* **25**, 725 (1997).
- Vanden Eynde, X. and Bertrand, P. *Surf. Interface Anal.* **27**, 157 (1999).
- Burell, M. C.; Bhatia, Q. S.; Chera, J. J., and Michael, R. S., *J. Vac. Sci. Technol. A* **8**, 2300 (1990).
- Green, P. E., Christensen, T. M. and Russell, T. R., *Macromolecules*, **24**, 252 (1991).
- Grobe III, G. L., Gardella, Jr., J. A., Hopson, W. L., McKenna, W. P., and Eyring, E. M., *J. Biomed. Meter. Res.* **21**, 211 (1987).
- Patel, N. M., Dwight, D. W., Hedrick, J. L., Webster, D. C., and McGrath, J. E. *Macromolecules*, **21**, 2689

- (1988).
- 37) Inoue, H., Matsumoto, A., Matsukawa, K., Ueda, A., and Nagai, S. *J. Appl. Polym. Sci.* **41**, 1815 (1990).
- 38) Yoon, S. C. and Ratner, B. D. *Macromolecules* **21**, 2392 (1988).
- 39) Gervais, M., Douy, A., Gallot, B., and Erre, R. *Polymer* **29**, 1779 (1998).
- 40) Bhatia, S. Q. and Burrell, M. C. *Polymer* **32**, 1948 (1991).
- 41) Kassis, C. M., Steehler, J. K., Betts, D. E., Guan, Z., Romack, T. J., DeSimone, J. M., and Linton, R. W. *Macromolecules* **29**, 3247 (1996).
- 42) Zhao, J., Rojstaczer, S. R., and Gardella, Jr., J. A. *J. Vac. Sci. Technol. A* **16**, 3046 (1998).
- 43) Galuska, A. A. *Surf. and Interface Anal.* **21**, 703 (1994).
- 44) Chen, X. and Gardella, Jr., J. A. *Macromolecules* **27**, 3363 (1994).
- 45) Chen, X., Lee, H. F., and Gardella, Jr., J. A. *Macromolecules* **26**, 4601 (1993).
- 46) Chen, X., Gardella, Jr., J. A., Ho, T., and Wynne, K. J. *Macromolecules* **28**, 1635 (1995).
- 47) Hearn, M. J., Ratner, B. D., and Briggs, D. *Macromolecules* **21**, 2950 (1988).
- 48) Hearn, M. J., Briggs, D., Yoon, S. C., and Ratner, B. D. *Surf. Interface Anal.* **10**, 384 (1987).
- 49) Kulmer, P. L., Matteson, H. L., and Gardella, Jr., J. A. *Langmuir* **7**, 2479 (1991).
- 50) Li, L., Chan, C.-M. and Weng, L. T. *Macromolecules* **30**, 3698 (1997).
- 51) Dhamodharan, R., Iyengar, R., Perutz, S., Dai, C.-A., Ober, C. K., Krammer, E. J. *Macromolecules* **29**, 1229 (1996).
- 52) Mazzanti, J. B., Reamey, R. H., Helfan, M. A., and Lindley, P. M. *J. Vac. Sci. Technol. A* **10**, 2419 (1992).
- 53) Lianous, L., Quet, C., and Duc, T. M. *Surface Interface Anal.* **21**, 14 (1994).
- 54) Green, F. P., Christensen, T. M., Russell, T. P., and Jerome, R. *J. Chem. Phys.* **92**, 1478 (1990).
- 55) Li, L., Chan, C.-M., Ng, K.-M. and Weng, L. T., *Polymer* **42**, 6841 (2001).
- 56) Li, L., Chan, C.-M., Ng, K.-M. and Weng, L. T., "Macromolecules" **33**, 8002 (2000).
- 57) Li, L., Ng, K.-M., Chan, C.-M., Feng, J., Zeng X.-M. and Weng, L. T., *Macromolecules* **33**, 5588 (2000).
- 58) Chauffoureaux, J. C., Dehennau, C., and van Rijkevorsel, J. *J. Rheol.* **23**, 1 (1979).
- 59) Shih, C. K. *Polym. Eng. Sci.* **16**, 742 (1976).
- 60) Antipov, E. M., Borisenkova, E. K., Kulichikhin, V. G., Plate, N. A., and Topchiev, A. V. *Makromol. Chem., Macromol. Symp.* **38**, 275 (1990).
- 61) Chan, C.-M., Nixon, A., and Venkatraman, S. *J. Rheol.* **36**, 807 (1992).
- 62) Chan, C.-M. and Feng, J. *J. Rheol.* **41**, 319 (1997).
- 63) Chan, C.-M. and Zhu, S.-H. *Polymers for Advanced Technologies* **8**, 257 (1997).
- 64) Tremblay, B. *J. Rheol.* **35**, 985 (1991).
- 65) Stewart, C. W. and J. M. Dealy, J. M. *J. Rheol.* **36**, 967 (1992).
- 66) Nam, S. *Intern. Polym. Processing* **1**, 98 (1987).
- 67) Hatzikiriakos, S. G. and J. M. Dealy, J. M. *J. Rheol.* **36**, 703 (1992).
- 68) Hatzikiriakos, S. G., Stewart, C. W. and Dealy, J. M. *Intern. Polym. Processing* **8**, 30 (1993).
- 69) Lo, H. H. K., Chan, C.-M., and Zhu, S. H. *Polym. Eng. Sci.* **39**, 721 (1999).