<Review>

(Accepted for publication : August 7, 2004)

Aspects of Theories of Adhesion for the 21st Century

K. W. Allen*

1. Introduction

The early part of the 1960s was evidently a period of emergence of ideas about adhesion and their evolution into a scientific discipline. At this time the number of publications was very small and they were spread over a variety of journals primarily concerned with polymer, organic or physical chemistry, with surface science, or with some other science. In the English language there were the first edition (1951) of de Bruyne's book¹⁾, the proceedings of two conferences held in 1952, one in London and the other in Cleveland Ohio, USA, and the papers from the meetings of the British Ministry of Supply Panel (1961) edited by Eley²⁾. There was no journal suitable for the publication of serious scientific work on the whole range of adhesion science. Within a short time there had emerged the Adhesion Society of Japan together with its journal; the Annual Conference was held initially at City University London and more recently at Oxford Brookes University, with the publication of its proceedings, and then by 1969 the American Journal of Adhesion.

Now, forty years later, adhesion science has matured and become recognised as respectable discipline in its own right, although it spans a number of sciences and technologies. It is an appropriate point in time at which to review just how far our understanding of the fundamental theories of adhesion has advanced, and how it may be expected to advance. Nowhere could be more appropriate than in this present journal, the most senior one dedicated to the

study of adhesion in all its aspects.

At the beginning of the period several "theories of adhesion" were being expounded. The instinctive concept of mechanical interlocking was always advanced as the obvious explanation, in spite of the fact that it was difficult to cite convincing examples which could demonstrate it.

The concept of inter-diffusion of polymer chain segments had been developed mainly by two Russian workers, Voyutskii and Vasenin. However this was only applicable to pairs of elastomers above their T_g s. It could not be extended satisfactorily to more general examples.

Another group of Russian workers, led by Deryagin, had investigated the part played by conventional electrostatic forces.

K. W. Allen

略歴 : Professor Allen presented the initial paper in 1963 at the first of the series of conferences, which is still running. He continued with responsibility for the organisation of this conference and the initiation and continuing of a programme of research for a taught MSc

degree course which ran for some years. In 1994 he was awarded the degree of Doctor of Science at City University London. Eventually, after thirty years, for factors outside the control of the University, all this work in London had to be discontinued. In 1990 he was appointed as a Senior Visiting Research Fellow at Oxford Brookes University and in 1998 was promoted to a Visiting Professor. He has been honoured by the award of the Ellinger Gardonyi and the Wake memorial medals and by the award of an Honorary Fellowship of the University by Oxford Brookes University. Professor Allen continues to be actively involved with all the scientific activities of the Joining Technology Research Centre at Oxford Brookes University.

* Joining Technology Research Centre
Oxford Brookes University
Oxford OX3 0BP
UK

Considerable time and effort were expended in trying to develop a single unified explanation and theory which would account for the whole range of adhesive phenomena—from Formula 1 Racing cars to reinforcement of road bridges and from artificial finger nails to beer bottle labels!

Now, forty years on, no one seeks a panacea or cure-all. There has to be a range of explanations to account for all the various situation. Moreover, not infrequently contributions from several mechanisms are involved—a situation which the present author advanced in 1969³⁾ although it is only recently that it has achieved acceptance.

In fact six distinct theories or mechanisms can be recognised and are involved, to a greater or less extent, in understanding the observed phenomena.

These can be conveniently described as:

1. mechanical interlocking
2. adsorption
3. chemical
4. electrostatic
5. diffusion
6. pressure sensitive

Each of these needs to be considered separately, although there is some degree of inter-relationship

2. Mechanical interlocking

Mechanical interlocking of an adhesive with the adherend surface is the intuitive explanation by the layman of many common examples of adhesion. It is common practice to roughen a wood surface with glass-paper so that the glue may, penetrate into the surface layers of the wood and provide a bond by a (crude) interlocking. A naive belief in this explanation persists even in the face of clear evidence that there is a negative correlation between surface rough-

Treatment of wood surface	Shear strength of joint
Planed	21.5
Sanded	16.3
Sawn	18.5
Combed	16.5
All given in MPa	

↑
Increase in roughness
↓

ness and bond strength in many examples and this in spite of an increase in total surface area, which should lead to stronger, bonding. (Table 1) However there are a number of examples where it has been demonstrated that inter-penetration on this sort of scale is important. The classical work of Borroff and Wake⁴⁾ on the adhesion of rubber to textiles demonstrated that the dominant influence in determining the bond strength achieved was embedding of the protruding fibre ends in the rubber. Somewhat similarly Haines⁵⁾ unequivocally demonstrated that the governing factor in adhesion to leather was the extent of embedding of the fibres of the corium into the adhesives, and that penetration of adhesive into the leather is not sufficient to provide a strong durable bond. A final example of this sort of interlocking is the traditional dental filling of restorations which involves drilling a cavity with an "ink-well" configuration, with an opening narrower than the main part of the cavity. (Fig. 1) This is then packed with a metal amalgam which expands on setting to form a strong mechanical bond between filling and tooth.

These involve a structure in which separation requires a mechanical force great enough to break one of the components, or perhaps that admixture of two components which constitutes the bonding layer. All the irregularities and crevices were of a relatively large (micrometer) size and clearly visible

Fig. 1 Configuration of cavities:
a. "Flower Pot"
b. "Ink Well"

Fig. 2 Polyethylene separated from anodised aluminium showing clumps of fibres.

with an optical microscope.

Just as one was ready to dismiss interlocking as, generally, of only slight significance, advances in our knowledge of surface structures led to its revival, albeit on a smaller scale. The first indication of this was, probably due to Packham⁶⁾ who was investigating the hot-melt adhesion of polyethylene to various metal or metal oxide surfaces. Some of his highest magnification photomicrographs of polymer films, which had been revealed by dissolving away the metal/oxide layer, showed clumps of hydrocarbon fibres. These clumps and their component fibers were on a scale in angstroms (10^{-10} m) rather than micrometres (10^{-6} m). He attributed these to penetration of the polymer into pores in the oxide film. (Fig. 2) Further advances in this area depended upon the development of extended resolution scanning electron microscopy which had higher resolution than previous techniques. Using this, Venables and his co-workers⁷⁾ revealed that the apparently smooth oxide films, particularly aluminium, had both pores and protruding whiskers on an angstrom scale. An adhesive both penetrates into these pores and enclosed the whiskers to give an interphase which was both strong and durable. Extension of this⁸⁾ has demonstrated that good adhesive bonds to a metal surface requires a surface which was irregular in structure, with both crevices and protruding features, all of which must themselves be strong and strongly attached to their underlying surfaces. Thus the

concept of mechanical interlocking has received fresh support and significance once this much smaller scale was recognised.

3. Adsorption

The secondary inter-molecular forces, sometimes called "van der Waals" forces, which are responsible for the physical adsorption of gases and vapours on solid substrates, provide a source of adhesive strength. These involve attractions between molecules with dipoles of various types but they fall into three groups:⁹⁾

- i dipole/dipole interactions – Keesom forces
This first group arise from the interaction and attraction of pairs of molecules which both have permanent dipoles.
- ii dipole/induced dipole interactions – Debye forces
The second group arise when a molecule with a permanent dipole approaches a molecule with no dipole and induces a temporary dipole in the neutral molecule and then an attraction arises
- iii molecule/molecule interactions – London Dispersion forces

The third group are universal, causing attraction between every pair of non-polar particles which approach each other sufficiently closely, irrespective of any recognisable dipoles. They arise from the instantaneous quantum mechanical asymmetry of the electron clouds and hence transitory dipoles which interact..

Fig. 3 Relationship between potential energy and inter-nuclear separation showing forces of attraction and repulsion and their resultant..

The potential energy of each of these has a similar pattern:

$$E = k/r^6$$

where E is the potential energy of a pair of molecules

k is term involving both universal constants and parameters characteristic of the particular pair of molecules

r is the distance of separation of the molecules

Thus the potential energy, and hence the attractive force, decreases very sharply as the distance of separation of the molecules increases – doubling the separation reduces the energy of interaction to a sixty-fourth, as illustrated in Fig. 3

The London dispersion forces are of ubiquitous significance and have some effect in every example of adhesion, irrespective of whatever other forces may also be involved. The relative values of some examples can be seen in Table 2

Although these forces are small, it can be shown that they are sufficient to account for attractions far greater than any observed strengths as is shown in some classical results in Table 3. The causes of this weakness have to be sought in other directions.

However it is important to recognise that, like

Table 2 Distribution over the three types of van der Waals interaction energies in various simple compounds

	Dipole (Debye units)	Keesom dipole/ dipole	Debye dipole/ induced dipole	London dispersion	Total
A	0.0	0.000	0.000	9.63	9.63
HI	0.38	0.025	0.113	25.87	26.17
HBr	0.78	0.687	0.502	21.94	23.13
HCl	1.03	3.08	1.005	16.83	20.92
NH ₃	1.50	13.31	1.55	14.74	29.60
H ₂ O	1.84	36.38	1.93	8.96	47.27

All energies are given in kJ mol⁻¹

Table 3 Tensile strength of materials calculated from fundamental data and compared with experimental results. (after de Boer)

	Primary bonds alone	Secondary van der Waals forces alone	Experimental
Sodium Chloride	400	> 20	0.6
P/F resin	4300	> 39	7.8

All given in MPa

gases physisorbed onto a solid, they can relatively easily be disrupted. In particular adhesives generally are very susceptible to displacement by water.

Since this concept depends upon classical physical chemistry which was developed to a high level in the first half of the twentieth century, there has been less obvious development during the last forty years. Nevertheless there has been consolidation and appreciation of the role of the secondary molecular forces in conjunction with other interactions of separation of the molecules

4. Chemical

It has now been shown conclusively that there are now a number of cases where adhesive bonding involves primary chemical bonding in addition to secondary van der Waals interactions. This is in spite of the difficulty in investigating this situation because all the relevant information has to be gathered from the surfaces exposed when joints have been broken. However the sophisticated techniques for surface analysis now available (eg. XPS and static SIMS) have produced clear evidence in a growing number of examples for covalent bonding in addition to other interactions. Where these primary forces are involved

they provide bonds which are much stronger and resistant to disruption than do the secondary bonds.

The most extensive exploration in this area has been in connection with coupling or primer agents, particularly in the composite industry. Here it is essential that good bonding exists between the reinforcing fibres and the polymer matrix in which they are embedded. This is if composite materials are to achieve their commercial potential and this bonding must be sustained under conditions of highest humidity, even prolonged immersion in water. This has been well recognised since the early 1960s and appropriate coupling agents (particularly, but not solely, silanes) have been used for a considerable period; but any adequate understanding of the mechanisms in-

involved has only been developed much more recently.

One of the first studies is due to Gettings and Kinloch¹⁰ who investigated the bonding between glycidoxy propyl trimethoxy silane and mild steel. Using static SIMS, they detected a FeSiO^+ ion and later, with stainless steel, also CrOSi^+ . Thus the presence of Fe-O-Si and Cr-O-Si bonds across the interface was clearly indicated. This work also gave clear evidence on the polymerisation of the silane to give a polysilane film of considerable strength. All of this is shown in the Fig. 4. More recently a range of investigations, using these and other techniques, eg Scanning Tunnelling Microscopy and Atomic Force Microscopy (STM, AFM) has provided further support for the formation of covalent bonds at the

Fig. 4 Static SIMS spectrum from a mild steel surface which has been treated with glycidoxy propyl trimethoxy silane; showing evidence of
a iron/oxygen/silicon bonds (FeSiO^+) at 100
b polymerisation of the silane (SiOH^+) and (SiO_2^-) at 45, 60 and 61

interphase of adhesive joints.

Alongside this direct experimental evidence there has been considerable discussion of the use of the concept of Lewis acid/base interactions in this context. This from the suggestion by Fowkes¹¹⁾ that the Work of Adhesion (W_A) is composed of a variety of contributions from a number of interactions thus:

$$W_A = W^d + W^h + W^{ab} + W^p + W^i + ?$$

where the superscripts represent:

- d London dispersion forces
- h hydrogen bonding
- ab acid-base interactions
- p dipole-dipole interaction
- i dipole-induced dipole interactions

Further, the Work of Cohesion can be similarly separated into components of surface free energy. Fowkes and others went on to suggest that the dipole components are negligible; then, following the Lewis approach (in which an acid is defined as a proton acceptor and a base as a proton donor). Hydrogen bonds are considered as acid-base interactions this relationship reduces to:

$$W_A = W^d + W^{ab}$$

This approach has been developed by various workers¹²⁾. Principally this has been based upon Drago's work¹³⁾ which involves a relationship of the form:

$$W_A = (C^A C^B + E^A E^B) n^{AB}$$

While all this has attracted a good deal of support¹³⁾, it has recently been attacked as fundamentally unsound^{14, 15)}.

One must conclude that this is still an area of debate.

Overall however one of the major advances in theoretical discussions in the last four decades has been in the demonstration of recognisable chemical bonding as a significant component of adhesion..

5. Electrostatic

Initially it is important to distinguish this from the mechanisms involving electron interactions involved in the discussions under the headings "Adsorption" and "Chemical" This is an entirely different explanation. The principal exponent has been the

Russian Academician Deryaguin¹⁶⁾. He considered the adhesion and separation of a pressure sensitive tape from a rigid substrate. When two substances of different electronegativity are in intimate contact, an electric double layer will be formed at the interface. In order to separate the two layers the electrostatic attraction of this double layer has to be overcome, and this produces a potential difference between the two which will increase until there is an electric discharge. The conditions for this are governed by Paschen's Law¹⁷⁾ which says that the potential to initiate a spark discharge depends upon the quantity of gas between the electrodes, that is the product of the gap length and gas pressure. Deryaguin assumed that the energy of the capacitance is equal to the energy of adhesion and proceeded to show good agreement between these. However Wake¹⁸⁾ has shown that the method used to determine the values of the various terms in the calculation was circular and flawed. Additionally, some attempts to repeat Deryaguin's measurements have not been successful. Thus, this theory has been largely discredited. However, the flashes of light and noise which certainly occur when a tape is stripped from a solid surface have never been satisfactorily explained. There evidently remains some understanding yet to be achieved here.

6. Diffusion

The diffusion of segments and chain ends of polymers was suggested as a mechanism for the adhesion of similar elastomers above their T_g s by several Russian workers. This was brought together and amplified in papers and then by a significant monograph by Voyutskii¹⁹⁾. This is now generally accepted, at least for the adhesion of a material to itself - "autohesion", although not for the adhesion of different polymers even if they are reasonably similar. While the initial work on this was due to Voyutskii and his colleagues, its quantitative development and general acceptance is due to Vasenin²⁰⁾. His consideration was derived from theories of mixing of liquids and begins from Fick's Laws of Diffusion²¹⁾.

Fick's first Law relates the quantity of material diffusing (in the X direction) across a plane normal to the concentration gradient:

$$dw = -D_t dt dc/dx$$

where w is quantity of material

D_t is diffusion coefficient

t is time

dc/dx is concentration gradient

From this Vasein deduced various functions for the dependence of D_t upon other factors including concentration and nature of the diffusing molecule, and derived a theoretical peel energy, assuming that this depended upon the depth of penetration, and the number of chains crossing the phase boundary.

$$P = k_4 (2Np/M)^{2/3} D_d^{1/2} t_c^{1/4}$$

Where P is peeling energy

M is Avogadro's number

k_4 is a constant

D_d is a constant which characterises the mobility of the macromolecules is related to D_t

N is number of chains crossing the crossing the boundary

and

p is density

t_c is time of contact

Experimentally measured points and calculation lines for polyisobutylene are shown in Fig. 5, and demonstrate good agreement. Most of this work was

Fig. 5 Relationship between peel energy and contact time for autohesion of poly-isobutylenes: (-----) lines calculated and (.....) points measured.

published in the early 1960s, a little after the Conferences began.

7. Pressure Sensitive.

While pressure sensitive adhesives are very familiar as adhesive tapes for many domestic as well as commercial purposes, they are quite different in their nature from all the other adhesives. They depend upon remaining as a stable liquid of very high viscosity, perhaps of the order of 10 Pa·s. They have to retain this viscosity throughout their useful life, never curing or cross-linking. The strength of their bond depends upon the pressure with which they are applied, because it all depends upon the flow under pressure of this highly viscous liquid to bring it into intimate contact with the adherend surface. To break the bond and separate the tape from the adherend requires the adhesive to flow in the opposite direction and eventually to yield. If it undergoes cross linking, as can easily happen if the tape is exposed to bright sunlight, then it becomes hard and brittle, the bond ceases to exist and the backing can be lifted away.

8. "Weak Boundary Layers"

While strictly not a theory of adhesion, it is common practise to include within a discussion of origins of the strength or weakness of adhesive bonds, this concept which is due to Bikerman²³. He contended that the cause of failure of adhesive bonds was the presence at the interface of a layer which was itself mechanically weak. This was sufficiently thin that it could not usually be detected by means which were then available but it was almost inevitably present. Nowadays this idea can be very broadly accepted, but it does not advance our concept of how and why adhesive bonds achieve both strength and durability, although it may help in diagnosing the cause of the failure of bonds to perform adequately.

9. Conclusion

Adhesive bonding is now perceived as a mature joining technology with most of the necessary materials and techniques well developed. Thus it is difficult to forecast any basic developments in this field during the next decade, let alone over any longer time-

span. Most of the changes which can be predicted lie in the practical use of adhesives and their use in a wide range of practical applications.

Considerable changes can be expected to evolve for the production of more environmentally benign – already taking place in the considerable replacement of the solvent based products.

Clearly the most exciting alteration is in the various applications of nano technology and these are expected to develop to a considerable extent.

References

- 1) de Bruyne N. A. and Houwink R. "Adhesion and Adhesives" Elsevier Amsterdam 1951
- 2) Eley D.D. "Adhesion" Oxford University Press London 1961
- 3) Allen K. W. "Aspects of Adhesion 5" ed. D. J. Alner.
- 4) Boroff E. M. and Wake W. C., Trans Inst Rubber Ind 1949; 25: 199 and 210
- 5) Haines B. M. In: Alner D. J. ed: Aspects of Adhesion Vol. 3, University of London Press 1967 p 40
- 6) Packham D.E. Adhesion of polyethylene to high energy substrates PhD Thesis, City University, London 1970
- 7) Venables J. D. "Adhesion 7" ed. K. W. Allen Applied Science Publishers London, 1983, p. 87
- 8) Allen K. W., Alsallim H. S. and Wake W. C. Faraday, Special Discussions of the Chem. Soc London 1972 No. 2
- 9) Allen K. W. "Aspects of Adhesion 1" ed., D. J. Alner, University of London Press, 1965 p. 14
- 10) Gettings M. and Kinloch A. J., *J. Materials Sci.* 12, 2049 (1977)
- 11) Fowkes F. M. J. "Adhesion 4", 155 (1972)
- 12) In "Acid-Base interactions: Relevance to Adhesion Science and Technology" ed. Mittal K. L. and Anderson H. R. VSP BV, Zeist, Netherlands pp. 380
- 13) Drago R. S., Vogel G. C. and Needham T. E., *J. AM Chem Soc* 93, 6014 (1971)
Drago R. S., Parr L. B. and Chamberlain C. S., *J. Am Chem Soc* 99, 3203 (1977)
- 14) Greiveldinnger M. and Shanahan M.E.R., *J. Colloid and Interface Sci.* 215, 170 (1999)
- 15) Huntsberger J. R., *J. Adhesion* 12, 3 (1981)
- 16) Deraguin B. V., *Research* 8, 70 (1955)
- 17) Paschen F. Wied. *Ann.* 37, 69 (1955) *see also:* Electricity and magnetism for degree students" 7th ed. by S. G. Starling Longmans Green, London 1946, p. 464
- 18) Wake W. C. "Adhesion and the formulation of Adhesives" 2nd edn. by W. C. Wake, Ap Science Publishers London 1982.89
- 19) Voyutskii S.S. "Autohesion and Adhesion of High Polymers" Moscow translated. V. Vakula Interscience, New York 1963
- 20) Vasenin R. M. "Adhesion: Fundamentals and Practice The Ministry of Technology Maclaren and Sons London 1969 p. 29
- 21) Fick Pogg. *Ann.* 94, 59 (1855) *see also* "The General Properties of Matter" Newman and Searle Ernest Benn 1928, p. 287
- 22) Bikerman J. J. "The Science of Adhesive Joint" 2nd edn., Academic Press, London 1968