RAMAN SPECTROSCOPIC STUDY OF SUPERCONDUCTING $\text{Bi}_{1.6}\text{Pb}_{0.4}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$ POLYCRYSTAL

CHIE WATANABE, SEIICHIRO HIGUCHI, YOHICH GOHSHI
MASASHI ONISHI*, MICHIHISA KYOTO* and MINORU WATANABE*

Department of Industrial Chemistry, Faculty of Engineering, University of Tokyo, Hongo, Bunkyo-ku, Tokyo, Japan

*Sumitomo Electric Industries, Taya-cho, Sakae-ku, Yokohama, Japan

Abstract - The polycrystalline samples of $\text{Bi}_{1.6}\text{Pb}_{0.4}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$ were prepared by the melt-quenching method, and examined by Raman spectroscopy. In these samples, the c-axis of each plate-like microcrystal was parallel to the surface of the samples. The Raman spectra of the two surfaces of a sample were found to differ each other, especially in the intensity of the 660 cm^{-1} phonon line. From the comparison of the x-ray powder diffraction patterns of these two surfaces, it is suggested that the difference of the Raman spectra is related to difference in amounts of the 2223 phase and that the 660 cm^{-1} phonon line can be assigned to the 2223 phase.

Key words Raman, superconductor, bismuth, polycrystal

Recent investigations of the Raman spectra of the Bi-2212 (Tc-80 K) have revealed that the frequencies of some phonon lines are dependent on Tc[1]. Thus, it is interesting to compare the Raman spectra of the Bi-2212 with that of the Bi-2223 (Tc-110 K) in order to investigate the relationship between Tc and the behavior of the phonons. However, there are few reports on the Raman spectra of the 2223 phase, though a large number of reports of the 2212 phase were published.

As for the 2223 phase, the Raman spectra of the ceramics which contained both of 2212 and 2223 phases was compared with the spectra of the 2212 single crystal by Sapriel et al[2]. However, the phonon lines of the 2223 phase could not be distinguished from those of the 2212 phase in the spectra obtained from the ab-plane of the crystals. The authors suggested that the additional phonon lines would be detected if the Raman spectra could be obtained from the ac- or bc-plane. Generally, it is quite difficult to grow the large single crystal of the 2223 phase enough for measuring the Raman spectra on the ac- or bc-plane.

Thus, we are studying the Raman spectra of the samples prepared by the melt-quenching method[3]. The samples prepared by this technique have such a characteristic that the c-axis of each plate-like microcrystal is oriented parallel to the surface of the sample. This orientation is suitable for measuring the Raman spectra on the ac- or bc-plane. In this paper, samples prepared by the melt-quenching method were examined by Raman spectroscopy, and the difference of the spectra between the 2212 and the 2223 phases was discussed.

EXPERIMENTAL

Sample Preparation The mixture of Bi_2O_3 , PbO , SrCO_3 , CaCO_3 and CuO , with the nominal composition of $\text{Bi}_{1.6}\text{Pb}_{0.4}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$, was melted in a platinum crucible at 1373 K for 20 min, and cooled quickly down to room temperature to obtain an amorphous plate. The thickness of the plate was about 1 mm. The plate was cut into 1 cm x 1 cm and heat-treated at 1113 K for 136 hours in air.

Fig.1. Raman spectra of surfaces (a) and (b)

Characterization Raman spectra were examined at room temperature with a back-scattering geometry, using a double-monochromator and a photomultiplier tube. The 514.5 nm line of an Ar⁺ laser was focused on a point spot (diameter 100 μm) as excitation source. The microstructures of the samples were observed by a scanning electron microscope (SEM). X-ray powder diffraction analysis with CuK α radiation were performed at room temperature to identify phases present in samples. As for measurement of superconducting properties, temperature dependence of resistivity was measured using a conventional four-probe dc method.

RESULTS AND DISCUSSION

All samples prepared by this procedure exhibited the zero-resistance at temperature below 104 K. Fig.1 shows the Raman spectra of the sample. The picture in this figure shows the surfaces (a) and (b), in which the spectra of (a) and (b) were measured respectively. It is clear that the intensity of the 660 cm^{-1} phonon line differ each other. This difference was observed for all samples prepared. The phonon lines at 460, 630 and 660 cm^{-1} were already recognized to be the phonon lines of superconducting phases[1].

The SEM photographs of surfaces (a) and (b) are shown in Fig.2. From this figure, it is found that the orientation of the microcrystals of the surfaces (a) and (b) is identical, and no clear difference can be noticed. Therefore, the difference in the 660 cm^{-1} line is not due to the difference in the orientation of the microcrystals on the surface.

Furthermore, the powder x-ray patterns of both surfaces are shown in Fig.3. The powders were scraped off from the surfaces about 40 μm in depth. Fig.3 shows that the amount of the 2223 phase is larger in the surface (b) than in the surface (a). This result strongly suggests that the difference in intensity of the 660 cm^{-1} line is caused by the difference in amounts of the 2223 phase and that the shoulder peak at 660 cm^{-1} is the phonon line of the 2223 phase. On the other hand, there is another assignment that the 660 cm^{-1} line originates in the 2212 phase and the 630 cm^{-1} line originates in the 2223 phase[4]. But in our result, the intensity of the 630 cm^{-1} line is larger than the 660 cm^{-1} line, corresponding to the fact that the amount of the 2212 phase is larger than that of the 2223 phase. Therefore, the 660 cm^{-1} line can be assigned to the 2223 phase.

In summary, the polycrystalline samples which contained both the 2212 and the 2223 phases were examined by Raman spectroscopy, SEM and x-ray powder diffraction. The 660 cm^{-1} phonon line was supported to arise from the 2223 phase.

REFERENCES

1. M. Boekholt, A. Erle, P. C. Splittgerber-Hunnekes and G. Guntherodt, *Solid State Commun.*, **74**, 1107 (1990).
2. J. Sapriel, L. Pierre, D. Morin, J. C. Toledano, J. Schneck, H. Savary, J. Chavignon, J. Primot, C. Daguet, J. Etrillard and H. Boyer, *Phys. Rev. B*, **39**, 339 (1989).
3. T. Komatsu, K. Imai, R. Sato, K. Matsushita and T. Yamashita, *Jpn. J. Appl. Phys.*, **27**, L533 (1988).
4. K. H. Kim, P. V. Huong, E. Oh-Kim, M. Lahlaye, S. K. Cho and B. C. Kwak, *J. the Less-Common Metals*, **164-165**, 1201 (1990).

Fig.2. SEM photographs of surfaces (a) and (b)

Fig.3. X-ray diffraction patterns of the surfaces (a) and (b)