Synthesis, Characterization and Crystal Structure of 2-[(*E*)-2-(4-Hydroxy-3-methoxyphenyl)ethenyl]-1-methylquinolinium 4-chlorobenzenesulfonate

Suchada CHANTRAPROMMA,^{*†} Boonwasana JINDAWONG,^{*} Hoong-Kun FUN,^{**}
P. S. PATIL,^{***} and Chatchanok KARALAI^{*}

^{*}Department of Chemistry, Faculty of Science, Prince of Songkla University, Hat-Yai,
Songkhla 90112, Thailand

^{**}X-ray Crystallography Unit, School of Physics, Universiti Sains Malaysia, 11800 USM, Malaysia

^{***}Department of Studies in Physics, Mangalore University, Mangalagangothri, Mangalore 574 199, India

The title compound, $C_{19}H_{18}NO_2^+ \cdot C_6H_4ClSO_3^-$, was synthesized and characterized by UV-Vis, FT-IR, NMR and single crystal X-ray diffraction. The compound crystallizes in the monoclinic *Pc* space group; $a = 7.8386(1)$, $b = 6.7731(1)$, $c = 21.7096(3)$ Å, $\beta = 108.476(1)^\circ$, $V = 1093.19(3)$ Å³, $Z = 2$ and $D_x = 1.470$ g cm⁻³. In the crystal packing, the cations and anions are linked by weak C-H...O interactions into individual chains along the *b*-axis. The anionic and the cationic chains are alternately arranged and interconnected to form a three-dimensional network. The second-harmonic generation (SHG) efficiency of the compound is about 0.5-times that of urea.

(Received September 28, 2006; Accepted December 11, 2006; Published on web February 26, 2007)

Organic molecules that exhibit second-order nonlinear optical (NLO) properties usually consist of a frame with a delocalized π system, and end-capped with either a donor or an acceptor substituent or both. The most important requirement for these materials to exhibit second-order NLO properties is for the molecules to be oriented in a non-centrosymmetric environment.¹ Benzenesulfonate is frequently used to co-

crystallize with cations to form compounds which are expected to have NLO properties.² Our continuing research on non-linear optical materials^{3,4} has led us to synthesize the title compound

Fig. 1 Chemical scheme of I.

Fig. 2 ORTEP view of I with the atomic-numbering scheme. Thermal ellipsoids of non-H atoms are drawn at the 50% probability level.

[†] To whom correspondence should be addressed.
E-mail: suchada.c@psu.ac.th and hkfun@usm.my

Table 1 Crystal and experimental data

Chemical Formula: $C_{19}H_{18}NO_2^+ \cdot C_6H_4ClO_3S^-$
Formula weight = 483.96
Crystal system: monoclinic
Space group: <i>Pc</i>
$Z = 2$
$a = 7.8386(1)$ Å
$b = 6.7731(1)$ Å
$c = 21.7096(3)$ Å
$\beta = 108.476(1)^\circ$
$V = 1093.19(3)$ Å ³
$D_x = 1.470$ g cm ⁻³
$\mu(\text{Mo } K\alpha) = 0.310$ mm ⁻¹
$T = 100.0(1)$ K
$F(0\ 0\ 0) = 504$
Crystal size = $0.22 \times 0.15 \times 0.06$ mm
θ range for data collection 2.74 to 30.00°
$R = 0.0371$
$R_w = 0.0792$
No. of unique data measured = 6151
No. of observed data with $[I > 2\sigma(I)] = 5510$
No. of parameters = 325
Goodness-of-fit = 1.033
$(\Delta\rho)_{\text{max}} = 0.298$ e.Å ⁻³
$(\Delta\rho)_{\text{min}} = -0.353$ e.Å ⁻³
Measurements; Bruker APEX2 CCD diffractometer
Program system: Apex2
Structure determination; direct method (SHELXTL)
Refinement; full-matrix least-squares

CCDC 620712 contains the supplementary crystallographic data for this paper. These data can be obtained free of charge from the Cambridge Crystallographic Data Centre via www.ccdc.cam.ac.uk/data_request/cif.

Fig. 3 Crystal packing of I, viewed down the *a*-axis. Hydrogen bonds are shown as dashed lines.

(I). We report here on the synthesis and the crystal structure of I, which crystallizes in the non-centrosymmetric monoclinic space group, *Pc*, and has a second-order nonlinear efficiency of 0.5 times that of urea.⁵

2-[(*E*)-2-(4-Hydroxy-3-methoxyphenyl)ethenyl]-1-methylquinolinium iodide (compound A) was prepared by the condensation of (1:1:1 molar ratio) of 1,2-dimethylquinolinium iodide (2.98 g, 10.05 mmol), vanillin (1.60 g, 10.05 mmol) and piperidine (1.00 ml, 10.00 mmol) in methanol (35 ml). The solid formed was filtered and re-crystallized from methanol to give dark-red crystals of A (3.00 g, 68%), mp. 248 – 250°C.

Silver(I) 4-chlorobenzenesulfonate (compound B) was synthesized according to our previous method.⁴ Compound I was synthesized by mixing a solution (1:1 molar ratio) of A (0.30 g, 0.72 mmol) in hot methanol (150 ml) and B (0.21 g, 0.72 mmol) in hot methanol (30 ml). The mixture turned dark-red and cloudy immediately. After stirring for 30 min, the precipitate of silver iodide was filtered, and the resulting solution was evaporated to yield an orange solid of I (re-crystallized from methanol): Yield 87%; Mp 262 – 264°C; ¹H-NMR (300 MHz, CDCl₃ + DMSO-*d*₆) (δ ppm): 3.98 (3H, s, OCH₃), 4.59 (3H, s, CH₃), 8.42 (1H, d, *J* = 9 Hz, H-3), 8.84 (1H, d, *J* = 9 Hz, H-4), 8.25 (1H, dd, *J* = 1.5, 7.8 Hz, H-5), 7.89 (1H, t, *J* = 7.8 Hz, H-6), 8.14 (1H, dt, *J* = 1.5, 7.8 Hz, H-7), 8.40 (1H, d, *J* = 7.8 Hz, H-8), 7.66 (1H, d, *J* = 15.6 Hz, H-1'), 8.05 (1H, d, *J* = 15.6 Hz, H-2'), 7.48 (1H, d, *J* = 1.8 Hz, H-2''), 6.97 (1H, d, *J* = 8.1 Hz, H-5'), 7.37 (1H, dd, *J* = 1.8, 8.1 Hz, H-6'), 7.76 (2H, d, *J* = 8.4 Hz, H-2''' and H-6'''), 7.27 (2H, d, *J* = 8.4 Hz, H-3''' and H-5'''); IR (KBr, cm⁻¹) 3432, 3077, 1584, 1521, 1374, 1189, 1031; UV (λ_{max}/nm (ε/10⁴ M⁻¹ cm⁻¹), CH₃OH) 220.5 (2.1), 252.9 (0.8), 310.6 (0.6), 440.1 (1.8), 574.8 (0.9).

The crystallographic and experimental parameters used for data collection and determining of the structure are given in Table 1. All of non-hydrogen atoms were refined anisotropically. The hydroxyl H atom was located in the difference map and isotropically refined. The remaining H atoms were placed at the calculated positions with the C-H distances in the range of 0.93 – 0.97 Å. The *U*_{iso} values were constrained to be 1.5*U*_{eq} of the carrier atoms for hydroxyl and methyl H atoms, and 1.2*U*_{eq}(C) for the remaining H atoms. The final refinement converged well. The largest peak and hole in the final difference map were 0.298 Å⁻³ at 0.88 Å from atom C1 and -0.353 Å⁻³ at 0.51 Å from atom S1, respectively.

The bond lengths and angles are normal.⁶ An ORTEP plot of the molecule at 50% probability is shown in Fig. 2. The

Table 2 Hydrogen-bonding geometry(Å, °)

D-H...A	D-H	H...A	D...A	D-H...A
O4-H1O4...O1 ⁱ	0.77(2)	1.90(2)	2.6576(19)	169(3)
C2-H2...O3	0.97	2.5543	2.921(3)	103
C3-H3...O1 ⁱⁱ	0.97	2.3409	3.189(3)	146
C5-H5...O3 ⁱⁱⁱ	0.95	2.2348	3.177(3)	175
C9-H9...O4 ^{iv}	0.97	2.5288	3.367(3)	144
C10-H10...O5 ^{iv}	0.96	2.3979	3.310(3)	159
C14-H14...O2	0.94	2.3539	3.296(2)	175
C17-H17...O2	0.93	2.4275	3.332(2)	163

i = *x*, 1-*y*, -1/2+*z*; ii = *x*, 1+*y*, *z*; iii = 1+*x*, *y*, *z*; iv = -1+*x*, -2+*y*, *z*.

asymmetric unit of I consists of C₁₉H₁₈NO₂⁺ and C₆H₄ClSO₃⁻ (Fig. 2). The cation is almost planar, as indicated by the dihedral angle between the quinolinium (N1/C7-C15) and the benzene (C18-C23) rings, being 4.21(8)° [2.59(9)°,³ and 2.8(1)°,⁴]. The H atoms attached to C16 and C17 are trans to each other; thus, the cation exists in an *E* configuration and the torsion angle C15-C16-C1-C18 is -177.82(18)°. In the asymmetric unit, the benzene ring in the 4-chlorobenzenesulfonate anion makes dihedral angles of 87.12(7)° and 83.02(9)°, respectively, with the quinolinium and the benzene rings of the cation. The corresponding values are 59.17(9)° and 60.59° in ref. 3 and 48.97(6)° and 51.63(7)° in ref. 4. The structure shows intramolecular weak C-H...O interactions, namely C14-H14...O2 and C17-H17...O2 (Table 2). The packing of the molecule down the *a*-axis is as shown in Fig. 3; the cations and anions are linked by weak C-H...O interactions into individual chains along the *b*-axis. The anionic and cationic chains are alternately arranged and interconnected to form a three-dimensional network.

Acknowledgements

BJ is grateful to the Higher Education Development Project: Postgraduate Education and Research Program in Chemistry, Royal Thai Government and Graduate School, Prince of Songkla University, for partial financial support. The authors thank Prince of Songkla University, the Malaysian Government and Universiti Sains Malaysia for the Scientific Advancement Grant Allocation (SAGA) grant No. 304/PFIZIK/653003/A118.

References

1. D. J. Williams, *Angew. Chem. Int. Ed. Engl.*, **1984**, 23, 690.
2. C. K. Lakshmanaperumal, A. Arulchakkaravarthi, N. Balamurugan, P. Santhanaraghavan, and P. Ramasamy, *J. Cryst. Growth*, **2004**, 265, 260.
3. B. Jindawong, S. Chantrapromma, H.-K. Fun, and C. Karalai, *Acta Cryst.*, **2005**, E61, o3237.
4. S. Chantrapromma, B. Jindawong, H.-K. Fun, P. S. Patil, and C. Karalai, *Acta Cryst.*, **2006**, E62, o1802.
5. S. K. Kurtz and T. T. Perry, *J. Appl. Phys.*, **1968**, 39, 3798.
6. F. H. Allen, O. Kennard, D. G. Watson, L. Brammer, A. G. Orpen, and R. Taylor, *J. Chem. Soc. Perkin Trans. 2*, **1987**, 18.