Zirconia versus titanium in dentistry: A review

Takao HANAWA

*Institute of Biomaterials and Bioengineering, Tokyo Medical and Dental University, 2-3-10 Kanda-surugadai, Chiyoda-ku, Tokyo 101-0062, Japan
Corresponding author, Takao HANAWA; E-mail: hanawa.met@tmd.ac.jp*

This review scientifically compares the properties of zirconia and titanium, but does not identify the best among them as an implant material. Surface treatment and modification to improve tissue bonding and inhibit bacterial adhesion are not considered in this review. The mechanical properties of titanium are superior to those of zirconia; some studies have shown that zirconia can be used as a dental implant, especially as an abutment. Extensive surface treatment research is ongoing to inhibit bacterial adhesion and improve osseointegration and soft tissue adhesion phenomena which make it difficult to evaluate properties of the materials themselves without surface treatment. Osseointegration of titanium is superior to that of zirconia itself without surface treatment; after surface treatment, both materials show comparable osseointegration. The surface morphology is more important for osseointegration than the surface composition. To inhibit bacterial adhesion, zirconia is superior to titanium, and hence, more suitable for abutments. Both materials show similar capability for soft tissue adhesion.

Keywords: Zirconia, Titanium, Bacterial adhesion, Osseointegration, Soft tissue adhesion

INTRODUCTION

Metal-free treatment is now popular in dentistry due to the esthetic problem of metal restoratives. Metals have long been used for dental restoratives. In dentistry, esthetics is among the predominant goals. Therefore, even if the mechanical properties of a material are insufficient, its esthetics is sometimes preferred. Metals or metallic materials are defined as “materials consisting of metallic bonds.” One of the characteristics of metals is metallic luster due to these metallic bonds. This disadvantage of metals has led to their substitution by ceramics and polymers in dentistry. There are always discussions and debates on material selection among dentists, manufacturers, and dental materials researchers. However, these discussions, debates may not always be based on scientific viewpoints such as materials science and engineering. Among the causes for debates is the propaganda from manufacturers which only highlight the merits of products that is believed by most of dentists and some of researchers. An interesting theme of recent debates is the selection of zirconia or titanium as dental implants. Comparing zirconia to titanium is almost equivalent to comparing ceramics with metals. The advantages of ceramics are high-temperature resistance, wear resistance, chemical stability, and importantly, white color for dentistry, while the disadvantages include low fracture toughness or brittleness. On the other hand, the advantages of metals are high fracture toughness based on high strength and elongation and good balance between rigidity and stiffness, while the disadvantages include corrosion and fatigue. As is well known, all materials have advantages and disadvantages; there is no material that shows only advantages. In this review, a scientific comparison of the properties of zirconia and titanium is attempted, but the best among them as an implant material is not judged.

Surface treatment and modification to improve tissue compatibility and inhibit bacterial adhesion are not considered in this review; nevertheless, recent research on tissue compatibility has focused on evaluation after surface treatment involving the surface morphology. In this review, the terms “zirconia” and “titanium” are used for general and comprehensive material names, while ZrO_2 and Ti are used when the compositions are clear.

OVERVIEW OF ZIRCONIA AND TITANIUM

Zirconia

Zirconia was originally discovered as a mineral in 1892¹⁾, and has been widely used as a refractory material for applications such as the outer wall of space shuttles owing to its high melting point of 2,715°C. The most stable phase at ambient temperature is monoclinic, which, upon heating, transforms into tetragonal and cubic phases²⁾. However, when sintered zirconia is cooled to ambient temperature, cracks are formed in zirconia due to the volume increase from the tetragonal phase to the monoclinic phase, which decreases the mechanical strength of zirconia³⁾. The history of zirconia and its application to medicine and dentistry are summarized in Table 1.

Many researchers have found that small amounts of calcia (CaO), magnesia (MgO), ceria (CeO_2), and yttria (Y_2O_3) in a solid solution of ZrO_2 can stabilize the tetragonal or cubic phase of ZrO_2 at ambient temperature, depending on the amount of oxide added. Fully stabilized zirconia (FSZ), consisting of only the cubic phase, shows the greatest ion conductivity and has been used in solid oxide fuel cells and oxygen sensors. On the other hand, partially stabilized zirconia (PSZ) contains the monoclinic or tetragonal phase in addition to the cubic phase. Classical theory shows that the strain energy of the surrounding material allows the

Table 1 History of zirconia application to medicine

Year	Material	Event and application	Reference
1892	ZrO ₂ mineral	Discovery	1)
1929	Stabilized zirconia: Polycrystalline ceramics	Development	
1937	Cubic zirconia in the form of microscopic grains	Development	
1969	Application to medicine	First paper of zirconia for medical use	14)
1973	Skull crucible process	Development	
1975	Ceramic steel: Zirconia consisting of tetragonal phase within large cubic-phase grains (PSZ)	Development	40)
1976	Commercial production		
1977	Y-TZP	Highest mechanical strength of 690 MPa	8, 9)
1985	Y-TZP	Clinically marketed as the ball head of an artificial hip joint	13)
2001	Marketed dental restoratives	CAD/CAM system, Dentsply Sirona	
2005	Marketed dental restoratives in Japan	CAD/CAM system, Dentsply Sirona	
2006	Zirconia implant	Abutment	20)

tetragonal or cubic structure to be retained. The surface tension associated with the decreased particle size of the crystal restricts the transformation from the cubic phase into the tetragonal phase and the following monoclinic phase^{4,5)}.

In 1975, ZrO₂ comprising a tetragonal phase within large cubic-phase grains showed a high transverse rupture strength of 650 MPa in a four-point bending test, whereas pure monoclinic ZrO₂ showed a strength of 250 MPa^{3,6)}. The mechanism of this high mechanical strength was as follows: When stress is added to zirconia by micro-cracking, the constraint strain energy of the metastable tetragonal phase decreases. The tetragonal phase transforms into the monoclinic phase accompanied by a volume increase of 3–4%, which generates resistance stress against the propagation of micro-cracks in zirconia⁷⁾. In 1977, a yttria-stabilized tetragonal zirconia polycrystalline (Y-TZP), including 98% of the tetragonal phase obtained by introducing a small amount of Y₂O₃, showed the highest mechanical strength of 690 MPa among the tested samples ranging from 10 to 98% tetragonal ZrO₂^{8,9)}. The bending strength increased by refining the density, grain size, and sintering conditions, and the fracture toughness was higher than that of alumina (Al₂O₃), which was used for the ball head of artificial hip joints. In terms of bending strength, Y₂O₃ was selected as an additive oxide in zirconia and Y-TZP became the major material for the ball head^{10–12)}.

In 1985, Y-TZP was clinically marketed as the ball head of an artificial hip joint in France¹³⁾ after the first paper regarding the application of zirconia for medical science was published in 1969¹⁴⁾. Besides its bending strength, Y-TZP is less likely to induce allergic hypersensitivity. Clinical Y-TZP comprises nearly 100% of the tetragonal phase of ZrO₂ stabilized

by approximately 3 mol% of Y₂O₃ in a solid solution of ZrO₂.

Y-TZP has an esthetic white color and translucency similar to human teeth, whereas the metal implanted in a tissue makes the soft tissue look gray^{15,16)}. Therefore, Y-TZP has become a major ceramic material in dentistry over the past two decades due to its white color and sufficient mechanical strength. When we need to restore decayed teeth with an inlay or a crown, at present, we can choose metallic or ceramic prosthesis by considering the color and biocompatibility. This is because Y-TZP is widely available for use as inlays, crowns, bridges, and abutments, which connect roots and artificial teeth in dental implants.

Titanium

The history of application of commercially pure titanium (CP Ti) and titanium alloys (Ti alloys) to medicine and dentistry is summarized in Table 2. The first report on CP Ti for medicine was presented in 1940, demonstrating excellent bone compatibility in an animal test¹⁷⁾. Thereafter, compatibility to bone and soft tissue of rabbits¹⁸⁾, non-cytotoxicity due to excellent corrosion resistance in biological environment¹⁹⁾, and excellent biocompatibility in dogs were reported. A large-scale industrial manufacturing process of titanium was achieved by the latter half of the 1940s, which made it possible to conduct considerable research for medical applications, owing to the excellent biocompatibility revealed in a long-term animal test²⁰⁾. Thereafter, the usefulness of CP Ti was widely recognized by the latter half of the 1960s through clinical evaluation^{20–22)}.

On the other hand, to avoid the fracture of CP Ti in the human body, an aerospace Ti-6Al-4V alloy was diverted to artificial joints and bone fixators^{20–22)}.

Table 2 History of titanium application to medicine and development of titanium alloys

Year	Material	Event and application	Reference
1791	Ti element in ore	Discovery of menachite, ore of titanium	
1795	Ti element in ore	Named as titan	
1910	Ti	99.9%Ti is smelled by Hunter	
1940	Ti	Confirmation of equivalent biocompatibility as stainless steel and cobalt-chromium alloy with animal test	17)
1940	Ti	Success of smelting by Kroll process	
1948	Ti	Launch of industrial production	
1951	Ti	Confirmation of both soft and hard tissue compatibility with animal test	18)
1957	Ti	Confirmation of non-toxicity with long-term implantation	19)
1959	Ti-Ni	Development of shape memory alloy in USA	25)
1960	Ti	Excellent results in artificial joints	20)
1960's	Ti	Marketing as surgical implants in UK and USA	
1970's	Ti-6Al-4V	Diverting aircraft material to orthopedic implants	
1978	Ti-Cu-Ni	Trial of dental casting	30)
1980	Ti-5Al-2.5Fe	Development in Europe	
1982	Ti	Development of investment material and casting machine for dental casting	31)
1985	Ti-6Al-7Nb	Development in Switzerland	23)
1993	Ti-13Nb-13Zr	Development in USA	
1993	Ti-12Mo-6Zr-2Fe	Development in USA	25)
1996	Ti-15Mo	Development in USA	26)
1998	Ti-29Nb-13Ta-4.6Zr	Development in Japan	28)
Around 2000	Ti-15Mo-5Zr-3Al	Development in Japan	Kobe Steel 24)

Thereafter, vanadium (V)- and/or aluminum (Al)-free $\alpha+\beta$ -type Ti alloys and β -type Ti alloys with low Young's modulus were developed. V, which shows cytotoxicity in Ti-6Al-4V alloy, was replaced by niobium (Nb), which is a safe element for developing a new $\alpha+\beta$ -type Ti-6Al-7Nb alloy²³. Other $\alpha+\beta$ -type alloys, Ti-6Al-2.5 iron (Fe) and Ti-6Al-2Nb-1 tantalum (Ta)-0.8 molybdenum (Mo), were developed in the 1970s²⁴.

On the other hand, β -type Ti alloys have been developed for medical use. Ti-13zirconium (Zr)-13Ta alloy (nearly β), as well as various β -type alloys, Ti-12Mo-6Zr-2Fe alloys²⁵, Ti-15Mo alloy²⁶, and Ti-15Mo-2.8Nb-0.2 silicon-0.28 oxygen (O) alloy²⁷, have been developed in the United States. Ti-15Mo-5Zr and Ti-15Mo-5Zr-3Al alloys²⁴ and Ti-29Nb-13Ta-4.6Zr alloy²⁸ have been developed in Japan. The history of development of β -type Ti alloys is well-summarized elsewhere²⁹. Young's modulus can decrease to 40–60 GPa in a β -type alloy.

In dentistry, CP Ti has been successfully performed

as dental implants since 1965³⁰. In 1982, a magnesia-system investment and argon-arc casting machine were developed, followed by the development of various dental-casting systems³¹.

MECHANICAL PROPERTIES BASED ON CRYSTAL STRUCTURE

Crystal structure of zirconia

The structure of zirconia has been reviewed elsewhere³². Y-TZP exhibits a high flexural strength^{6,33-35}, which increases with surface modification³⁶. The fracture strength of one-piece zirconia implants is decreased with the preparation and cyclic loading. However, the resultant values are still within clinically acceptable limits³⁷. ZrO₂ is a polymorphic material and forms three structures, monoclinic, tetragonal, and cubic, as shown in Fig. 1. The monoclinic phase is stable at ambient temperatures of up to 1,170°C, the tetragonal phase is

Fig. 1 Phase transformation of pure ZrO_2 by temperature.

Fig. 2 Schematic of stress-induced transformation from tetragonal phase to monoclinic phase, generating resistance to micro-crack extension.

Fig. 3 Phase transformation of titanium by temperature.

stable at temperatures of 1,170–2,370°C, and the cubic phase is stable over 2,370°C^{38,39}. A mixture of stabilizing oxides such as CaO , MgO , Y_2O_3 , or CeO_2 allows transformation to the metastable tetragonal structure at ambient temperature. Grinding or sandblasting in dental treatment generates a tetragonal to monoclinic transformation in the surface³⁹. The volume is expanded by the transformation from the tetragonal phase to the monoclinic phase. This phase transformation results in compression of cracks, thereby retarding its growth and enhancing fracture toughness (Fig. 2). This mechanism is well-known as transformation toughening⁴⁰. Zirconia possibly transforms to the monoclinic phase with moisture and stress, which is a demerit for dental implants. This mechanical degradation is known as “aging”³⁹. Transformation to the monoclinic phase reduces strength, toughness, and density, which in turn leads to micro-cracking on the surface. This micro-crack helps water penetration and causes corrosion⁴¹. Degradation at ambient temperature of Y-TZP involves roughening, increased wear and micro-cracking, grain pull-out, generation of particle debris, and premature failure⁴². The aging process depends on factors such as porosity, residual stress, grain size, and the content of the stabilizer⁴³. Aging affects the mechanical properties of zirconia *in vitro*, even though the values are within clinically acceptable limits^{44,45}.

Crystal structure of titanium

The crystal structures of the CP Ti and Ti alloys can be obtained from books^{46,47}. CP Ti is composed of hcp crystals (α phase) at ambient temperatures and of bcc crystals (β phase) over 882°C, as shown in Fig. 3. Real pure Ti does not exist, because Ti easily dissolves impurities such as O, carbon (C), and nitrogen (N) from the environment. Pure Ti containing these impurities is called CP Ti, which is classified into four grades according to its impurity content and the resulting mechanical properties. The higher the grade number and impurity, the higher is the tensile strength and offset yield stress and lower is the elongation. CP Ti is used for applications such as maxillofacial prosthetic plates, miniplates, sternal wires, and dental implants.

Ti alloys are categorized as α -type, $\alpha+\beta$ -type, and β -type alloys, according to the quantities and types of their alloying elements. Various alloys have been developed but the Ti-6Al-4V alloy, an $\alpha+\beta$ -type alloy, is the most conventional one for medical use. This alloy shows good workability, heat treatment ability, and weldability, as well as corrosion resistance, strength, and biocompatibility. The extra low-interstitial (ELI)-grade alloy, containing small amounts of interstitial impurities (O, C, and N), is used for biomaterials. The Ti-6Al-4V ELI alloy shows great toughness because the impurities decrease the fatigue strength with the notch

Table 3 Mechanical properties of zirconia and titanium

Mechanical property	Y-TZP	CP Ti (Grade 2)	Ti-6Al-4V Alloy
Tensile strength (MPa)	—	345	860 (annealed)
Bending strength (MPa)	1,100 (without HIP) 1,800 (with HIP)	400	950
Young's modulus (GPa)	210	100	110
Vickers Hardness (HV)	1,200	150–170	270–320
Fracture toughness (MPa m ^{1/2})	6–8	66	50

effect. The ELI alloy is used for bone fixation plates, screws, bone nails, and the stems of artificial hip joints. Ti-6Al-4V alloy has an extremely large 0.2% offset yield strength of 895 MPa, which is much larger than that of stainless steel and Co-Cr-Mo alloys, making plastic deformation difficult even under a large load. Ti alloys contain not only α and β phases but also α' , α'' , and ω metastable phases, which influences the mechanical property.

Mechanical properties

The mechanical properties of Y-TZP, CP Ti, and Ti-6Al-4V alloys are summarized in Table 3.

Usually, it is impossible to conduct a tensile test for brittle materials such as ceramics, so only a compressive or bending test is conducted to evaluate the strength of ceramics. Therefore, it is difficult to directly compare the strength of ceramics with metals, whose strength is evaluated with a tensile test. The bending strength of Y-TZP is 1,000 MPa, which itself is sufficiently large in both Y-TZP and Ti for dental use. However, the strength of zirconia is good, but comparatively lesser than that of titanium³²⁾.

The fracture toughness, K_{IC} , of Y-TZP is 6–8 MPa m^{1/2}, which is much higher than that of Al₂O₃, at 3.1–5.5 MPa m^{1/2}. Therefore, Y-TZP is believed to be a high-fracture-toughness material, and called “white metal.” However, this toughness value is still one order smaller than that of CP Ti, at 66 MPa m^{1/2}. In addition, the notch stability is generally low in ceramics. One-piece zirconia abutments exhibit a significantly lower fracture resistance than titanium abutments. The mode of failure is specific to the abutment material and design, with the zirconia abutment fracturing before the retentive abutment screw⁴⁸⁾.

There is no periodontal ligament between the implant fixture and alveolar bone, so the absorption of occlusal force is necessary. Therefore, Young's modulus is an important property for dental implants because materials with low Young's modulus can absorb occlusal pressure and occlusal force is not conducted directly to the alveolar bone. The Young's modulus for CP Ti and α + β -type Ti alloys is 100–110 GPa and that of β -type Ti alloys is 40–90 GPa. However, β -type Ti alloys show small strength. It is difficult to simultaneously obtain both small Young's modulus and large tensile strength.

On the other hand, Young's modulus of ZrO₂ is 210 GPa, which increases with the increase in the strength of Y₂O₃ up to 280 GPa.

A large Young's modulus generates the difficulty of fastening screw because screwing fixation is achieved by the elastic deformation of a screw. In abutment, the screwing part is sometimes loosened because the screw fixation is achieved by the elastic deformation of the screwing material and substrate material. The axial force generated by elastic deformation is predominant to the fix. Therefore, Y-TZP has a problem of fixation by screwing.

CHEMICAL STABILITY AND REACTIVITY

Zirconia

Zirconia is categorized as an inert ceramic, as per all biomaterials textbooks. Therefore, to improve adhesion strength to bonding reagents, the surfaces of Y-TZP are treated by mechanical surface modification^{49,50)} followed by chemical surface treatment^{51,52)}. The commonly used mechanical surface modifications include Al₂O₃ sandblasting or tribochemical silica coating. The surface is then cleaned by alcohol and water, and then dried. Thereafter, the chemical surface treatment is performed by applying a primer treatment, including 10-methacryloyloxydecyl dihydrogen phosphate (MDP)^{53,54)}. The phosphate groups of MDP interact with the hydroxyl groups on the zirconia surface by hydrogen bonding. The problem with this treatment is that it may decrease the durability of zirconia by creating micro-cracks or inducing a phase transformation on the Y-TZP surface. Closer investigations of the zirconia surface may provide insight into the surface treatment process. Zirconia does not bond to other materials without surface treatment.

Metal oxides including ZrO₂ form hydroxyl groups on themselves because of a reaction with moisture in the air, as shown in Fig. 4A⁵⁵⁾. These hydroxyl groups dissociate in aqueous solutions, such as body fluid, to form electric charges⁵⁵⁻⁵⁷⁾. These charges depend on the pH of the surrounding solution, and are balanced between positive and negative at a certain pH, as shown in Fig. 4B. This pH is defined as the point of zero charge (PZC), which is a unique value depending on each oxide and an indicator of the acidic or basic property of the surface. For ZrO₂, PZC is 3.6–4.2⁵⁸⁾. Therefore, the surface of ZrO₂ in the

Fig. 4 Formation of hydroxyl group on metal oxide (A) and dissociation of surface hydroxyl group on metal (B).

human body is relatively alkaline.

The concentration of the surface hydroxyl group on the (100), (110), and (111) planes of single-crystalline zirconia⁵⁹⁾ and Y-TZP⁶⁰⁾ increases after immersion in water. The (110) plane preferentially reacts with water molecules, which is explained by the oxygen atom position of the (110) crystalline plane. In addition, phosphate ions are incorporated in the zirconia surfaces in Hanks' solution. However, the numbers of hydroxyl and phosphate groups formed on the surface of Y-TZP are smaller than those formed on titanium. In addition, calcium ion is not confirmed on the Y-TZP surface. The above results are similar to those obtained for metallic zirconium⁶¹⁾.

Titanium

Titanium is an excellent corrosion-resistant material. Ti element itself is extremely active, resulting in a low standard electrode potential of -1.63 V vs. NHE in the reaction $\text{Ti} \rightarrow \text{Ti}^{2+} + 2\text{e}^-$. This activity induces chemical stability due to immediate stabilization by a reaction with the environment. The resultant stability leads to difficulty in smelting, a high corrosion resistance, and safety issues in the human body. The corrosion resistance of CP Ti is very high⁶²⁻⁶⁵⁾ because the Ti atom immediately reacts with water molecules in aqueous solutions and moisture in the air, and forms a very thin titanium oxide film on its surface. This oxide film is immediately repaired even when it is ruptured by scratching; hence, the reaction of the Ti atom with the external environment is inhibited, resulting in apparent inactivity of CP Ti and Ti alloys. This property directly contributes to their corrosion resistance and safety. The surface oxide film on CP Ti mainly consists of amorphous or low-crystalline and non-stoichiometric TiO_2 . As a considerable portion of oxidized titanium remains as Ti^{2+} and Ti^{3+} in the surface oxide film, the oxidation process can only be fully completed on the uppermost part of the surface film.

One of the reasons for the excellent biocompatibility

of titanium is the excellent corrosion resistance, which, however, is not a sufficient condition for biocompatibility. Even the best corrosion-resistant metal, Au, is inferior in tissue compatibility. In addition, electric plating of platinum to CP Ti improves the corrosion resistance but depletes bone formation⁶⁶⁾, because the surface property of CP Ti is shielded and the bone formation ability is prevented. These results reveal that hard-tissue compatibility is not induced only by the corrosion resistance. In other words, corrosion resistance is a necessary, but not sufficient, condition for biocompatibility; there are other contributing factors.

In case of TiO_2 , the PZC of rutile is 5.3 and that of anatase is 6.2⁵⁷⁾; therefore, TiO_2 does not show an outstanding acid or basic property but shows almost a neutral property. The concentration of surface hydroxyl groups on TiO_2 is relatively large $\sim 4.9\text{--}12.5$ nm⁻²^{56,67)}. After immersion in an aqueous solution, this concentration or wettability increases, which promotes the adsorption of proteins such as integrin and cytokine.

The composition and chemical state of a surface oxide film vary according to the surrounding environment, while the film is macroscopically stable. A passive film undergoes continuous partial dissolution and re-precipitation in the electrolyte from the microscopic viewpoint. Hence, in this sense, the surface composition is always changing according to the environment⁶⁸⁾. CP Ti and Ti alloys easily form calcium phosphates on themselves in a biological environment and sulfite and sulfide, especially under a cell culture⁶⁹⁻⁷³⁾. CP Ti is stabilized after the formation of calcium phosphate in Hanks' solution⁶¹⁾. In addition, calcium and phosphorus are detected at the interface between CP Ti and bone tissue⁷⁴⁻⁷⁶⁾. One of the reasons for the excellent hard-tissue compatibility in titanium may be its ability to form calcium phosphate. Bone screws and nails made of Ti alloys form callus during implantation; consequently, the bone is sometimes re-fractured when the devices are retrieved⁷⁷⁾. Therefore, when devices must be retrieved

after healing, they are made of 316L-type stainless steel. This assimilation occurs due to the excellent hard tissue compatibility of Ti alloys. A proper surface treatment may inhibit bone formation and bonding of the Ti alloy-contacting bone tissue.

BACTERIAL ADHESION

The adhesion of oral bacteria to zirconia *in vitro* is evaluated from the viewpoint of orthopedics⁷⁸. Zirconia reduces plaque formation on the implant surface, which leads to good healing and a successful implant treatment³². Some difference in the inhibition of growth and adhesion of selected oral bacteria on titanium and zirconia *in vitro* were observed and the plaque formation on the zirconia surface might be less than that on the titanium surface^{79,80}. Zirconia showed a significantly lesser adhesion of bacteria than titanium in an *in vivo* study^{81,82}. In the analysis of 20 healthy participants, titanium-related sites presented the highest total microbial count and higher counts of pathogenic species⁸³. Compared to titanium, zirconia abutments may represent a material surface less attractive for early plaque retention⁸⁴.

On the other hand, the bacterial adhesion to zirconia was similar to that to titanium^{79,82}. There was no significant difference in bacteria adhesion between titanium and zirconia *in vitro* when titanium and zirconia coating with saliva were incubated with *Streptococcus sanguis*⁸⁵. Titanium- and zirconia-related surfaces are promptly colonized by a bacterial community similar to those found in the remaining adjacent teeth, suggesting a selective adhesion of different bacterial genotypes for titanium or zirconia surfaces⁸⁶. In a biofilm formation test, zirconia implant surfaces with low surface roughness are comparable to titanium surfaces with respect to the initial bacterial adhesion and biofilm formation⁸⁷. In addition, both titanium and zirconia groups presented similar microbial counts and diversity over time, and the microbiota was very similar to that colonizing the remaining teeth. Clinical findings were consistent with a healthy condition with no significant difference regarding marginal bone loss between zirconia and titanium⁸⁸.

According to the above references, zirconia is superior or similar to inhibiting bacterial adhesion against titanium. Therefore, zirconia is an appropriate abutment of the implant from the viewpoint of bacterial adhesion.

BONE FORMATION AND BONE BONDING

CP Ti shows a unique property, “osseointegration,” among metals, which is defined as the “formation of a direct interface between an implant and bone, without intervening soft tissue. No scar tissue, cartilage or ligament fibers are present between the bone and implant surface. The direct contact of bone and implant surface can be verified microscopically”⁸⁹. This concept generated and significantly accelerated studies on the

reaction between hard tissue and CP Ti, followed by those on surface treatment. In this sense, the term “osseointegration” is invented for the CP Ti implant. Extensive research on the hard-tissue compatibility of Ti has been reported; introducing everything is outside the scope of this review, and hence, readers are directed to a book in which this is reviewed⁴⁶. The excellent hard-tissue compatibility of CP Ti was confirmed by studies on the formation ability of calcium phosphate in simulated body fluids; evaluation of osteoblast activity and calcification; histological and molecular-biological evaluation of titanium implanted in animals, in terms of bone formation, bone contacting rate, and bone bonding strength; and clinical results. The above results revealed that, when CP Ti is implanted in bone, the surrounding tissue contacts the titanium surface in an early stage and the bone bonding strength is high. Important factors governing hard-tissue compatibility are the adhesion and proliferation of osteogenic cells because of factors such as surface morphology (roughness) and wettability. Bone formation occurs in the inflammatory response period, osteoblast induction period, and bone formation period. The surfaces of titanium implants and the titanium-bone interface reaction have been characterized to explain the importance of surface morphology, wettability, and energy for osseointegration^{90,91}. The surface of titanium implants stored for a long time after manufacturing becomes contaminated and the bone conduction ability decreases during storage⁹².

On the other hand, research on zirconia dental implants has been reviewed^{32,93}. Most of the studies investigated bone-to-implant contact (BIC) around zirconia in rabbits, pigs, dogs, sheep, and rats, and showed that zirconia implants exhibit excellent BIC⁹⁴.

Several studies have revealed that zirconia implants show comparable osseointegration to titanium implants. When the BIC of zirconia implants was compared with those of titanium and alumina, there was no statistical difference among the BICs of the three types of implants⁹⁵. In addition, no difference in osseointegration between the acid-etched zirconia and titanium implants was observed⁹⁶⁻⁹⁸. The coated zirconia and titanium implants showed a higher removal torque than the machined zirconia implants, suggesting that surface-modified zirconia implants can attain high stability in bones⁹⁹. There is no significant influence of the evaluated zirconia and titanium on the outcomes of interest. Comparing different animal models, significant differences for the evaluated variables were found¹⁰⁰. When four zirconia and four titanium implants were placed in New Zealand white male rabbits, the percentage of implant surface covered with bone was comparable for the two materials. A similar rate of bone apposition on zirconia- and surface-modified titanium implant surfaces during early healing was obtained¹⁰¹. Zirconia showed comparable biological responses of osteoblast-like cells to titanium for a short time during the cell culture period. Most genes related to cell adhesion and signal showed a similar expression level between titanium and zirconia¹⁰². No significant

Table 4 Method and results of review papers comparing properties of zirconia with those of titanium

Title	Author and reference	Method	Conclusions
Zirconia dental implants: A literature review	Özkurt and Kazazoğlu, 2011 ⁹³⁾	This review started with a PubMed search from 1975 to 2009. The inclusion criteria for articles were as follows: (1) Articles were related to zirconia dental implants and (2) abstracts were obtained when the full texts could not be obtained. Articles on zirconia implants for orthopedic usage were excluded from the review.	On the basis of available peer-reviewed data, osseointegration of zirconia dental implants may be comparable with that of titanium implants. They were also found to have low, well-distributed, and similar stress distribution when compared to titanium implants. The surface roughness of zirconia was found to be comparable to that of titanium implants.
Zirconia in dental implantology: A review	Apratim <i>et al.</i> , 2015 ³²⁾	Literature was searched to retrieve information about zirconia dental implant and studies were critically analyzed. PubMed database was searched for information about zirconia dental implant regarding mechanical properties, osseointegration, surface roughness, biocompatibility, and soft tissue health around it. The literature search was limited to English language articles published from 1975 to 2015.	Some of the properties of zirconia seem to be suitable for making it an ideal dental implant, such as biocompatibility, osseointegration, favorable soft-tissue response, and esthetics due to light transmission and its color. It was also found that most of the studies on zirconia dental implants are short-term studies and there is a need for more long-term clinical trials to prove that zirconia is worth enough to replace titanium as a biomaterial in dental implantology.
Osseointegration of zirconia dental implants in animal investigations: A systematic review and meta-analysis	Pieralli <i>et al.</i> , 2018 ¹⁰⁰⁾	Data on the osseointegration rate were extracted considering BIC, removal torque analysis (RTQ), and push-in tests. Meta analyses were conducted using multilevel multivariable mixed-effect linear regression models. The Sidak method was used in case of multiple testing. Sources. An electronic screening of the literature (MEDLINE/Pubmed, Cochrane Library and Embase) and a supplementary manual search were performed.	No significant influence of the evaluated bulk materials on the outcomes of interest could be detected. When comparing different animal models, significant differences for the evaluated variables could be found. These results might be of interest for the design of further animal investigations.
Biological effect of the abutment material on the stability of pre-implant marginal bone levels: A systematic review and meta-analysis.	Sanz-Sánchez <i>et al.</i> , 2018 ¹⁰³⁾	A protocol was developed to answer the following question: “What is the effect of the abutment material on stability and health of the peri-implant hard tissues?” Randomized controlled trials (RCTs), controlled clinical trials (CCTs), or prospective case series (CS) with at least 6 months of follow-up were included, and meta-analyses were performed to compare abutment materials with titanium and to evaluate the impact of various abutment materials on bone changes (primary outcome), probing depth, plaque levels, and pre-implant mucosal inflammation.	Twenty-nine publications from 33 investigations were included. Results from the meta-analyses demonstrated no significant differences between the different abutment materials when compared to titanium, in regard to the changes in marginal bone levels. The meta-analysis reported a significantly greater increase in bleeding on probing for titanium compared to zirconia abutments. When evaluating the behavior of each material different from titanium, there was a significant bone loss over time for all individual materials except for titanium nitride. This systematic review has shown that the abutment material has minimal impact on marginal bone levels when compared to the standard titanium.

Table 4 continued

Title	Author and reference	Method	Conclusions
Is zirconia a viable alternative to titanium for oral implant? A critical review	Sivaraman <i>et al.</i> , 2018 ¹⁵⁾	The literature search for articles in PubMed and Cochrane Library database from 1990 till December 2016.	Zirconia implants are a promising alternative to titanium with a superior soft-tissue response, biocompatibility, and esthetics with comparable osseointegration. However, further long-term longitudinal and comparative clinical trials are required to validate zirconia as a viable alternative to the titanium implant.
Zirconia compared to titanium dental implants in preclinical studies—A systematic review and meta-analysis	Roehling <i>et al.</i> , 2019 ¹¹³⁾	In March 2017, electronic (MEDLINE, EMBASE) and hand search was performed to identify preclinical studies comparing zirconia and titanium implants. Primary outcomes were BIC, RTQ, and push-in (PI) measurements. Secondary outcomes included biologic width (BW) dimensions.	Zirconia and titanium implants demonstrate a similar soft and hard tissue integration capacity. However, titanium tended to show a faster initial osseointegration process compared to zirconia. Importantly, not only material characteristics but predominantly animal species and study protocols can significantly influence the outcomes.
Zirconia abutments in the anterior region: A systematic review of mechanical and esthetic outcomes	Naveau <i>et al.</i> , 2019 ¹²⁴⁾	An electronic search was conducted in Medline (PubMed) for studies on zirconia abutments. All clinical studies with at least a 1-year follow-up and case series (>5 abutments) published after 2013 were included. Mechanical and esthetic outcomes were collected.	No difference was found between prefabricated and custom abutments or internal and external implant connections regarding fractures or screw loosening. All authors reported “good to excellent” esthetic integration in terms of restorations and soft-tissue color and the presence and height of papillae. The most difficult esthetic parameters to achieve were root convexity, soft-tissue color, and texture and level of mucosa.

difference between zirconia and titanium was observed regarding changes in the marginal bone levels. A zirconia abutment had minimal impact on marginal bone levels when compared to the standard titanium¹⁰³⁾. Collagen fiber orientation was similar, regardless of the implant material, demonstrating a predominantly parallel or parallel-oblique pattern¹⁰⁴⁾. On the basis of the available peer-reviewed data, the osseointegration of zirconia dental implants may be comparable with that of titanium implants⁹³⁾.

On the other hand, some papers have demonstrated the preference of zirconia over titanium. Bone healing around zirconia implants was found to be relatively more than that around titanium implants¹⁰⁵⁾. A similar rate of bone apposition on zirconia and surface-modified titanium implant surfaces during early healing was found when a histological examination of early bone apposition around zirconia dental implants at 2 and 4 weeks after insertion was compared to that of surface-modified titanium implants¹⁰⁶⁾.

On the contrary, several studies have supported the excellence of titanium for osseointegration compared to zirconia. The removal torque values of machined zirconia implants, sandblasted zirconia implants, and acid-etched titanium implants were evaluated. Machined

zirconia showed the least removal torque value, while acid-etched titanium implants showed the highest value, followed by sandblasted zirconia implants¹⁰⁷⁾. Comparing the biomechanical properties of six types of implant surfaces, the removal torque value of zirconia implants was the least¹⁰⁸⁾. Zirconia implants are not currently recommended because their clinical use lacks scientific support¹⁰⁹⁾. Compared to titanium, zirconia is inferior in osseointegration and requires improvement by surface modification. The removal torque value of zirconia implants was improved after surface modification, but was not more than that of titanium implants. It is known that Y-TZP is not capable of bonding chemically with hard tissues directly^{110,111)}. The bone tissue response throughout the healing periods was characterized by a constant bone remodeling accompanied by resorption of the old bone in favor of the new bone formation at both titanium and zirconia implants. Surface roughness had a positive effect on BIC, although not showing statistical significance. Due to the poor survival rate, the experimental zirconia implants investigated may not be suitable for clinical use¹¹²⁾. Titanium tended to show a faster initial osseointegration process compared to zirconia¹¹³⁾. At 12 weeks, the only significant difference in the removal torque was between titanium and

sandblasted zirconia, with titanium demonstrating the higher value⁵⁰). The adhering U2OS osteoblast cells were significantly more displaced from differently modified titanium surfaces by challenging sub-gingival pathogens than those from Ti-Zr alloys and zirconia variants¹¹⁴. BMP4 and 7 are more expressed in osteoblasts exposed to the CP Ti surface, suggesting that the CP Ti surfaces can provide some advantages to immediate load implantology¹¹⁵).

Although titanium shows superior osseointegrative property than zirconia, zirconia shows almost the same gratitude of osseointegration after surface treatment. Surface roughness is the most predominant factor governing osseointegration. The methods and results of review papers corresponding to this review are summarized in Table 4. Most of them revealed that titanium is superior for osseointegration than zirconia, followed by the comments that more studies are necessary.

SOFT-TISSUE ADHESION

The adhesion of soft tissue to materials is necessary when they are used as abutments in dental implant systems. If the adhesion between the device and soft tissue is not sufficient, bacteria can invade the interface between the junctional epithelium; this results in irritation between the device and bacteria, thereby causing the implant to loosen, shake, and fall out.

Some studies have revealed that soft tissue adhesion to zirconia is comparable to that to titanium. Zirconia abutments were attached to soft tissues in a clinical study and there was no loosening and fracture of the abutment screw over three years¹¹⁶). The collagen fiber orientation around zirconia implants was parallel to the implant surface, similar to that in the case of titanium¹⁰⁴. Zirconia showed similar probing depth to titanium⁷⁹). The distance from the peri-implant mucosa to the apical termination of the barrier epithelium for zirconia was less than that for titanium, and zirconia had less mucosal color change as compared to titanium. On the other hand, healing of soft tissue around the titanium abutment was better than that around the zirconia abutment^{117,118}). There was no significant difference in the soft tissue response between zirconia and titanium abutments¹¹⁹). When zirconia and titanium implants were inserted in the extraction sites of monkeys, both implants showed the same peri-implant soft tissue dimensions¹²⁰).

On the other hand, some studies have demonstrated the merit of zirconia to soft tissue compatibility. Zirconia showed favorable interaction with the soft tissue³²). A high-wettability surface of zirconia using a CO₂ laser is important to cell adhesion⁸²). In addition, zirconia showed superior soft tissue integration compared to titanium for an oral implant in terms of reaction to bacteria^{15,121}). The presence of more remodeling and/or inflammatory phenomena around titanium implant abutments than those around zirconia abutments of a different design was observed during the early stages but not at 1 year¹²²).

One study showed the merit of titanium for soft tissue adhesion. Smooth titanium implant surfaces provide the best opportunities for a soft tissue seal to form on bacterially contaminated implant surfaces¹²³).

CONCLUSIONS

The mechanical property of titanium is superior to that of zirconia, while some studies have shown that zirconia is acceptable for use as a dental implant, especially for abutment. The current surface treatment research has been focusing on inhibiting bacterial adhesion and improving osseointegration and soft tissue adhesion, which make it difficult to evaluate the properties of materials themselves without surface treatment. The osseointegration of titanium is superior to that of zirconia itself without surface treatment, while surface morphology is a more important factor for osseointegration than surface composition. In the case of bacterial adhesion, zirconia is superior to titanium, suggesting that it is suitable for abutments. On the other hand, both materials show similar property for soft tissue adhesion. We would like to demonstrate again that all materials have both advantages and disadvantages, so optimal materials must be selected according to the purpose.

ACKNOWLEDGMENTS

The projects “Creation of Life Innovation Materials for Interdisciplinary and International Researcher Development” and “Cooperative project amount medicine, dentistry, and engineering for medical innovation—Construction of creative scientific research of the viable material *via* integration of biology and engineering” were supported by the Ministry of Education, Culture, Sports, Science and Engineering, Japan.

REFERENCES

- 1) Audley JA. The use of zirconia as a refractory material. *Nature* 1917; 99: 375-376.
- 2) Scott HG. Phase relationships in the zirconia-yttria system. *J Mater Sci* 1975; 10: 1527-1535.
- 3) Turp V, Tuncelli B, Sen D, Goller G. Evaluation of hardness and fracture toughness, coupled with microstructural analysis, of zirconia ceramics stored in environments with different pH values. *Dent Mater J* 2012; 31: 891-902.
- 4) Lange FF. Transformation toughening. *J Mater Sci* 1982; 17: 225-234.
- 5) Ashizuka M, Kiyohara H, Ishida E, Kuwabara M, Kubota Y, Tsukidate T. Fatigue behavior of Y₂O₃-partially stabilized zirconia. *Yogyo-Kyokai-Shi* 1986; 94: 432-439. (in Japanese)
- 6) Denry I, Kelly JR. State of the art of zirconia for dental applications. *Dent Mater* 2008; 24: 299-307.
- 7) Piconi C, Maccauro G. Zirconia as a ceramic biomaterial. *Biomaterials* 1999; 20: 1-25.
- 8) Gupta TK, Bechtold JH, Kuznicki RC, Cadoff LH, Rossing BR. Stabilization of tetragonal phase in polycrystalline zirconia. *J Mater Sci* 1977; 12: 2421-2426.
- 9) Gupta TK, Lange FF, Bechtold JH. Effect of stress-induced phase transformation on the properties of polycrystalline zirconia containing metastable tetragonal phase. *J Mater Sci*

- 1978; 13: 1464-1470.
- 10) Pascual C, Jurado JR, Duran P. Electrical behavior of doped-yttria stabilized zirconia ceramic materials. *J Mater Sci* 1983; 18: 1315-1322.
- 11) Gravie RC, Hannink RH, Pascoe RT. Ceramic steel? *Nature* 1975; 258: 703-704.
- 12) Hulbert SF. The use of alumina and zirconia in surgical implants. In: Hench LL, editor. *An introduction to bioceramics*. Singapore: World Scientific; 1993. pp. 25-40.
- 13) Clarke IC, Manaka M, Green DD, Williams P, Pezzotti G, Kim YH, *et al*. Current status of zirconia used in total hip implants. *J Bone Joint Surg Am* 2003; 85: 73-84.
- 14) Helmer JD, Driskell TD. Research on bioceramics. Symp. on Use of Ceramics as Surgical Implants. SC, USA; Clemson University; 1969.
- 15) Sivaraman K, Chopram A, Narayan AI, Balakrishnan D. Is zirconia a viable alternative to titanium for oral implant? A critical review. *J Prosthodont Res* 2018; 62: 121-133.
- 16) Ueda K. Zirconia powder. *J Dent Mater* 2016; 35: 261-264. (in Japanese)
- 17) Bothe RT, Beaton LE, Davenport HA. Reaction of bone to multiple metallic implants. *Surg Gynec Obsstet* 1940; 71: 598-602.
- 18) Leventhal GS. Titanium, a metal for surgery. *J Bone Joint Surg Am* 1951; 33A: 473-474.
- 19) Beder OE, Stevenson JK, Jones TW. A further investigation of the surgical application of titanium metal in dogs. *Surgery* 1957; 41: 1012-1015.
- 20) Williams DF. Titanium and Titanium Alloys. In: Williams DF, editor. *Biocompatibility of Clinical Implant Materials*. Boca Raton, FL, USA: CRS Press; 1982. pp. 10-44.
- 21) Williams DF. Biological Effects of Titanium. In: Williams DF, editor. *Systematic Aspects of Biocompatibility*. Boca Raton, FL, USA: CRS Press; 1982. pp. 170-177.
- 22) Pillar RM, Weatherly GC. Development in Implant Alloys. In: Williams DF, editor: *Clinical Reviews in Biocompatibility*, Vol. 1, Boca Raton, FL, USA: CRC Press; 1982. pp. 371-473.
- 23) Semlitsch M, Staub F, Weber H. Titanium-aluminum-niobium alloy development for biocompatible, high strength surgical implants. *Biomed Tech* 1985; 30: 334-339.
- 24) Rao VB, Houska CR. Kinetics of the phase-transformation in a Ti-15Mo-5Zr-3Al alloy as studied by X-ray-diffraction. *Metal Trans A* 1979; 10: 355-358.
- 25) Wang K, Gustavson L, Dumbleton J. Low modulus, high strength, biocompatible titanium alloy for medical implants. In: Froes FH, Caplan HL, editors. *Titanium '92: Science and Technology*, Warrendale, PA, USA: TMS; 1993. pp. 2697-2704.
- 26) Zardiackas LD, Mitchell DW, Disegi JA. Characterization of Ti-15Mo beta titanium alloy for orthopaedic implant applications. In: Browns SA, Lemons JE, editors. *Medical Applications of Titanium and Its Alloys*, West Conshohocken, PA, USA: ASTM; 1996. pp. 60-75.
- 27) Fanning JC. Properties and processing of a new metastable beta titanium alloy for surgical implant applications. In: Blenkinsop PA, Evans WJ, Flower H, editors. *Titanium '95: Science and Technology*, Cambridge, UK: The University Press; 1996. pp. 1800-1807.
- 28) Kuroda D, Niinomi M, Morinaga M, Kato Y, Yashiro T. Design and mechanical properties of new b type titanium alloys for implant materials. *Mater Sci Eng A* 1998; A243: 244-249.
- 29) Niinomi M. Design and development of metallic biomaterials with biological and mechanical biocompatibility. *J Biomed Mater Res Part A* 2019; 107A: 944-954.
- 30) Waterstrat RM, Rupp NW, Franklin O. Production of a cast titanium-base partial denture. *J Dent Res* 1978; 57, Special Issue, 254.
- 31) Miura I, Ida K, editors. *Titanium in Dentistry*. Tokyo, Japan: Quintessence; 1988. (in Japanese)
- 32) Apratim A, Eachempati P, Salian KKK, Singh V, Chhabra S, Shah S. Zirconia in dental implantology: A review. *J Int Soc Prev Community Dent* 2015; 5: 147-156.
- 33) Piconi C, Maccauro G. Zirconia as a ceramic biomaterial. *Biomaterials* 1999; 20: 1-25.
- 34) Chai J, Chu FC, Chow TW, Liang BM. Chemical solubility and flexural strength of Zirconia- based ceramics. *Int J Prosthodont* 2007; 20: 587-595.
- 35) Yilmaz H, Aydin C, Gul BE. Flexural strength and fracture toughness of dental core ceramics. *J Prosthet Dent* 2007; 98: 120-128.
- 36) Qeblawi DM, Muñoz CA, Brewer JD, Monaco EA Jr. The effect of zirconia surface treatment on flexural strength and shear bond strength to a resin cement. *J Prosthet Dent* 2010; 103: 210-220.
- 37) Kohal RJ, Wolkewitz M, Tsakona A. The effects of cyclic loading and preparation on the fracture strength of zirconium-dioxide implants: An in vitro investigation. *Clin Oral Implants Res* 2011; 22: 808-814.
- 38) Chevalier J, Gremillard L, Virkar AV, Clarke DR. The tetragonal-monoclinic transformation in zirconia: Lessons learned and future trends. *J Am Ceram Soc* 2009; 92: 1901-1920.
- 39) Suresh A, Mayo MJ, Porter WD, Rawn CJ. Crystallite and grain-size-dependent phase transformations in Yttria-Doped zirconia. *J Am Ceram Soc* 2003; 86: 360-362.
- 40) Garvie RC, Hannink RH, Pascoe RT. Ceramic steel? *Nature* 1975; 258: 703-704.
- 41) Sato T, Shimada M. Transformation of Yttria-Doped tetragonal ZrO₂ polycrystals by annealing in water. *J Am Ceram Soc* 1985; 68: 356-359.
- 42) Chevalier J. What future for zirconia as a biomaterial? *Biomaterials* 2006; 27: 535-543.
- 43) Deville S, Chevalier J, Gremillard L. Influence of surface finish and residual stresses on the ageing sensitivity of biomedical grade zirconia. *Biomaterials* 2000; 27: 2186-2192.
- 44) Watanabe M, Iio S, Fukuura I. Ageing behaviour of Y-TZP. In: Claussen N, Ruhle M, Heuer AH, editors. *Science and Technology of Zirconia II (Advances in Ceramics)* Vol. 12. Columbus, OH, USA: The American Ceramic Society; 1984. pp. 391-398.
- 45) Att W, Grigoriadou M, Strub JR. ZrO₂ three-unit fixed partial dentures: Comparison of failure load before and after exposure to a mastication simulator. *J Oral Rehabil* 2007; 34: 282-290.
- 46) Brunette DM, Tenvall P, Textor M, Thomsen P, editors. *Titanium in medicine*. Berlin, Germany: Springer; 2001.
- 47) Leyens C, Peters M, editors. *Titanium and titanium alloys*, Köln, Germany: Wiley-VCH; 2003.
- 48) Foonq JK, Judqu RB, Palamara JE, Swain MV. Fracture resistance of titanium and zirconia abutments: an in vitro study. *J Prosthet Dent* 2013; 109: 304-312.
- 49) Schliephake H, Hefti T, Schlottig F, Gédet P, Staedt H. Mechanical anchorage and peri-implant bone formation of surface-modified zirconia in minipigs. *J Clin Periodontol* 2010; 37: 818-828.
- 50) Hoffmann O, Angelov N, Zafiropoulos GG, Andreana S. Osseointegration of zirconia implants with different surface characteristics: an evaluation in rabbits. *Int J Oral Maxillofac Implant* 2012; 27: 352-358.
- 51) Inokoshi M, Minakuchi S. Bond strategy for zirconia ceramics. *J J Dent Mater* 2016; 35: 265-268. (in Japanese)
- 52) Cooper FL, Stanford C, Feine J, McGuire M. Prospective assessment of CAD/CAM zirconia abutment and lithium disilicate crown restorations: 2.4 year results. *J Prosthodont Dent* 2016; 116: 33-39.
- 53) Hao L, Lawrence J, Chian KS. Osteoblast cell adhesion on a laser modified zirconia based bioceramic. *J Mater Sci Mater Med* 2005; 16: 719-726.
- 54) Miyake N, Miura T, Tanabe K, Hisanaga R, Yamashita S,

- Sato T, *et al.* Effect of physicochemical surface modifications on bovine serum albumin adsorption to tetragonal zirconia polycrystal in vitro through the change of the zeta potential. *J Oleo Sci* 2016; 65: 1003-1010.
- 55) Boehm HP. Functional groups on the surfaces of solids. *Angew Chem* 1966; 5: 533-544.
  - 56) Boehm HP. Acidic and basic properties of hydroxylated metal oxide surfaces. *Discuss Faraday Soc* 1971; 52: 264-289.
  - 57) Parfitt GD. The surface of titanium dioxide. *Prog Surf Membr Sci* 1976; 11: 181-226.
  - 58) Muhammad S, Hussain ST, Waseem M, Naeem A, Hussain J, Tariq Jan M. Surface charge properties of zirconium oxide. *Iran J Sci Technol A* 2012; A4: 481-486.
  - 59) Oishi M, Tsutsumi Y, Chen P, Ashida M, Doi H, Hanawa T. Surface changes of yttria-stabilized zirconia in water and Hanks solution characterized using XPS. *Surf Interface Anal* 2018; 50: 587-591.
  - 60) Oishi M, Tsutsumi Y, Chen P, Nakaishi M, Ashida M, Doi H, *et al.* Surface characterization of commercially available yttria-stabilized tetragonal zirconia polycrystalline in water and Hanks' solution using XPS. *Dent Mater J* 2019; 38: 496-504.
  - 61) Tsutsumi Y, Nishimura D, Doi H, Nomura N, Hanawa T. Difference in surface reactions between titanium and zirconium in Hanks' solution to elucidate mechanism of calcium phosphate formation on titanium using XPS and cathodic polarization. *Mater Sci Eng C* 2009; 29: 1702-1708.
  - 62) Nakayama Y, Yamamuro T, Kotoura Y, Oka M. In vivo measurement of anodic polarization of orthopaedic implant alloys: comparative study of in vivo and in vitro experiments. *Biomaterials* 1989; 10: 420-414.
  - 63) Asri RIM, Harun WSW, Samykano M, Lah NAC, Ghani SAC, Tarlochan F, *et al.* Corrosion and surface modification on biocompatible metals: A review. *Mater Sci Eng C* 2017; 77: 1261-1274.
  - 64) Manam NS, Harun WSW, Shri DNA, Ghani SAC, Kurniawan T, Ismail MH. Study of corrosion in biocompatible metals for implants: A review. *J Alloys Compd* 2017; 701: 698-715.
  - 65) Eliaz N. Corrosion of metallic biomaterials: A Review. *Materials* 2019; 12: 407.
  - 66) Itakura Y, Tajima T, Oho S, Matsuzawa J, Sudo H, Yamamoto S. Osteocompatibility of platinum-plated titanium assessed in vitro. *Biomaterials* 1989; 10: 489-493.
  - 67) Westall J, Hohl H. A comparison of electrostatic models for the oxide/solution interface. *Adv Colloid Interface Sci* 1980; 12: 265-294.
  - 68) Kelly EJ. Electrochemical behavior of titanium. *Mod Aspect Electrochem* 1982; 14: 319-424.
  - 69) Hanawa T, Ota M. Calcium phosphate naturally formed on titanium in electrolyte solution. *Biomaterials* 1991; 12: 767-774.
  - 70) Hanawa T, Ota M. Characterization of surface-film formed on titanium in electrolyte using XPS. *Appl Surf Sci* 1992; 55: 269-276.
  - 71) Healy KE, Ducheyne P. The mechanisms of passive dissolution of titanium in a model physiological environment. *J Biomed Mater Res* 1992; 26: 319-338.
  - 72) Serro AP, Fernandes AC, Saramago B, Lima J, Barbosa MA. Apatite desorption on titanium surfaces —The role of albumin adsorption. *Biomaterials* 1977; 18: 963-968.
  - 73) Hiromoto S, Hanawa T, Asami K. Composition of surface oxide film of titanium with culturing murine fibroblasts L929. *Biomaterials* 2004; 25: 979-986.
  - 74) Sundgren JE, Bodo P, Lundstrom I. Auger electron spectroscopic studies of the interface between human tissue and implants of titanium and stainless steel. *J Colloid Interface Sci* 1986; 110: 9-20.
  - 75) Esposito M, Lausmaa J, Hirsch JM, Thomsen P. Surface analysis of failed oral titanium implants. *J Biomed Mater Res* 1999; 48: 559-568.
  - 76) Sundell G, Dahlin C, Andersson M, Thuvander M. The bone-implant interface of dental implants in humans on the atomic scale. *Acta Biomater* 2017; 48: 445-450.
  - 77) Sanderson L, Ryan W, Turner PG. Complications of metalwork removal injury. *Injury* 1992; 23: 29-30.
  - 78) Hisbergues M, Vendeville S, Vendeville P. Zirconia: Established facts and perspectives for a biomaterial in dental implantology. *J Biomed Mater Res B Appl Biomater* 2009; 88: 519-529.
  - 79) van Brakel R, Cune MS, van Winkelhoff AJ, de Putter C, Verhoeven JW, van der Reijden W. Early bacterial colonization and soft tissue health around zirconia and titanium abutments: An in vivo study in man. *Clin Oral Implants Res* 2011; 22: 571-577.
  - 80) Re D, Pellegrini G, Francinetti P, Augusti D, Rasperini G. In vivo early plaque formation on zirconia and feldspathic ceramic. *Minerva Stomatol* 2011; 60: 339-348.
  - 81) Rimondini L, Cerroni L, Carrassi A, Torricelli P. Bacterial colonization of zirconia ceramic surfaces: An invitro and in vivo study. *Int Oral Maxillofac Implants* 2002; 17: 793-798.
  - 82) Scarano A, Piattelli M, Caputi S, Favero GA, Piattelli A. Bacterial adhesion on commercially pure titanium and zirconium oxide disks: An in vivo human study. *J Periodontol* 2004; 75: 292-296.
  - 83) Nascimento C, Pita MS, Santos ES, Monesi N, Pedrazzi V, Albuquerque Jr RF, *et al.* Microbiome of titanium and zirconia dental implant abutments. *Dent Mater* 2016; 32: 93-101.
  - 84) Nakamura K, Kanno T, Mikkeding P, Ortengren U. Zirconia as a dental implant abutment materials: A systematic review. *Int J Prosthodont* 2010; 23: 299-309.
  - 85) Lee BC, Jung GY, Kim DJ, Han JS. Initial bacterial adhesion on resin, titanium and zirconia in vitro. *J Adv Prosthodont* 2011; 3: 81-84.
  - 86) de Freitas AR, de Oliveira Silva TS, Ribeiro RF, de Albuquerque Jr RF, Pedrazzi V, do Nascimento C. Oral bacterial colonization on dental implants reported with titanium or zirconia abutments: 6-month follow-up. *Clin Oral Investig* 2018; 22: 2335-2343.
  - 87) Al-Ahmad A, Karygianni L, Wartenhorst MS, Bächle M, Hellwig E, Follo M, *et al.* Bacterial adhesion and biofilm formation on yttria-stabilized, tetragonal zirconia and titanium oral implant materials with low surface roughness —an in situ study. *J Med Microbiol* 2016; 65: 596-604.
  - 88) Raffaini FC, Freitas AR, Silva TSO, Cavagioni T, Oliveira JF, Albuquerque RF, *et al.* Genome analysis and clinical implications of the bacterial communities in early biofilm formation on dental implants restored with titanium or zirconia abutments. *Biofouling* 2018; 34: 173-182.
  - 89) Brånemark PI, Hansson BO, Adell R, Breine U, Lindström J, Hallén O, *et al.* Osseointegrated implants in the treatment of the edentulous jaw. Experience from a 10-year period. *Scand J Plastic Reconstruct Surg Hand Surg* 1977; 11 (Suppl 16): 1-132.
  - 90) Rupp F, Liang L, Geis-Gerstorfer J, Scheideler L, Hüttig F. Surface characteristics of dental implants: A review. *Dent Mater* 2018; 34: 40-57.
  - 91) Shah FA, Thomsen P, Palmquist A. A review of the impact of implant biomaterials on osteocytes. *J Dent Res* 2019; 97: 977-986.
  - 92) Art W, Hori N, Takeuchi M, Ouyang J, Yang Y, Anpo M, *et al.* Time-dependent degradation of titanium osteoconductivity: an implication of biological aging of implant materials. *Biomaterials* 2009; 30: 5352-5363.
  - 93) Özkurt Z, Kazazoglu E. Zirconia dental implants: A literature review. *J Oral Implantol* 2011; 37: 367-376.
  - 94) Siddiqi A, Khan AS, Zafar S. Thirty years of translational research in zirconia dental implants: A systematic review of the literature. *J Oral Implantol* 2017; 43: 314-326.

- 95) Dubruille JH, Viguier E, Le Naour G, Dubruille MT, Auriol M, Le Charpentier Y. Evaluation of combinations of titanium, zirconia, and alumina implants with 2 bone fillers in the dog. *Int J Oral Maxillofac Implants* 1999; 14: 271-127.
- 96) Depprich R, Zipprich H, Ommerborn M, Mahn E, Lammers L, Handschel J, *et al.* Osseointegration of zirconia implants: An SEM observation of the bone-implant interface. *Head Face Med* 2008; 4: 25.
- 97) Gahlert M, Röhling S, Wieland M, Sprecher CM, Kniha H, Milz S. Osseointegration of zirconia and titanium dental implants: A histological and histomorphometrical study in the maxilla of pigs. *Clin Oral Implants Res* 2009; 20: 1247-1253.
- 98) Gahlert M, Roehling S, Sprecher CM, Kniha H, Milz S, Bormann K. In vivo performance of zirconia and titanium implants: A histomorphometric study in mini pig maxillae. *Clin Oral Implants Res* 2012; 23: 281-286.
- 99) Sennerby L, Dasmah A, Larsson B, Iverhed M. Bone tissue responses to surface-modified zirconia implants: A histomorphometric and removal torque study in the rabbit. *Clin Implant Dent Relat Res* 2005; 7 (Suppl 1): S13-S20.
- 100) Pieralli S, Kohal RJ, Hernandez EL, Doerken S, Spies BC. Osseointegration of zirconia dental implants in animal investigations: A systematic review and meta-analysis. *Dent Mater* 2018; 34: 171-182.
- 101) Hoffmann O, Angelov N, Gallez F, Jung RE, Weber FE. The zirconia implant-bone interface: A preliminary histologic evaluation in rabbits. *Int J Oral Maxillofac Implants* 2008; 23: 691-695.
- 102) Gong SH, Lee H, Pae A, Noh K, Shin YM, Lee JH, *et al.* Gene expression of MC3T3-E1 osteoblastic cells on titanium and zirconia surface. *J Adv Prosthodont* 2013; 5: 416-422.
- 103) Sanz-Sánchez I, Sanz-Martin I, de albornoz AC, Figuero E, Sanz M. Biological effect of the abutment material on the stability of peri-implant marginal bone levels: A systematic review and meta-analysis. *Clin Oral Implants Res* 2018; suppl.18: 124-144.
- 104) Tete S, Mastrangelo F, Bianchi A, Zizzari V, Scarano A. Collagen fiber orientation around machined titanium and zirconia dental implant necks: An animal study. *Int J Oral Maxillofac Implants* 2009; 24: 52-58.
- 105) Schultze-Mosgau S, Schliephake H, Radespiel-Tröger M, Neukam FW. Osseointegration of endodontic endosseous cones: Zirconium oxide vs titanium. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 2000; 89: 91-98.
- 106) Hoffmann O, Angelov N, Gallez F, Jung RE, Weber FE. The zirconia implant-bone interface: A preliminary histologic evaluation in rabbits. *Int J Oral Maxillofac Implants* 2008; 23: 691-695.
- 107) Gahlert M, Gudehus T, Eichhorn S, Steinhauser E, Kniha H, Erhardt W. Biomechanical and histomorphometric comparison between zirconia implants with varying surface textures and a titanium implant in the maxilla of miniature pigs. *Clin Oral Implants Res* 2007; 18: 662-668.
- 108) Ferguson SJ, Langhoff JD, Voelter K, von Rechenberg B, Scharnweber D, Bierbaum S, *et al.* Biomechanical comparison of different surface modifications for dental implants. *Int J Oral Maxillofac Implants* 2008; 23: 1037-1046.
- 109) Kohal RJ, Att W, Bächle M, Butz F. Ceramic abutments and ceramic oral implants. An update. *Periodontol* 2000 2008; 47: 224-243.
- 110) Garvie RC, Urban D, Kennedy DR, McMeuer JC. Biocompatibility of magnesium partially stabilized zirconia (Mg-PSZ Ceramics). *J Mat Sci* 1984; 19: 3224-3228.
- 111) Tateishi T, Yunoki H. Research and development of advanced biomaterials and application to the artificial hip joint. *Bull Mech Engr Lab* 1987; 45: 1-9.
- 112) Mihatovic I, Golubovic V, Becker J, Schwarz F. Bone tissue response to experimental zirconia implants. *Clin Oral Invest* 2017; 21: 523-532.
- 113) Roehling S, Schlegel KA, Woelfler H, Gahlert M. Zirconia compared to titanium dental implants in preclinical studies —A systematic review and meta-analysis. *Clin Oral Implants Res* 2019; 30: 365-395.
- 114) Zhao B, van der Mei HC, Rustema-Abbing M, Busscher HJ, Ren Y. Osteoblast integration of dental implant materials after challenge by sub-gingival pathogens; a co-culture study in vitro. *Int J Oral Sci* 2015; 7: 250-258.
- 115) Palmieri A, Pezzetti F, Brunelli G, Lo Muzio L, Scarano A, Scapoli L, *et al.* Short-period effects of zirconia and titanium on osteoblast MicroRNAs. *Clin Implant Dent Relat Res* 2008; 10: 200-205.
- 116) Fujisawa R, Kuboki Y. Preferential adsorption of dentin and bone acidic proteins on the (100) face of hydroxyapatite crystals. *Biochim Biophys Acta* 1991; 1075: 56-60.
- 117) Welander M, Abrahamsson I, Berglundh T. The mucosal barrier at implant abutments of different materials. *Clin Oral Implants Res* 2008; 19: 635-641.
- 118) Zembic A, Sailer I, Jung RE, Hammerle CH. Randomized-controlled clinical trial of customized zirconia and titanium implant abutments for single-tooth implants in canine and posterior regions: 3-year results. *Clin Oral Implants Res* 2009; 20: 802-808.
- 119) van Brakel R, Meijer GJ, Verhoeven JW, Jansen J, de Putter C, Cune MS. Soft tissue response to zirconia and titanium implant abutments: An in vivo within-subject comparison. *J Clin Periodontol* 2012; 39: 995-1001.
- 120) Kohal RJ, Weng D, Bächle M, Strub JR. Loaded custom-made zirconia and titanium implants show similar osseointegration: An animal experiment. *J Periodontol* 2004; 75: 1262-1268.
- 121) Brönemark PI. The biologic origin of osseointegration. In: *The osseointegration book: From calvarium to calcaneus*. Berlin, Germany: Quintessence Books; 2005. p. 22.
- 122) Kumar Y, Jain V, Chauhan SS, Bharate V, Koli D, Kumar M. Influence of different forms and materials (zirconia and titanium) of abutments in peri-implant soft-tissue healing using matrix metalloproteinase-8: A randomized pilot study. *J Prosthet Dent* 2017; 118: 475-480.
- 123) Zhao B, van der Mei HC, Subbiahdoss G, de Vries J, Rustema-Abbing M, Kuijter R, *et al.* Soft tissue integration versus early biofilm formation on different dental implant materials. *Dent Mater* 2014; 30: 716-727.
- 124) Naveau A, Rignon-Bret C, Wulfman C. Zirconia abutments in the anterior region: A systematic review of mechanical and esthetic outcomes. *J Prosthet Dent* 2019; 121: 775-781.