—原 報—

アセチル・セルローズの粘度と塗料被膜の機械的性質

(陸軍科學研究所)

篠田 録・稻垣 英吉

昭和11年10月25日受理

1. 序 論

アセチル・セルローズの粘度と塗料被膜の性質については既に厚木、篠田兩氏(工化大正13, 27, 87)の報告があるが、本報告に於ては粘度の異なるアセチル・セルローズを同濃度で同一溶剤に溶解して得る塗料被膜の性質と粘度との關係を述べ、尙粘度の異なるアセチル・セルローズを混合して溶液を作る時所望の粘度を與へる配合比の計算法、粘度と被膜の強度及び被膜の曝露による強度變化について報告する。

2. アセチル・セルローズの配合と粘度

粘度の異なる數種のニトロ・セルローズを混合して出来る溶液の粘度については既に Duclaux (Bull. Soc. Chim., 1920, 27, 414) Kumickel (Kolloidchem. Beiheft, 1928, Bd. 26, Heft1—5) 厚木、石原(工化, 昭5, 33, 1403)等の報告がある。

こゝでは粘度の異なるアセチル・セルローズを混合して6% アセトン溶液を作り 25±0.1°C に於て其の粘度を求めて、配合比と粘度との關係を検べた。次に實驗結果を示すが、表中粘度の單位はすべて cp. で、用ひた粘度計は著者等の考案した

大きさ(本誌, 昭11, 12, 221)のものである。

試料 番號	試料 番號	η
3	13	
I	0%	100
	25	75
	50	50
	74.96	25.04
	100	0
		355.5
		167.0
		78.24
		35.14
		16.15

試料 番號	試料 番號	η
5	9	
II	0%	100%
	24.88	75.12
	50	50
	74.98	25.02
	100	0
		163
		70.60
		48.98
		35.45
		25.65

試料 番號	試料 番號	η
7	11	
III	0%	100%
	25	75
	50.02	49.98
	75.02	49.98
	100	0
		149
		119.1
		94.08
		71.84
		59.15

之等の結果を粘度の對數と配合比とを兩軸として圖示すれば次圖の如くで、何れも直線關係となる。從つて次の實驗式が得られる。

$$\log \eta = ax + b$$

ここに η ……6%アセトン溶液の粘度

x ……配合比

a, b ……恒数

本実験式によつて計算した η 計算値 と実験より求めた η 実験値 との相違の η 計算値 に對する百分率を求めると次表の如し。

試料 番號	試料 番號	η 實驗値	η 計算値	$\frac{\eta \text{ 實驗値} - \eta \text{ 計算値}}{\eta \text{ 計算値}} \times 100$	
3	13				
I	0%	100%	355.5	363.8	-2.3
	25	75	167.0	167.0	0
	50	50	78.24	76.66	+2.1
	74.96	25.04	35.14	35.23	-0.3
	1.0	0	16.15	16.15	0
試料 番號	試料 番號	〃	〃	〃	
5	9				
II	0%	100%	103	101.2	+1.8
	24.88	35.12	70.60	71.73	-1.6
	50	50	48.98	50.70	-3.4
	74.98	25.02	35.45	35.50	-1.2
	100	0	25.65	25.41	+0.9
試料 番號	試料 番號	〃	〃	〃	
7	11				
III	0%	100%	149	150.4	-0.9
	25	75	119.1	119.1	0
	50.02	49.98	94.08	93.95	+0.1
	75.02	24.98	71.84	74.68	+3.8
	100	0	59.15	59.15	0

尙厚木石原兩氏の實驗結果を引用して計算した結果は次の如くである (文献前出)。

測定温度 25±0.1°C		全濃度 1g/100cc 但し η ……比粘度(水=1)		
高ニトロ・セルロース (精製綿)	低ニトロ・セルロース (薄葉紙)	η 実験値	η 計算値	$\frac{\eta \text{ 実験値} - \eta \text{ 計算値}}{\eta \text{ 計算値}} \times 100$
100%	0%	122.5	122.5	0
75	25	63.5	61.5	+3.2
50	50	28.9	30.9	-6.5
25	75	15.6	15.5	+0.6
0	100	7.8	7.8	0

全濃度 2g/100cc 但し η ……比粘度 (アセトン=1)				
高ニトロ・セルロース	低ニトロ・セルロース (酸分解)	η	η	η
100%	0%	169	169	0
75	25	101	67.1	+40
50	50	55	55.7	-0.4
25	75	32	32	0
0	100	18.4	18.4	0

即ち粘度のかなり異なるアセチル・セルローズ

も、粘度差の少ない試料も共に実験値と計算値とかなりよく一致し、ニトロ・セルローズの場合についても同様である。

此の関係を應用して粘度の異なる二種の纖維素エステルを混合して任意の粘度をもつ試料を得たい時、夫等二つの試料の配合比は計算法によるか、或は作圖法即ち夫々の濃度 100% に對應して夫々 $\log \eta$ をとり、直線にて結び、直線上の所望粘度の對數の處より縦軸に平行線を引き、横軸を切る點を以て夫々の配合比を求める事が出来る。

3. 皮膜の強度と粘度との關係

アセチル・セルローズ	6g
アセトン	60cc
ベンゼン	19々
アルコール	19々

ベンジル・アルコール

2々

上記配合で溶液を作り其の上澄液 35 cc を 10×13 cm の水銀面上の硝子板上に流し鹽化カルシウムを入れたデシケーター中で室温約 30°C にて成膜する。剝離後10日を経たるものを更に真空乾燥器にて 60°C にて乾燥し更に20日間部屋に放置したる後シヨツパー試験器にて 22°C 90% R.H.の下で抗張力及び屈曲度を求む。

試料番號 1 及び 2 は被膜を形成せず。粘度及び表面張力は 6% アセトン溶液につき 25°C にて測定し、表面張力測定には du-Noüy 法を用いた。尙粘度の異なる試料を配合して作った溶液の粘度は前項に述べた方法で計算した。

生成被膜を觀察するに粘度の低い試料程龜甲型の模様が判然と現れ且龜甲の大きさが小さい傾向あり。被膜を作らない試料を高粘度試料と混合して

試料番號	製 造 所	粘度 cp.	表面張力 dyne/cm	厚さ mm	抗 張 力 kg/mm ²	延伸率 %	屈曲度 回
1	國 産	7.59	27.8	—	—	—	—
2		11.7	—	—	—	—	—
3		16.2	28.3	0.105	5.93	32.9	19
4		22.2	27.8	0.100	5.78	18.2	25
5		25.6	28.4	0.098	6.42	34.2	23
6	獨 國 I. G.	30.9	—	0.110	6.79	41.3	22
7		59.1	29.0	0.120	7.03	45.0	20
8		97.9	29.4	—	—	—	—
9		103	29.4	0.108	7.34	48.9	23
10		117	—	0.105	6.90	47.4	26
11	獨 國 I. G.	149	28.3	0.105	6.85	45.3	29
12	獨 國 Hyden	206	28.8	0.120	7.95	46.4	18
13	獨 國 I. G.	355	29.4	—	—	—	—
14		593	29.4	0.125	7.02	45.0	25
21 (1.....2g 13.....4g)		99.6	—	—	—	—	—
22 (1.....2g 14.....4g)		137	—	0.110	6.86	46.4	13
23 (1.....0.5g 13.....5.5g)		263	—	—	—	—	—
24 (1.....1.1g 14.....4.9g)		274	—	0.107	6.95	45.8	15

作つた時には著しき模様が出るが何れもミクロメーターで測定する程度では平滑である。之等については後に譲る事とする。

表面張力は粘度の高いほど稍大きい傾向はあるらしいが、著しい差は認められない。

アセチル・セルローズの粘度約 16 cp. 以上のものは被膜を與へるも約 12 cp. 以下の試料は纖維素の崩壊著しく凝集力弱く成膜しない。即ち被膜形成限界の粘度は 12~16 cp. の中間に位すると考へられる。尙被膜形成能力は溶液の分散度（試料番號 1, 2, 3, 4, 5, 6, 及び 14 は本實驗に用ひた溶劑でやゝ白濁してゐる）溶劑の蒸發速度等に支配せられるが、本配合の如くほどドープの夫に等しい混合溶劑にて成膜しない試料は工業上價值がない。

機械的性質に就いて述べるに低粘度試料被膜の抗張力は稍小さく且脆い。粘度がある範圍以上になると粘度と抗張力との關係はない。同方法で製造したアセチル・セルローズでは粘度の高いほど抗張力大であるが（K. Werner u. H. Englmann, Angew. Chem., 1929, 42, 438）本實驗に用ひた試料は原料及び製造條件が異なると思はれ、此の原因による粘度と抗張力間に關係なく（荒木、工化、昭 5, 33, 773；昭 8, 36, 226）且醋酸基に基く理由等も考へられる。厚木、篠田兩氏（文献前出）の研究の如くアセチル・セルローズを酸で後処理すると銅價は増加するも同時に粘度を増加するやうな事實は興味深い。

被膜を形成せぬ試料を高粘度品と混合して作る被膜の強度は之に相當する粘度をもつ試料と同程度であるが、屈曲度に於て著しい差がある。

4. 曝露後の皮膜の強度

前項と同様にて成膜したものを木板に張つて屋

上に南面して次の期間曝露した。

自昭和10年8月20日—至昭和10年9月25日

晴 12 日 曇 14 日 雨 11 日

最高温度 50°C 最低温度 18°C

1 週間室内に放置の後 20°C 70% R. H. にて被膜の強度を求む。

試料番號	厚さ mm	抗張力 kg/mm ²	延伸率 %	屈曲度 回
3	0.110	6.12	5.93	8
4	0.108	5.93	4.05	8
5	0.115	6.28	6.23	11
7	0.108	6.68	21.2	15
8	0.112	6.38	14.7	10
9	0.120	6.67	23.0	12
13	0.110	7.05	24.4	20
21	0.110	6.50	21.8	16
23	0.109	7.03	34.1	13

上表を見るに低粘度試料は高粘度試料に比し曝露前と比較して延伸率及屈曲度の減少著しい。之は重溶劑の蒸發及び曝露による纖維素分子の崩壊等によるものと考へられる。抗張力は低粘度試料 3, 4 は曝露前に比し稍増加するが、曝露の結果重溶劑把持力（溶媒和力）少なく、重溶劑の蒸發大きく緊縮が大きくなつたものと考へられる。之より高粘度試料は一般に抗張力延伸率及び屈曲度を減少し紫外線に曝露した結果（J. Grard, Bull. Soc. Chim., 1933, 53, 1307）と同様である。

被膜を形成せぬ試料を高粘度品と混合して作つた被膜は曝露の結果之と同程度の粘度をもつ試料と凡て同様に機械的性質を示す。

5. アセチル・セルローズの粘度と塗料被膜の機械的性質との關係

a) アセチル・セルローズ及びドープの性質

ドープの配合は厚木、篠田兩氏（文献前出）の報告による。

アセチル・セルロース	8g	ベンジル・アルコール	2℥
アセトン	60cc	トリアセチン	1℥
ベンゼン	19℥	トリフェニール・フォスフェート	1g
アルコール	17℥		

ドーブ 番 號	原料アセチル・セルロース				ドーブ		
	製 造 會 社	粘度	醋酸基		比重	粘度	粘 度 ※ (グリセリン=100)
1)	獨 國 I. G.	35.8 ^{cp.}	50.8 [%]		0.851	102 ^{cp.}	20.8
2)		59.1	52.6		0.851	182	33.9
3	佛 國 Rhône	103	54.7		0.851	313	63.6
4	獨 國 I. G.	149	53.0		0.851	493	100
5	獨 國 Hyden	206	54.4		0.851	572	116

※ グリセリン比重 $\frac{25}{25} = 1.25:90$

尙ドーブに使用した溶剤稀釋劑重溶劑及び可塑劑は何れも市販最純品である。

b) 緊張度試験

ドーブを塗装せる羽布の緊張性は氣壓、溫度、濕度等によつて異なるが、實際問題として甚だ重要な性質である。

本性質測定法として①木枠に張つた羽布に一定量のドーブを塗装し、其の中央に一定荷重を與へて生ずる歪みによつて判定する方法、②指で塗面を叩き生ずる音の高低によつて知る方法、③一定の高さより一定の球を塗面に落下して、球の飛躍する高さによる方法、④ Sward の硬度計によるもの、⑤一定の長さの羽布にドーブを塗装した時起る羽布の緊縮による方法等あり、之等の中3及び4は G. M. Kline (Farben Ztg., 1933, 38, 1771) によると不適當である。5 は當所にて研究の結果大きい誤差を起し易く、2 は本研究に使用せる如き性質のドーブにては音の高低は判定し難い。依つてこゝでは G. M. Kline (文獻前出) E. K. O. Schmidt. (Farben Ztg., 1934, 39, 1049) 等を参照して圖の如き装置を使用した。

本器は輕合金製で、メーターは 0.01 mm 刻度

である。ハンドルを回轉するときは皿は自重で垂下し圖の如く水平に敷いた羽布に 30g に相當する力を與へる。

25 cm 平方の木枠に可及的に一定張力 10kg/m で張つた羽布を恒濕恒溫槽に暫く放置した後重錘のはじめの位置を読み、次に逐次荷重を加へて夫に對する垂下距離を読み、最後に荷重を除く時の垂下距離の回復を讀んだ。次いで此の羽布面にドーブを塗装し一定條件の下に乾燥した後、塗装前と同様の測定を行ふ。尙メーターの讀みは荷重の増減の後漸時平衡に達せず。よつて塗面を鉛筆で軽く叩いて平衡を速かにするやうにした。

實驗結果：塗装條件 24°C, 72% R.H. でドーブの塗装量概ね 1kg/m² を 5 回に分けて縦横交互に刷毛にて塗布した。何れも 30 分以内にて次回作業

をなし得る。

圖は上述の如く測定した實驗の一例を示すもの

で、何れのドーブも之と同型である。

乾燥を 22°C, 70% R. H. の條件で1週間繼續した時の荷重 1 kg による垂下距離の $\frac{(\text{塗装後})}{(\text{塗装前})} \times 100$ の1例を示す。

ドーブ	1日	2日	3日	4日	6日	7日
%	27.6	25.1	22.7	22.3	20.7	20.2

即ち塗装後はじめの3日位までは垂下距離の減少率大である。此の事は溶剤が盛んに蒸發してミセル間引力が大きくなり塗膜は緊縮する事大きい結果で、測定に際しては此の期

間經過後が誤差を少なくする事となる。

次にドーブの1~5の結果を一括して表とする。

1kg 荷重による垂下距離 (mm)

ドーブ 番 號	塗裝量 kg/m ²	塗膜量 g/m ²	塗 裝 前 (24°C; 72% R.H.)	塗 裝 後	
				1 日 (25°C; 70% R.H.)	6 日 (21°C; 72% R.H.)
1	1.03	30	19.99	6.31 (31.6)	5.81 (29.1)
2	1.07	31	18.00	4.97 (27.6)	3.73 (20.7)
3	1.08	31	18.05	5.34 (29.6)	4.57 (25.3)
4	1.00	30	18.19	5.87 (32.2)	5.50 (30.2)
5	1.01	30	18.75	5.77 (30.9)	4.98 (26.5)

1/2 kg 荷重による垂下距離 (mm)

ドーブ 番 號	塗裝前	塗 裝 後	
		1 日	2 日
1	16.57	4.44 (26.8)	4.01 (24.2)
2	14.55	3.09 (21.2)	1.98 (13.6)
3	14.38	3.40 (23.6)	2.76 (19.2)
4	14.78	3.97 (26.9)	3.67 (24.8)
5	15.46	3.86 (24.9)	3.13 (20.2)

() 内は何れも (塗裝後の垂下距離)/(塗裝前の垂下距離) × 100 なり。

1/2 kg 荷重に於ける疲労 (mm)

ドーブ 番 號	塗裝前	塗 裝 後	
		1 日	6 日
1	1.67 (10)	0.36 (8.1)	0.24 (6.0)
2	1.61 (11)	0.34 (11)	0.22 (11.0)
3	1.87 (13)	0.36 (11)	0.24 (8.7)
4	1.79 (12)	0.40 (10)	0.30 (8.2)
5	1.51 (9.8)	0.34 (8.8)	0.25 (8.0)

() 内は 1/2 kg 荷重による始めの垂下距離に対する疲労の%を示す。

c) 抗力試験

ドーブを塗装した羽布を幅 3 cm に可及的に織り目に沿つて切斷しチャック間の距離を 10 cm とし 18°C, 60% R. H. でシヨツパー・ゴム試験器にて抗力及び延伸率を測定した。但し試料は塗装後室温に 2 週間放置したものを使用した。

試料	塗装量 kg/m ²	抗力		抗力増加率		延伸率	
		縦 kg	横 kg	縦 %	横 %	縦 %	横 %
麻布のみ	0	55	54	—	—	77	78
ドーブ 1	1.03	80	74	45	37	19	21
ドーブ 2	1.03	83	79	51	46	20	22
ドーブ 3	1.03	83	76	51	41	14	24
ドーブ 4	1.03	87	70	58	30	12	22
ドーブ 5	1.01	76	72	38	33	17	15

抗力増加率 = $\frac{(\text{塗装布の抗力}) - (\text{麻布の抗力})}{(\text{麻布の抗力})} \times 100$

上に得た緊張度並びに抗力試験の結果を圖示すると次の如くなる。

緊張性を見るに塗装後 6 日の 1 kg 荷重による垂下距離は塗装前に比べて 20—30% 減少するに至り、1/2 kg 荷重による疲労は 0.2—0.3 mm である。

抗力は何れも 30—60% の増加率を示し、延伸率は麻布のみの時に比較して著しく減少する。

ドーブを塗装した麻布の緊張性、疲労及び抗力

は原料アセチル・セルローズの性質即ち皮膜の強度、弾性、可塑性及びドーブが繊維間に滲透するの難易或ひは塗装法即ち塗装の均一性、塗膜量等に関係するもので、後者による誤差大きくなり、立ち入つた事は述べられないが、粘度 35—200 cp. のアセチル・セルローズを原料としたドーブでは塗膜の緊張性、疲労及び抗力はアセチル・セルローズの粘度の大小によると云へる。尙此の事はアセチル・セルローズ皮膜の強度がアセチル・セルローズの粘度によらない既述の結果と並行するものである。

d) 衝撃試験

緊張度試験と同様にドーブを塗装した試験枠を塗装後 1 晝夜經過後 80°C に 4 時間保ちたる後塗面の中央に下圖の要領で黄銅製球 (445 g 或は 945 g) を作用する時塗面に龜裂を生ぜしや否やを檢べた。其の結果供試ドーブは何れも 1 回の衝撃では何等變化を示さない。

項で述べた處と同様である。

e) 塗装の状況

緊張度試験に用いた試料の横断面をウルトラパークによつて撮影した。之を觀察するにドーブ 1 の如き低粘度アセチル・セルローズを原料としたものは、麻布の繊維の間によくドーブは滲透し略正弦曲線をなす絲の横の方向が全く見られず、し

かも塗面は平滑である。此の原因について毛管現象が考へられるが、表面張力は既に述べた如くアセチル・セルローズの粘度によつて大きな差違を認めない、従つてドーブの滲透は主に粘度の大小によるものと考へられ、且粘度の小さいものが塗

麻 布 の み

ド ー ブ 1

ド ー ブ 3

ド ー ブ 5

面平滑となる事は粘度の小さいものは溶液の擴りが大きい事（中島、工化、昭8, 37, 752）で、ある程度説明出来る。

1) 其の他の性質

其の他のドーブとして要求される性質例へば耐熱性耐油性の試験を行つた。

耐熱性は原料アセチル・セルローズの安定度即ち硫酸分によるもので、約3°C/分の割合にて150°Cまで加熱するとき塗面に變化なきや否や觀察するに本研究に用ひた如き硫酸分の少ない試料（0.04%以下）より調製したドーブにては何れも變化を示さない。

耐油性は塗面の物理的並びに化學的性質によるもので、塗面に揮發油を滴下するときは直ちに、オイルワニス油類は24時間湛へた後に之等油類が滲透せしや否や觀察するに供試ドーブでは何れも變化なし。

6. 總 括

1) 粘度の異なる纖維素エステルを混合して所望粘度の溶液を得るには次式によるか又は作圖法で容易に其の配合比を求められる。

$$\log \eta = ax + b$$

η ……所望の粘度

$a, b, \dots$ 恒数

$x, \dots$ 配合比

2) アセチル・セルローズの皮膜形式限界の粘度は12~16 cp. で表面張力には大した関係はないらしい。皮膜の抗張力は粘度が25 cp. 迄のものでは稍低い、それ以上では兩者の間に一定の関係は認められない。

3) 皮膜を曝露するとき粘度 25 cp. 以下のものは脆くなる事著しい。

4) 粘度 35~200 cp. のアセチル・セルローズを原料とせる5種のドープを作り塗膜の機械的性質を検べた處 35 cp. のものは稍脆いが實用上何等差支へない。尙粘度の低い試料の塗面平滑となり麻布の間にドープがよく滲透するのは粘度の大小に基くものである。

終に臨み御指導を賜つた厚木教授に深く感謝する。

CELLULOSE INDUSTRY

THE JOURNAL OF THE CELLULOSE INSTITUTE, TOKYO, JAPAN

VOL. 12 December, 1936, No. 12

ON THE RELATION BETWEEN THE VISCOSITY OF ACETYLCELLULOSES AND THE MECHANICAL PROPERTIES OF DOPES PREPARED THEREFROM

By R. SHINODA and E. INAGAKI

(Received October 25, 1936)

This report will deal with the following problems:

- (1) An empirical formula representing the viscosity of the mixed acetylcelluloses, those to be mixed having different viscosity.
- (2) The relation between the viscosity of acetylcelluloses and the strength of their films.
- (3) The change of the mechanical properties of acetylcellulose films by weathering.
- (4) The relation between the viscosity of acetylcelluloses and the mechanical properties of their dopes.

The results obtained are briefly abstracted from the original Japanese paper as follows.

- (1) The viscosity of the mixed acetylcelluloses, those to be blended having different viscosity, may be expressed by the following empirical formula:

$$\log \eta = ax + b$$

where ηViscosity of 6% solution of mixed acetylcelluloses in acetone at 25°C

x.....Mixing ratio of two acetylcelluloses

The above formula is identical with that obtained by Duclaux (Bull. Soc. Chim., 1920, **27**, 414) regarding to nitrocellulose. The experimental data, as compared that calculated by the above formula, coincide with each other practically good, as seen in the table I.

Table I

The number of samples and their mixing ratio				η exp. cp.	η calc. cp.	$\frac{\eta \text{ exp.} - \eta \text{ calc.}}{\eta \text{ calc.}} \times 100$
3		13				
0	%	100	%	355.5	363.8	-2.3
25		75		167.0	167.0	0
50		50		78.24	76.66	+2.1
74.96		25.04		35.14	35.23	-0.3
100		0		16.15	16.15	0

The number of samples and their mixing ratio				η exp. cp.	η calc. cp.	$\frac{\eta \text{ exp.} - \eta \text{ calc.}}{\eta \text{ calc.}} \times 100$
5		9				
0	%	100	%	103.0	101.2	+1.8
24.88		75.12		70.60	71.73	-1.6
50		50		48.98	50.70	-3.4
74.98		25.02		35.45	35.90	-1.2
100		0		25.65	25.41	+0.9
7		11				
0	%	100	%	149.0	150.4	-0.9
25		75		119.1	119.1	0
50.02		49.98		94.08	93.95	+0.1
75.02		24.98		71.84	74.68	+3.8
100		0		59.15	59.15	0

(2) With regard to the relation between the viscosity of acetylcelluloses and the strength of their films, the following results were obtained.

Table II

The number of samples	Viscosity cp.	Surface tension dyne/cm	Thickness mm	Tensile strength kg/mm ²	Elongation %	Folding numbers
1 made in Japan	7.59	27.8	—	—	—	—
2 "	11.7	—	—	—	—	—
3 "	16.2	28.3	0.105	5.93	32.9	19
4 "	22.2	27.8	0.100	5.78	18.2	25
5 "	25.6	28.4	0.093	6.42	34.2	23
5 "	30.9	—	0.110	6.79	41.3	22
7 made in Germany	59.1	29.0	0.120	7.03	45.0	20
9 made in France	103	29.4	0.108	7.34	48.9	23
10 made in Japan	117	—	0.105	6.90	47.4	26
11 made in Germany	149	28.3	0.105	6.85	45.3	29
12 "	206	28.8	0.120	7.95	46.4	18
14 "	593	29.4	0.125	7.02	46.0	25
22 (1.....2g 14.....4g)	137	—	0.110	6.86	46.4	13
24 (1.....1.1g 14.....4.9g)	274	—	0.107	6.95	45.8	15

Remarks: (1) The samples made in Japan were specially prepared in our laboratory in order to obtain acetylcelluloses of various viscosity.

(2) The films were made of the following composition of acetylcellulose solution.

Acetylcellulose	6g
Acetone.....	60cc
Benzene	19 "
Alcohol	19 "
Benzyl alcohol	2 "

From the above data, the following facts will be seen:

a) When the viscosity of acetylcellulose goes beyond a certain limit, the acetylcellulose will no longer form film. Such a limiting viscosity seems to lie between 12 and 16 centipoises.

b) As to the relation of viscosity of acetylcellulose to the tensile strength of its film, there seems to be a certain relation between them but not clear: i. e. the tensile strength is somewhat weak up to 25 centipoises.

c) The tensile strength of films prepared from the mixed acetylcelluloses, the viscosity of one component of which was too small to form film are almost the same as that of one cellulose, having the nearly equal viscosity to the mixed one, but the former may be inferior in the folding number to the latter.

(3) As well known, the mechanical properties of acetylcellulose films become worse by weathering. In order to make clear the relation between the viscosity of acetylcelluloses and the degree of damage, effected by weathering, in mechanical properties of their films, weathering test during about one month in summer was carried out. The results obtained are described in the following table III.

Table III

The number of samples	Viscosity cp.	Thickness mm	Tensile strength kg/mm ²	Elongation %	Folding numbers
3	16.2	0.110	6.12	5.66	8
4	22.2	0.108	5.93	4.05	8
5	25.6	0.115	6.28	6.26	11
7	59.1	0.108	6.68	21.2	15
8	97.9	0.112	6.38	14.7	10
9	103.0	0.120	6.67	23.0	10
13	355	0.110	7.05	24.4	20
21 (mixed)	99.6	0.110	6.50	21.8	16
23 (mixed)	263	0.109	7.03	34.1	13

Remarks: The data of the mechanical properties before weathering are given in the Table II.

From the above results, it will be seen that the elongation and the folding number of films prepared from low viscosity acetylcelluloses seem to decrease more considerably by weathering than films from high viscosity one. This fact will be due to the evaporation of heavy solvents contained in films and the degradation of cellulose molecules during weathering. These phenomena will be more remarkably found in the film of low viscosity acetylcellulose than in that of high viscosity one. The increase in the tensile strength may be resulted by contraction of films, for instance No. 3 and No. 4, owing to the evaporation of heavy solvents. The low viscosity acetylcelluloses seem to have lower capacity to keep the solvent in film construction than the high viscosity acetylcelluloses.

By weathering, the films prepared from mixed acetylcelluloses represent almost the same result in mechanical properties as that prepared from the one acetylcellulose having nearly the equal viscosity to the mixed one.

(4) With regard to dopes the following mechanical properties were tested: tautness test, strength test, beating resistance and doping test. The properties of acetylcelluloses used in this experiment, and composition of dopes prepared therefrom are shown in the following table IV.

Table IV

The number of dopes	Category of acetylcellulose	Viscosity cp.	Acetyl-group %
1	made in Germany	35.8	50.8
2	" " "	59.1	52.6
3	made in France	103	54.7
4	made in Germany	149	53.0
5	" " "	206	54.4

The composition of dope:

Acetylcellulose	8g
Acetone	60cc
Benzene.....	19cc
Alcohol	17cc
Benzyl alcohol	2cc
Triacetin	1cc
Triphenylphosphate.....	1g

(By Atsuki and Shinoda)

The tautness test was carried out by the tester, shown in the following figure

The results obtained are shown in the following table V.

Table V

Falling distance (mm) with 1 kg weight					
The number of dopes	Amount of dope kg/m ²	Weight of film on the linen g/m ²	Falling distance before doping at 24°C, 72% R.H.	Falling distance after doping	
				after 1 day (25°C, 70% R.H.)	after 6 days (21°C, 72% R.H.)
1	1.03	30	19.99	6.31	5.81
2	1.07	31	18.09	4.97	3.73
3	1.08	31	18.05	5.34	4.57
4	1.00	30	18.19	5.87	5.50
5	1.01	30	18.75	5.77	4.98
Falling distance (mm) with ½ kg weight					
1			16.57	4.44	4.01
2			14.55	3.09	1.88
3			14.38	3.40	2.76
4			14.78	3.97	3.67
5			15.46	3.86	3.13

The strength of doped linen was tested with Schopper's rubber testing instrument. The results obtained are shown in the following table VI.

Table VI

Samples	Amount of dope kg/m ²	Strength kg		Increase ratio in strength %		Elongation %	
		warp	weft	warp	weft	warp	weft
Linen only	0	55	54	—	—	77	78
Dope 1	1.03	80	74	45	37	19	21
" 2	1.03	83	79	51	46	20	22
" 3	1.03	83	76	51	41	14	24
" 4	1.06	87	70	58	30	12	22
" 5	1.01	76	72	38	33	17	15

The results shown in the above two tables are plotted in the following figures.

It will be seen from the above tables and figures, that there is no relation among the viscosity of acetylcellulose, the tautness and the strength of doped linen within the viscosity range of acetylcelluloses used, 35~200 cps.

Also in the beating resistance the authors cannot find any relation between them.

In doping, however in order to make it to penetrate uniformly into linen there seems to be a suitable viscosity of dope. When the viscosity of dope is too high, the dope does not penetrate uniformly into linen as seen in the photograph in the original Japanese paper. The mechanical properties of the doped linen, which was penetrated moderately into inside, are superior to that penetrated unsufficiently.

As to the viscosity of dope, consequently, the above facts must be deeply considered on the selection of acetylcellulose.

The authors wish to express their thanks for kind instructions of Prof. K. Atsuki.