Scanning electron microscope and acoustic emission studies of itacolumites

Hiroyuki Suzuki*, Takuo Yokoyama* and Masao Nishihara**

Abstract Fabric of itacolumite, or flexible quartzite, was studied in detail under SEM, and the existence of narrow uniform intergranular void spaces between interlocked quartz grains was ascertained. The void spaces are interconnected with each other and extend three-dimensionally throughout the rock mass.

For clarifying the mechanical behavior of itacolumite, slab specimens of itacolumites were deformed and ruptured in the simple bending test, and acoustic emission (AE) signals were recorded and analyzed. Quite a large number of AE events were recorded in itacolumites. AE frequency and amplitude of itacolumite are smaller than those of well-cemented sandstone. AE event counts decrease linearly with respect to maximum amplitude in both logarithmic diagram, and the *m*-value of itacolumite is similar to that of porous rocks.

The results obtained by SEM and AE studies suggest that the fabric and deformation process of itacolumite are schematically represented by a jigsaw puzzle model.

Key words: itacolumite, flexible quartzite, SEM studies, AE studies, fabric, jigsaw puzzle model

Introduction

Itacolumite is a peculiar type of quartzites (either sedimentary or metamorphic) which exhibits some flexibility when it was split into a thin slab (Suzuki & Shimizu, 1993), and so it is often referred to as flexible "sandstone" (Von Eschwege, 1823). The flexibility exhibited by such a brittle material as itacolumite is worthy of note, because it may have some suggestion for an invention of ideal "flexible ceramics", which are eagerly needed in modern technology (Sakanaka *et al.*, 1988). The flexibility of itacolumite is not caused by its constituent minerals but by its fabric (Dusseault, 1980). Itacolumite is mainly composed of interlocking quartz grains and each quartz grain is separated from each other by a narrow space (Wetherill, 1867; Suzuki &

Shimizu, 1993). Such peculiar grain-to-grain fabric of itacolumite cannot be precisely observed under optical microscope but it will be best identified under scanning electron microscope (SEM).

Dusseault (1980) used SEM for the detailed observation of the Indian and North American itacolumites. He showed that all grains were interlocked but adjoining grain surfaces were not in direct contact and uniform separation of several microns existed between grains. Further he noted that crystal forms of quartz grains were excellent and little pitting or crystal face erosion could not be observed. Verma (1982), however, reported the evidence of chemical corrosion such as solution channels and etched cavities on grain surfaces of quartz from SEM observation of the Brazilian, Indian and Appalachian itacolumites. The present authors extended the SEM studies to the observation of surface features of quartz grains and intergranular void spaces of itacolumite.

On the other hand, when a thin slab of itacolumite is wiggled, obscure clattering sounds are

Received October 5, 1992. Accepted April 8, 1993.

* Science and Engineering Research Institute, Doshisha University, Kyoto 602, Japan.

** Shimogamo Miyazaki-cho, Sakyo-ku, Kyoto 606, Japan.

emitted. This phenomenon suggested that AE analysis might be applicable for the study of itacolumite. The AE study is known to be very useful for clarifying the fabric (especially porosity) and deformation process of rocks (Mogi, 1962a; Mae & Nakao, 1968; Fonseka *et al.*, 1985; Meredith *et al.*, 1990). In this study, thin slabs of itacolumites were deformed and fractured with a simple bending apparatus and the accompanying AE signals were recorded and analyzed. The AE characteristics (such as event count rate, frequency and maximum amplitude) of itacolumites are very unique.

On the basis of results obtained by SEM and AE studies, the jigsaw puzzle model (DeVries & Jugle, 1968; Sakanaka, 1989) is extended to deformation process of itacolumite. The results of experimental studies on the origin of inter granular void spaces will be presented in a separate paper.

Specimens studied

Itacolumites are known only from India, Brazil, North America and France (Suzuki & Shimizu, 1993). Among them, the Indian, Brazilian and North American itacolumites are rather easy to obtain and were used for the present study. Specimens of the Indian itacolumite were collected at the famous itacolumite locality of the Kaliana Hill in Haryana State. Specimens of the Brazilian and North American itacolumites were obtained from geological supply companies. The former specimens were collected from Mt. Itacolumi in Minas Gerais State, from which the name itacolumite was derived. Specimens of the North American itacolumite were collected at the Appalachian Mountains in North Carolina and Georgia. Itacolumites are usually found as small masses or thin layers along bedding planes or joints in a thick sequence of non-flexible quartzites (Tuomey, 1848; Medlicott, 1874; Derby, 1884). Peculiar fabric of itacolumite can be ascertained by comparison with the fabric of non-flexible quartzite. Hence, specimens of non-flexible quartzites were obtained from the same localities of the Brazilian and Indian itacolumites and used for the SEM study.

The petrography (such as microscopic texture, mineral composition, grain size, preferred orien-

tation and porosity) of these specimens was described by Suzuki & Shimizu (1993). Lithologically, the Indian itacolumite is a sedimentary quartzite (quartzose sandstone), while the Brazilian and Appalachian itacolumites are metamorphic quartzites (micaceous schistose quartzites). These three itacolumites are all assigned to be the Precambrian.

In the AE study, AE characteristics of itacolumites were compared with those of well-cemented sandstone of the Paleogene Muro Group. This sandstone is fine-grained and is classified as a lithic arenite. Matrices are composed of cryptocrystalline quartz and clay minerals. Porosities measured with a helium-gas-displacement pycnometer are 5.1%. Slab specimen of this sandstone does not exhibit any flexibility.

SEM studies

Observation of fractured surface

The freshly fractured surfaces of specimens were observed under SEM (Plate I). In all the specimens of the Brazilian, Indian and Appalachian itacolumites, each quartz grain has an irregular shape and is separated by a narrow space from adjacent grains. Small protrusion of one grain is adjoining with small depression of neighboring grains, so that grains as a whole are interlocked well. The interlocked grain boundaries are not so much sutured as stylolite. Quartz grains of the Indian itacolumite are highly-irregularly shaped, while those of the Brazilian and Appalachian specimens are somewhat equidimensionally polyhedral. Platy crystals of muscovite give an anisotropic feature to the Brazilian and Appalachian itacolumites.

For the comparison with itacolumite, fractured surfaces of the Indian and Brazilian non-flexible quartzites which are thought to be the mother rock of itacolumite were also observed under SEM. In the photomicrographs shown in Plate II, uniform intergranular spaces are not or rarely observed. Especially in the Indian non-flexible quartzite, small isolated voids are only sporadically observed. The fractured surface of the non-flexible quartzite consists predominantly of intragranular fractures which are characterized

Fig. 1. Block diagram of AE measuring system in bending test of a slab specimen.

by conchoidal fractography (Plate II-1B, 2B).

Surface texture of quartz grains

The separate quartz grains can be easily rubbed off from corners of a specimen of itacolumite. These grains were boiled in 15% dilute HCl for 20 minutes and then cleaned in distilled water before drying. Then, surface of quartz grain was observed under SEM. The photomicrographs of SEM images are shown in Plate III. Each separated grain is usually composed of a single quartz crystal, but it is also frequently observed that one grain is an aggregate of a few or several quartz crystals whose boundaries are not or partly separated (Plate III-4).

Grain surface of the Indian itacolumite is dissimilar to those of the Brazilian and Appalachian itacolumites, and it has a highly-rugged relief. Smooth surface at the lower right corner (Plate III-1) will be an intragranular fracture surface which was caused at the time of grain separation. Equidimensional polyhedral grains with flat surfaces are the distinct feature of the Brazilian and Appalachian itacolumites. Polyhedral quartz grains often show that three edges of a trigonal pyramid join together with an angle of about 120 degrees to form an apex (Plate III-2, 4).

Intergranular void

After cyanoacrylate resin was permeated into intergranular voids of a small chip of itacolumite, the chip was immersed in hydrofluoric acid (55% dilute) for a few days so that all the quartz grains

were completely dissolved away. The cyanoacrylate resin can not be affected by hydrofluoric acid. Consequently, the remained cyanoacrylate resin is a three dimensional skeleton of the intergranular void as shown in Plate IV. It is clearly observed that the intergranular narrow space with uniform thickness extends laterally and vertically throughout the specimen without interruption.

AE studies

Method of study

Simple three-point bending tests of slabs of itacolumites were performed using the Instron-type testing machine. In order to monitor the AE output, two transducers with a wide range of resonant frequency were used. Acoustic signals were amplified by a preamplifier with a fixed gain of 40 dB and frequency range of 50 kHz to 2 MHz. Signals were then discriminated by a local processor. Threshold level of 120 mV was set to exclude noise signals and the dead time of 1 microsecond was adopted. The block diagram of AE measuring system is shown in Fig. 1. This system was originally developed for the study of small specimen such as composite materials.

Arriving time, oscillation number, maximum amplitude, peak time and continuous time of each AE signal were recorded. Using these data, AE event count rate, frequency, maximum amplitude and relationship between maximum amplitude and event count were analyzed. Similar experi-

Fig. 2. AE event count rate as a function of time for itacolumites (A: North Carolina, B: India, C: Brazil) and well-cemented Muro sandstone (D).

Table 1. Size of specimen and loading rate for bending tests and AE studies

Specimen	Width (mm)	Thickness (mm)	Span between supports (mm)	Loading rate (mm/min.)
Indian itacolumite	12.5	7.0	80.0	0.05
Brazilian itacolumite	12.0	5.0	80.0	0.05
North Carolinian itacolumite	12.0	5.0	40.0	0.05
Well-cemented sandstone	20.0	5.0	100.0	0.10

ments were performed on the well-cemented sandstone of the Paleogene Muro group, which is regarded as a representative of common rigid rocks. Size of specimens and loading rate for bending tests and AE studies are given in Table 1.

AE event count rate

AE event count rate of three kinds of itacolumites and the well-cemented Muro sandstone

were analyzed and the results are shown in Fig. 2. A large number of AE event are recorded in the bending test of itacolumites. At the initial stage of bending experiments on the Brazilian and Appalachian itacolumites, AE event is not or rarely recorded. But after this stage, the event count rate increases gradually and attains to a maximum value at the maximum load and few cracks are formed in the lower surface of the specimen. After the maximum load is attained, the event count rate decreases gradually and finally decline to zero.

The AE event count rate of the Indian itacolumite shows a similar increasing and decreasing pattern, but AE is recorded from the beginning of bending experiment. During this experiment,

Fig. 3. Distribution of AE frequency for itacolumites (A: North Carolina, B: Brazil, C: India, data obtained in earlier 40 minutes, D: India, data obtained in later 20 minutes) and well-cemented Muro sandstone (E). Total counts are assumed to be 1000 in each case.

total counts of AE event were too large to be recorded in a floppy disk and recording was interrupted for few minutes during the replacement of floppy disks. This misrecording would not constitute a serious obstacle to the interpretation, because it happened during regularly-increasing period of event count rate.

The AE event count rate of the well-cemented Muro sandstone is quite different from that of itacolumites. The AE event count rate rises instantaneously at the maximum load when the specimen is ruptured. After the maximum load is attained, no AE signal is recorded. An extremely small number of AE event are recorded

from the beginning to the maximum load.

AE frequency

In this experiment, AE frequency was calculated simply from oscillation number and duration of each AE signal. AE frequencies ranging from 50 to 350 kHz were used for analysis. The results of frequency analysis of three kinds of itacolumites and the well-cemented Muro sandstone are shown in Fig. 3. The distribution patterns of AE frequencies of three kinds of itacolumites are quite similar and AE signals with frequencies ranging from 80 to 100 kHz are predominant. AE frequencies higher than 170 kHz and lower than 70 kHz are rarely re-

Fig. 4. Distribution of AE maximum amplitude for itacolumites (A: North Carolina, B: Brazil, C: India, data obtained in earlier 40 minutes, D: India, data obtained in later 20 minutes) and well-cemented Muro sandstone (E). Total counts are assumed to be 1000.

corded. The misrecording in the experiment of the Indian itacolumite happened to offer a chance for comparing the AE characteristics of the earlier stage (increasing stage of event count rate) with that of the later stage (peak time and decreasing stage). As shown in Fig. 3, the distribution pattern of AE frequency in the earlier stage is very similar to that of the later stage.

On the other hand, AE frequencies of the Muro sandstone are widely distributed between 90 and

220 kHz, and the range between 110 and 170 kHz is most predominant.

AE amplitude

AE signals with maximum amplitude between 40 and 80 dB were used. The results are shown in Fig. 4. The distribution patterns of AE amplitude obtained from the Indian, Brazilian and Appalachian itacolumites are quite similar, and the most predominant amplitude is about 50 dB. AE signals with amplitude larger than 70 dB

Fig. 5. Relationship between AE event count and maximum amplitude, and m -value for itacolumites (A: North Carolina, B: India, data obtained in earlier 40 minutes, C: Brazil) and well-cemented Muro sandstone (D).

are quite scarce. In the case of the Indian itacolumite, the predominant AE signals in the later stage of experiment has a little larger amplitude than those in the earlier stage.

The distribution pattern of AE amplitude of the Muro sandstone is similar to those of itacolumites at first sight; nevertheless closer inspection reveals the fact that AE signals with amplitude larger than 65 dB are more frequently recorded from the Muro sandstone than from the itacolumites. That is, AE signals with larger amplitude are recorded in the experiment of the Muro sandstone. The difference of distribution pattern of AE amplitude between the Muro sandstone and three itacolumites is more clearly indicated in the difference of the m -value, as described in the following section.

Ishimoto & Iida (1939) found that the number of earthquakes $N(V_p)$ having a maximum trace amplitude of seismogram between V_p and $(V_p + dV_p)$ was expressed by

$$N(V_p)dV_p = kV_p^{-m}dV_p$$

$$\text{or} \quad \log N(V_p) = -m \log V_p + \log k$$

where k and m are constants.

The same relation is applicable to the AE events related to microcracking in rock deformation (Mogi, 1962a). This equation means that number of microcracking decreases linearly with respect to maximum trace amplitude both in logarithmic scale.

The relationship between the maximum am-

Fig. 6. Relationship between AE event count and maximum amplitude, and m -value in earlier stage (A) and in later stage (B) in bending test of Indian itacolumite.

plitude and event count of AE obtained in present experiments is shown in Figs. 5 & 6. In these figures, the maximum amplitude is expressed in mV. The $\log N(V_p)$ - $\log V_p$ relation of the itacolumites and the Muro sandstone is nearly linear. The m -value of itacolumite which is calculated by the method of least squares is between 2.18 and 2.99, while that of the well-cemented Muro sandstone is 1.76 (Table 2). As shown in Fig. 6, the m -value of the Indian itacolumite becomes smaller in the later stage of experiment.

Bending test

Typical load-deflection curves of the North Carolinian itacolumite and the Muro sandstone obtained in this bending tests are shown in Fig. 7. The specimen of the Muro sandstone is broken

Table 2. m -value of various types of rocks and itacolumites

Rock specimen	m -value	
North Carolinian itacolumite	2.99	This study
Brazilian itacolumite	2.59	
Indian itacolumite (early 40 minutes)	2.41	
Indian itacolumite (later 20 minutes)	2.18	
Well-cemented sandstone	1.76	Mogi (1962a, 1962b)
Pumice A	2.47	
Pumice B	2.30	
Pumice C	2.38	
Pumice D	2.20	
Pumice E	2.44	
Pumice F	2.33	
Pumice G	2.65	
Granite A	1.61	
Granite B	1.74	
Granite C	1.68	
Granite D	1.65	
Diabase	1.65	
Andesite	2.03	
Coal A	1.90	
Coal B	1.75

Fig. 7. Load-deflection curves in bending tests of North Carolinian itacolumite (A) and well-cemented Muro sandstone (B).

into two pieces instantaneously at the maximum load and can not sustain load any more. On the other hand, fracturing of the specimen of the North Carolinian itacolumite occurs gradually,

Table 3. Bending strength of itacolumites and the well-cemented Muro sandstone

Specimen	Bending strength (kgf/cm ²)
Indian itacolumite	20.5
North Carolinian itacolumite A	44.0
North Carolinian itacolumite B	40.5
Well-cemented sandstone	240.0

perhaps grain by grain, and the specimen is able to support load still after the maximum load.

Bending strength (modulus of rupture) of a slab (Fig. 1) is calculated by the following formula :

$$SB = (3PL) / (2bd^2)$$

where SB: bending strength (kgf/cm²)
 P: applied load (kgf)
 L: span between supports (cm)
 b: width of slab (cm)
 d: thickness of slab (cm)

Bending strength of three kinds of itacolumites and the Muro sandstone were determined (Table 3). Itacolumite is a weak rock and its bending strength is 1/5 to 1/12 of the well-cemented Muro sandstone.

Discussion

Fabric of itacolumite

Itacolumite and non-flexible quartzite were compared under the SEM, and the distinct fabric of itacolumite was clearly observed. As Dusseault (1980) pointed out, quartz grains are interlocked, but adjoining grain surfaces are not in direct contact. Gap of several to tens microns exists uniformly between grains (Plate I). No infilling minerals are found. As described in later section, in AE studies, porous nature of itacolumite is also inferred from a large number of event counts, lower frequency, smaller amplitude and larger *m*-value. But the porosities of itacolumites are 6 to 19% and they are not higher than those of reservoir sandstones (Suzuki & Shimizu, 1993). Therefore, the important feature of itacolumite fabric is not the total volume of voids but the uniform distribution of nar-

row intergranular void spaces interconnected throughout the rock mass (Plates I & IV).

Fractured surface of itacolumite pass predominantly through intergranular void spaces, while that of non-flexible quartzite mainly cut through quartz grains owing to lack of intergranular voids (Plates I & II).

Difference between sedimentary and metamorphic quartzites

Features of fractured surface and also of grain surface of the Indian itacolumite are distinct from those of the Brazilian and Appalachian itacolumites (Plates I & III). Petrographical studies of itacolumites show that the Indian itacolumite is matured quartzose sandstone and the Brazilian and Appalachian itacolumites are metamorphic quartzites (Suzuki & Shimizu, 1993).

Irregular shape and highly-rugged surface of quartz grains in the Indian itacolumite may be formed by pressure solution of quartz at grain contact and quartz precipitation in interstitial voids of sandstone during diagenesis.

The morphology of equidimensional polyhedral grain of the Brazilian and Appalachian itacolumites is attributed to a recrystallization during metamorphism. During recrystallization, irregular grain boundaries are adjusted to reduce grain boundary tension. Consequently, grain shapes approach an equilibrium condition with strain-free polygonal grains, triple junctions, and interfacial angles of about 120 degrees (Wilson, 1973). Such polygonal grains are frequently observed in the Brazilian and Appalachian itacolumites (Plate III-2,4). Fresh crystals of muscovite will be also the products of metamorphism.

Evidence of chemical texture

As to the problem whether any evidence of chemical dissolution of quartz-grain surface can be observed or not (Dusseault, 1980; Verma, 1982), present authors can not offer any definite conclusion, yet they are inclined to support Verma's opinion. As Dusseault (1980) reported, crystal forms of quartz grains are commonly well preserved (Plate III), but as shown in Fig. 8, closer inspection reveals the fact that crystallographically oriented triangular etch pits (Wilson, 1979) can be, though very rarely, observed on grain

Fig. 8. SEM photomicrograph showing crystallographically oriented triangular etch pits on surface of a quartz grain (lower right) in Brazilian itacolumite. (Scale bar is 0.1 mm in length.)

surface of the Brazilian itacolumite. Further study is needed to solve this problem, because definite criteria for identifying chemical texture on quartz-grain surface have not been established yet (Marshall *et al.*, 1987).

AE characteristics of itacolumite

It is a commonly accepted assumption that AE-generating mechanism in rock deformation under room temperature and atmospheric pressure is directly related to cracking process rather than other process such as twin formation or dislocation (Kranz, 1983; Meredith *et al.*, 1990). This assumption is also applicable to itacolumites. The AE characteristics of itacolumites are unique and different from those of the well-cemented Muro sandstone. A large number of event, predominance of AE with lower frequency, lacking of AE with higher maximum amplitude, and larger m -value are the characteristics of itacolumites. According to previous authors (Mogi, 1962a; Mae & Nakao, 1968; Meredith *et al.*, 1990), these characteristics are similar to AE characteristics of soft porous rocks, while AE characteristics of the well-cemented Muro sandstone are like those of hard rigid rocks. AE characteristics of itacolumite are consistent with its peculiar grain-to-grain fabric. Existence of intergranular voids between interlocked grains

permits to generate abundant microcracking at grain contact, and it prevents the transmission of AE with higher frequency and larger amplitude through rock mass (Meredith *et al.*, 1990). The predominance of AE signals with lower frequency may also be attributed to the predominance of frictional movements at each grain contact.

The differences of grain shape and grain surface between the Indian itacolumite and the Brazilian and Appalachian itacolumites are indicated in the differences of total event count and starting time of AE output. Distribution patterns of AE frequency and maximum amplitude are not affected by those differences.

m -value and fabric

Mogi (1962a, 1962b) clarified that the m -value representing relationship between maximum amplitude and event count was closely related with the fabric of rocks. He calculated the m -value of various types of rocks. As shown in Table 2, the m -value of igneous rocks and coal is between 1.61 and 2.03, while that of pumice is between 2.20 and 2.65. He concluded that the m -value is "large (2.0-2.7)" for "very porous materials", "moderate (1.0-2.0)" for "compact heterogeneous materials", and "very small (0.3-1.0)" for "nearly homogeneous materials". In the present study, the m -value of itacolumite is between 2.18 and 2.99, and that of the Muro sandstone is 1.76. Then, itacolumite is defined as "very porous material" and the Muro sandstone as "compact heterogeneous material" according to Mogi's definition. This is well consistent with the fact that itacolumite is a porous material as shown by SEM observation. This conclusion also does not contradict with the results of Mae & Nakao (1968) who showed that the m -value of rocks is consistently related with the modulus of rigidity.

Further, the peculiarity of itacolumite fabric is shown by the change of m -value during deformation. Mogi (1962b) showed that the m -value gradually increases during successive deformation stage of common rigid rocks, and he attributed this phenomenon to the increase and growth of microcracks in rocks. In the present study, as shown in Fig. 6, the m -value of itacolumite decreases in the later stage of defor-

mation. This will be ascribed to diminishing of intergranular void in the upper side of bent specimen by compressive stress and also partly to collapse of small protrusion and depression by stress concentration, both of which will contribute to the increase of rigidity of the specimen to some extent.

Deformation process of itacolumite : jigsaw puzzle model

On the basis of results obtained by SEM and AE studies, the fabric of itacolumite will be well represented schematically by a jigsaw puzzle model with wider space between pieces. Conceptual similarity of fabric between itacolumite and jigsaw puzzle was first pointed out by DeVries & Jugle (1968), and Sakanaka (1989) showed a schematic figure of the initial stage of deformation (Fig. 9a & 9b). The present authors extended this model to fracturing stage (Fig. 9c).

Figure 9a shows an undeformed state. Once a load is added, the upper part contracts and each grain comes to contact horizontally with each other and the lower part expands to a limited extent where small depression and protrusion come to touch (Fig. 9b). Until this condition is attained for all grains, no or infrequent AE is recorded. Further loading causes frictional movements at each grain contact and abundant AE of lower frequency and smaller amplitude will be emitted.

Additional loading will induce a stress concentration on grain contact at small depression and protrusion in the lower part, and intragranular fracturing in small scale will occur (Fig. 9c) and AE of higher frequency and larger amplitude will be emitted. But the emitted sound will be difficult to arrive at the AE sensors owing to the absorption of energy by void. As void diminishes, AE of higher frequency and larger amplitude will be able to arrive at the sensors.

At the maximum load, large fissures appear in the lower part, but owing to the higher compressive strength, quartz grains are still interlocked in the upper part and are not yet fractured. After the maximum load is attained, fractures propagate into the upper part and unfractured grains decreases, hence AE events gradually decline and finally disappear.

Fig. 9. A jigsaw puzzle model for the fabric and fracturing process of itacolumite. a: Before deformation, b: Deformed state, c: Fracturing stage (a, b: after Sakanaka, 1989)

Some remarks on “flexible ceramics”

Results of the present study suggest that jigsaw puzzle-like fabric of aggregate made of brittle material can exhibit considerable flexibility under room temperature and atmospheric pressure. The bending strength of itacolumites, however, is so low that itacolumites are very weak

rocks as shown in Table 3. This is because quartz grain has a low value of tensile strength. Therefore the utility of itacolumites as industrial materials is very limited. If similar jigsaw puzzle-like fabric can be produced in aggregate made of ceramics with higher tensile strength, this aggregate will be an ideal "flexible ceramics"; however, supreme strength can not be realized in this aggregate owing to existence of intergranular voids.

Conclusion

For clarifying the fabric of itacolumites, SEM observation was carried out on fractured surface, grain surface and intergranular void space of the Indian, Brazilian and Appalachian itacolumites.

All the itacolumites have a common feature that constituting quartz grains are irregularly shaped and are separated from other grains by uniformly-narrow void spaces. These intergranular voids are well interconnected and extends three-dimensionally throughout the rock mass.

On the other hand, the Indian itacolumite is dissimilar to the Brazilian and Appalachian itacolumites in having more irregular grain shape and rugged relief of grain surface.

Porous nature of itacolumites is also ascertained by the AE study. Slab specimens of itacolumites were deformed and fractured in simple bending tests and accompanying AE signals were recorded and analyzed. AE characteristics of itacolumites (great numbers of event count, lower frequency, smaller amplitude and larger *m*-value) are similar to those of very porous rocks.

The results obtained by SEM and AE studies verify that the fabric of itacolumites can be schematically represented by the jigsaw puzzle model. This model can be further applied to the deformation process, especially fracturing stage, of itacolumites.

Acknowledgements

The authors express their gratitude to Dr. Katayama of Doshisha University for generously permitting us to use the AE measuring system for bending test and the computer program of AE analysis. They also thank the late Dr. D. N. Wadia in India and Dr. D. Shimizu for providing

us specimens of the Indian itacolumite and the Indian non-flexible quartzite, respectively. Thanks are also due to Messrs. K. Kobayashi, M. Uegaki, H. Ohta and T. Mizoe for help with experiments. Acknowledgement is also due to an anonymous referee for constructive comments.

References

- Derby, O. A., 1884, On the flexibility of itacolumite. *Amer. Jour. Sci.*, **28**, 203-205.
- DeVries, R. C. and Jugle, D. B., 1968, Structure-property relation in flexible sandstone. *Jour. Amer. Ceramic Soc.*, **51**, 387-390.
- Dusseault, M. B., 1980, Itacolumite: the flexible sandstone. *Quart. Jour. Eng. Geol. London*, **13**, 119-128.
- Fonseka, G. M., Murrell, S. A. F. and Barnes, P., 1985, Scanning electron microscope and acoustic emission studies of crack development in rocks. *Int. J. Rock Mech. Min. Sci. & Geomech. Abstr.*, **22**, 273-289.
- Ishimoto, M. and Iida, K., 1939, Observations sur les séismes enregistrés par le microsismographe construit dernièrement (1). *Bull. Earthq. Res. Inst. Tokyo Univ.*, **17**, 443-478. (in Japanese with French abstract)
- Kranz, R. L., 1983, Microcracks in rocks: a review. *Tectonophysics*, **100**, 449-480.
- Mae, I. and Nakao, K., 1968, Characteristics in the generation of micro-seismic noises in rocks under uniaxial compressive load. *Zairyou (Materials)*, **17**, 908-913. (in Japanese with English abstract)
- Marshall, J. R., Whalley, W. B. and Krinsley, D. H., 1987, The origin of some "chemical" textures on quartz-grain surfaces: interpretation and environmental implications. In Marshall, J. R., ed., *Clastic particles*. Van Nostrand Reinhold, New York, 248-253.
- Medlicott, H. B., 1874, Note on the habitat in India of the elastic sandstone, or so called itacolumyte. *Rec. Geol. Surv. India*, **7**, 30-31.
- Meredith, P. G., Main, J. G. and Jones, C., 1990, Temporal variations in seismicity during quasi-static and dynamic rock failure. *Tectonophysics*, **175**, 249-268.
- Mogi, K., 1962a, Study of elastic shocks caused by the fracture of heterogeneous materials and its relations to earthquake phenomena. *Bull. Earthq. Res. Inst. Tokyo Univ.*, **40**, 125-173.
- 1962b, Magnitude-frequency relation for elastic shocks accompanying fractures of various materials and some related problems in earthquake. *Bull. Earthq. Res. Inst. Tokyo Univ.*, **40**, 831-853.
- Sakanaka, K., 1989, Soft rock. *Seramikkusu (Ceramics)*, **24**, 94-95 (in Japanese).

- , Kameyama, T. and Fukuda, K., 1988, Possibility of synthesis of flexible ceramics. *Jour. National Inst. Chemical Eng. Japan*, **83**, 395-400. (in Japanese with English abstract)
- Suzuki, H. and Shimizu, D., 1993, Petrography of Indian, Brazilian and Appalachian itacolumites. *Jour. Geol. Soc. Japan*, **99**, 391-401.
- Tuomey, M., 1848, *Report on the geology of South Carolina*. Johnston, Columbia, pp. 9, 78-80.
- Verma, V. K., 1982, Flexibility in itacolumites from Brazil, India and United States. *Jour. Indian Assoc. Sediment.*, **3**, 19-28.
- Von Eschwege, M., 1823, Esquisse géognostique du Brésil. *Annales des Mines*, **8**, 410-413.
- Wetherill, C. M., 1867, Experiments on itacolumite, (articulite), with the explanation of its flexibility and its relation to the formation of the diamond. *Amer. Jour. Sci.*, **44**, 61-68.
- Wilson, C. J. L., 1973, The prograde microfabric in a deformed quartzite sequence, Mount Isa, Australia. *Tectonophysics*, **19**, 39-81.
- Wilson, P., 1979, Experimental investigation of etch pit formation on quartz sand grains. *Geol. Mag.*, **116**, 477-482.

(要 旨)

Suzuki, H., Yokoyama, T. and Nishihara, M., 1993, Scanning electron microscope and acoustic emission studies of itacolumites. *Jour. Geol. Soc. Japan*, **99**, 443-456. (鈴木博之・横山卓雄・西原正夫, 1993, 走査型電子顕微鏡およびアコースティック・エミッションによるイタコルマイトの研究. 地質雑, **99**, 443-456.)

インド・ブラジル・アパラチア産イタコルマイト(撓曲性コーツァイト)の組織を走査型電顕で観察した。共通する特徴として各石英粒子がかみ合っていて、かつ石英粒子の間に一様な狭い空隙が存在し、この空隙は孤立して存在するのではなく、3 次元的に連結していることが明らかになった。一方、インド産とブラジルおよびアパラチア産とでは、粒子の形態や表面構造に違いがみられ、それぞれ堆積性コーツァイトと変成コーツァイトの特徴を示すものと解された。また、イタコルマイトと固結砂岩の板状試料を単純曲げ試験で破壊させ、発生する AE の特徴を比較した。イタコルマイトでは、多数の AE が記録され、卓越周波数は小さく、振幅も小さいものが多い。両対数グラフで振幅-頻度関係が示す直線の勾配 m は、空隙の多い岩石の値に類似する。以上の結果から、イタコルマイトの組織と変形過程はジグソーパズルでモデル化できることがより一層明確となった。

Explanation of Plates

Plate I SEM photomicrographs of fractured surfaces of itacolumites. (Each white scale bar is 1 mm in length.)

1. Indian itacolumite
2. Brazilian itacolumite
3. North Carolinian itacolumite
4. Georgian itacolumite

Plate II SEM photomicrographs of fractured surfaces of non-flexible quartzites. (Each white scale bar is 0.5 mm in length.)

- 1A & 1B. Indian non-flexible quartzite
- 2A & 2B. Brazilian non-flexible quartzite

Plate III SEM photomicrographs of quartz-grain surfaces of itacolumites. (Distance between white hooked marks is 0.1 mm.)

1. Indian itacolumite
2. Brazilian itacolumite
- 3 & 4. North Carolinian itacolumite

Plate IV SEM photomicrographs of skeleton of intergranular void spaces. Void spaces were impregnated with cyanoacrylate resin, then quartz grains were completely dissolved away by hydrofluoric acid. (Each white bar is 0.5 mm in length.)

1. Indian itacolumite
2. Brazilian itacolumite
3. North Carolinian itacolumite
4. Georgian itacolumite