Silicon to Silicone: Stretching the Capabilities of Micromachines with Electroactive Polymers

Roy Kornbluh* Non-member

Ron Pelrine* Non-member

Harsha Prahlad* Non-member

Seiki Chiba* Member

Electroactive polymer transducers have many features that are desirable for MEMS devices. An especially attractive type of electroactive polymer is dielectric elastomer. Dielectric elastomers, transducers that couple the deformation of a rubbery polymer film to an applied electric field, show particular promise with features such as simple fabrication in a variety of size scales, high strain and energy density, high efficiency and fast speed of response, and inherent flexibility, environmental tolerance, and ruggedness. A variety of actuator configurations has been demonstrated at the small size scales needed for MEMS devices, including rolled “artificial muscle” actuators, framed and bending beam actuators for efficient opto-mechanical switches, and diaphragm and thickness mode actuators for pumps and valves. The performance benefits of electroactive polymers can allow for new generations of devices in microrobotics, communications, and biotechnology. Several challenges remain for electroactive polymers, including microfabrication, integration with driving electronics, and operational lifetime.

Keywords : electroactive polymers, artificial muscle, actuators, MEMS, optical MEMS, RF switches, microfluidics, microrobots

1. Introduction

MEMS devices can be small enough and inexpensive enough to be integrated with many objects that we encounter in our day-to-day or work-related activities. Microelectronics, based on silicon substrates, has allowed many objects and machines to be “smarter” by exchanging and processing information. MEMS can enable these technologies to not only be smarter, but to physically interact with people, other devices, and the environment. To physically interact, the objects must be capable of converting between electrical and mechanical energy. In other words, MEMS devices must include electromechanical transducers such as actuators, sensors, or generators. The ability to successfully be applied to MEMS devices is dependent on the performance of these transducers.

Transducers based on polymers are an attractive approach for MEMS applications. Polymers can be selected that are low in cost, compatible with a variety of fabrication techniques, and able to withstand a wide range of environmental conditions. Polymers are compliant enough to deform under applied loads, yet rugged enough not to break in two. In the past decade, polymers have increasingly been investigated as electromechanical transducers. Various polymer transducer technologies are under development ⁽¹⁾.

Electroactive polymer transducers can be generally classified into two categories: electrochemical and field activated. Electrochemical polymers use electrically driven mass transport of ions or electrically charged species to effect a change in the shape (or vice versa). Field-activated polymers use an electric field to effect a shape change by acting directly on charges within the polymer (or vice versa). Each type of electroactive polymer has

advantages and disadvantages for particular applications. Electrochemical polymers typically can exert high forces and can be driven by low voltages. However, they are relatively slow and limited in size (since they are dependent on molecular transport), require high currents and are relatively energy inefficient. Electrochemical polymers operate best over a narrow range of temperatures and must often be kept moist. In contrast, field-activated polymers can be fast, efficient, and relatively insensitive to temperature and humidity fluctuations. They operate at relatively high voltages and low currents, which usually requires additional voltage conversion components but makes the size and capacity of wires and interconnects lighter and less critical.

A type of field-activated electroactive polymer transducer that embodies the desirable properties of polymers is dielectric elastomers ⁽²⁾. These polymer transducers can convert a large amount of energy per unit mass or volume. They are rubbery materials that can undergo extremely large strains. Silicones and acrylics are the two classes of polymers that have best demonstrated exceptional performance as energy transducers. In fact, the maximum strains and energy densities demonstrated in these dielectric elastomers exceed those of any field-activated material, including single-crystal piezoelectric ceramics and magnetostrictive ceramics ⁽³⁾. Dielectric elastomers are based on a simple two-dimensional structure that can be fabricated at small size scales. Numerous dielectric elastomer elements can be fabricated on a single large polymer substrate. Combined with their inherent ruggedness, energy efficiency, and fast speed of response, dielectric elastomers are attractive for many MEMS applications.

Several existing MEMS technology areas that have profound benefits to society can take advantage of these electroactive polymer devices. These areas include microrobots for extending

* Roy Kornbluh (roy.kornbluh@sri.com),
SRI International
333 Ravenswood Ave., Menlo Park, California 94025

Table 1. MEMS applications for electroactive polymers.

Application	Common Existing Electrical Actuator Technology	Potential Advantages of Electroactive Polymers
Micro mirrors and other micro optic devices	Electrostatics, piezoelectrics	Higher speeds, transparent, shock resistant, less sensitive to dust, lower heat output
Micro robots	Electromagnetics, electrostatics, piezoelectrics, shape memory alloys	High energy density with large strokes well matched to robotic applications; suitable for direct-drive designs; able to scale up or down
Micro and Nano Assembly Automation	Electromagnetics, piezoelectrics, electrostatics	High speeds, good match for direct drive approaches, low cost
Mini and micro speakers	Electromagnetics, electrostatics	Lighter weight; more flexibility in design shape (e.g., conformal, flat); higher power; lower-cost materials
Micro nozzles and Inkjets	Piezoelectrics, thermal bubble jets	More controllable than bubble jets; better mechanical match to displacements and pressure than piezoelectrics
Micro switches (relays)	Electrostatics	Faster, higher pressures, less sensitive to dust
Micro fluidics (pumps, valves)	Electrostatics (including electrosmotic and other field-based drives), piezoelectrics, electromagnetics	Higher energy and power density; large strokes and good pressures for many micro pump applications such as micro lab chips

human sensory and motor capabilities, microoptical and electrical switches for improved communications, micropumps, valves and other microfluidic components for biotechnology, micro power generators to eliminate batteries and wires, and arrays of microdevices for making smart structures. These and other related technology areas and the benefits of electroactive polymers over existing actuator technologies are summarized in Table 1. Following a description of the dielectric elastomer technology in general, examples in the area of micro-robots, micro-optics and microfluidics are presented.

2. Principle of Operation of Dielectric Elastomers

Dielectric elastomer transducers are based on the electromechanical response of an elastomeric dielectric film with compliant electrodes on each surface. These transducers may be actuators, generators, or sensors. Actuators based on dielectric elastomer technology operate on the simple principle shown in Figure 1. When a voltage is applied across the compliant electrodes, the polymer shrinks in thickness and expands in area.

The net volume change of the polymer materials that we investigated is small because of their high bulk moduli. Therefore, the electrodes must be compliant, to allow the film to strain. The observed response of the film is caused primarily by the interaction between the electrostatic charges on the electrodes⁽⁴⁾. Simply put, the opposite charges on the two electrodes attract each other, while the like charges on the electrodes repel each other. Using this simple electrostatic model, we can derive the effective pressure produced by the electrodes on the film as a function of the applied voltage⁽⁵⁾. This pressure, p , is

$$p = \epsilon_r \epsilon_0 E^2 = \epsilon_r \epsilon_0 (V/t)^2 \quad (1)$$

where ϵ_r and ϵ_0 are the permittivity of free space and the relative permittivity (dielectric constant) of the polymer, respectively; E is the applied electric field; V is the applied voltage; and t is the film thickness. The response of the polymer is functionally similar to that of electrostrictive polymers, in that the response is directly related to the square of the applied electric field.

Many polymer materials can function as dielectric elastomer actuators, so, unlike most other electroactive polymers, different polymer materials can be selected for different applications, depending on the desired performance and physical properties.

(a) Functional element of dielectric elastomer actuators. Polymer Film compresses in thickness and expands in area when a voltage is applied across the film.

(b) Typical thickness or planar strain response to applied electric field for a film with no external loads.

Fig 1. Principle of operation of dielectric elastomer actuators.

The best-performing materials (those with greatest strains) are based on commercially available formulations of silicone rubber (polydimethyl siloxane) and acrylic elastomers.

Both silicone and acrylic materials have produced more than 100% strain. The specific energy density associated with such large deformations is greater than that produced by any other field-induced actuator technology. Because the pressure response is due to the electrostatic charges (electric field activated), it is very rapid. The strain response is limited in speed by the damping of the polymer and the modal frequencies that result from the elasticity of the polymer and the driven inertia. More details are given by Kornbluh et al.⁽⁶⁾.

Dielectric elastomers also can be operated in generator mode: a bias voltage is applied across the polymer, and the deformation of the polymer causes a change in the capacitance. If the capacitance decreases, there is a net production of electrical energy. For example, in large strain deformations the amount of electrical energy generated per unit volume of material, e , is

$$e = \epsilon_r \epsilon_0 E^2 = \epsilon_r \epsilon_0 (V/d)^2 \dots\dots\dots (2)$$

The operation of dielectric elastomers as generators is discussed in more detail by Pelrine ⁽⁷⁾.

The same transducer structure can serve as either an actuator, generator, or sensor, depending on how it is electrically driven.

In the actuator mode, the dielectric elastomers apply a mechanical pressure in response to an applied electric field. The reverse of this process can also yield a sensor. In this mode of operation, an applied pressure on the polymer film results in a change in capacitance between the compliant electrodes of the film. The change in capacitance is due to both the increase in planar area and a decrease in film thickness, and can be measured directly to determine the applied pressure. Since the polymer materials can be very soft in nature, they add minimum stiffness to the overall MEMS structures when used as a sensor. In addition, since the electric impedance and the output of a dielectric elastomer transducer are related to the deformation of the polymer film, it follows that these transducers could also be used to detect strain at the same time as performing actuation or generation. For example, the capacitance of a linear actuator could be directly related to the amount of its linear motion.

The basic element shown in Figure 1 can be incorporated into a wide variety of transducer configurations. For example, the film and electrodes can be formed into a tube, rolled into a scroll, supported by a frame, or laminated to a flexible substrate to produce bending. Which configuration is best depends on the application and properties of the film. In some cases, such as bending beam actuators (unimorphs and bimorphs), the film can be laminated directly to a structure whose shape or dynamics we want to control. The resulting composite may be considered to be a “smart structure.”

Polymer films have been fabricated by a variety of techniques including spin casting and dip coating. Electrodes have been applied by a variety of techniques including spray coating through a mask or screen printing. Photolithographic patterning of metallic traces and rigid polymer frames on the compliant dielectric elastomer has been demonstrated ⁽⁸⁾⁽⁹⁾.

3. Microrobots for Extending Human Presence and Reducing Drudgery

Microrobots, like larger robots, offer the promise of extending human presence to locations that are dangerous, dirty, or simply boring. However, microrobots can be inexpensive and unobtrusive enough that they may find much wider usage than larger robots. Small size and low cost confer several advantages over larger robots. Although each microrobot is small and weak, many small robots can act together in a swarm to accomplish a task. These swarms can cover an area faster and more reliably than individual larger robots. The swarms are inherently fault tolerant since many individual robots could fail. Imagine a swarm of small robots that continuously inspect and clean the surface of a ship ⁽¹⁰⁾, or paint a house, for instance.

Small robots can also provide access to hard-to-reach places where larger robots simply cannot enter. Such small robots can inspect inside the walls of a home for pests, inspect the intestinal tract of a person for polyps and remove them, perform search and rescue in a pile of rubble (for example, when a building collapses during an earthquake), and in small pipes and cavities in factories and power plants to detect chemical contamination or other flaws.

Fig. 2. Biologically inspired “inchworm” robotic platform using a rolled dielectric elastomer actuator.

Small robots are also very light and can be transported in space probes to fan out and study the surfaces of planets or asteroids. To perform all these tasks, the microrobots must have good mobility and dexterity. We can look to nature to provide inspiration. Insects and worms have excellent mobility and dexterity. Key to realizing such biologically inspired robots are actuators that can effectively reproduce the behavior of natural muscle.

Dielectric elastomers have been shown to be able to replicate several important features of natural muscle. These features include high peak power density, large strain, and high compliance ⁽¹¹⁾. Like natural muscle, dielectric elastomer “artificial muscle” can be multifunctional in the sense that it can also serve as a position sensor and the structure of the robot itself ⁽¹²⁾.

Robotic platforms using an inchworm-like propulsion system (Figure 2) could eventually be used to make small robots for tasks such as inspection in narrow pipes. This robotic platform is 16 mm in length. The body of the inchworm is also the rolled dielectric elastomer actuator that allows for propulsion. The rolled actuator has high strains and is flexible to allow for motion over rough surfaces or through convoluted pipes. This inchworm uses electrostatic clamps that enable it to travel over both vertical and horizontal surfaces.

Robots like the inchworm of Figure 2 are resistant to shock and a large amount of abuse. One could even step on such a robot and have it crawl away. This ability is in sharp contrast to the brittle and delicate nature of micromachined silicon-based devices.

4. Microoptical and Electrical Devices for Communication and Information Exchange

The amount of data transmitted over optical fiber is doubling every nine months ⁽¹³⁾. All-optical switches, in which there is no conversion of the information in the beam between light and electricity, are desirable because they are faster, can carry more information, and require less power than approaches that must convert the received signals to electrical signals before switching can take place.

Today’s switches typically can switch 256 inputs to 256 outputs. Newer versions that can switch between 1024 inputs and outputs are emerging. With the increase in data rates and number of lines, the demands on switching technology become more severe. A technology that can rapidly switch between a large number of inputs and outputs in a reliable, cost-effective, low-power manner would have widespread application. Existing technologies have shortcomings that can be addressed by electroactive polymer actuation.

The most mature of the all-optical switches are those based on

solid state materials such as lithium niobate, a ferroelectric crystalline material whose refractive properties can be controlled by an electric field (typically at 20 to 30 V). Solid state switches based on lithium niobate with as many as 48 inputs and outputs have been demonstrated⁽¹⁴⁾. Several problems limit the number of inputs and outputs. The waveguides require long physical length, making large-scale integration difficult. Problems also exist with crosstalk, particularly when multiple frequencies are used, such as in dense wavelength division multiplexing. The excessive light attenuation in this material can require large amounts of power and cause overheating. Since the material is affected by thermal instabilities, sophisticated thermal management is required. In addition, control electronics is relatively slow, a bottleneck for the optical switch.

Approaches based on opto-mechanical devices can address some of the problems of the solid state switches. These devices typically are silicon micromachined and use arrays of tilting mirrors⁽¹⁴⁾ that are usually electrostatically actuated. Such devices have been under investigation for several years⁽¹⁵⁾⁽¹⁶⁾. The mirrors are typically fabricated on silicon. Switching speeds of about 0.1 to 0.5 ms have been demonstrated. Other MEMS devices have been built that can steer an optical or other electromagnetic beam with variable beam deflection. One example is a variable blaze grating reported in⁽¹⁷⁾. It should be noted that most existing MEMS devices based on electrostatic actuators have relatively small deflections because the stroke of the electrostatic actuator is generally limited.

While having the advantage of being compact, energy efficient and low loss, opto-mechanical switches based on electrostatic micromachined devices do have some drawbacks. Air gap electrostatic devices are limited by the electric breakdown strength of air and therefore have intrinsically low force-to-mass ratio. This lower force limits their speeds. For example, existing response times are typically on the order of 0.2 ms for movements large enough to switch an optical beam. In contrast, response times are estimated at 0.01 ms for a 100- μ m-wide polymer actuator. Already, response times of 0.01 ms have been shown on macroscaled actuators.

A problem with silicon-based devices, in general, is that they require relatively expensive fabrication. Air gap electrostatic devices generally operate using submicron gaps that must be carefully patterned to prevent shorting. A high level of precision cannot be maintained over large areas, so large-area devices are currently difficult to fabricate. By contrast, the polymer actuators themselves set the gap, so there is only a single step, film deposition on a flat surface, in forming the gap. We believe that it may be feasible to make large-area devices by using monolithic polymer substrates.

Other opto-mechanical MEMS devices use piezoelectric ceramics in place of electrostatics. Piezoelectric devices require sol-gel or similarly sophisticated fabrication processes and would be expensive to fabricate over large areas. The long-term reliability of these devices may be an issue as well, since piezoelectric ceramics tend to crack under repeated high strains.

Many of the newer technologies such as bubble switches, thermo-optic switches, and liquid crystal switches each have attractive features, but are still largely unproven. Many of these devices have larger attenuation of the optical signal than desired. In addition, many of these devices are N-squared. That is, they are simply binary switches, and therefore a number equal to the

number of inputs multiplied by the number of outputs would be required. Some of these devices, such as the bubble switch and thermo-optic switch require a significant amount of energy to operate and might not scale well to larger numbers of inputs and outputs.

Technologies that can successfully switch large arrays of light might also find use in new types of very bright or large-area displays that are a fraction of the cost of today's large displays. Other unique photonic devices might also be possible. These devices would have a significant effect on consumer electronics as well as industrial automation and instrumentation.

Electroactive polymers offer the low-cost fabrication, speed of response, low attenuation, efficiency, and scalability demanded for optical switches. While such switches have not yet been fabricated, several small electro-optic devices have been made that offer some insight into their expected performance.

Figure 3 shows a framed actuator exhibiting an interesting optical effect: When actuated, the optical density of the electrode changes because of the stretching expansion of the film, and the optical density changes from dark to semitransparent.

We also built micro light scanners using a "unimorph" type of bending beam actuator. Unimorphs are formed by bonding an active dielectric elastomer to a thin beam that can bend but not stretch. The elongation of the dielectric elastomer causes the beam to bend. Bimorph actuators are similar, except that active film is used on both sides of the beam to enhance the bending.

Unimorph and bimorph actuators based on dielectric elastomers are similar in a number of ways to piezoelectric unimorphs and bimorphs. However, dielectric elastomer unimorphs and bimorphs can bend in much sharper angles because the strains they achieve

Fig. 3. Optical switch based on the change in transparency of the electrode of a dielectric elastomer due to the high strain during actuation. The electrodes are carbon fibrils. The elastomer is acrylic.

Fig. 4. Unimorph type of bending beam actuator: linear array of silicone unimorphs approximately 10 mm long (top left), schematic of unimorph structure (top right), scanned laser beam trace from a unimorph (middle and bottom).

are orders of magnitude larger. Bending angles as high as 270 degrees have been observed, and 360-degree or more bending is undoubtedly possible with optimization. Beam lengths were typically 2 to 10 mm, and operating frequencies of 10 to 50 Hz were achieved. Smaller beams could move much faster. Figure 4 shows a linear array of unimorphs undergoing 180 degrees of bending.

Arrays of 5 to 10 unimorphs were demonstrated. These can be fabricated in batch processes. We demonstrated arrays of unimorphs pushing paper, which suggests paper-feeder applications. Unimorphs can also be used to change the angles of mirrors. Figure 4 shows laser light scanning with a 2-mm unimorph. Such a device can form the basis of an opto-mechanical switch.

The tunable RF circuit is a related application that could also benefit from fast, reliable, and efficient switches. Many of the structures shown here for optical applications could also be adapted for use as electromechanical microswitches or relays.

5. Microfluidic Devices for Biotechnology and Materials Processing

Just as the ability to put large numbers of electrical switches on a chip allowed for a revolution in information processing, the ability to put a large number of pumps, valves, or other fluidic devices in a small area can revolutionize fluid handling and allow for great advancement in areas such as biotechnology, chemistry, and materials science.

In biotechnology, microfluidic devices promise to allow for rapid screening of pharmaceuticals—for example, understanding the roles of proteins and genes. Recently, the ability to rapidly screen for disease-causing agents and bioweapons has received much interest. In chemistry and materials science, microfluidic devices can allow for combinatorial methods to be used to screen for virtually any desired feature of compounds or material. Improved magnets, conductors, and light-emitting polymers are but a few examples.

Diaphragm actuators can form the basis of a simple micropump. Figure 5 shows the structure of a diaphragm actuator.

We have demonstrated a wide range of diaphragm actuators as small as 50 μm on a side. Pumping pressures as high as 20 kPa have been demonstrated. Theoretical calculations indicate that much higher diaphragm pressures, around 1 MPa, should be feasible.

Strokes are relatively large compared to those produced with other types of diaphragms, such as piezoelectric-driven diaphragms. Typically, silicone dielectric elastomers achieve displacements of 10% of the diaphragm diameter, while acrylic elastomers could easily achieve displacements of 50% of the diaphragm diameter. These acrylic elastomers can actuate from an essentially flat configuration to one that is hemispherical.

The large volume displacements per stroke of electroactive polymer actuators allows for tolerance of greater leakage and backflow losses in the valves. Passive flapper valves can be used, simplifying the pump design.

We demonstrated the potential of the diaphragm actuator for micropump applications by building a simple proof-of-principle minipump. The 20 mm diaphragm could pump as much as 40 ml/min of air at pressures of about 1 kPa.

Another promising actuator configuration for microfluidics is the enhanced thickness-change shear mode actuator, as shown in

Fig. 5. Diaphragm actuator: schematic of structure (top), photos of large out-of-plane displacement possible with an acrylic dielectric elastomer (bottom).

Fig. 6. Enhanced thickness change using a shear mode actuator: surface change in silicone gel on top of acrylic dielectric elastomer with electrodes in grid pattern (top two photos), schematic of basic element (bottom).

Figure 6. In the shear mode actuator, a relatively thick passive layer on top of the active dielectric elastomer greatly enhances the change in thickness during actuation. It is possible to create virtually any desired pattern of bumps and troughs on a single substrate by simply patterning the electrodes on one surface of the dielectric elastomer. These bumps and troughs could act as valves or pumping elements in a “lab-on-a-chip” type of microfluidic system. Such a device could also be the basis of a smart skin that controls the fluid flow such as in a boat or airplane.

6. Conclusion

Electroactive polymers based on dielectric elastomers have many desirable features for micro scale transducers. These features include low-cost fabrication on a variety of substrates, inherent flexibility, ruggedness and shock tolerance, high strain and energy output, high efficiency, and fast speed of response. These features will enable MEMS devices to interact with people and the environment and thereby extend their usefulness. Particular areas that can benefit include microrobots, microoptical and electrical switches, and other microfluidic components.

Various actuator configurations have been explored for practical applications, including small rolled “artificial muscle” actuators for microrobots, framed actuators and bending beam actuators for optical and electrical switching, diaphragm actuators, and shear mode actuators for microfluidics. Many of these configurations can be fabricated with simple techniques that can allow for individual microscopic devices or large arrays of elements on a

single polymer substrate.

Many technical challenges remain. Electronics for driving the relatively high voltages of the dielectric elastomer, though feasible, are not currently available and must be developed. Just as there are cost and fabrication advantages to integrating silicon-based MEMS devices with silicon chips, there are many potential benefits to integrating polymer-based devices with circuitry formed on polymer substrates. These circuits are an emerging technology that can complement electroactive polymers. However, we note that we have already demonstrated the ability to integrate electroactive polymers with silicon substrates and photolithographic techniques already used in microfabrication today⁽¹⁸⁾. Many aspects of lifetime and environmental tolerance also must be carefully examined to enable the technology to succeed.

Acknowledgments

Much of the basic dielectric elastomer technology was developed at SRI International under the management of the Micromachine Center of Japan, in the Industrial Science and Technology Frontier Program, Research and Development of Micromachine Technology of the Ministry of International Trade and Industry (Japan), and was supported by the New Energy and Industrial Technology Development Organization. The authors also wish to acknowledge the many employees at SRI who have helped make possible the results presented here.

(Manuscript received November 20, 2003)

References

- (1) P. Sommer-Larsen and R. Kornbluh : "Polymer Actuators", *Proc. Actuator 2002, 8th International Conference on New Actuators*, Bremen, Germany (June), pp. 371-378 (2002)
- (2) R. Kornbluh, R. Pelrine, Q. Pei, and V. Shastri : "Application of Dielectric EAP Actuators", *Electroactive Polymer (EAP) Actuators as Artificial Muscles—Reality, Potential and Challenges*, ed. Y. Bar-Cohen, pp. 457-495, SPIE Press, Bellingham, Washington (2001)
- (3) R. Pelrine, R. Kornbluh, Q. Pei, and J. Joseph : "High-Speed Electrically Actuated Elastomers with Over 100% Strain", *Science* **287**:5454, pp. 836-839 (2000)
- (4) R. Pelrine, R. Kornbluh, and G. Kofod : "High-Strain Actuator Materials Based on Dielectric Elastomers", *Advanced Materials* **2000** **12**:16, pp. 1223-1225 (2000b)
- (5) R. Pelrine, R. Kornbluh, J. Joseph, and J. Marlow : "Analysis of the Electrostriction of Polymer Dielectrics with Compliant Electrodes as a Means of Actuation", *Sensors and Actuators A: Physical* **64**, pp. 77-85, (1998)
- (6) R. Kornbluh, R. Pelrine, Q. Pei, S. Oh, and J. Joseph : "Ultrahigh Strain Response of Field-Actuated Elastomeric Polymers", *Proc. SPIE, Smart Structures and Materials 2000: Electroactive Polymer Actuators and Devices (EAPAD)*, Y. Bar-Cohen, ed., **3987**, pp. 51-64 (2000)
- (7) R. Pelrine, R. Kornbluh, J. Eckerle, P. Jeuck, S. Oh, Q. Pei, and S. Stanford : "Dielectric Elastomers: Generator Mode Fundamentals and Applications", in *Smart Structures and Materials 2001: Electroactive Polymer Actuators and Devices*, ed. Y. Bar-Cohen, *Proc. of SPIE*, Vol. 4329, pp. 148-156, (2001)
- (8) R. Kornbluh, R. Pelrine, J. Joseph, R. Heydt, Q. Pei, and S. Chiba : "High-Field Electrostriction of Elastomeric Polymer Dielectrics for Actuation", *Smart Structures and Materials 1999: Electroactive Polymer Actuators and Devices*, ed. Y. Bar-Cohen, *Proc. SPIE*, **3669** pp. 149-161, (1999)
- (9) R. Heydt and S. Chhokar : "Refreshable Braille Display Based on Electroactive Polymers", to be published in Proc. 23rd Intl. Display Research Conf., Phoenix, Arizona (15-18 September 2003)
- (10) A. Flynn, R. Brooks, and L. Tavrow : "Twilight and Cornerstones: A Gnat Robot Double Feature", Massachusetts Institute of Technology Artificial intelligence Laboratory Memo 1126 (1989)
- (11) R. Kornbluh, R. Full, K. Meijer, R. Pelrine, and S. Shastri : "Engineering a Muscle: An Approach to Artificial Muscle Based on Field-activated Electroactive Polymers", *Neurotechnology for Biomimetic Robots*, eds. J. Ayers, J. Davis, and A. Rudolph, MIT Press, pp. 137-172 (2002)
- (12) Q. Pei, S. Stanford, M. Rosenthal, R. Pelrine, R. Kornbluh, K. Meijer, and R. Full : "3-D Multifunctional Electroelastomer Actuators and Their Application for Biomimetic Walking Robots", *Smart Structures and Materials 2002: Industrial and Commercial Applications of Smart Structures Technologies*, ed. A. McGowan, *Proc. SPIE*, Vol. 4698, pp. 246-253 (2002)
- (13) S. Walsh : "Microsystems, Micromachines and Optical Networks: The Second Wave", *Micromachine Devices*, Vol. 6, No. 1, January, pp. 4-6 (2001)
- (14) D. Bishop, C. Giles, and S. Das : "The Rise of Optical Switching", *Scientific American*, January, pp. 88-94 (2001)
- (15) K. Akimoto, et al. : "Evaluation of Comb-Drive Nickel Micromirror for Fiber Optical Communication", *Proc. Tenth Annual International Workshop on Micro Electro Mechanical Systems*, Nagoya, Japan, Jan. 26-30, pp. 66-71 (1997)
- (16) C. Marxer, et al. : "Vertical Mirrors Fabricated by Reactive Ion Etching for Fiber Optical Switching Applications", *Proc. Tenth Annual International Workshop on Micro Electro Mechanical Systems*, Nagoya, Japan, Jan. 26-30, pp. 49-54 (1997)
- (17) D. Burns and V. Bright : "Micro Electro Mechanical Variable Blaze Gratings", *Proc. Tenth Annual International Workshop on Micro Electro Mechanical Systems*, Nagoya, Japan, Jan. 26-30, pp. 55-60 (1997)
- (18) S. Lacour, R. Pelrine, S. Wagner, and H. Prahald : "Photoconductive High-Voltage Switches of Thin-Film Amorphous Silicon for EAP Actuators", *Smart Structures and Materials 2003: Electroactive Polymer Actuators and Devices*, ed. Y. Bar-Cohen, *Proc. SPIE*, Vol. 5051, pp. 412-418 (2003)

Roy Kornbluh

developing and applying new transducer technologies.

(Non-member) was born in New York, United States of America, in 1960. He received his B.S. in mechanical engineering from Cornell University, Ithaca, New York (1982) and an M.S. in mechanical engineering from the Massachusetts Institute of Technology (1984), Cambridge Massachusetts, United States of America. He is a senior research engineer at SRI international where he works on

Ron Pelrine

(Non-member) was born in New Jersey, United States of America, on March 28, 1957. He received his B.S. in physics (1979) from the Massachusetts Institute of Technology; his M.S. in physics (1981) from the University of Washington; and his Ph.D. in mechanical engineering (1988) from the University of Texas (Austin). Dr. Pelrine is the director of the Advanced Transducers Program at SRI International.

Harsha Prahald

and applying new transducer technologies.

(Non-member) was born in Thiruvananthapuram, India in 1976. Dr. Prahald received his B.E. in mechanical engineering (1997) from Regional Engineering College, Trichy, India; his M.S. and Ph.D. in aerospace engineering (1999 and 2002) from the University of Maryland, College Park, United States of America. He is a Research Engineer at SRI International where he works on developing

Seiki Chiba

(Member) was born in Sendai City, Miyagi, Japan on July 9, 1952. He received his Ph.D. in Metallurgy & Material Science at the University of Wales (Britain). He jumped to the Ph.D. Course without doing the M.S. Course. He is presently an executive director at SRI International. He has been supervising advanced R&D projects awarded from Japanese Government.