electrochemical cell for hydrogen detection enables investigation of hydrogen permeation behavior at a selected area.

The purpose of this study is to develop the area-selective technique for electrochemical hydrogen detection with laser local activation. This newly developed technique was applied to measure hydrogen permeation behavior of iron at selected areas of various grain structures.

2. Experimental

2.1. Specimen

A 1.0 mm-thickness plate-type specimen was machined from an iron sheet. The chemical composition of the investigated iron is shown in **Table 1**. One side of the specimen for the hydrogen detection was mechanically ground under running water with SiC paper up to #1500, and then nickel was plated electrochemically in 0.312 kmol m⁻³ NiSO₄ / 0.781 kmol m⁻³ H₃BO₃ solution at 4 mA cm⁻² for 720 s. After nickel deposition, hydrogen entry (laser local activation) side of the specimen was mechanically ground under running water by SiC paper up to #4000 and then polished with colloidal silica.

2.2. Detection of Permeated Hydrogen after Laser Local Activation

A schematic drawing of cross section of cell unit (corrosion cell, specimen, and hydrogen detection cell) for electrochemical detection of permeated hydrogen with laser local activation is presented in **Fig. 2**. A specimen was placed between the corrosion cell (hydrogen entry side) and the hydrogen detection cell. The hydrogen detection side (nickel plated side) of the specimen was attached on the hydrogen

detection cell and the hydrogen entry side (laser local activation side) was attached on the corrosion cell, and then 0.2 cm³ of 1 kmol m⁻³ NaOH solution was introduced to the hydrogen detection cell. Pt wires were used as counter electrode, CE, and reference electrodes, RE, for the hydrogen detection cell. To measure permeated hydrogen through the specimen electrochemically, the specimen was polarized at -30 mV vs. Pt. After the current of hydrogen detection cell reached sufficiently low and steady value (it took about 72 ks after the potential was applied), the corrosion cell (the left side of the specimen in **Fig. 2**) was filled with 0.1 kmol m⁻³ NaCl solution. A schematic drawing of the experimental system for detection of permeated hydrogen with laser local activation is shown in **Fig. 3**. The cell unit was placed on XYZ stage, and the specimen was irradiated with a focused Nd-YAG laser (wave length 532 nm, pulse frequency 10 s⁻¹, pulse duration 8 ns, and power 20 mW at the front of the lens) for 10 s at several selected areas. The hydrogen permeation current was continuously recorded after the corrosion cell was filled with the NaCl solution.

2.3. Surface Observation

The surface morphology of the polished specimen before and after the tests was observed by scanning electron microscopy, SEM. Prior to the surface observation, the specimen was chemically etched with 3% nital solution for 5 s, then rinsed well with highly purified water and dried under air stream. An inverse pole figure (IPF) map of the specimen was also taken by electron backscatter diffraction, EBSD.

3. Results and Discussion

Figure 4 shows a typical example of SEM (back scattered electron) surface image of the specimen. The grains with an average size of 500 μm are clearly observed in the figure. From the IPF map, the observed grains in **Fig. 4** were assigned to each of (111), (103), (112), and (113).

Figure 5 shows SEM (back scattered electron) surface image (a) before and (b) after the tests, and (c) IPF map corresponding to **Fig. 5(b)**. In the figure (b) and (c), the circles and “P-x” indicate the irradiated area; the horizontal white

Fig. 2. Schematic drawing of cell unit (corrosion cell, specimen, and hydrogen detection cell) for electrochemical hydrogen detection cell with a corrosion cell.

Fig. 3. Schematic drawing of experimental system for detection of permeated hydrogen with laser local activation.

line close to P-1 in the figure was accidentally introduced during a sample preparation prior to the SEM observation. A clear difference is not found in the specimen surface between (a) and (b), which indicates that severe corrosion did not occur during the test and the dissolution reaction occurred mainly at the laser irradiated areas. From Fig. 5(b), it is noticed that laser irradiated different grain areas.

Fig. 4. SEM (back scattered electron) surface image of the specimen.

From Fig. 5(c), P-1 is triple point of (111), (112), (113) grains, P-2 is triple point of (112), (113), (213) grains, P-3 is inside (103) grain, and P-4 is inside (112) grain. However, it should be noted that the size of the irradiated area is different between these four areas due to an insufficient control of laser irradiation. The laser local activation with size-controlled would be essential to investigate hydrogen generation rate or hydrogen entry efficiency at a selected area. To achieve this, further improvement and optimization of the technique will be required.

The hydrogen permeation currents were measured at the four different areas shown in Fig. 5. **Figure 6** shows changes in hydrogen permeation current, (a) total duration of the experiment and (b) expansion of P-3 shown in Fig. 6 (a), after the laser irradiation. The arrows in the figure indicate times when the laser was irradiated. Changes of the hydrogen permeation currents are observed after the laser irradiation. Independent of the areas, the hydrogen permeation current increases suddenly after a certain time of laser irradiation, reaches a maximum value, and then decreases. It finally returns to almost the same value before the laser irradiation. The results shown here indicate that indirect activations of hydrogen generation and entry reactions were produced by the laser local activation.

A time lag, t_{lag} , was determined from the hydrogen permeation current as presented in **Fig. 7**, which enlarges the

Fig. 5. SEM (back scattered electron) surface image (a) before and (b) after the tests, and (c) IPF map corresponding to Fig. 5(b). (Online version in color.)

Fig. 6. Changes in hydrogen permeation current, (a) total duration of the experiment and (b) expansion of P-3 in (a) after the laser irradiation at different areas shown in Fig. 5.

Fig. 7. Determination method of t_{lag} from detected hydrogen permeation current.

hydrogen permeation current of P-1 shown in Fig. 6(a). At approximately 250 s after the irradiation, the hydrogen permeation current starts to increase, and a plateau region is observed before the decrease of the current. This result suggests that constant concentration of H_{ad} at the entry

side was achieved during laser irradiation. Several methods have been proposed to determine $D_H^{23,24)}$ from hydrogen permeation data. In the present study, the time lag method, $t_{lag} = L^2/(2D_H)$, was used to calculate D_H from the results shown in Fig. 6. In the equation, L is the thickness of the specimen. The difference of D_H was subtle among the four laser irradiated areas shown in Fig. 5 and the average D_H of the specimen was about $4.2 \times 10^{-9} \text{ m}^2 \text{ s}^{-1}$; this value is in good agreement with previously reported D_H of iron.²⁵⁾ With improving the accuracy of the irradiation position and size, this technique has a potential to visualize preferential entry sites for hydrogen in a relationship with grain structure such as a specific grain boundary or a particular grain orientation.

4. Conclusion

A combined technique of electrochemical cell with laser local activation for hydrogen detection was newly developed, and it was applied to measure hydrogen permeation behavior of iron at different grain structures. The increase of hydrogen permeation current was observed after the laser irradiation, suggesting that indirect activations of hydrogen generation and entry reactions were produced by a focused pulse YAG laser irradiation. The measured hydrogen permeation current makes it possible to calculate hydrogen diffusion coefficient. A clear dependence of hydrogen diffusion coefficient on grain structure was not found for iron.

REFERENCES

- 1) Y. Mukai: *Kobe Steel Eng. Rep.*, **55** (2005), 30.
- 2) S. Matsuyama: Delayed Fracture, Nikkan Kyogyo Shimben, LTD., Tokyo, (1989), (in Japanese).
- 3) T. Michler, Y. Lee, R. P. Gangloff and J. Naumann: *Int. J. Hydrogen Energ.*, **34** (2009), 3201.
- 4) K. Ebihara, T. Iwamoto, Y. Matsubara, H. Yamada, T. Okamura, W. Urushihara and T. Omura: *ISIJ Int.*, **54** (2014), 153.
- 5) H. Hatano, M. Fujinami, K. Arai, H. Fujii and M. Nagumo: *Acta Mater.*, **67** (2014), 342.
- 6) M. Koyama, H. Springer, S. V. Merzlikin, K. Tsuzaki, E. Akiyama and D. Rabbe: *Int. J. Hydrogen Energ.*, **39** (2014), 4634.
- 7) A. Nagao, C. D. Smith, M. Dadfarnia, P. Sofronis and I. M. Robertson: *Procedia Mater. Sci.*, **3** (2014), 1700.
- 8) T. Matsuno, Y. Sekito, E. Sakurada, T. Suzuki, K. Kawasaki and M. Suehiro: *ISIJ Int.*, **54** (2014), 2369.
- 9) A. Nagao, M. L. Martin, M. Dadfarnia, P. Sofronis and I. M. Robertson: *Acta Mater.*, **74** (2014), 244.
- 10) D. Hirakami, T. Manabe, K. Ushioda, K. Noguchi, K. Takai, Y. Hata, S. Hata and H. Nakashima: *Tetsu-to-Hagane*, **101** (2015), 59.
- 11) T. Michler, J. Naumann, M. Hock, K. Berreth, M. P. Balogh and E. Sattler: *Mater. Sci. Eng. A*, **628** (2015), 252.
- 12) I. Park, S. Lee, H. Jeon and Y. Lee: *Corros. Sci.*, **93** (2015), 63.
- 13) P. R. Sere, M. Zapponi, C. I. Elsner and A. R. Di Sali: *Corros. Sci.*, **40** (1998), 1711.
- 14) T. Kushida: *ISIJ Int.*, **43** (2003), 470.
- 15) K. Takai: *Zairyo-to-Kankyo*, **60** (2011), 230 (in Japanese).
- 16) A. Nagao, K. Hayashi, K. Oi and S. Mitao: *ISIJ Int.*, **52** (2012), 213.
- 17) E. Akiyama and S. Matsuoka: *J. Jpn. Inst. Met.*, **77** (2013), 622 (in Japanese).
- 18) M. A. V. Devanathan and Z. Stachurski: *J. Electrochem. Soc.*, **111** (1964), 619.
- 19) J. McBrean, L. Nanis and W. Beck: *J. Electrochem. Soc.*, **113** (1966), 1218.
- 20) H. Okada, G. Itho and M. Kanno: *J. Jpn. Inst. Light Met.*, **42** (1992), 112.
- 21) K. Yanada, M. Sakairi, T. Kikuchi, Y. Oya and Y. Kojima: *Surf. Interface Anal.*, **42** (2010), 189.
- 22) M. Sakairi, M. Kinjyo and T. Kikuchi: *Electrochim. Acta*, **56** (2011), 1786.
- 23) T. Tsuru: *Zairyo-to-Kankyo*, **63** (2014), 3 (in Japanese).
- 24) M. Sakairi: *Electrochemistry*, in press (in Japanese).
- 25) T. Kushida: *Zairyo-to-Kankyo*, **49** (2000), 195 (in Japanese).