Thermodynamics of the α - γ Transformation of Iron Alloys*

By Tsuguyasu Wada**

Synopsis

The thermodynamics of the α - γ transformation of iron alloys was discussed. The partial free energy of transferring a solute Y from α - to γ -alloy, $\Delta^0 G_Y^{\alpha \rightarrow \gamma \text{Fe}}$, was evaluated from known thermodynamic properties of the alloys. It was shown that the energy of carbon, $\Delta^0 G_C^{\alpha \rightarrow \gamma \text{Fe}}$, was not a linear function of temperature but should be curved at about 1000°K, probably due to the magnetic ordering of α -iron. The energy was calculated according to the Zener-Hillert theory taking account of the magnetic entropy of the α -iron, and an agreement between the theoretical and the experimental values was obtained. Similar evaluations were carried out for Fe-N, Fe-Ni, and Fe-Mn alloys. Discussions were also made on the thermodynamics of the martensite and bainite reactions.

I. Introduction

It was about two decades ago when the thermodynamical theories were proposed by Zener¹⁾ and by Oelsen²⁾ for α - γ equilibrium in iron alloys. These may be called the single-parameter theory. In spite of its crudeness, this theory was recognized to be useful for considering the α - γ equilibrium of iron alloys. Thus the fruitful applications³⁾⁻⁵⁾ have been made in the works performed before the middle of 1950's. Some problems, however, such as the anomalous γ -loop in Fe-Cr system were remained not interpreted by this theory.

In 1955 Zener⁶⁾ again proposed a two-parameter theory, in which the free energy change for α - γ transformation of iron was separated into the magnetic and nonmagnetic parts which were independently influenced by addition of alloying elements. Thus interpretations became possible for the γ -loop of the Fe-Cr system and for the different influences of an alloying element on the M_s temperature and on the transformation at higher temperatures. The theory was refined by Weiss and Tauer,⁷⁾ who recalculated the magnetic and the nonmagnetic energies on the basis of the current specific heat data.

Another approach to the two-parameter theory has been made by Svechnikov and Lesnik⁸⁾ from a purely thermodynamic viewpoint. They assigned two parameters to the free energy change for transformation of pure solute and to the difference in the interchange energies between α - and γ -phases. The γ -loop in the Fe-Cr system is also explainable with this approach by taking account of the temperature dependence of either or both of the two parameters. It seems unusual for a metallic system that the interchange energy has a large configurational entropy term. In fact, however, if the difference in the free energy of chromium between α - and γ -Fe-Cr alloys is a linear function of temperature, its entropy term of about 1.2 e.u. is

necessary in order to interpret its γ -loop as pointed out by the present author.⁹⁾ This is quite higher than the value expected for the difference in the atomic configurations between bcc and fcc structures. It may consequently be suggested that some excess entropy should arise from the non-configurational source.

Recently, Hillert, T. Wada, and H. Wada¹⁰⁾ extended the Zener's two-parameter theory for analysing Fe-Ni and Fe-Mn alloys, and showed that a reasonable partial free energy curve could be obtained by taking account of the temperature-dependent magnetic entropy term. This approach may be an answer to the question how the free energy of transformation depends on the temperature. The present author formerly reported a work⁹⁾ in which a linear dependence on the temperature, namely a constant entropy of transformation, was assumed. Though this may be good as a crudest approximation, our prime interest at present is to know the precise behaviour of the free energy of transformation as a function of the temperature and composition. The statistical-thermodynamics may be a useful tool for this purpose, if the microscopic quantities necessary for its calculation could be sufficiently available.

Among the statistical-thermodynamical calculations so far published on the transformation of iron alloys, those by Kaufman, Radcliffe, and Cohen¹¹⁾, and by Aaronson, Domian, and Pound¹²⁾ are the outstanding ones for the austenite $\rightarrow$ proeutectoid ferrite transformation. The model adopted by these authors was essentially the one with pairwise interactions. McLellan showed, on the other hand, that the partial free energy of solute in Fe-C¹³⁾ and Fe-N¹⁴⁾ alloys had an appreciable non-configurational entropy term, which may be mainly due to the change in the vibrational entropy. It is a problem of great interest for us what size and what kind of the non-configurational entropies are associated with the iron solid solutions.

In the present article, a critical discussion will be offered for the α - γ equilibrium in some iron alloys. The applications to the bainite and martensite reactions will also be briefly presented.

II. Basic Formulation

When α - and γ -phases are in equilibrium with each other, the chemical potential of a component i in the two phases are identical. The activity of i , which is usually referred to different standard states for each phase, has generally a relationship such as

$$\ln a_i^\alpha - \ln a_i^\gamma = \Delta G_i^{\alpha \rightarrow \gamma \text{Fe}} / RT \dots \dots \dots (1)$$

* Received June 20, 1967.

** National Research Institute for Metals, Nakameguro, Meguro-ku, Tokyo.

where a_i^α and a_i^γ are the activity of i in α - and γ -phase respectively, and $\Delta G_i^{\alpha \rightarrow \gamma \text{Fe}}$ is an energy for transferring one mole of i from the standard state in α -iron to that in γ -iron.

From a general relation of the statistical thermodynamics,

$$-\ln a_i^* = \frac{\partial \ln Q}{\partial n_i} \quad (2)$$

is given, where Q is the partition function of the alloy, n_i is the number of atom i , a_i^* is the absolute activity of i . The condition of equilibrium is $a_i^{\alpha} = a_i^{\gamma}$, or

$$\frac{\partial}{\partial n_i} \left(\ln \frac{Q^\alpha}{Q^\gamma} \right) = 0 \quad (3)$$

if the energy zero points for both Q 's are taken equal. If the partition functions of the standard states of the both phases are denoted by $^\circ Q^\alpha$ and $^\circ Q^\gamma$, we can easily derive a relationship,

$$\Delta G_i^{\alpha \rightarrow \gamma \text{Fe}} / RT = - \frac{\partial}{\partial n_i} \left(\ln \frac{^\circ Q^\gamma}{^\circ Q^\alpha} \right) \quad (4)$$

Eqs. (1) and (4) hold true for any component of the alloy. For iron, it may often be convenient to select the standard state as pure iron, because most systems in problem are the dilute solution in iron. For a solution which is so dilute as the Raoult's law is valid for the solvent, Eq. (1) becomes

$$\ln x_{\text{Fe}}^\alpha - \ln x_{\text{Fe}}^\gamma = \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma} / RT \quad (5)$$

where x_{Fe}^α and x_{Fe}^γ are the mole fractions of iron in each phase, and $\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}$ is the free energy change for transformation of pure Fe from α to γ . As $x_{\text{Fe}}^\alpha, x_{\text{Fe}}^\gamma \simeq 1$, Eq. (5) becomes approximately

$$\sum x_j^\gamma - \sum x_j^\alpha = \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma} / RT \quad (6)$$

where $\sum x_j$ represents the sum of the mole fractions of constituents other than iron.

For the activity of a solute, it is sometimes convenient to adopt the standard state as its infinite dilution. Then Eq. (1) gives the following relation for a dilute solution of the solute Y .

$$\ln x_Y^\alpha - \ln x_Y^\gamma = \Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} / RT \quad (7)$$

If we alternatively adopt a standard state of Y as its pure metal,

$$\Delta G_Y^{\alpha \rightarrow \gamma} = \Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta A_Y^{\alpha \rightarrow \gamma} \quad (8)$$

putting

$$\Delta A_Y^{\alpha \rightarrow \gamma} \equiv RT \ln (\gamma_Y^\alpha / \gamma_Y^\gamma)_{x_Y \rightarrow 0} \quad (9)$$

where γ_Y is the Raoultian activity coefficient of Y . Since it is a good approximation over a relatively wide range of composition that

$$\frac{RT \ln \gamma_Y^\alpha}{(1 - x_Y^\alpha)^2} = A_Y^\alpha \quad \text{and} \quad \frac{RT \ln \gamma_Y^\gamma}{(1 - x_Y^\gamma)^2} = A_Y^\gamma,$$

Eq. (1) gives an approximation for wider range of composition as

$$\ln x_Y^\alpha - \ln x_Y^\gamma = [\Delta G_Y^{\alpha \rightarrow \gamma} - A_Y^\alpha (1 - x_Y^\alpha)^2 + A_Y^\gamma (1 - x_Y^\gamma)^2] / RT \quad (10)$$

or

$$\ln x_Y^\alpha - \ln x_Y^\gamma = [\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} + A_Y^\alpha x_Y^\alpha (2 - x_Y^\alpha) - A_Y^\gamma x_Y^\gamma (2 - x_Y^\gamma)] / RT \quad (11)$$

Thus the α - γ equilibrium is determined approximately by $\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}$ and $\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}}$, and more exactly by $\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}$, $\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}}$, or $\Delta G_Y^{\alpha \rightarrow \gamma}$, A_Y^α and A_Y^γ .

A_Y is known as the interchange energy in the zeroth approximation of the quasi-chemical method. It is also a quantity similar to the excess stability which was recently proposed by Darken¹⁵⁾ based on a more general basis.

There is a phase boundary where the total free energy of α -phase is equal to that of γ -phase. This line has been called by several terms, i.e. the T_0 line, the allotropic phase boundary, the equi-energy line, etc. For a system in which Eq. (10) or (11) is a good approximation, the T_0 composition $x_Y(T_0)$ is given by the following equation.⁹⁾

$$x_Y(T_0) = [\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma} \pm \{(\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma})^2 + 4 \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma} \Delta A_Y^{\alpha \rightarrow \gamma}\}^{1/2}] / 2 \Delta A_Y^{\alpha \rightarrow \gamma} \quad (12)$$

Eq. (12) may be expanded in a series that

$$x_Y(T_0) = - \frac{\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}}{\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}} + \left(\frac{\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}}{\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}} \right)^2 \times \frac{\Delta A_Y^{\alpha \rightarrow \gamma}}{\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}} - 2 \left(\frac{\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}}{\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}} \right)^3 \times \left(\frac{\Delta A_Y^{\alpha \rightarrow \gamma}}{\Delta G_Y^{\alpha \rightarrow \gamma \text{Fe}} - \Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}} \right)^2 + \dots \quad (13)$$

which may be useful for a dilute solution by neglecting unnecessary high-order terms.

III. The Value of $\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}$

The difference in the free energy between α - and γ -iron was first evaluated by Johansson,¹⁶⁾ and then many estimations have been made by using current data of the specific heat and the heat of transformations. The values of $\Delta G_{\text{Fe}}^{\alpha \rightarrow \gamma}$ below 1200°C are shown in Fig. 1. The Darken and Smith's¹⁷⁾ one (DS) was accepted to be reliable especially in the medium temperature range. However, Kaufman and Cohen¹⁸⁾ pointed out that $\Delta H_{\text{Fe}}^{\alpha \rightarrow \gamma}$ by DS in the low temperature range seemed too high in view of the experimental specific heat measurement by Normann and Scheil.¹⁹⁾ Another criticism for the DS curve was made by Weiss and Tauer⁷⁾ (WT) who pointed out the existence of anti-ferromagnetism in γ -iron with Néel temperature about 80°K and moment 0.57 Bohr magnetons, and also that the Debye temperature of γ -iron estimated by DS should be slightly changed. As shown in Fig. 1, however, the curve WT shows a $\Delta H_{\text{Fe}}^{\alpha \rightarrow \gamma}$ higher than DS and therefore may not be able to escape from the same criticism as for DS in its low temperature portion.

Kaufman, Clougherty, and Weiss²⁰⁾ (KCW) reported a new evaluation. They selected the Debye temperature of γ -iron as the same as α -iron, 432°K,

Fig. 1. The values of $\Delta G_{Fe}^{\alpha+\gamma}$. (0° to 1200°K)
 DS : Darken and Smith¹⁷⁾ WT : Weiss and Tauer⁷⁾
 F : Fisher²¹⁾ KC : Kaufman and Cohen¹⁸⁾ GO :
 Gilbert and Owen²³⁾ KB : Kohlhaas and Braun²⁴⁾
 KCW : Kaufman, Clougherty, and Weiss²⁰⁾ OC :
 Orr and Chipman.⁶⁵⁾

and made thorough investigations on the electronic and magnetic specific heats for both phases.

Fisher,²¹⁾ Kaufman and Cohen,²²⁾ and Owen and Gilbert²³⁾ have given formulas representing $\Delta G_{Fe}^{\alpha+\gamma}$ within some temperature ranges; namely,

Fisher:

$$\Delta G_{Fe}^{\alpha+\gamma} = 1238 - 0.395T - 12.5 \times 10^{-4}T^2$$

(up to 500°K)

Kaufman and Cohen:

$$\Delta G_{Fe}^{\alpha+\gamma} = 1202 - 2.63 \times 10^{-3}T^2 + 1.54 \times 10^{-6}T^3$$

(200° to 900°K)

Owen and Gilbert:

$$\Delta G_{Fe}^{\alpha+\gamma} = 1474 - 3.4 \times 10^{-3}T^2 + 2 \times 10^{-6}T^3$$

(800° to 1100°K)

As shown in Fig. 1, the $\Delta G_{Fe}^{\alpha+\gamma}$ curves for these formulas can be reasonably connected with each other at their overlapping temperature ranges, thus forming a curve for the whole range below 1100°K.

Recently, Kohlhaas and Braun²⁴⁾ (KB) gave a curve according to their measurements on the specific heat of γ -alloys. This curve is in reasonable agreement with the F-KC-OG curve. As Kaufman and Cohen¹⁸⁾ have pointed out, their value is in good agreement with the Johansson's early work. Therefore we may find similarities between Johansson's, F-KC-OG's, and KB's values.

The newest evaluation was made by Orr and Chipman,⁶⁵⁾ which was very close to the DS line as shown in Fig. 1.

As a conclusion, we have three important groups for value of $\Delta G_{Fe}^{\alpha+\gamma}$ below 1100°K, namely, (1) Darken-Smith and Orr-Chipman, (2) Johansson, Fisher, Kaufman-Cohen, Owen-Gilbert, and Kohlhaas-Braun, and (3) Kaufman-Clougherty-Weiss. The Darken and Smith's value in the low temperature region seems to be open to question, but above 800°K it may be quite reliable. In the work by Hillert, T. Wada, and H. Wada,¹⁰⁾ the Kohlhaas and Braun's value was used for the low temperature region, because it was the best one for explaining the experimental results. However, we do not have any sufficient reason to judge the small differences, for instance, between KB and KCW.

For the range from 1200° to 1600°K, where $\Delta G_{Fe}^{\alpha+\gamma}$ has negative values, we have some experimental facts available for selecting the values of $\Delta G_{Fe}^{\alpha+\gamma}$. Hillert, T. Wada, and H. Wada¹⁰⁾ made careful measurements on the difference between the solute concentrations at $\alpha/\alpha+\gamma$ and $\gamma/\alpha+\gamma$ boundaries in iron alloys with some loop-forming elements. As these alloys were sufficiently dilute to regard the iron as being obeyed by Raoult's law, Eq. (5) was valid for α - γ equilibrium, namely,

$$\ln \left(\frac{1-x^\alpha}{1-x^\gamma} \right) = \frac{\Delta G_{Fe}^{\alpha+\gamma}}{RT} \quad \dots\dots\dots (5)'$$

where x^α and x^γ are the mole fractions of the solute at $\alpha/\alpha+\gamma$ and $\gamma/\alpha+\gamma$ boundary. The results at temperatures in neighbourhood of 1150°C are shown in Table 1. The values of $\Delta G_{Fe}^{\alpha+\gamma}$ calculated by several authors are listed in Table 2. We may find that the experimental results seem to favour the low values given by DS or KCW. The same conclusion may also be derived from the work by Fischer et al.⁶⁶⁾

In Fig. 2, $\Delta G_{Fe}^{\alpha+\gamma}$ curves by DS and KCW for above 1100°K are shown. They are slightly different with each other in high temperature region, since KCW improved the evaluation of $\Delta H_{Fe}^{\alpha+\gamma}$ at upper transition temperature from -165 cal/mol selected by DS to -224 cal/mol, taking account of a recent value of -263 ± 70 cal/mol reported by Ferrier and Olette.²⁵⁾ Though the KCW curve is a newer evaluation and therefore probably more reliable one, we could not simply discard the DS value for the following reason.

Table 2. Maximum $\Delta G_{Fe}^{\alpha+\gamma}/RT$ by several authors¹⁰⁾

Author	Ref.	Max. $\Delta G_{Fe}^{\alpha+\gamma}/RT$
Darken and Smith	17)	-0.0059
Zener	1)	-0.0077
Oelsen	2)	-0.0083
Kaufman et al.	20)	-0.0061
Kohlhaas and Braun	24)	-0.0072

Table 1. Equilibrium concentration x^α and x^γ for α stabilizers¹⁰⁾

Alloying element	Temperature (°K)	x^α (at%)	x^γ	$\ln \frac{1-x^\alpha}{1-x^\gamma}$	$\Delta G_{Fe}^{\alpha+\gamma}/RT$ (Kaufman et al. ²⁰⁾)
Mo	1371	1.98	1.34	-0.0065	-0.0061
Sb	1424	1.67	1.13	-0.0055	-0.0059
Sn	1373	1.34	0.75	-0.0060	-0.0061
W	1438	1.75	1.20	-0.0056	-0.0059

Fig. 2. The values of $\Delta G_{Fe}^{\alpha \rightarrow \gamma}$. (1100° to 1800°K)
 DS: Darken and Smith¹⁷⁾
 KCW: Kaufman, Clougherty, and Weiss²⁰⁾

The melting point of bcc iron is 1539°C (Darken and Gurry²⁶⁾), 1536°C (Benz and Elliott²⁷⁾), 1535°C (Buckley and Hume-Rothery⁶³⁾), or 1534°C (Hellawell and Hume-Rothery,²⁸⁾ Hansen²⁹⁾), while that for fcc iron is estimated to be 1531°C (Darken and Gurry²⁶⁾) or 1528°C,⁶³⁾ i.e. about 8° to 6°C lower than bcc, by extrapolating the solidus and liquidus lines between the austenite and the liquid. Since the entropy of fusion of bcc iron is 1.9 e.u., the difference in the m.p. of about 8° to 6°C corresponds to the energy difference of 15 to 11 cal, which is in rather better agreement with DS than KCW. However, the accuracy of the extrapolation of the γ /liquid phase boundaries is not so high. It should also be noticed that the Orr and Chipman's evaluation⁶⁵⁾ is closer to KCW rather than DS in the γ - δ region.

Cohen et al.^{30,31)} found that an hcp phase, ϵ , exists as a modification of iron under a high pressure. Though the ϵ -phase is not stable at 1 atm pressure, its free energy is lower than that of γ -phase at temperatures below 390°K. The energy relationship estimated by these authors is represented in Fig. 3.

IV. Fe-C and Fe-N Alloys

We will start our discussion on some real systems

Fig. 3. Free energy-temperature relations for the modifications of iron³⁰⁾

with the Fe-C alloy, an interstitial alloy of practically most importance. Our prime interest is to determine the $\Delta G_C^{\alpha \rightarrow \gamma Fe}$, the energy of transfer of one mole of carbon dissolved in α -iron into γ -iron. When the Henrian activities of carbon in the phases which are in equilibrium with each other are written as $^{\circ}a_C^{\alpha}$ and $^{\circ}a_C^{\gamma}$, respectively, Eq. (1) gives a relation

$$\ln ^{\circ}a_C^{\alpha} - \ln ^{\circ}a_C^{\gamma} = \Delta G_C^{\alpha \rightarrow \gamma Fe} / RT \dots \dots \dots (14)$$

where $\Delta G_C^{\alpha \rightarrow \gamma Fe}$ is the energy of transfer of one mole of carbon from an infinitely dilute α -alloy into an infinitely dilute γ -alloy. Then our first work to be made is to estimate $^{\circ}a_C^{\alpha}$ and $^{\circ}a_C^{\gamma}$ for both phases.

Activity measurements of carbon in Fe-C alloys were made by Smith,³²⁾ Dünwald and Wagner,³³⁾ Scheil et al.³⁴⁾ and Bungardt et al.³⁵⁾ by means of CH_4/H_2 or CO/CO_2 equilibrium methods. The results of these authors give a basis for discussing the thermodynamic behaviour of the austenite phase. McLellan¹³⁾ and quite recently Chipman³⁶⁾ have reanalysed Fe-C alloys using these experimental data. Calculations were also made by Kaufman, Radcliffe, and Cohen,¹¹⁾ and Aaronson, Domian, and Pound¹²⁾ in connection with the transformation of Fe-C alloys. The calculations by the latter two groups are based on the pairwise interaction model, while McLellan¹³⁾ evaluated the vibrational entropy change under an assumption that the configurational entropy is substantially ideal.

A brief discussion will now be given on the statistical-thermodynamics of the interstitial alloys. Let the number of the iron and the interstitial atoms be n_{Fe} and n_i , respectively, and the number of the interstitial sites per one Fe atom be β . When the solute-solute repulsive energy is not very high, the solute atoms could be regarded as being distributed randomly among the possible interstitial sites. Then the partition function Q of the alloy can be written as

$$Q = K(T) n_{Fe} \frac{\beta^{n_{Fe}} n_i!}{n_i! (\beta n_{Fe} - n_i)!} \times \exp \left[\frac{n_i \epsilon_{Fe-i} - \bar{X} \epsilon_{ii}}{kT} \right] q^I \dots \dots \dots (15)$$

where $K(T)$ is the partition function of an Fe atom, ϵ_{Fe-i} the interaction energy of Fe- i per one i atom, $\bar{X}$ the number of the i - i pair, ϵ_{ii} the repulsive energy of an i - i pair, q^I the non-configurational partition function that includes the electronic, vibrational, and the magnetic terms. $\bar{X}$ becomes $Z_i n_i^2 / 2\beta n_{Fe}$ in random mixing, where Z_i is the co-ordination number of interstitial sites.

From Eq. (15) we obtain an expression for the activity of i as follows:

$$\ln a_i = - \frac{\partial \ln Q}{\partial n_i} = \ln \frac{n_i}{\beta n_{Fe} - n_i} - \frac{\epsilon_{Fe-i}}{kT} + \frac{Z_i n_i}{\beta n_{Fe}} \cdot \frac{\epsilon_{ii}}{kT} + \frac{\bar{G}_i^{nc}}{RT} \dots \dots \dots (16)$$

where $\bar{G}_i^{nc}$ denotes the non-configurational term of the

partial free energy of i . Eq. (16) may be rewritten by using mole fraction $x_i (= n_i/n_i + n_{Fe})$ and the energies per mole as

$$\ln a_i = \ln \frac{x_i}{\beta - (1 + \beta)x_i} - \frac{E_{Fe-i}}{RT} + \frac{x_i}{\beta(1-x_i)} \times \frac{Z_i E_{ii}}{RT} + \frac{\bar{G}_i^{nc}}{RT} \dots (17)$$

The number of the octahedral interstice in the austenite is the same as that of the host atom, and thus $\beta=1$ for the austenite. On the other hand, the number of the distorted octahedral interstice in α -iron gives $\beta=3$.

When $x_i \ll 1$, it is approximately written that

$$\frac{x_i}{1-x_i} \cdot \frac{Z_i E_{ii}}{RT} \approx -\ln \left(1 - x_i \frac{Z_i E_{ii}}{RT} \right) \dots (18)$$

So Eq. (17) is written as an approximate form for the austenite,

$$\ln a_i = \ln \frac{x_i}{1 - (2 + Z_i E_{ii}/RT)x_i} - \frac{E_{Fe-i}}{RT} + \frac{\bar{G}_i^{nc}}{RT} \dots (19)$$

Most of the previous investigators including Takeuchi and Kachi,³⁷⁾ Smith,³²⁾ and Kaufman et al.¹¹⁾ started, however, with non-random models. Kaufman et al.¹¹⁾ assumed that the occupancy of an interstitial site by a solute atom prevents $(z-1)$ of the surrounding interstitial sites from being occupied by other interstitial atoms. Then the configurational entropy term becomes¹¹⁾

$$\bar{s}_i^{conf.} = -k \ln \frac{x_i}{1 - (z+1)x_i} \dots (20)$$

Kaufman et al. gave 5 for z in Fe-C austenite.

McLellan et al.⁶⁴⁾ assumed in their recent report that the blocked sites can be overlapped, and obtained an expression somewhat different from Eq. (20). The difference becomes appreciable when x_i is higher than 0.08.

Darken and Smith³⁸⁾ considered that the energy of a carbon atom is dependent on whether it has a nearest neighbor carbon atom or not. Then an equation of the activity of carbon in the austenite phase has been obtained as

$$\ln a_c = \ln \frac{n_c}{n_{Fe} - (13 - 12\theta_2)n_c} + I \dots (21)$$

where $\theta_2 = \exp(-E/RT)$ and E is the energy required to bring two gram atoms of carbon into nearest neighbor sites. Eq.(21) can be rewritten by using mole fraction x_c as

$$\ln a_c = \ln \frac{x_c}{1 - (14 - 12\theta_2)x_c} + I \dots (22)$$

from experimental results, E was evaluated to be 1500 cal/mol on the average, which gives $14 - 12\theta_2$ to be 7.6. This should be compared with 6 of Kaufman et al.¹¹⁾

In general, the non-randomness in the solute distribution may have influences on the entropy term and also on the $\bar{X}$. So the first term of Eq.(19) is changed

into

$$\ln \frac{x_i}{1 - (2 + p + qZ_i E_{ii}/RT)x_i} \dots (23)$$

where the parameter p may be regarded as an apparent decrease in the effective sites around a carbon atom, and q may be the ratio of the effective number of i - i pair to that in the random mixing. So-called quasi-chemical³⁹⁾ approach assumes that

$$\frac{(\text{Number of empty site-empty site pair})}{(\text{Number of empty site-}i\text{ pair})^2} \times (\text{Number of } i\text{-}i \text{ pair}) = \exp \left(-\frac{\epsilon_{ii}}{kT} \right) \dots (24)$$

Namely,³⁷⁾

$$\frac{\bar{X} [(n_{Fe} - n_i)Z_i/2n_{Fe}]}{(1/2n_i Z_i - \bar{X} Z_i)^2} = \exp \left(-\frac{\epsilon_{ii}}{kT} \right) \dots (25)$$

When $n_i \ll 1$ so that $n_i \gg \bar{X}$, Eq.(25) can be approximately written as

$$\bar{X} \approx \frac{Z_i n_i^2}{2n_{Fe}} \exp \left(-\frac{E_{ii}}{RT} \right) \dots (26)$$

Thus we obtain

$$q \approx \exp \left(-\frac{E_{ii}}{RT} \right) \dots (27)$$

We would expect a simple relationship that

$$\frac{12-p}{12} = q \dots (28)$$

since the number of the nearest neighbour interstitial sites is 12 in fcc. Then substituting Eqs. (27), (28) into (23), we obtain an expression of the activity of i based on a nonrandom quasi-chemical approach as follows:

$$\ln a_i = \ln \frac{x_i}{1 - [14 - 12(1 - E_{ii}/RT) \exp(-E_{ii}/RT)]x_i} - \frac{E_{Fe-i}}{RT} + \frac{\bar{G}_i^{nc}}{RT} \dots (29)$$

This is a quite similar expression to that by Darken and Smith, except $(1 - E_{ii}/RT)$ multiplying the last term in the denominator.

Aaronson, Domian and Pound¹²⁾ offered a detailed discussion on the statistical models of the Fe-C alloys, and clarified the differences among models and the activity expressions so far published. However, the present author is rather skeptical for paying much attention only to the configurational entropy. McLellan regarded the all excess entropy to be attributed to the vibrational one, the configurational entropy being practically ideal. Though the non-configurational entropy, or $\bar{G}_i^{nc}$ in the present paper, would not be highly dependent on the composition, we have no confidence for this to be constant within the accuracy required to judge the various pairwise interaction models.

Recently Chimpan³⁶⁾ made a recalculation by computer with data of Smith,³²⁾ Scheil et al.,³⁴⁾ and Bungardt et al.,³⁵⁾ and obtained the activity of carbon in the austenite with respect to graphite as the standard state as

$$\log a_C^a = \log y_C - 0.959 + 2336/T + (2.05 + 2000/T)y_C \dots (30)$$

where $y_C = n_C/n_{Fe}$. In comparing this expression with Darken and Smith's Eq. (21), E was obtained as about 2400 cal/mol instead of 1500 cal/mol. Though Eq. (30) is quite a simplified one, its applicability may be strikingly wide as will be mentioned below.

So far our discussion was concentrated upon the activity in the austenite. For α -phase, we unfortunately do not have any detailed knowledge. However, the equilibrium concentration of α -phase, x_C^e , is usually very much lower than that of austenite. Therefore the activity of Eq. (17) can be expressed as a good approximation by

$$\ln a_i^a = \ln x_i^a - \ln 3 - \frac{E_{Fe-i}}{RT} + \frac{\bar{G}_i^{nc,a}}{RT} \dots (31)$$

since $\beta=3$ for the α -phase. We consequently obtain an expression,

$$\ln a_i^a - \ln a_i^r = \ln \frac{x_i^a}{x_i^r} - \ln 3 + \ln (1 - \delta x_i^r) - \frac{E_{Fe-i}^a - E_{Fe-i}^r}{RT} + \frac{\bar{G}_i^{nc,a} - \bar{G}_i^{nc,r}}{RT} \dots (32)$$

or using an activity with respect to the infinite dilution as a standard state,

$$\ln {}^\circ a_C^a - \ln {}^\circ a_C^r \simeq \ln (x_i^a/x_i^r) + \ln (1 - \delta x_i^r) \dots (32)'$$

where δ is 2 in the ideal interstitial solution, 6 in the Kaufman's model, about 7.6 in the Darken and Smith's evaluation, about 8.3 by Chimpan at 1000°C. In the last two evaluations, δ is a function of temperature.

The $\Delta^\circ G_C^{a \rightarrow r Fe}$ can thus be determined from the known $\alpha/\alpha+\gamma$ and $\gamma/\alpha+\gamma$ boundary in the Fe-C phase diagram and the expression for the activity of carbon in both phases. Darken and Gurry²⁶⁾ pointed out, however, that the heat of transfer $C(\text{in } \alpha) \rightarrow C(\text{in } \gamma)$ thus determined showed some inconsistencies when combined with other thermodynamic quantities. Smith⁴⁰⁾ evaluated from the measurements^{17), 40)} of

activity of carbon and the Fe-C phase diagram that

$$C(\text{in } \alpha) = C(\text{in } \gamma) \quad \Delta H_a = -15600 \dots (a)$$

and from other thermodynamic quantities,

$$C(\text{gr.}) = C(\text{in } \gamma) \quad \Delta H_b = +10100 \dots (b)$$

$$3Fe(\alpha) + C(\text{gr.}) = Fe_3C(\text{cem.}) \quad \Delta H_c = +5100 \dots (c)$$

Combining them,

$$Fe_3C(\text{cem.}) = 3Fe(\alpha) + C(\text{in } \alpha) \quad \Delta H_d = \Delta H_b - \Delta H_a - \Delta H_c = +20600 \dots (d)$$

Many measurements⁴¹⁾⁻⁴³⁾ with thermal or internal friction methods suggested, however, that the experimental heat of the reaction (d) was 10 to 12 kcal/mol. Thus a serious disagreement existed between the calculated and the experimental heat of solution of cementite in α -iron. Recently Swartz⁴⁴⁾ reported that the ΔH_d of 10 to 12 kcal/mol involved the effect of the self-stress in cementite precipitates, and obtained 14.8 kcal/mol for the stress-free cementite. There still remains about 6 kcal as the difference between the calculated and the Swartz's values.

The $\Delta^\circ G_C^{a \rightarrow r Fe}$ was recalculated by using the data of $\alpha/\alpha+\gamma$ and $\gamma/\alpha+\gamma$ boundaries²⁹⁾ and two expressions by Chipman³⁶⁾ and by Kaufman et al.¹¹⁾ for the activity of carbon in the austenite. The results are shown in Table 3, and plotted in Fig. 4. The values

Fig. 4. The value of $\Delta^\circ G_C^{a \rightarrow r Fe}$

Table 3. $\Delta^\circ G_C^{a \rightarrow r Fe}$ calculated from the Fe-C phase diagram

Temperature (°K)	C (at%)		From Kaufman*		From Chipman**		$RT \ln \left[\frac{1-x_C^a}{1-x_C^r} \right]$ (cal/mol)	By Darken and Smith ¹⁷⁾ $\Delta G_{Fe \rightarrow r}^{a \rightarrow r}$ (cal/mol)
	$\alpha/\alpha+\gamma$	$\gamma/\alpha+\gamma$	$\log \frac{{}^\circ a_C^a}{{}^\circ a_C^r}$	$\Delta^\circ G_C^{a \rightarrow r Fe}$ (cal/mol)	$\log \frac{{}^\circ a_C^a}{{}^\circ a_C^r}$	$\Delta^\circ G_C^{a \rightarrow r Fe}$ (cal/mol)		
1153	0.015	0.26	-1.246	-6570	-1.250	-6590	5.6	6
1123	0.031	0.60	-1.317	-6740	-1.328	-6830	12.8	13
1093	0.046	1.10	-1.409	-7050	-1.429	-7150	22.8	23
1043	0.071	2.10	-1.530	-7310	-1.584	-7560	42.4	46
996	0.095	3.61	-1.687	-7680	-1.748	-7860	71.2	83

* ${}^\circ a_C^r$ is calculated from Kaufman's expression.¹¹⁾

** ${}^\circ a_C^r$ is calculated from Chipman's expression.³⁶⁾

of x_c^0 estimated from the phase diagram²⁹⁾ seem reliable enough because the $\Delta G_{Fe\gamma}^{a\rightarrow\gamma}$ calculated from them is in good agreement with that of Darken and Smith¹⁷⁾ as shown in Table 3.

The straight line of $\Delta^\circ G_C^{a\rightarrow\gamma Fe}$ from the Chipman's activity expression gives

$$\Delta^\circ G_C^{a\rightarrow\gamma Fe} = -16\,500 + 8.6T \dots\dots\dots (33)$$

which is in good agreement with that by Smith. Even if the Kaufman's activity expression is adopted, ΔH_a of about -15.0 kcal is obtained. Thus the heat of transfer of C(in α) $\rightarrow$ C(in γ) is believed to be about -16 kcal in the temperature range from $1\,000^\circ$ to $1\,150^\circ$ K.

On the other hand, Swartz's evaluation that $\Delta H_d = 14.8 \pm 0.2$ kcal/mol seems quite reliable between $1\,000^\circ$ to 500° K. In this temperature range, ΔH_c for the reaction

should be regarded as 7.0 kcal/mol on the average rather than 5.1 kcal/mol, though the latter may be correct at $1\,000^\circ$ K. The ΔH_b for the reaction

may also be obtained by the new evaluation of Chipman,³⁶⁾

$$\Delta G_b^\circ = 10.680 - 4.373T \dots\dots\dots (34)$$

which shows a fairly good agreement with the Darken and Gurry's value mentioned above.

From these ΔH 's, $\Delta H_C^{a\rightarrow\gamma Fe}$ is estimated as

$$\Delta H_C^{a\rightarrow\gamma Fe} = 10.68 - 7.0 - 14.8 = -11.1 \text{ kcal/mol}$$

we have another combination of the free energies for the reaction as follows.

ΔG_f above is based on the Chipman's evaluation³⁶⁾ at $1\,000^\circ$ K, and ΔG_h is obtained by a linear approximation of KB in the range 900° to 500° K. The agreement of the enthalpy term between the former and the present combination is quite good.

In Fig. 4 a straight line was drawn in the range below $1\,000^\circ$ K according to a tentative equation that

$$\Delta^\circ G_C^{a\rightarrow\gamma Fe} = -11\,100 + 3.1T \dots\dots\dots (35)$$

which is in agreement with the free energy (i) within a reasonable accuracy. We consequently should regard the $\Delta^\circ G_C^{a\rightarrow\gamma Fe}$ to be curved at about $1\,000^\circ$ K, and this trend is similar to that of the free energy of solution of cementite into α -iron which has been pointed out by Swartz.⁴⁴⁾

We have other two points in the high temperature region in Fig. 4. The one at $1\,273^\circ$ K is the Smith's

measurement⁴⁰⁾ with Fe-Si alloy. The another at $1\,772^\circ$ K is estimated from the δ - γ equilibrium: the T_0 composition between δ and γ at the peritectic temperature is estimated to be 0.60 at%, and $\Delta^\circ G_C^{a\rightarrow\gamma Fe}$ is obtained by Eq. (13) using $\Delta^\circ G_{Fe\gamma}^{a\rightarrow\gamma}$ of Kaufman et al.²⁰⁾

Thus the experimental evidences so far published suggest that the $\Delta^\circ G_C^{a\rightarrow\gamma Fe}$ may be an S-shaped curve. On the other hand, Hillert, Wada, and Wada¹⁰⁾ obtained the S-shaped curves for $\Delta^\circ G_{Mn}^{a\rightarrow\gamma Fe}$ and $\Delta^\circ G_{Ni}^{a\rightarrow\gamma Fe}$ in Fe-Mn and Fe-Ni alloys, and explained them by an equation

$$\Delta^\circ G_Y^{a\rightarrow\gamma Fe} = \Delta^\circ H_Y^{a\rightarrow\gamma Fe} - T \Delta^\circ S_Y^{a\rightarrow\gamma Fe} - \frac{dT_C}{dx_Y} (^\circ S_{Fe}^\alpha)_{Mag} \quad (36)$$

where dT_C/dx_Y is the change in the Curie temperature by addition of the solute Y, and $(^\circ S_{Fe}^\alpha)_{Mag}$ is the magnetic entropy of α -iron. Eq. (36) is based on the Zener's two-parameter theory.

The broken line in Fig. 4 was obtained by Eq. (36) with $\Delta^\circ H_Y^{a\rightarrow\gamma Fe} = -11\,100$ cal/mol, $\Delta^\circ S_Y^{a\rightarrow\gamma Fe} = -2.3$ e.u., and $dT_C/dx_Y = -1\,900$. These parameters were determined by a trial and error method. The value of $(^\circ S_{Fe}^\alpha)_{Mag}$ is based on that by Weiss and Tauer.^{7),10)} As the effect of carbon on the Curie temperature is unknown, the value $dT_C/dx_Y = -1\,900$ may have a meaning only as a parameter. But it should be noticed that the value $\Delta^\circ S_C^{a\rightarrow\gamma Fe} = -2.3$ is very close to the ideal value of the difference in the partial entropy of carbon between α - and γ -alloys, $-R \ln 3 = -2.18$. This fact may suggest that almost all parts of the non-configurational entropy is regarded to be the magnetic entropy.

The curve given by Eq. (36) is thus in good agreement with the experimental $\Delta^\circ G_C^{a\rightarrow\gamma Fe}$. In the works so far published, however, the magnetic term of the excess energy of solution was usually ignored, most part of it being attributed to the change in the vibrational entropy.^{13),14)} Only the work by Swartz⁴⁴⁾ suggested the change in the heat of solution of cementite into α -iron at about $1\,000^\circ$ K to be caused by the magnetic transformation in the host lattice. It seems quite reasonable that a carbon atom dissolved in the iron lattice changes the electronic state around it, thereby gives rise an influence on the spin-spin interaction energy between iron atoms surrounding it. The measurements of the Mössbauer effect of interstitial iron alloys⁴⁵⁾ show that an unusual charge distribution exists around the carbon or nitrogen atom. Consequently in the temperature range near the Curie temperature, where an appreciable transition of the spin-order to disorder is easily occurred by a slight change in the energy state, the partial excess entropy of solution of carbon in α -iron becomes a large positive value because of its spin-disordering effect for the host lattice. In the temperature range far apart from the Curie temperature, on the other hand, the carbon has practically no influence for changing the ordered or disordered states of the host lattice, only the heat of solution of the carbon being different in these two states. Thus the S-shaped curve is understandable. Though

Eq. (36) was not derived on a sound theoretical base,* the result seems quite acceptable.

A little difference is observed between the calculated and experimental curves in the temperature range 900° to 1 300°K. The experimental curve lies in a higher temperature side than the calculated one, as if the $(^{\circ}S_{Fe}^{\alpha})_{Mag}$ value slightly shifts towards the high temperature side. The reason of this is not clear, but it is naturally possible that some differences exist between the thermal and the impurity disordering. This may be a point to be confirmed in future. Another problem is the position of the point at 1 772°K, which was evaluated in this work by using the Kaufman's $\Delta G_{Fe}^{\alpha \rightarrow \gamma}$. But if we use the Darken and Smith's $\Delta G_{Fe}^{\alpha \rightarrow \gamma}$, $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ becomes about 1.6 kcal/mol and deviates remarkably from the calculated value.

Our discussion on the Fe-C alloy has been so far devoted on the value of $\Delta^{\circ}G_C^{\alpha \rightarrow \gamma Fe}$. It is also an important problem how the phase boundaries or the T_0 temperature can be determined with this energy. In this article, however, only a brief discussion will be offered on the bainite and the martensite reactions in the later section. We would next go forward into other alloy systems.

Though the Fe-N alloy is also an important interstitial alloy, the experimental knowledge is less than the Fe-C alloy. The solubility of nitrogen in $\alpha(\delta)$ - and γ -iron has been reported by Sieverts et al.,⁴⁶⁾ Darken et al.,⁴⁷⁾ Paranjpe et al.,⁴⁸⁾ and Fast and Verrijp.⁴⁹⁾ McLellan¹⁴⁾ used the result by the last investigators for the solubility in α -iron, while for that in γ - and δ -iron the results by the first and the second investigators are quite in agreement. From these results, the ratio of the equilibrium concentrations $x_N^{\alpha}/x_N^{\gamma}$ is obtained at 1 400° and 910°C to be 0.50 ± 0.02 and 0.172 ± 0.01 , respectively. Since the concentrations are very low, the concentration ratio is practically equal to the activity ratio. Then the $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ is obtained to be -2 300 and -4 490 cal/mol at 1 400° and 910°C, respectively. On the other hand, the eutectoid point of Fe-N alloy is 8.75 at% at 590°C,²⁹⁾ and the $\alpha/\alpha + \gamma$ composition at the eutectoid temperature is 0.40 at%.²⁹⁾ Unfortunately the activity expression in Fe-N austenite is not known. But when an ideal interstitial alloy is assumed, i.e. $\delta = 2$ in Eq. (32), $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ at 590°C is obtained to be -6 890 cal/mol. If the δ is assumed to be 5 by considering that Fe_4N is a saturated alloy, $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ is obtained to be -7 540 cal/mol at that temperature. These values were plotted in Fig. 5. It is observed that the points at the three temperatures do not lie on a straight line, even if the uncertainty in the $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ at 590°C due to the activity expression is taken into account.

A calculation was made by using Eq. (36) taking $\Delta^{\circ}H_N^{\alpha \rightarrow \gamma Fe}$, $\Delta^{\circ}S_N^{\alpha \rightarrow \gamma Fe}$, and dT_C/dx_N as -10 800 cal/mol, -3.3 e.u., and -1 400, respectively. Then a curve was obtained as shown in Fig. 5 by a dashed line. The agreement was quite good between the calculated and the experimental values. Though the parameters given above were quite arbitrarily chosen, the entropy

of -3.3 suggests that some excess entropy may exist in addition with the configurational and the magnetic ones, probably of the vibrational entropy. This is only an inference because of the uncertainties in the values of the parameters. Nevertheless, the present results and also a fact that the heat of solution of nitrogen in α -iron varies with temperature^{26),44)} may suggest that the magnetic entropy plays an important role in $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$ of the Fe-N alloy.

V. Fe-Mn and Fe-Ni Alloys

Hillert, Wada, and Wada¹⁰⁾ have measured the concentrations of Mn and Ni in α - and γ -phases which are in equilibrium with each other at temperature around 820°C. Although these measurements were carried out only at one or two temperatures and therefore did not clarify the temperature dependence of $\Delta^{\circ}G_Y^{\alpha \rightarrow \gamma Fe}$, we also evaluated it from δ - γ equilibrium and from T_0 temperatures. Then the plot of them did not show a linear relationship as seen in Fig. 6.

In order to account for the strong variation of $\Delta^{\circ}G_Y^{\alpha \rightarrow \gamma Fe}$ with temperature, Eq. (36) was applied using informations on the effect of Ni and Mn on the Curie temperature of iron.^{50),51)} The values of $\Delta^{\circ}H_Y^{\alpha \rightarrow \gamma Fe}$ and $\Delta^{\circ}S_Y^{\alpha \rightarrow \gamma Fe}$ were estimated as shown in Table 4. Thus the theoretical curves were drawn in Fig. 6, which came close to the experimental points determined at around 820°C. Furthermore, the values obtained for $\Delta^{\circ}S_Y^{\alpha \rightarrow \gamma Fe}$ may be of the correct sign for bcc $\rightarrow$ fcc transformation. But the size of their absolute values seems

Fig. 5. The value of $\Delta^{\circ}G_N^{\alpha \rightarrow \gamma Fe}$

Fig. 6. The values of $\Delta^{\circ}G_{Ni}^{\alpha \rightarrow \gamma Fe}$ and $\Delta^{\circ}G_{Mn}^{\alpha \rightarrow \gamma Fe}$

* Recently Nishizawa and Hillert⁶⁷⁾ derived Eq. (36) from an exact thermodynamical basis.

Table 4. Parameters for calculation of $\Delta^{\circ}G_{\gamma}^{a-\gamma\text{Fe}}$ curve from Eq. (36)¹⁰⁾

Alloying element	dT_0/dx (°K/mol)	Ref.	$\Delta^{\circ}H_{\gamma}^{a-\gamma\text{Fe}}$ (cal/mol)	$\Delta^{\circ}S_{\gamma}^{a-\gamma\text{Fe}}$ (e.u.)
Mn	-1500	50)	-4 500	-0.74
Ni	- 400	51)	-2 740	-0.80

somewhat too large for the atomic rearrangement only, and probably some excess entropy may be involved. The measurements by Smith and Shuttleworth⁵⁴⁾ show that the Mn in dilute Fe-Mn alloys has a partial excess entropy probably arising from an electronic term. However, as the sign of this excess entropy is inverse for explaining the $\Delta^{\circ}S_{\gamma}^{a-\gamma\text{Fe}}$, this may be mainly attributed to the properties in α -phase.

In Fig. 6, the values given by Kaufman and Cohen²²⁾ are also shown. Though their value is fairly close to the present one at temperatures around 750°K, the difference becomes quite serious in the higher or the lower temperatures. The dashed lines in Fig. 6 were calculated from the phase diagrams using the approximate Eq. (7). But Eq. (7) may bring some inaccuracies into $\Delta^{\circ}G_{\gamma}^{a-\gamma\text{Fe}}$ at low temperatures, while at high temperatures the phase diagrams themselves have no sufficient accuracy.

The Zener's suggestion seems capable of explaining the variation of $\Delta^{\circ}G_{\text{Mn}}^{a-\gamma\text{Fe}}$ and $\Delta^{\circ}G_{\text{Ni}}^{a-\gamma\text{Fe}}$ with temperature. Hillert, Wada, and Wada also calculated¹⁰⁾ the phase diagrams of Fe-Mn and Fe-Ni systems from the values of $\Delta^{\circ}G_{\gamma}^{a-\gamma\text{Fe}}$ obtained. The Fe-Ni diagram calculated was in good agreement with the new-determined one by Goldstein and Ogilvie.⁵⁵⁾ Furthermore, Hillert et al. measured¹⁰⁾ the distribution of Mn between γ and carbide phase in the temperature range between 1 045° and 1 317°K, and compared the results with the distribution between α and carbide phase determined by Kuo and Hultgren,⁵²⁾ and Gurry et al.,⁵³⁾ through $\Delta^{\circ}G_{\text{Mn}}^{a-\gamma\text{Fe}}$ obtained. The agreement was quite good in this comparison.¹⁰⁾ These facts may be the strong supports for the present $\Delta^{\circ}G_{\gamma}^{a-\gamma\text{Fe}}$.

VI. Martensite Reactions

The thermodynamic principle for considering the martensite reaction has been given in an article by Kaufman and Cohen.¹⁸⁾ It was noticed that the driving force of the reaction at M_s was about 300 cal/mol for Fe-C alloy without dependence on the carbon content, while that for Fe-Ni alloy increased with the nickel content.¹⁸⁾ Gilbert and Owen⁵⁶⁾ reported that the free energy change for the martensitic transformation rather increased with the concentration of the alloying element in Fe-Ni and Fe-Cr alloys. Even for the Fe-C and Fe-N alloys, Imai, Izumiyama, and Tsuchiya⁵⁷⁾ recently reported that the driving force increased strongly with increasing C or N contents. In order to find the true value of the driving force, a calculation will be made by using the new-evaluated free energies.

The Fe-C and Fe-N martensite are at first taken up for the calculation. The free energy difference $\Delta G^{a-\gamma}$ between γ and α Fe-C alloys with the same

carbon content is given by

$$\Delta G^{a-\gamma} = G_{\gamma} - G_{\alpha} = RT \left[x_{\text{Fe}} \ln \frac{a_{\text{Fe}}^{\gamma}}{a_{\text{Fe}}^{\alpha}} + x_{\text{C}} \ln \frac{a_{\text{C}}^{\gamma}}{a_{\text{C}}^{\alpha}} \right] \\ \simeq x_{\text{Fe}} \Delta G_{\text{Fe}}^{a-\gamma} + x_{\text{C}} \left[\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}} - RT \ln \frac{(1-\delta^{\gamma}x_{\text{C}})}{(1-\delta^{\alpha}x_{\text{C}})} \right] \quad (37)$$

The value of δ^{γ} has been discussed in the previous section. There is some uncertainty in the δ^{α} , on the other hand. It should be noticed, however, that the contribution of the last term is quite small compared with that of $\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}}$ in a dilute solution. Therefore, an approximation could be made, without any serious error, as $\delta^{\gamma}=6$ and $\delta^{\alpha}=\delta^{\gamma}/3=2$ since $\beta=3$ in the α -alloy. Then Eq. (37) becomes

$$\Delta G^{a-\gamma} = x_{\text{Fe}} \Delta G_{\text{Fe}}^{a-\gamma} + x_{\text{C}} \left[\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}} - RT \ln \frac{(1-6x_{\text{C}})}{(1-2x_{\text{C}})} \right] \dots\dots (38)$$

Using $\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}}$ evaluated in section IV we can calculate the energy difference $\Delta G^{a-\gamma}$ at a given temperature and composition.

The M_s temperatures of Fe-C and Fe-N alloys were summarized by Imai, Izumiyama, and Tsuchiya⁵⁷⁾ in addition to their own experimental results. Kaufman and Cohen^{18),22)} also reported the M_s temperature up to about 7.5at% C. These are shown in Fig. 7. The results by Imai et al. give a curve common to both Fe-C and Fe-N alloys, while Kaufman and Cohen gave nearly straight line for Fe-C alloy within the above concentration range. The line by the latter investigators lies within the scattering of the former's value given by the dashed line in Fig. 7.

Table 5 and Fig. 8 show the results of the calculation by Eq. (38). In this calculation, the $\Delta G_{\text{Fe}}^{a-\gamma}$ is taken from the Kaufman, Clougherty, and Weiss's value²⁰⁾, and the $\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}}$ was determined by the equation

$$\Delta^{\circ}G_{\text{C}}^{a-\gamma\text{Fe}} = -11\,100 + 3.1T \dots\dots\dots (35)'$$

As shown in Table 5 the contribution of the last term of Eq. (38) is very small, so that the influence of changing the statistical model may not be large. As a comparison, $\Delta G^{a-\gamma}$ was also calculated by using the $\Delta G_{\text{Fe}}^{a-\gamma}$ by Kohlhaas and Braun, the results of which are shown in the last column in Table 5. These two results show that the driving force does not much increase with the carbon content.

Fig. 7. M_s temperature of Fe-C and Fe-N alloys

Table 5. The driving force $\Delta G^{a \rightarrow \gamma}$ for the martensite reaction in Fe-C alloy

M_s temperature (°K)	x_C (at%)		$(1-x_C) \Delta G_{Fe}^{a \rightarrow \gamma}$ (KCW) (cal/mol)		$x_C \Delta G_C^{a \rightarrow \gamma Fe}$ (cal/mol)	
	Imai et al.	Kaufman et al.	Imai et al.	Kaufman et al.	Imai et al.	Kaufman et al.
700	0.9±0.7	1.4	416	414	-80±60	-125
600	2.2±0.8	2.8	571	568	-203±70	-259
500	3.7±0.9	4.2	721	718	-353±80	-401
400	5.6±0.9	5.6	870	870	-551±90	-551
300	7.9±1.0	7.0	1 000	1 009	-804±100	-712

M_s temperature (K°)	$-x_C RT \ln \left(\frac{1-6x_C}{1-2x_C} \right)$ (cal/mol)		$\Delta G^{a \rightarrow \gamma}$ (cal/mol)		$\Delta G^{a \rightarrow \gamma}$ (cal/mol) (Using $\Delta G_{Fe}^{a \rightarrow \gamma}$ by KB)	
	Imai et al.	Kaufman et al.	Imai et al.	Kaufman et al.	Imai et al.	Kaufman et al.
700	0.5	1.2	336± 60	289	372± 60	325
600	2.4	4.0	370± 70	313	366± 70	309
500	6.4	8.1	374± 80	325	332± 80	282
400	13.0	13.0	332± 90	332	245± 90	245
300	22.0	16.4	218±100	313	98±100	192

Fig. 8. The driving force $\Delta G^{a \rightarrow \gamma}$ for the martensite reaction in Fe-C and Fe-N alloys

However, the above expression of $\Delta G_C^{a \rightarrow \gamma Fe}$ is valid only within 1 000° to 500°K, and below 500°K or above ca. 5at% carbon that expression may give somewhat over-estimation for $\Delta G_C^{a \rightarrow \gamma Fe}$. In addition, the present calculation assumed the non-configurational excess energy in dilute range to be unchanged even in the higher concentrations. For these reasons, the reliability may be much less in the high concentration range than in the dilute range. Furthermore, the linear approximation of M_s temperature taken by Kaufman may give inaccuracies in both low-concentration and high-concentration ends. The present author consequently feels that the true value of $\Delta G^{a \rightarrow \gamma}$ is almost independent, or slightly increases with the carbon content if we rely on the KCW's $\Delta G_{Fe}^{a \rightarrow \gamma}$.

The strong increase of $\Delta G^{a \rightarrow \gamma}$ by carbon content reported by Imai et al. may be attributed to the improper use of the Gilbert-Owen's $\Delta G_{Fe}^{a \rightarrow \gamma}$ out of its range of validity and to the choice of the values for the difference in the free energy of solution of C or N in the γ - and α -alloys. As seen in Table 5, these two

Table 6. The driving force $\Delta G^{a \rightarrow \gamma}$ for the martensite reaction in Fe-N alloy

M_s temperature (°K)	$\Delta G^{a \rightarrow \gamma Fe}$ (kcal/mol)	$\Delta G^{a \rightarrow \gamma}$ (cal/mol)
700	-8.2	343
600	-8.7	377
500	-9.1	390
400	-9.5	352
300	-9.8	248

energies are most important for estimating $\Delta G^{a \rightarrow \gamma}$.

The driving force was also calculated for Fe-N martensite, using the same M_s curve as Fe-C given by Imai et al and $\Delta G_N^{a \rightarrow \gamma Fe}$ reported in the section IV. The $\Delta G_{Fe}^{a \rightarrow \gamma}$ by KCW and the same δ 's as Fe-C were again used. The results were very close to the $\Delta G^{a \rightarrow \gamma}$ in Fe-C alloy (Table 6).

Since Fe-Ni and Fe-Mn are substitutional alloys, Eq. (38) should be changed for these alloys as follows.

$$\begin{aligned} \Delta G^{a \rightarrow \gamma} &\approx x_{Fe} \Delta G_{Fe}^{a \rightarrow \gamma} + x_{Ni} \Delta G_{Ni}^{a \rightarrow \gamma Fe} + [x_{Fe} x_{Ni}^2 \\ &\quad - x_{Ni} (2x_{Ni} - x_{Ni}^2)] \times (A' - A) = x_{Fe} \Delta G_{Fe}^{a \rightarrow \gamma} \\ &\quad + x_{Ni} \Delta G_{Ni}^{a \rightarrow \gamma Fe} - x_{Ni}^2 \Delta A^{a \rightarrow \gamma} \dots\dots\dots (39) \end{aligned}$$

Though the contribution of the last term seems very little in a dilute solution, the A 's are not always known. Therefore by using T_0 composition, x_{Ni}^0 , where $\Delta G^{a \rightarrow \gamma} = 0$, we obtain

$$\begin{aligned} \Delta G^{a \rightarrow \gamma} &= x_{Fe} \Delta G_{Fe}^{a \rightarrow \gamma} + x_{Ni} \Delta G_{Ni}^{a \rightarrow \gamma Fe} \\ &\quad - x_{Ni}^2 \left[\frac{x_{Fe}^0 \Delta G_{Fe}^{a \rightarrow \gamma} + x_{Ni}^0 \Delta G_{Ni}^{a \rightarrow \gamma Fe}}{(x_{Ni}^0)^2} \right] \\ &= \left[x_{Fe} - \left(\frac{x_{Ni}}{x_{Ni}^0} \right)^2 x_{Fe}^0 \right] \Delta G_{Fe}^{a \rightarrow \gamma} \\ &\quad + \left[x_{Ni} \left(1 - \frac{x_{Ni}}{x_{Ni}^0} \right) \right] \Delta G_{Ni}^{a \rightarrow \gamma Fe} \dots\dots\dots (40) \end{aligned}$$

From Eq. (40) we can calculate $\Delta G^{a \rightarrow \gamma}$ when T_0 composition is known.

The driving force of the martensite reaction in Fe-Ni alloy was calculated by using $\Delta^\circ G_{\gamma \rightarrow \alpha}^{\text{Fe}}$ determined in section V and $\Delta G_{\gamma \rightarrow \alpha}^{\text{Fe}}$ by KCW. The values of the M_s temperature and the T_0 composition were cited from the work by Kaufman and Cohen,^{(22), (18)} from which $\Delta G^{a \rightarrow \gamma}$ was obtained from Eq. (40) as shown in Fig. 9. The results are thus in agreement with the Kaufman's one in the dilute range, while a considerable departure appears in the high concentration range. This may be caused by the difference in the value of $\Delta^\circ G_{\text{Ni}}^{\text{Fe}}$ between the Kaufman's evaluation and the present one, which was mentioned in the section V. The regular-solution-like expression with respect to the term involving A should be suitable for such a metallic system, and Eq. (40) is valid without any other assumption for A . Therefore the present results for Fe-Ni martensite should have almost the same reliability for low and high concentration ranges, in contrast with the case of the Fe-C alloy.

The results by Gilbert and Owen^{(23), (56)} are also shown in Fig. 9. These may be considered to be in good agreement with the Kaufman's and present works, since the point at 5%Ni by Kaufman seems to be involving somewhat higher inaccuracy than others.

We have concentrated our discussion into a criticism of the driving force in the reaction from austenite to a supersaturated ferrite. There should be other problems of importance, such as the energy difference between martensite and supersaturated ferrite, the physical meaning of the driving force, and the kinetics. Some of them have already been explained by other investigators in the excellent reviews⁽¹⁸⁾ and research papers.^{(21), (23), (57)}

VII. Bainite Reaction

The essential feature of the bainite reaction is the precipitation of ferrite from metastable austenite by an edgewise growth mechanism. The thermodynamical driving force is consequently the energy evolved in the decomposition of a metastable austenite into a ferrite and an austenite which are in equilibrium with each other, or $-\Delta G^{\gamma \rightarrow \alpha/\gamma}$. This energy $-\Delta G^{\gamma \rightarrow \alpha/\gamma}$ is positive in all temperature ranges below $\gamma/\alpha + \gamma$ phase boundary, while the bainite reaction actually starts

Fig. 9. The driving force $\Delta G^{a \rightarrow \gamma}$ for the martensite reaction in Fe-Ni alloy

at temperatures which are appreciably below the $\gamma/\alpha + \gamma$ boundary.

A reason why the edgewise growth is prevailing may be that the diffusion of carbon from the tip of the edge is easier than that from a planar interface. This means that the bainitic ferrite is essentially the same as the Widmanstätten ferrite. Since the diffusion coefficient of carbon is quite higher than the substitutional solutes, the partitioning of them, for instance of manganese, does not occur practically in early stage of the reaction.^{(58), (59)}

The tip of the edge has a curvature of small radius, and therefore an effect of the interfacial energy should be taken into account. Zener⁽⁶⁰⁾ and Hillert⁽⁶¹⁾ have discussed the edgewise growth of plates of ferrite in an austenite matrix. Kaufman, Radcliffe, and Cohen⁽¹¹⁾ reported a detailed thermodynamic analysis of the reaction, in which the rate of growth was calculated upon the basis of the Zener-Hillert treatment.

The effect of the interfacial energy may be considerable in the formation of thin plates. It is known that a relationship exists between the direction of the growth of the ferrite plates and the crystallographic direction of the matrix. This means that the interfacial energy, or the coherency, of the side-interface between ferrite and austenite has some influences on the driving force.

The edgewise growth of the lamellar plates with spacing S is schematically shown in Fig. 10. Consider a volume of thickness S and unit width, in which one ferrite plate is involved, and let the energy evolved by its growth Δg be ΔG^b . Then,

$$\Delta G^b = \frac{S \Delta G^{\gamma \rightarrow \alpha/\gamma}}{V} \Delta g + 2\sigma \Delta g \quad \dots\dots\dots(41)$$

where V is the molar volume of the alloy and σ is the interfacial energy. The condition of equilibrium is $\Delta G^b/\Delta g = 0$, or

$$\Delta G^{\gamma \rightarrow \alpha/\gamma} + 2\sigma V/S = 0 \quad \dots\dots\dots(42)$$

Thus the line at which the driving force is zero lies somewhat lower position of the $\gamma/\alpha + \gamma$ phase boundary. The lines drawn in Fig. 11 illustrate the lines of $\Delta G^b = 0$ when $2\sigma V/S = 50$ and 100 cal/mol, respectively. The $X_{\gamma\alpha}^e$ line ($\rho \sim 15 \text{ \AA}$) by Kaufman et al.⁽¹¹⁾ is also shown. Since the thickness of the ferrite plate, and consequently the curvature of their tip, vary with the carbon content of the metastable austenite if the spacing is constant, the $\Delta G^b = 0$ line and $X_{\gamma\alpha}^e$ line should not be coincide with each other. If the curvature ρ is constant, the spacing S becomes large with decreas-

Fig. 10. Edgewise growth model of ferrite plate

Fig. 11. The line $\Delta G^b = 0$ and B_S temperature

ing temperature or increasing carbon content. In the real bainite reaction, even the spacing S may decrease with decreasing temperatures, since the spacing has a relation to the diffusivity of carbon,⁶¹⁾ which decreases with decreasing temperature. Therefore the $\Delta G_b = 0$ line of the real system may show somewhat higher departure from $\gamma/\alpha + \gamma$ boundary in the low temperature region than in high temperature region.

If the interfacial energy σ has a value about 200 erg/cm², the values of $2\sigma V/S$ of 50 and 100 cal/mol correspond to S of about 120 and 60 Å, respectively. These values seem too low for the reaction in the upper bainite region, but in some temperature ranges they seem reasonable in view of the value of ρ evaluated by Kaufman.¹¹⁾

It is not sound enough how the interfacial energy plays its role in the bainite reaction.⁶²⁾ In addition, the value of the interfacial energy between α - and γ -iron is not known in detail. It is possible, however, that the α - γ interfacial energy would be greatly dependent on the temperature, since the interface probably associates a partial disordering of spins as well as of the atomic arrangements. The detailed knowledges about this may be required for further study on the diffusional transformation of iron alloys at low temperatures.

VIII. Conclusions

For discussing the transformation and the phase equilibrium of iron alloys, the partial free energy difference of a solute Y between dilute γ - and α -alloys, $\Delta^0 G_Y^{\alpha \rightarrow \gamma \text{Fe}}$, is an important quantity. This energy may not be generally a linear function of temperature owing to the magnetic order-disorder transformation of α -iron. Re-examination of the Fe-C alloy showed that the $\Delta^0 G_Y^{\alpha \rightarrow \gamma \text{Fe}}$ would have an S-shape, as expected by the Zener-Hillert equation (36). The same tendency was observed in Fe-N alloy, as well as Fe-Ni and Fe-Mn alloys which were previously reported.

The experimental confirmation seems to be still required for the feature of $\Delta^0 G_Y^{\alpha \rightarrow \gamma \text{Fe}}$. Also the detailed behaviour of the spin-disordering associated with the dissolution of a solute should be clarified in future.

Nevertheless the present discussion is expected to be valuable for finding a line on which the energy of the transformation could be estimated.

Acknowledgements

The author wishes to express his thanks to Prof. M. Hillert, Royal Institute of Technology, Stockholm, for his valuable comments on the original version of this paper. Thanks are also due to Dr. H. Wada for her helpful discussion and assistance.

REFERENCES

- 1) C. Zener: *Trans. AIME*, **167** (1946), 513.
- 2) W. Oelsen and F. Wever: *Arch. Eisenhüttenw.*, **19** (1947/48), 97; W. Oelsen: *Stahl u. Eisen*, **69** (1946), 468.
- 3) W. A. West: *Trans. AIME*, **167** (1946), 535.
- 4) F. W. Johns and W. I. Pumphrey: *J. Iron Steel Inst.*, **163** (1949), 121.
- 5) K. W. Andrews: *J. Iron Steel Inst.*, **184** (1956), 414.
- 6) C. Zener: *Trans. AIME*, **203** (1955), 615; U. Roesler, H. Sato, and C. Zener: *Theory of Alloy Phases*, (1955), 255, ASM.
- 7) R. J. Weiss and K. J. Tauer: *Phys. Rev.*, **102** (1956), 1490.
- 8) U. N. Svechnikov and A. G. Lesnik: *Fizika Metall.*, **3** (1956), 87.
- 9) T. Wada: *J. Japan Inst. Metals*, **25** (1961), 707; *Sci. Rep. Res. Inst., Tohoku Univ.*, **A-13** (1961), 215.
- 10) M. Hillert, T. Wada, and H. Wada: *J. Iron Steel Inst.*, **205** (1967), 539.
- 11) L. Kaufman, S. V. Radcliffe, and M. Cohen: *Decomposition of Austenite by Diffusional Processes*, (1962), 313, John Wiley & Sons, New York.
- 12) H. I. Aaronson, H. A. Domian, and G. M. Pound: *Trans. Met. Soc. AIME*, **236** (1966), 753.
- 13) R. B. McLellan: *Trans. Met. Soc. AIME*, **233** (1965), 1664.
- 14) R. B. McLellan: *Trans. Met. Soc. AIME*, **230** (1964), 1468.
- 15) L. S. Darken: *Trans. Met. Soc. AIME*, **239** (1967), 80; 90.
- 16) C. H. Johansson: *Arch. Eisenhüttenw.*, **11** (1937), 241.
- 17) L. S. Darken and R. P. Smith: *Indust. Eng. Chem.*, **43** (1951), 1815.
- 18) L. Kaufman and M. Cohen: *Progress in Metal Physics*, **7** (1958), 168.
- 19) E. Scheil and W. Normann: *Arch. Eisenhüttenw.*, **30** (1959), 751.
- 20) L. Kaufman, E. V. Clougherty, and R. J. Weiss: *Acta Met.*, **11** (1963), 323.
- 21) J. C. Fisher: *Trans. AIME*, **185** (1949), 688.
- 22) L. Kaufman and M. Cohen: *Trans. AIME*, **206** (1956), 1393.
- 23) W. S. Owen and A. Gilbert: *J. Iron Steel Inst.*, **196** (1960), 142.
- 24) R. Kohlhaas and M. Braun: *Arch. Eisenhüttenw.*, **34** (1963), 391.
- 25) A. Ferrier and M. Olette: *Compt. Rend.*, **254** (1962), 2322.
- 26) L. S. Darken and W. Gurry: *Physical Chemistry of Metals*, (1953), McGraw-Hill, New York.
- 27) M. G. Benz and J. F. Elliott: *Trans. Met. Soc. AIME*, **221** (1961), 323.
- 28) A. Hellawell and W. Hume-Rothery: *Phil. Trans. Roy. Soc.*, **249** (1957), 417.
- 29) M. Hansen: *Constitution of Binary Alloys*, (1958), McGraw-Hill, New York.
- 30) L. D. Blackburn, L. Kaufman, and M. Cohen: *Acta Met.*, **13** (1965), 533.
- 31) R. C. Ruhl and M. Cohen: *Acta Met.*, **15** (1967), 159.
- 32) R. P. Smith: *J. Amer. Chem. Soc.*, **68** (1946), 1163.

- 33) H. Dünwald and C. Wagner: *Z. Anorg. Allgem. Chem.*, **199** (1931), 321.
- 34) E. Scheil, T. Schmidt and J. Wünnig: *Arch. Eisenhüttenw.*, **32** (1961), 251.
- 35) K. Bungardt, H. Preisendanz, and G. Lehnert: *Arch. Eisenhüttenw.*, **35** (1964), 999.
- 36) J. Chipman: *Trans. Met. Soc. AIME*, **239** (1967), 2.
- 37) S. Takeuchi and S. Kachi: *J. Japan Inst. Metals*, **14** (1950), No. 2, 1.
- 38) L. S. Darken and R. P. Smith: The Appendix of the REF. 17).
- 39) R. H. Fowler and E. A. Guggenheim: *Statistical Thermodynamics*, (1939), 358, Cambridge University Press.
- 40) R. P. Smith: *J. Amer. Chem. Soc.*, **70** (1948), 2724.
- 41) C. A. Wert: *Trans. AIME*, **188** (1950), 1242.
- 42) E. Lindstrand: *Acta Met.*, **3** (1955), 431.
- 43) P. Stark, B. Averbach, and M. Cohen: *Acta Met.*, **6** (1958), 149.
- 44) J. C. Swartz: *Trans. Met. Soc. AIME*, **239** (1967), 68.
- 45) P. M. Gielen and R. Kaplow: *Acta Met.*, **15** (1967), 49.
- 46) A. Sieverts, G. Zapf, and H. Moritz: *Z. Phys. Chem.*, **183** (1938), 19.
- 47) L. S. Darken, R. P. Smith, and C. W. Filer: *Trans. AIME*, **191** (1951), 1174.
- 48) V. G. Paranjpe, M. Cohen, M. B. Bever, and C. F. Floe: *Trans. AIME*, **188** (1950), 261.
- 49) T. O. Fast and M. B. Verrijp: *J. Iron Steel Inst.*, **180** (1955), 337.
- 50) M. Fallot: *Ann. Physik, Ser.*, 11. **6** (1936), 305.
- 51) M. Peschard: *Rev. Metall. Mem.*, **22** (1925), 663.
- 52) K. Kuo and A. Hultgren: *Jernkontorets Ann.*, **135** (1951), 449.
- 53) R. W. Gurry, J. Christakos, and L. S. Darken: *Trans.* **53** (1961), 187.
- 54) R. P. Smith and R. Shuttleworth: *Acta Met.*, **13** (1965), 623.
- 55) J. I. Goldstein and R. E. Ogilvie: *Trans. Met. Soc. AIME*, **233** (1965), 2083.
- 56) A. Gilbert and W. S. Owen: *Acta Met.*, **10** (1962), 45.
- 57) Y. Imai, M. Izumiyama, and M. Tsuchiya: *Sci. Rep. Res. Inst., Tohoku University*, **A17** (1965), 173; *J. Japan Inst. Metals*, **29** (1965), 428.
- 58) G. R. Purdy, D. H. Weichert, and J. S. Kirkaldy: *Trans. Met. Soc., AIME*, **230** (1964), 1025.
- 59) H. I. Aaronson and H. A. Domian: *Trans. Met. Soc. AIME*, **236** (1966), 781.
- 60) C. Zener: *Trans. AIME*, **167** (1946), 550.
- 61) M. Hillert: *Jernkontorets Ann.*, **141** (1957), 757.
- 62) M. Hillert: *Decomposition of Austenite by Diffusional Processes*, (1962), 197, and its discussions, John Wiley & Sons, New York.
- 63) R. A. Buckley and W. Hume-Rothery: *J. Iron Steel Inst.*, **196** (1960), 403.
- 64) R. B. McLellan, T. L. Garrard, S. J. Horowitz, and J. A. Sprague: *Trans. Met. Soc. AIME*, **239** (1967), 528.
- 65) R. L. Orr and J. Chipman: *Trans. Met. Soc. AIME*, **239** (1967), 630.
- 66) W. A. Fischer, K. Lorenz, H. Fabritius, A. Hoffmann, and G. Kalwa: *Arch. Eisenhüttenw.* **37** (1966), 79.
- 67) T. Nishizawa and M. Hillert: Private communication.