Features of Surface Nitriding Revealed by Mössbauer Spectroscopy

C. CORDIER-ROBERT and J. FOCT

Laboratoire de Métallurgie Physique de l'URA 234, Université de Lille 1, Bat C6, 59655 Villeneuve d'Ascq Cédex, France.

(Received on September 29, 1995; accepted in final form on April 12, 1996)

Two different nitriding surface treatments of austenitic stainless steel have been studied: gaseous nitriding in a $\text{NH}_3\text{--H}_2$ mixture performed at temperatures between 700 and 900°C and nitrogen ion implantation with different dose rates between 5×10^{16} to $1.5 \times 10^{17} \text{ N}_2^+$ ions cm^{-2} and different current densities between 1 to $5 \mu\text{A cm}^{-2}$. The microstructure of the coating was studied by X-ray diffraction and Mössbauer spectroscopy. The discussion emphasizes the role of thermodynamical equilibrium conditions at high temperatures and of the process parameters at low temperatures on the phases which constitute the layer.

KEY WORDS: surface treatment; nitriding; stainless steel; phase transformation; Mössbauer spectroscopy.

1. Introduction

Nitrogen alloying has been shown to be very efficient for improving some mechanical properties of austenitic stainless steel (SS). It was therefore tempting to obtain a localized increase of the mechanical strength at the surface of a stainless steel by surface nitriding. Meanwhile, depending on the steel, on the process of nitriding and the parameters, temperature, time, gas further thermal treatment, ... surface nitriding may lead to very different results. The aim of this paper is to compare two very different features of these processes and to determine which nitriding process and nitriding conditions are likely to offer optimized microstructures tailored for good mechanical strength and corrosion resistance. Two very different cases are compared: gaseous nitriding and ion implantation of austenitic stainless steels. Because the mechanical properties and corrosion resistance are to a large extent determined by the phase transformation of austenite and the nitrogen distribution and redistribution, the discussion is mainly based on the results of X-ray diffraction and Mössbauer spectroscopy.

2. Experimental Procedure

Gaseous nitriding of austenitic 304 SS (17–20% Cr, 8–11% Ni, <2% Mn, <0.008 C and balance Fe) was performed on 20 μm thick foils in $\text{NH}_3\text{--H}_2$ gas mixtures for 6 h. The nitriding temperature varied from 700 to 900°C and the amount of NH_3 in the gas mixture from 2.4 to 100 vol%. At the end of the nitriding process, the specimens were water quenched to room temperature (Table 1).

The surface of thick 316L SS specimens (17.59% Cr, 12.03% Ni, 2.3% Mo, 1.876% Mn, 0.09% Cu, 0.386% Si, 0.072% N, 0.023% C and balance Fe) were implanted with N_2^+ ions. The influence of the dose rate of N_2^+ on the microstructure in a 316L SS is studied in this paper

for ion implantation performed in the range 5×10^{16} – $1.5 \times 10^{17} \text{ N}_2^+$ ions cm^{-2} . Nitrogen implantation was carried out under 80 keV potential. The current density was 1 or $5 \mu\text{A cm}^{-2}$ and the temperature of specimens was maintained below 70°C (Table 2). It was shown by X-ray diffraction and transmission Mössbauer spectroscopy that the nitrogen distribution was not homogeneous at the surface of the steel.

Conventional mode X-ray diffraction (XRD) and grazing X-ray diffraction (GXR) techniques were employed at room temperature with a cobalt anticathode (wavelength 0.17902 nm). The diffractograms corresponding to gaseous nitrided and ion implanted samples are presented in Figs. 1 and 2, respectively. The Mössbauer spectra were obtained in conversion electron Mössbauer (CEMS) or transmission mode (TMS). The choice of TMS and of CEMS, respectively, for gaseous nitrided specimens and ion implanted samples is determined by the difference of thickness of the nitrided zone. The spectra are given in Figs. 3 and 4. The Mössbauer equipment includes a 1024 multichannel analyser. The velocity of the driving unit has a triangular profile and the source is one 25 mCi ^{57}Co in rhodium

Table 1. Gaseous nitriding conditions of 304 stainless steel thin foils and X-ray Diffraction (XRD) phase determination. The chemical potential of nitrogen $\mu(\text{N})$ is controlled by the decomposition of ammonia $\mu(\text{N}) = K(T) \cdot (P(\text{NH}_3)) / (P(\text{H}_2))^{3/2}$.

Temperature (°C)	NH_3/H_2 ratio (%)	$\mu(\text{N})/K(T)$	XRD phases	Sample number
—	—	—	γ	S_0
700	100	$\rightarrow \infty$	$\gamma + \gamma' + \epsilon + \text{CrN}$	S_1
800	2.43	1.4×10^{-3}	γ	S_2
800	42.2	34.7×10^{-3}	$\gamma + \text{CrN}$	S_3
810	8	4.7×10^{-3}	$\gamma + \alpha' + \text{CrN}$	S_4
900	4.3	2.6×10^{-3}	$\gamma + \alpha' + \text{CrN}$	S_5
900	3.1	1.8×10^{-3}	$\alpha' + \text{CrN}$	S_6

Table 2. Summary of the implantation conditions of the austenitic 316L stainless steel (the temperature is maintained below 70°C and the tension is 80 keV) and results of X-ray diffraction (a is the lattice parameter and X the nitrogen content determined by GXRD and CEMS).

Sample	Current density ($\mu\text{A cm}^{-2}$)	N_2^+ dose rate (ions cm^{-2})	Phases	a (nm)	X (GXRD) (N/100Me)	X (CEMS) (N/100Me)
(a)	0	0	γ	0.3595	0	0
(b)	1	5×10^{16}	γ	0.3595	0	8
			γ_R	0.364	7	
(c)	1	10^{17}	γ	0.3595	0	12
			γ_R	0.370	15	
			CrN		50	
(d)	1	1.5×10^{17}	γ	0.3595	0	18
			γ_R	0.378	26	
			CrN		50	
(e)	5	2×10^{17}	γ	0.3595	0	10.3
			γ_R	0.3695	14.5

Fig. 1. X-ray diffractograms of gas-nitrided 304 thin foils obtained with a $\text{CoK}\alpha$ source at room temperature: (a) S_0 , (b) S_2 , (c) S_3 , (d) S_4 , (e) S_5 , (f) S_6 .

matrix.¹⁾ The counter used for TMS is a NaI(Tl) scintillator. For CEMS a proportional 96% $\text{He}/4\% \text{CH}_4$ gas flow electron counter was employed. The isomer shift data, obtained from the Mössbauer spectra, refer to the center of the α Fe spectrum.

Fig. 2. GXRD pattern, at room temperature, of the austenitic steel 316L (a), implanted with $1 \mu\text{A cm}^{-2}$ ion current density and dose rate of 5×10^{16} (b), 10^{17} (c) and 1.5×10^{17} (d), $\text{N}_2^+ \text{cm}^{-2}$ and with $5 \mu\text{A cm}^{-2}$ ion current density and dose rate of 2×10^{17} $\text{N}_2^+ \text{cm}^{-2}$ (e). The tension was 80 keV and the temperature of the sample was maintained below 70°C.

3. Results and Discussion

In the as-received conditions 304SS is γ austenite of which the lattice parameter is 0.3585 nm. After nitriding at 800°C with 2.43 vol% NH_3/H_2 ratio the sample was still austenitic and the lattice parameter was 0.3590 nm (Fig. 1, Table 1). According to the variation of austenite lattice parameters vs. the interstitial nitrogen occupation rate $X^{2,3)}$ this parameter increase corresponds to about

Fig. 3. Transmission Mössbauer spectra at room temperature of 304 thin foils: (a) before nitriding S_0 , and after nitriding (Table 1): (b) S_3 , (c) S_4 , (d) S_5 , (e) S_6 . V^j environment corresponds to iron atoms with j nitrogen atoms first neighbours in j phase. The symbol prime is used when two iron environments are relative to the same number of nitrogen first neighbours but when the metallic substitutional neighbours are different in nature or amount (for example O^γ and $O^{\gamma'}$).

0.5N/100Me. This amount of nitrogen introduced by gaseous method is rather small. At the same temperature, but with 42 vol% NH_3/H_2 ratio, CrN chromium nitride is detected by X-ray diffraction and the austenitic phase is nitrogen enriched and noted γ_R . When at this temperature the NH_3/H_2 ratio is 8 vol%, in addition to γ and CrN nitride, magnetic α' martensite phase was detected in the material after quenching the specimens. It was shown by TMS that the amount of nitrogen in the α' martensite was about $0.2 \pm 0.1\%$ (Fig. 3). This value results from the environment abundancies (A_i) of sites O and I ($6X = A_i$).⁴⁾ This nitrogen content is consistent with the slight tetragonality of the martensite $c/a \approx 1.015 \pm 0.010$.

CrN nitride is formed by migration of Cr atoms induced by the attractive interaction between Cr and N. Clearly the migration of substitutional Cr atoms is favoured by the nitriding temperature higher than 700°C. After CrN precipitation, Cr concentration in austenite as well as the Cr equivalent decrease, γ transforms into

Fig. 4. CEMS spectra, at room temperature, of the austenitic 316L stainless steel unimplanted (a) and implanted at the conditions summarized in Table 2 (b)–(e). E_i environment corresponds to iron atoms with i nitrogen atoms first neighbours in $\gamma_R + \gamma_P$ phase. E'_i is used when two iron environments are relative to the same number of nitrogen first neighbours but when the metallic substitutional neighbours are different. E_A site corresponds to iron atoms in MeN like structure⁷⁾ where Me represents metallic atoms.

α' according to Schaeffler⁵⁾ and Long and Delong⁶⁾ diagrams. The M_s temperature initially low in 304 SS (less than -120°C) increases when the chromium concentration in austenite decreases. At 900°C when nitriding is performed under low nitrogen potential (S_6), the formation of CrN leads to Cr depletion of the austenite. When the NH_3/H_2 ratio increases from 3.1 to 4.3 vol%, i.e., when the nitrogen potential increases, the nitrogen concentration in the austenite phase as well as its stability increase and the amount of retained austenite also increases.

The as-received 316L SS has a f.c.c. structure, noted γ with a lattice parameter of 0.3595 nm. By GXRD analyses, after implantation at $5 \times 10^{16} \text{ N}_2^+ \text{ ions cm}^{-2}$, another f.c.c. phase, noted γ_R , is detected, having a lattice parameter of 0.3640 nm which corresponds to 7N/100Me (where Me represents the metallic atoms of a MeN_x

austenitic solid solution^{2,3)}). CrN coexists with initial γ and γ_R for an implantation dose of $10^{17} \text{ N}_2^+ \text{ ions cm}^{-2}$ (Table 2), the lattice parameter of γ_R is 0.370 nm and the nitrogen concentration 15N/100Me. By increasing the dose rate to $1.5 \times 10^{17} \text{ N}_2^+ \text{ ions cm}^{-2}$, the nitrogen concentration in γ_R increases to 26N/100Me, and γ_R coexists with CrN chromium nitride and γ (Fig. 2). The interstitial octahedral site occupation rate in γ_R corresponding to about 25% is much higher than any equilibrium value known for Fe-N and Fe-Cr-N austenite. It can be only partially favoured by an increasing solubility induced by chromium alloying, the major reason arises from the implantation process itself and the kinetics of nitrogen redistribution. Nitrogen interstitial are driven into austenite lattice by implantation and the resulting supersaturated austenite appears to be an intermediate stage before CrN or (Cr-Me)N nitride formation.⁷⁾ On the one hand the metal atom f.c.c. structure does not change but the local Cr enrichment needs Cr diffusion. This diffusion is induced by nitrogen superconcentrations leading to high Cr chemical potential gradient and by mechanical conditions created by ion impacts. Therefore from GXRD and CEMS analysis, γ_R appears to be an intermediate stage between $\gamma(\text{Fe-Me})\text{-N}$ and CrN phases. This result indicates that the nitrogen distribution is not homogeneous. Local nitrogen enrichment leads to the formation of $\gamma + \gamma_R$ zones. As shown by CEMS, the implantation with the highest dose, $1.5 \times 10^{17} \text{ N}_2^+ \text{ ions cm}^{-2}$, and with $1 \mu\text{A cm}^{-2}$ current density induced the formation of a metastable (type MeN, NaCl like structure) f.c.c. phase, similar to that observed previously by Bauer-Grosse *et al.*⁷⁾ This phase should correspond to a very fine dispersion of clusters or preprecipitates.

Structural results obtained by Mössbauer spectroscopy and X-ray diffraction clearly show that, during surface nitriding, atom redistribution occurs and may induce phase transformations leading to nitrides and α' martensite. The reason for this transformation is clearly due to the free enthalpy changes induced by nitrogen alloying $\Delta G(\text{N})$ at the surface of the specimen. In the case of gaseous nitriding, chemical potential of nitrogen in the $\text{NH}_3\text{-H}_2\text{-N}_2$ gas phase may—either induce nitrogen enrichment of austenite (Fig. 1(b))—or if it is still higher lead to the formation of chromium nitride and chromium depletion in the γ matrix which undergoes martensite transformation during cooling (Fig. 1(f)). Other phases such as, γ' Fe_4N -like structure and h.c.p. ϵ have been also detected after gaseous nitriding of 304 SS. Because gaseous nitriding occurs at high temperature, there is no barrier against evolution of the system towards equilibrium. The microstructure of the nitrided layer is mainly determined by thermodynamics. There is no contradiction between results obtained here and in other studies.^{8,9)} It is possible to embrittle austenite⁸⁾ as well as to reinforce the surface⁹⁾ depending on the nitriding conditions (chemical potential of N $\mu(\text{N})$ and temperature). Depending on the properties desired (*e.g.*, wear resistance, fatigue life, corrosion resistance, stress corrosion resistance, hardness), different microstructures may be desired. The thermochemical conditions for nitride precipitation have been studied vs. temperature

and $\mu(\text{N})$ in ternary Fe-Me-N alloys¹⁰⁾ and may be employed as a first estimation for austenitic stainless steel.

When the nitriding process is performed at highly metastable conditions at low temperature such as those reigning during ion implantation, the evolution of the microstructure towards equilibrium is interrupted by unfavorable diffusion. The appearance of a nitrogen-enriched γ_R austenitic phase indicates that, despite the low temperature, atomic redistribution of Cr and N occurs as a results of the chemical driving force and not only as a consequence of the implantation phenomenon itself (influence of current density for the same dose—redistribution of substitutional atoms shown by Mössbauer data related to iron O⁷⁾).

Determination whether the formation of γ_R after ion implantation results from a spinodal-like process similar to that observed in ϵ ¹¹⁾ or by nucleation and growth requires transmission electron microscopy observations of the implanted zone.

The comparison of nitrogen distribution and nitride formation in ion implanted and gas nitrided SS show great differences which are not due to the composition of the two steels studied (304 and 316L) but to the process itself which in the case of gaseous nitriding leads to a system mainly determined by thermodynamics, while in the case of ion implantation the alloys remains in highly metastable conditions. The possible interest of such a microstructure depends to a large extent on the service conditions which determine the evolution of the microstructure.

4. Conclusion

The comparison of two nitriding methods which greatly differ from each other by how close they approach chemical equilibrium conditions indicates that the nitriding surface treatment can lead to very different properties.

At high temperature (*i.e.* for gaseous nitriding), diffusion of nitrogen and of substitutional alloying elements such as Cr results in a microstructure which can be approached by thermodynamical equilibrium. The austenite phase may be either stabilised (γ_R) or destabilised (α'), the parameter which determines the structure is the chemical potential of nitrogen in the gas phase.

At low temperature, even though the nitrogen content may be very high and the driving force ΔG for phase transformation (nitride precipitation) very large, the system may be kept in highly metastable conditions by the limited diffusion of the alloying elements. In this case, the parameters which determine the microstructure and the properties of the coating are the ion implantation conditions and possible heat treatments.

REFERENCES

- 1) C. Cordier-Robert, L. Bourdeau, T. Magnin and J. Foct: *J. Mater. Sci. Lett.*, **13** (1994), 352.
- 2) K. H. Jack: *Proc. R. Soc.*, **A208** (1951), 200.
- 3) L. Cheng, A. Böttger, Th. H. De Keijser and E. J. Mittemeijer: *Scr. Metall.*, **24** (1990), 509.

- 4) J. Foct and P. Rochegude: *Hyp. Int.*, **28** (1986), 1075.
- 5) A. Schaeffler: *Met. Prog.*, **56** (1949), 680.
- 6) G. J. Long and W. T. Delong: *Weld J.*, **52** (1973), 281.
- 7) E. Bauer-Grosse, C. Frantz and G. Le Caer: Proc. of 1st Int. High Nitrogen Steel Cong., Inst. Met., Lille, (1988), 310.
- 8) B. Billon: Inst. Phys. Conf. Ser., **68** (1983), 367.
- 9) S. Siebert: *Bull. Cercle Étud. Métaux*, Tome XVI, No. 10 (1995), 21.1.
- 10) P. Perrot and J. Foct: Proc. of 2nd Int. High Nitrogen Steel Cong., Stahleisen, Aachen, (1990), 32.
- 11) P. Rochegude and J. Foct: *Phys. Status Solidi*, **88** (1985), 137.