On the earing in cup-drawing with non-uniform die clearance: analytical, numerical and experimental approaches

Zhenzhu WANG*, Wenzheng DONG***, Qiquan LIN* and Gen BU*

*School of Mechanical Engineering, Xiangtan University,
27, Yanggutang, Yuhu District, Xiangtan, 411105, China
E-mail: wzdong@xtu.edu.cn

**Department of Mechanical Engineering, Gifu University,
1-1 Yanagido, Gifu, 501-1193, Japan

Received: 9 February 2021; Revised: 12 April 2021; Accepted: 26 April 2021

Abstract

To minimize the earing incurred by the planar anisotropic properties of sheets, a non-uniform die clearance model was proposed for the cup drawing process. The theoretical earing profile height model with non-uniform die clearance was developed based on the combination of radial strain and thickness strain. The Hill 1948 yield criteria was applied to predict geometric earing profile and the anisotropic parameters were calibrated by optimization. It is observed that the predictions of the theoretical model are in agreement with the results of the cup drawing experiments, and the earing profile height is increasingly decreased by the non-uniform die clearance model. Further to this, a numerical model of the deep drawing process was also carried out using the commercial finite element software Abaqus. The results show that the cup drawing with non-uniform die clearance can not only minimize the earing profile height but also reduce the opening springback and twist springback in the split-ring process.

Keywords : Earing, Non-uniform die clearance, Cup drawing process, Earing profile height, Springback

1. Introduction

As one of the crucial processes in sheet metal forming, the deep drawing is usually used to manufacture thin plate parts with axisymmetric, square, or complex shape in many industrial fields, which probably show the wavy edge profile on the outline, that is earing as shown in Fig. 1(e), the book by Beddoes and Bibby (1999). In deep drawing, the plastic deformation in sheet metal varies with the inhomogeneity of material properties and stress distribution, the direction of the material with lower yield stress gives priority to plastic deformation, and then the material with larger yield stress deforms subsequently. The sequence of deformation leads to uneven plastic flow of the material and produces earing. However, earing is undesirable since it needs additional processing to trim, and even affects the subsequent forming processes.

To reduce the earing profile height, many attempts have been applied from the earing controllability, including optimizing the initial blank shape, improving the blank holder and lubricate condition. The shape of the initial blank sheet is closely related to earing profile height, Kishor et al. proposed an analytical formula to optimize the shape of the initial blank, they reduced the size of the blank at the position where the ear was larger, and then transferred the modified blank to the circular die cavity for cup drawing, and finally obtained a cup-shaped piece with low ears (Kishor and Kumar, 2002). Das et al. modified the analytical model based on Kishor's model, and analyzed the influence of the correction coefficient on the earing profile height (Das et al., 2013). Wang et al. presented a multi-step iterative design analysis methodology to determine the initial blank of stamping parts with arbitrarily shaped, they constructed the objective function based on the geometric deviation of the expected contour and the corrected blank contour and then used the corrected blank obtained at the end of each iteration as the initial blank for the next iteration (Wang et al., 2009). Finally, the optimized initial blank profile was obtained via the joint iteration of finite element calculation and MATLAB. This method is very suitable for the optimization calculation of the blank of any shape such as a circle or

rectangle.

Improving the contact between the deformation zone of the sheet flange and the blank holder ring can also reduce the earing. Siegert et al. proposed a segmented drawing die; this device used eight hydraulic cylinders under the blank holder to control the blank holder force, which can reduce the earing height by controlling the plastic flow sequence of materials (Siegert et al., 1996. Siegert et al., 1997). Tian et al. presented an annular cone-shaped dual blank holder structure to provide variable blank holder forces during stamping, which can effectively improving the wrinkling, tearing, and shape accuracy (Tian et al., 2015). Qin et al. successively proposed the deep drawing method of radial, mixed radial, and circumferential segmental blank holder, they found that these methods can be better improve the formability of the sheet metal via analyzing the wrinkle, fracture, and shape accuracy of cylindrical and square box-shaped parts (Qin et al., 2015; Kong et al., 2015; Mao et al., 2018). Srirat et al. investigate the effect of initial blank shape on earing, wrinkling, and tearing by using the sequential approximate optimization with radial basis function network, which greatly improves the utilization rate of the material (Srirat et al., 2012a, 2012b). Kitayama et al. developed a segment blank holder force (S-VBHF) method to optimize the initial blank shape successfully by using a sequential approximate optimization (Kitayama et al., 2015, 2016).

Besides, using local lubrication technology or optimizing the clearance between convex and concave molds can also suppress earing, but there are few reports. In this paper, we aim at proposing a non-uniform die clearance deep drawing process to reduce earing. In section 2, the analytical formula that relates the cup height to yield stress directionalities and non-uniform die clearance is summarized via constructing the distribution function of non-uniform die clearance. In section 3, the uniaxial loading test of the DC04 steel sheet was carried out, and the anisotropic parameters of Hill 1948 yield theory were identified and analyzed. Meanwhile, cup drawing tests with the uniform or non-uniform die clearance were conducted, and the coefficients of the non-uniform die clearance distribution function were determined. Finally, in section 4, a detailed analysis on the influences of the non-uniform die clearance on the earing and springback is discussed by using the Abaqus platform.

2. Non-uniform clearance model in the cup drawing process

2.1 Characteristic in cup drawing process with non-uniform die clearance

Generally, to obtain a cup-shaped parts with a more uniform height, the clearance between punch and die should be as uniform as possible in deep drawing of cylindrical cup. However, the clearance is not completely consistent during

Fig. 1 Schematic of the non-uniform clearance deep drawing process: (a) non-uniform clearance; (b) strain state at each deformation zone; stress state at (c) big clearance and (d) small clearance; (e) cup parts with or without earing

non-uniform deep drawing, but is distributed regularly along the circumferential direction, as shown in Fig. 1(a). In the non-uniform deep drawing process, the blank sheet can be divided into five zones as shown in Fig. 1(b): flange area (Zone-I), die fillet area (Zone-II), wall area (Zone-III), punch fillet area (Zone-IV), and the bottom area (Zone-V). The stress state of Zone-III at the small clearance is a non-uniaxial loading state, and it evolves towards an ironing process in the later stage of drawing, as shown in Fig. 1(d). While the stress state at the big clearance is uniaxial loading state due to the large clearance, as shown in Fig. 1(c). Utilizing this uneven stress state in the Zone-III, we attempt to reduce the earing height via designing a small clearance in the valley direction and a big clearance in the peak direction.

2.2 Derivation of earing profile height with non-uniform die clearance

As we all know, sheet metal has significant anisotropy after rolling, we often use r -value to characterize the anisotropy of the material. The r -value can be given as:

$$r = \frac{\varepsilon_w}{\varepsilon_t} \quad (1)$$

From Fig. 2, at the flange area (Zone-I), the radial strain in angle θ (or in angle $\theta+90^\circ$) is parallel to the circumferential strain in angle $\theta+90^\circ$ (or in angle θ). Assuming that, the compression strain in angle θ (or $\theta+90^\circ$) lead to identical radial strain in angle $\theta+90^\circ$ (or θ). According to the law of volume incompressibility and Chung et al.'s assumption (Chung et al., 1996), the r -value in an arbitrary angle $\theta+90^\circ$ can be written as:

$$r_{\theta+90} = \frac{\varepsilon_w|_{\theta+90}}{\varepsilon_t|_{\theta+90}} = \frac{\varepsilon_{\theta+90}}{\varepsilon_t|_{\theta+90}} = \frac{\varepsilon_r|_{\theta}}{-(\varepsilon_r|_{\theta+90} + \varepsilon_{\theta+90})} = -\frac{\varepsilon_r|_{\theta}}{\varepsilon_r|_{\theta} + \varepsilon_{\theta}} \quad (2)$$

From Eq. (2), the following relationship can be derived:

$$\varepsilon_{\theta} : \varepsilon_r|_{\theta} : \varepsilon_t|_{\theta} = -(r_{\theta+90} + 1) : r_{\theta+90} : 1 \quad (3)$$

Fig. 2 The strain state of the element at an arbitrary angle θ on the flange area (Zone-I)

According to Yoon et al.'s studies, for the anisotropic material, the circumferential strain for the cup wall should contain the isotropic and anisotropic terms, it can be written as (Yoon et al., 2011):

$$\varepsilon_{\theta} = \varepsilon_{\theta}^{ISO} + \beta \varepsilon_{\theta}^{ANI} = \ln \frac{R_c}{R} + \beta \ln \frac{\sigma_{(\theta)}^Y}{\sigma_{ref}^Y} = \ln \left(\frac{R_c}{R} \left(\frac{\sigma_{(\theta)}^Y}{\sigma_{ref}^Y} \right)^{\beta} \right) \quad (4)$$

Then, by inserting Eq. (4) into Eq. (3), the radial strain in an arbitrary angle θ can be written as:

$$\varepsilon_r|_{\theta} = -\left(\frac{r_{\theta+90}}{1 + r_{\theta+90}} \right) \ln \left(\left(\frac{\sigma_{(\theta)}^Y}{\sigma_{ref}^Y} \right)^{\beta} \frac{R_c}{R} \right) \quad (5)$$

From Eq. (5), the radial strain is mainly affected by r -value and yield stress directionalities, the $\sigma_{(\theta)}^y$ will be derived in section 3.1, where

$$R_c \leq R \leq R_b' \quad (6-a)$$

$$0.5 \leq \beta \leq 1 \quad (6-b)$$

$$\sigma_{ref} = \left(\int_0^{2\pi} \sigma_{(\theta)}^y d\theta \right) / 2\pi \approx (\sigma_0 + 2\sigma_{45} + \sigma_{90}) / 4 \quad (6-c)$$

At the wall area (Zone-III), the thickness strain in an arbitrary angle θ can be also derived from the Eqs. (3) and (5):

$$\varepsilon_t|_{\theta} = \frac{\varepsilon_r|_{\theta}}{r_{\theta+90}} = \frac{1}{1+r_{\theta+90}} \ln \left(\left(\frac{\sigma_{ref}}{\sigma_{(\theta)}^y} \right)^{\beta} \frac{R}{R_c} \right) \quad (7)$$

The above thickness strain is only valued for the region great than zero, viz., $\varepsilon_t|_{\theta} > 0$. Then, the wall thickness in an arbitrary angle θ can be derived from the Eqs. (3) and (7):

$$t|_{\theta} = t_0 \exp(\varepsilon_t|_{\theta}) = t_0 \left(\left(\frac{\sigma_{ref}}{\sigma_{(\theta)}^y} \right)^{\beta} \frac{R}{R_c} \right)^{\frac{1}{1+r_{\theta+90}}} \quad (8)$$

As mentioned before, in the non-uniform deep drawing process, the clearance between punch and die is non-uniform. When the sheet metal flows through the die cavity in the direction of the small clearance, the additional thickness strain will be produced due to the ironing like a process in small clearance, it can be written as:

$$\varepsilon_t^*|_{\theta} = \ln \left(\frac{t^*|_{\theta}}{t|_{\theta}} \right) \quad (9)$$

Here, assume $t^*|_{\theta}$ is equal to the clearance between punch and die.

The earing profile has extreme properties between rolling (RD) and transverse (TD) direction, according to the assumption in section 2.1, the distribution function of the clearance along circumference direction should have at least two cosine terms, one of which is used to obtain the extreme value of the function, and the other is used to obtain the situation where the maximum value (or minimum value) is not equal. Thus, the distribution function of the clearance between punch and die can be written as:

$$z(\theta) = z_{cp} + A_1 \cos 2\theta + A_2 \cos 4\theta + \dots + A_n \cos 2n\theta \quad (10)$$

Here, n is a positive integer, while the extreme of function $z(\theta)$ is just equal to $2n$. In this work, we only discuss the case of $n=2$, viz., there are two maxima and two minima clearances, $A_1, A_2, \dots, A_n$ are the constant for control the amplitude of the Eq. (10).

At the wall area (Zone-III), the circumferential strain can be regarded as approximately zero ($\varepsilon_{\theta}=0$) due to no deformation in-wall diameter. Then, the additional radial strain in an arbitrary angle θ can be derived from the law of volume incompressibility, Eqs. (9) and (10):

$$\varepsilon_r^*|_{\theta} = -(\varepsilon_{\theta} + \varepsilon_t^*|_{\theta}) = -\varepsilon_t^*|_{\theta} = \ln \left(\frac{t|_{\theta}}{t^*|_{\theta}} \right) = \ln \left(\frac{t|_{\theta}}{z(\theta)} \right) \quad (11)$$

Substituting the Eqs. (8) and (10) into the Eq. (11), then

$$\varepsilon_r^*|_{\theta} = \ln \left[\left(\frac{t_0}{z_{cp} + A_1 \cos 2\theta + A_2 \cos 4\theta} \right) \left(\left(\frac{\sigma_{ref}}{\sigma_{(\theta)}^Y} \right)^{\beta} \frac{R}{R_c} \right)^{\frac{1}{1+\eta+90}} \right] \quad (12)$$

From Eqs. (5) and (12), the total radial strain in the whole deep drawing can be obtained:

$$\varepsilon_r^{Total}|_{\theta} = \varepsilon_r|_{\theta} + \varepsilon_r^*|_{\theta} = \ln \left[\left(\frac{t_0}{z_{cp} + A_1 \cos 2\theta + A_2 \cos 4\theta} \right) \left(\left(\frac{\sigma_{ref}}{\sigma_{(\theta)}^Y} \right)^{\beta} \frac{R}{R_c} \right)^{\frac{1}{1+\eta+90}} \right] \quad (13)$$

To quickly assess of earing profile, Yoon et al.'s proposed an analytical formula to approximate the earing height profile, which was the integral of the total radial strain from R' to R_b . From Fig. 3, the total cup height in the arbitrary angle θ can be expressed as (Yoon et al., 2006):

$$H_{\theta} = t_0 + r_p + H(\varepsilon_r|_{\theta}) + H(\varepsilon_r^*|_{\theta}) = t_0 + r_p + \int_{R'}^{R_b} \exp(\varepsilon_r^{Total}|_{\theta}) dR \quad (14)$$

If $H(\varepsilon_r^*|_{\theta}) = 0$, Eq. (14) reduces to (Yoon et al., 2011) with no ironing process as shown in Fig. 3(b), which is regarded as uniform clearance deep drawing.

Substituting the Eq. (13) into Eq. (14)

$$H_{\theta} = t_0 + r_p + \frac{t_0}{z_{cp} + A_1 \cos 2\theta + A_2 \cos 4\theta} \left(\frac{\sigma_{ref}}{\sigma_{(\theta)}^Y} \right)^{\beta} \frac{(R_b^2 - R'^2)}{2R_c} \quad (15)$$

Fig. 3 Non-uniform deep drawing process: (a) schematic of cup height; cup height at (b) big clearance, or (c) small clearance

In Eq. (15), the R' is the outer radius of the ring with the same area as the punch arc, it can be obtained by applying the volume constancy:

$$\pi(R'^2 - R_p^2) = \pi^2 r_p R_p + 2\pi r_p^2 \quad (16-a)$$

$$R'^2 = \pi R_p r_p + R_p^2 + 2r_p^2 \quad (16-b)$$

Here, the detailed derivation of Eq. (16-b) can be seen in Ref. (Schuler et al. 1998).

In Eq. (15), the R_p , r_p , R_b , R_c , and t_0 are the parameters of tools and blank sheet, they can be measured directly. The $\sigma_{(\theta)}^Y$ and σ_{ref} can be obtained by the experiment true stress-strain curves indirectly. Assuming that the cup height is

equal in all direction during non-uniform die clearance deep drawing, then, the A_1 and A_2 can be determined as follow:

$$H_{0^\circ} = H_{45^\circ} \quad (17-a)$$

$$H_{0^\circ} = H_{90^\circ} \quad (17-b)$$

3. Experiments

3.1 Uniaxial tension test

In this paper, the DC04 with 1.2 mm thickness was cut into the shape as shown in Fig. 4(a). Monotonic loading tests were carried out with the SANS tensile testing machine at 0° , 45° and 90° to the rolling direction, all tests were duplicated three times at a tensile speed of 2 mm/min. The measured mechanical properties such as Young's modulus, yield stress, and r -value (Lankford's plastic strain ratio at the true strain of 0.2) are shown in Table 1. The stress-strain curve can be obtained through the force-extensometer displacement, which was fitted by a linear combination of Hollomon (1945, $\sigma = K(\varepsilon^p)^n$) and Voce (1948, $\sigma = \sigma^0(1 - A \exp(-B\varepsilon^p))$) strain hardening equation, as shown in Fig. 5(b). It shows that the DC04 steel sheet has significant anisotropy behavior. The coefficients for the strain hardening laws are given in Table 2.

Fig.4 (a) Geometry and size of the adopted specimen, (b) uniaxial tensile tests for DC04 at different directions

Table 1. Yield stress and r -value input data to determine Hill 1948 coefficients

Lable	E_{0° [GPa]	E_{45° [GPa]	E_{90° [GPa]	σ_{0° [MPa]	σ_{45° [MPa]	σ_{90° [MPa]	r_{0°	r_{45°	r_{90°
Value	69.409	106.358	64.807	148.964	154.013	148.218	2.12	1.88	2.56

Table 2. Coefficients of the hardening laws for DC04

Lable	$f(\varepsilon^p) = \alpha \cdot K(\varepsilon^p)^n + (1-\alpha) \cdot \sigma^0(1 - A \exp(-B\varepsilon^p))$ (Sung et al., 2010)					
	α	K [MPa]	n	σ^0	A	B
RD	0.4384	777.9322	0.7772	468.0805	0.4461	17.8746
DD	0.4316	781.3211	0.7572	475.7063	0.4284	18.0189
TD	0.4074	774.3908	0.8564	460.9453	0.4713	17.3080

3.2 Cup drawing test

The experiment equipment for the uniform or non-uniform deep drawing process is a hydraulic loading apparatus developed by Beihang University, as shown in Fig. 5(a). The main tools and process parameters are listed in Table 3.

Besides, the die cavity is designed to be non-circular shape as shown in Fig. 5(d), the main dimension of the three dies is listed in Table 4.

Fig. 5 Laboratory-based sheet forming machine system: (a) overview; (b) tools; (c) cup parts; (d) illustration of the die cavity dimension at an angle θ from RD

Table 3. Main tools and forming parameters

No.	Parameters	Values
1	Punch radius[mm]	25
2	Punch fillet radius[mm]	5
3	Die fillet radius[mm]	10
4	Blank sheet radius[mm]	42.5
5	Sheet thickness[mm]	0.8
6	Punch velocity[mm/min]	50
7	Blank holder force[kN]	40
8	Friction coefficient (Zang et al., 2014)	0.15

Table 4. The dimension of the die cavity along the RD

Dimension	Type-A	Type-B	Type-C
D_{0° [mm]	25.88	25.80	25.80
D_{15° [mm]	25.88	25.85	25.83
D_{30° [mm]	25.88	25.90	25.86
D_{45° [mm]	25.88	25.96	25.88
D_{60° [mm]	25.88	25.90	25.86
D_{75° [mm]	25.88	25.85	25.83
D_{90° [mm]	25.88	25.80	25.80
Average clearance [mm]	0.88	0.865	0.837

To clarify the influence of non-uniform clearance on earing, the sensitivities of earing profile and % earing height were performed by using the method of directional placement of the blank sheet, viz., the rolling direction (RD) of the circular blank should be aligned with the 0° and 45° directions of the die cavity respectively during non-uniform deep drawing. From Fig.6, the notation “Type-B- 0° ” and “Type-C- 0° ” stands for the rolling direction (RD) of the circular blank is aligned with the D_{0° of the die cavity, and the notation “Type-B- 45° ” and “Type-C- 45° ” stands for the RD is aligned with the D_{45° . For “Type-A”, “Type-B- 0° ”, and “Type-C- 0° ”, the peaks of earing profile occurred at the rolling direction (RD) and transverse direction (TD), where the peak values at transverse direction (TD) decrease with the decrease of clearance deviation obviously, as shown in Fig. 6(a). For “Type-B- 45° ”, the peak of the earing profile occurred at 50° along the RD. For “Type-C- 45° ”, it’s difficult to point out where the peak is, due to the small deviation of earing height. These indicate the angular rotation between the rolling direction (RD) of the blank sheet and die cavity will seriously affect the distribution law of the earing profile. Besides, the % earing profile is also obtained, and it is calculated as follows (Kishor and Kumar, 2002):

$$\% \text{ earing height} = \frac{(\max. \text{ cup height} - \min. \text{ cup height})}{\min. \text{ cup height}} \times 100 \quad (18)$$

From Fig. 6(b), it shows that the % earing height is significantly affected by the non-uniform die clearance value and the method of placing the blank sheet, the % earing height of “Type-C- 45° ” is only 0.64%. All these indicate that the proper coupling of non-uniform die clearance and the anisotropy of the blank sheet can effectively reduce the height of the ears, this also proves the idea proposed in section 2.1.

Fig. 6 Five different cup drawing test: (a) earing profile; (b) % earing height

3.3 Yield criteria and identification of the anisotropic parameters

The deformation of the blank sheet during the whole deep drawing process can be regarded as a plane stress state; thus, the anisotropic Hill 1948 yield function can be expressed as (Hill, 1948):

$$F\sigma_{yy}^2 + G\sigma_{xx}^2 + H(\sigma_{xx} - \sigma_{yy})^2 + 2N\sigma_{xy}^2 = \bar{\sigma}^2 \quad (19)$$

By utilizing the relation as follow:

$$\sigma_{xx} = \sigma_{(\theta)}^Y \cos^2 \theta, \sigma_{yy} = \sigma_{(\theta)}^Y \sin^2 \theta, \sigma_{xy} = \sigma_{(\theta)}^Y \sin \theta \cos \theta \quad (20)$$

Table 5. Different methods of calculating anisotropic parameters in Hill 1948 yield function

Method	Input parameters	Equations	Reference
<i>r</i> -value based (Hill-R)	$r_{0^\circ}, r_{45^\circ}, r_{90^\circ}$	$F = \frac{2 \cdot r_{0^\circ}}{r_{90^\circ}(1 + r_{0^\circ})} \quad H = \frac{2 \cdot r_{0^\circ}}{1 + r_{0^\circ}}$ $G = \frac{2}{1 + r_{0^\circ}} \quad N = \frac{2 \cdot (r_{0^\circ} + r_{90^\circ}) \cdot (r_{45^\circ} + 0.5)}{r_{90^\circ}(1 + r_{0^\circ})}$	(Kawka and Makinouchi, 1996)
Stress based (Hill-S)	$\sigma_{0^\circ}, \sigma_{45^\circ}, \sigma_{90^\circ}, \sigma_b$	$F = \frac{\sigma_{0^\circ}^2}{\sigma_{90^\circ}^2} - 1 + \frac{\sigma_{0^\circ}^2}{\sigma_b^2} \quad H = 1 + \frac{\sigma_{0^\circ}^2}{\sigma_{90^\circ}^2} - \frac{\sigma_{0^\circ}^2}{\sigma_b^2}$ $G = 1 - \frac{\sigma_{0^\circ}^2}{\sigma_{90^\circ}^2} + \frac{\sigma_{0^\circ}^2}{\sigma_b^2} \quad N = \frac{4\sigma_{0^\circ}^2}{\sigma_{45^\circ}^2} - \frac{\sigma_{0^\circ}^2}{\sigma_b^2}$	(Cazacu et al., 2001)
Combined (Hill-SR)	$\sigma_{0^\circ}, \sigma_{45^\circ}, \sigma_{90^\circ}, r_{90^\circ}$	$F = \frac{2\sigma_{0^\circ}^2}{\sigma_{90^\circ}^2 \cdot (1 + r_{90^\circ})} \quad H = \frac{2\sigma_{0^\circ}^2 \cdot r_{90^\circ}}{\sigma_{90^\circ}^2 \cdot (1 + r_{90^\circ})}$ $G = 2 - \frac{2\sigma_{0^\circ}^2 \cdot r_{90^\circ}}{\sigma_{90^\circ}^2 \cdot (1 + r_{90^\circ})} \quad N = \frac{4\sigma_{0^\circ}^2}{\sigma_{45^\circ}^2} - 1 + \frac{\sigma_{0^\circ}^2 \cdot (r_{90^\circ} - 1)}{\sigma_{90^\circ}^2 \cdot (1 + r_{90^\circ})}$	(Cazacu et al., 2001)

Table 6. Coefficients for the Hill 1948 yield function (DC04)

Lable	For calculate the yield stress				For FEM			
	F	G	H	N	R11	R22	R33	R12
Hill-R	0.5308	0.641	1.359	2.7891	1	1.0287	1.3064	1.0371
Hill-S/R	0.5709	0.5384	1.4616	2.9878	1	0.992	1.3427	1.002
Hill-OPT	0.4005	0.4037	0.5963	1.4632	1	1.0016	1.1151	1.0125

The yield stress in arbitrary angle θ can be derived from Eqs. (18) and (19):

$$\sigma_{(\theta)}^y = \frac{\bar{\sigma}}{\sqrt{F \sin^2 \theta + G \cos^2 \theta + H + (2N - F - G - 4H) \sin^2 \theta \cdot \cos^2 \theta}} \quad (21)$$

From the Hill 1948 yield function, the model parameters F , G , H , and N can be directly calculated by an analytical method, namely based on yield stress (Hill-S), r -value (Hill-R), or combined stress and r -value (Hill-SR), as listed in Table 5 (Lian et al., 2018). Besides, the parameters F , G , H , and N can be indirectly calculated by the optimized parameters $R11$, $R22$, $R33$, and $R12$, namely based on optimization (Hill-OPT), here the calibration was performed in the co-simulation of Isight, Python code, and Abaqus, which was to minimize the absolute difference area between the experiment and simulation of true stress-strain curves. The detailed calculation flow chat was shown in Fig. 7(a) and (b), and the identified material coefficients of the Hill 1948 yield function are presented in Table 6. The yield stress calculated from Eq. (21) is given in Fig. 7(c), it can be found that the Hill-OPT has a good agreement with the experiment, while the Hill-R and Hill-SR show a great deviation from experiment data, this may be caused by the cumulative error of many input data.

Fig. 7 (a) Analytical method, and (b) FEM optimization flow chat, (c) yield stress vs. angle from rolling

3.4 Determine the analytical model coefficients of earing profile height

According to the Eqs. (15) and (17), the coefficients A_1 and A_2 can be obtained if the middle clearance z_{cp} is given first. In the Fig. 8, the notation “Type-C-45°” and “Type-A” stands for the experiment results of cup height, it shows that the cup height of “Type-C-45°” is reduced significantly compared with “Type-A”. Based on the non-uniform clearance of the “Type-C-45°”, assume the initial middle clearance z_{cp} is equal to average clearance of “Type-C-45°”, viz., $z_{cp}(initail) = [(25.88 - 25) + (25.80 - 25)]/2 = 0.84$ (mm). In order to compare the earing height of the present analytical approach and the experiment result (“Type-C-45°”), various of the initial middle clearance z_{cp} and deceleration factor β are investigated, and the coefficients A_1 and A_2 are listed in table 7. According to the data of table 7, the cup height can be calculated by using Eq. (15), as showed in Fig. 8, and its trend likes a straight line. Meanwhile, the present analytical approach has a small deviation with “Type-C-45°” when the z_{cp} is equal to 0.83 and 0.84, the constant β also has a little effect on the cup height.

Table 7. Coefficients for cup height of present analytical approach, Eq. (15)

Initial middle clearance z_{cp} [mm]	deceleration factor β	A_1	A_2
0.82	0.5	3.313E-04	0.007
	1.0	6.682E-04	0.014
0.83	0.5	3.353E-04	0.0071
	1.0	6.763E-04	0.0141
0.84	0.5	3.394E-04	0.0072
	1.0	6.845E-04	0.0143

Fig. 8 Comparison of cup height calculated using different coefficients of z_{cp} and β

Fig. 9 Comparison of non-uniform clearance calculated using different coefficients of z_{cp} and β

According to Table 7 and Eq. (10), the distribution curves of the non-uniform clearance can be also obtained, Fig. 9 compares the experiment data of the non-uniform clearance with the calculated data by using Eq. (10), which were considered various z_{cp} and β . It is observed that all the curves by using Eq. (10) have a similar tendency with the clearance of “Type-C-45°”, while the peak or valley of the calculated curves still have a large deviation from the “Type-C-45°”, especially when $\beta = 0.5$. From the analysis of Fig. 8 and Fig. 9, the z_{cp} can affect the overall cup height obviously, and the deceleration factor has a weak influence on the cup height, but has a huge influence on the amplitude of the non-uniform clearance function. Due to the physical meaning of this factor, only the situation in the range of 0.5~1.0 is considered in Eq. (10), the details have been discussed in Ref. (Yoon et al., 2011). Thus, the largest deceleration factor can be selected in the tooling design to determine the distribution of non-uniform clearance.

4. FEM analysis of non-uniform die clearance function in cup drawing

A 3D finite element model (FEM) was developed to simulate the non-uniform die clearance deep drawing using Abaqus/Explicit platform. In this model, the punch, die, and blank holder are defined as 3D bilinear rigid quadrilateral discrete rigid body elements with four nodes (R3D4). The blank sheet has been meshed with 8-node linear brick with reduced integration elements (C3D8R). From section 2.2, the main deformation of the blank sheet occurs in the flange area during deep drawing. To save simulation cost, the blank sheet is divided into two parts, namely the center area and the outer ring area. The number of elements is 35 with a single bias ratio of 2 in the center area, while the number is 5 with no bias in the thickness direction, and the mesh size of the outer ring area is 0.6 mm. The boundary loading condition of punch stroke is 40 mm, the forming step time is 0.01 s. For the plastic part, the hardening model is assumed to be isotropic at room temperature during all the simulations.

4.1 The effect of different anisotropy parameters on prediction earing in uniform deep drawing

To verify the importance of anisotropy parameters for predicting earing profile, it is necessary to analyze different parameters to evaluate the predictive ability of earing. From Fig. 10, it shows that the notation “FEM-Hill-R” and “FEM-Hill-SR” predict a larger earing profile, and the notation “FEM-Hill-OPT” shows a good agreement with the experimental result in the range from rolling direction (RD) to diagonal direction (DD), but the earing profile height at transverse direction (TD) cannot be predicted well. It also found that the deviation of the earing valley is large; this is because the Hill 1948 yield theory cannot accurately predict the situation where the principal axis of anisotropy does not coincide with the principal axis of stress, as introduced by Lian and Barlat (Lian et al., 1989).

From the above analysis, the parameter “Hill-OPT” in Table 6 will be used for finite element analysis of non-uniform die clearance deep drawing.

Fig. 10 Experiment and predicted earing profiles of uniform cup drawing: (a) FEM-Hill-R; (2) FEM-Hill-SR; (3) FEM-Hill-OPT; (4) earing profile

4.2 Effect of the non-uniform die clearance directionalities

As for the influence of non-uniform die clearance on earing profile, the uniform and non-uniform clearance cup drawing with the anisotropy coefficients of Hill-OPT are presented in Fig. 11. From Fig. 11(a)-(e), it shows that the equivalent plastic strain (PEEQ) is more uniform in the top edge of the cup wall during the non-uniform clearance deep

Fig. 11 Distribution of the equivalent plastic strain (PEEQ): (a) Type-A; (b) Type-C-45°; (c) Eq. (10) $z_{cp}=0.84$, $\beta=1.0$; (d) Eq. (10) $z_{cp}=0.83$, $\beta=1.0$; (e) Eq. (10) $z_{cp}=0.82$, $\beta=1.0$;

drawing process, and the peaks of earing profile at angle 0° and 90° are decrease obviously as shown in Fig. 12(a).

The % earring height is also reduced significantly as shown in Fig. 12(b), the “Type-C-45° (FEM)” shows the lowest % earring height. In addition, Fig. 12(a) also shows that when the middle clearance (z_{cp}) is equal to 0.83, the earring profile is close to the “Type-C-45° (FEM)”, while when $z_{cp} = 0.82$, the earring profile deviates greatly from that of “Type-C-45° (FEM)”. This indicates that the use of Eq. (10) to calculate the non-uniform clearance profile must be combined with the reasonable z_{cp} value to reduce the % earring height more effectively.

Fig. 12 Comparison of experiment and FEA: (a) earring profile; (b) % earring height

Fig. 13 Comparison of thickness distribution between experiment and FEA: (a) schematic diagram of thickness measurement at different cup height; (b) Type-A (FEM); (c) Type-C-45° (FEM); (d) Eq. (10) $z_{cp}=0.83, \beta=1.0$

To clarify the influence of non-uniform clearance on the thickness of cup wall during deep drawing, the thickness along the circumference at different heights of cup wall was measured by finite element simulation, and the measured position is shown in Fig. 13 (a). From Fig. 13(c) and 13(d), it shows that the thickness of the top of the cup wall is

uneven during non-uniform deep drawing, but this unevenness generally tends to one of side of the cup wall. In the present study, the inside of cup is circular, and the outside is non-circular. From Fig. 13(b) and 13(c), it reveals that the circumference thickness trend of simulated measurement is consistent with the experimental, the simulated value of “Type-C-45° (FEM)” is slightly higher than the experimental value. Fig. 13(b) shows that the maximum deviation of circumference thickness during uniform deep drawing is only 0.02 mm. The deviation of “Type-C-45° (FEM)” is up to 0.08mm in the non-uniform deep drawing, and this deviation difference decreases as the height of the cup wall decreases, as shown in Fig. 13(c). From Fig. 13(d), by substituting $z_{cp} = 0.83$ into the Eq. (10) for simulation, it can be seen that the maximum deviation of circumference thickness is 0.04. In addition, from Fig. 13(b), (c), and (d), it is found that the thickness deviation of cup wall at H3 and H1 is greater than 0.1 mm, which can also reflect the deviation of the circumference thickness less than the overall thickness deviation of the cup.

4.3 Analysis of split-cut springback

To evaluate the influence of non-uniform clearance deep drawing on springback, the numerical simulations of the split-ring test are carried out during cup drawing, ring trimming, and springback after splitting as shown in Fig. 14(a). To save the simulation time, a quarter of the model is used, a ring with the height of 6 mm is split at the cup height of 17.5 mm of the cup wall for simulation, the rolling direction (RD) of the ring is fixed, and the other side of the ring is stressed to realize the split-cut springback process. The intrados profile of the ring wall is measured as shown in Fig. 14(b), and Fig. 14(c) shows that the “Type-A” with uniform clearance has a significant springback, and the “Type-C-45°” also has a large springback with the same value of non-uniform die clearance as the experiment. However, the springback is small when the clearance value calculated by Eq. (10) is used for simulation.

Fig. 14 Split-ring test: (a) diagram before and after springback; (b) profile of the intrados of the ring wall

It is worth mentioning that the twist springback is found in the split-ring test, Fig. 15(a) shows two forms of twist springback, viz., the angle φ_1 and φ_2 . From Fig. 15(b) and (c), it can be seen that “Type-A” and “Type-C-45°” have a large twist springback, while the angle φ_1 and φ_2 are reduced obviously by using the calculated non-uniform die clearance. Particularly, the middle clearance (z_{cp}) in Eq. (10) can also affect the twist springback, the smaller z_{cp} , the smaller twist springback angle. It has also been reported that the twist springback can effectively be reduced by optimizing the initial blank shape, this indicates that improving the flow uniformity of the material is crucial to improve these defects (Kitayama et al., 2019).

Fig. 15 Twist springback in the split-ring simulation: (a) schematic diagram of twist springback, (b) the twist springback angle ϕ_1 , and (c) ϕ_2

5. Conclusions

The main findings of the present work can be summarized as follows:

(1) A new analytical model for predicting earing profile height was developed, which considers both yield stress and the die clearance directionalities simultaneously. The non-uniform die clearance distribution function was also presented based on the proposed theory.

(2) The non-uniform die clearance cup drawing test showed that the configurations of the initial blank have a considerable effect on earing profile due to the anisotropy of material properties. The material direction with lower yield strength should be arranged in the direction with a larger die clearance; otherwise, the material direction with high yield strength should be configured. Using such a blank orientation arrangement method for the cup drawing test can significantly minimize the earing height.

(3) The numerical optimization model and analytical model for the anisotropic parameter identification of the Hill 1948 yield function are discussed. The results show that the anisotropic parameters obtained by the numerical optimization method have a more approximate tendency for predicting the yield stress and earing profile.

(4) The earing and springback behavior is evaluated by finite element simulation for the cup drawing process with non-uniform die clearance. The results show that the non-uniform die clearance cup drawing can not only effectively reduce the earing height, but also reduce the opening springback and twist springback in the split-ring process.

Nomenclature

ε_p	plastic strain	$\bar{\sigma}$	effective stress
ε_r	radial strain	σ_r	radial stress
ε_θ	circumferential strain	σ_θ	circumferential stress

ε_t	thickness strain	$\sigma_{(\theta)}^Y$	tensile yield stress in angle θ
ε_w	width strain	σ_{ref}	the average of tensile yield stress
$\varepsilon_{\theta}^{ISO}$	isotropic circumferential strain	r	Lankford plastic strain ratio (r -value)
$\varepsilon_{\theta}^{ANI}$	anisotropic circumferential strain	$r_{\theta+90}$	r -value in angle $\theta + 90$
$\varepsilon_{\theta+90}$	circumferential strain in angle $\theta + 90$	t_0	initial thickness of blank sheet
$\varepsilon_r _{\theta}$	radial strain in angle θ	$t _{\theta}$	the wall thickness before ironing
$\varepsilon_t _{\theta}$	thickness strain in angle θ	$t^* _{\theta}$	the wall thickness after ironing
$\varepsilon_w _{\theta}$	width strain in angle θ	$z(\theta)$	the non-uniform clearance function
$\varepsilon_r _{\theta+90}$	radial strain in angle $\theta + 90$	z_{cp}	the middle clearance
$\varepsilon_t _{\theta+90}$	thickness strain in angle $\theta + 90$	β	deceleration factor
$\varepsilon_t^* _{\theta}$	the additional thickness strain	F, G, H, N	anisotropic coefficients
$\varepsilon_r^* _{\theta}$	the additional radial strain	r_p	radius of punch fillet
$\varepsilon_r^{Total} _{\theta}$	the total radial strain	R_c	radius of punch
H_{θ}	the cup height	R_b	radius of blank sheet
$H(\varepsilon_r _{\theta})$	the cup height due to radial strain	R'_b	instantaneous radius of blank
$H(\varepsilon_r^* _{\theta})$	the cup height due to additional radial strain	R'	original radius of a cup height r_p of the initial blank sheet
$A_1, \dots, A_n$	the constant for control the amplitude of the Eq. (10), n is positive integer	α	the weight coefficients of combination of Hollomon and Voce model
$r_{0^\circ}, r_{45^\circ}, r_{90^\circ}$	Lankford coefficients of experiment	K, n	the coefficient of Hollomon model
$\sigma_{0^\circ}, \sigma_{45^\circ}, \sigma_{90^\circ}$	initial yield stress of experiment	σ°, A, B	the coefficient of Voce model
$\sigma_{xx}, \sigma_{yy}, \sigma_{xy}$	stress tensor	$H_{0^\circ}, H_{45^\circ}, H_{90^\circ}$	The cup height in angle $0^\circ, 45^\circ, 90^\circ$
$E_{0^\circ}, E_{45^\circ}, E_{90^\circ}$	Young's modulus of experiment		

Acknowledgment

The authors would like to acknowledge financial support by the Natural Science Foundation of Hunan Province, China (Grant No. 2020JJ4578, 2019JJ50604) and the Key Program of the Scientific Research Foundation of the Education Department of Hunan Province, China (Grant No. 19A499).

References

- Beddoes, J., and Bibby, M., Principles of metal manufacturing processes (1999), p.159, Butterworth-Heinemann.
- Cazacu, O., and Barlat, F., Generalization of drucker's yield criterion to orthotropy, Mathematics Mechanics of Solids, Vol.6, No.6 (2001), pp.613-630.
- Chung, K., Lee, S. Y., Barlat, F., Keum, Y. T., and Park, J. M., Finite element simulation of sheet forming based on a planar anisotropic strain-rate potential, International Journal of Plasticity, Vol.12, No.1 (1996), pp.93-115.
- Das, P., Panda, S. K., and Pratihari, D. K., Modification of initial blank shape to minimize earing in deep drawing process, Advanced Materials Manufacturing and Characterization, Vol.3, No.1 (2013), pp.99-104.
- Hill, R., A theory of the yielding and plastic flow of anisotropic metals, Proceedings of the Royal Society of London. Series A, Mathematical and Physical Sciences, Vol.193, No.1033 (1948), pp.281-297.
- Kawka, M., and Makinouchi, A., Plastic anisotropy in fem analysis using degenerated solid element, Journal of Materials Processing Technology, Vol.60, No.1-4 (1996), pp.239-242.
- Kishor, N., and Kumar, D. R., Optimization of initial blank shape to minimize earing in deep drawing using finite element method, Journal of Materials Processing Technology, Vol.130, No.02 (2002), pp.20-30.
- Kitayama, S., Ishizuki, R., Yokoyaka, M., Kawamoto, K., Natsume, S., and Adachi, K., Noguchi, T., and Ohtani, T., Numerical optimization of variable blank holder force trajectory and blank shape for twist springback reduction using sequential approximate optimization, International Journal of Advanced Manufacturing Technology, Vol.103, No.1 (2019), pp.63-75.
- Kitayama, S., Koyama, H., Kawamoto, K., Miyasaka, T., and Noda, T., Optimization of blank shape and segmented variable blank holder force trajectories in deep drawing using sequential approximate optimization, International

- Journal of Advanced Manufacturing Technology, Vol.91, No.5 (2016), pp.1-13.
- Kitayama, S., Saikyo, M., Kawamoto, K., and Yamamichi, K., Multi-objective optimization of blank shape for deep drawing with variable blank holder force via sequential approximate optimization, Structural and Multidisciplinary Optimization, Vol.52, No.5 (2015), pp.1001-1012.
- Kong X. H., Qin S. J., Lu H., Zheng X., Experimental Research on Deep Drawing Process Using Radial Segmental Blank Holders with Conical Die, China Mechanical Engineering (in Chinese), Vol.26, No.18 (2015), pp.2528-2532+2538.
- Lian J, Barlat F, and Baudelet B., Plastic behaviour and stretchability of sheet metals, Part I: A yield function for orthotropic sheet under plane stress conditions, International Journal of Plasticity, Vol.5.No.1 (1989), pp.51-66.
- Lian, J., Shen, F., Jia, X., Ahn, D. C., Chae, D. C., Münstermann, S., and Bleck, W., An evolving non-associated Hill48 plasticity model accounting for anisotropic hardening and r-value evolution and its application to forming limit prediction, International Journal of Solids and Structures, Vol.151 (2018), pp.20-44.
- Mao Y. B, Kong X. H., Li X. X., Yang L., Wang N., and Qin S. J., Deep drawing of square cup with segment-blank-holder technique, Journal of Netshape Forming Engineering (in Chinese), Vol.10, No.06 (2018), pp.57-64.
- Qin, S. J., Gai, B. B., Kong, X. H., and Deng, C., Analytical solutions of strain of axisymmetric curved part in sheet metal forming process using direct integral method, International Journal of Mechanical Sciences, Vol.101 (2015), pp.49-58.
- Schuler, G., Metal forming handbook (1998), p.162-165, Springer Science and Business Media, Berlin.
- Siegert, K., Wagner, S., and Ziegler, M., Closed loop control of the friction force. International Congress Exposition, Detroit, (1996) 960824
- Siegert, K., Ziegler, M., and Wagner, S., Closed loop control of the friction force. Deep drawing process, Journal of materials processing technology, Vol.71, No.1 (1997), pp.126-133.
- Srirat J., Kitayama, S., and Yamazaki, K., Optimization of Initial Blank Shape with a Variable Blank Holder Force in Deep-Drawing via Sequential Approximate Optimization, Journal of Advanced Mechanical Design Systems & Manufacturing, Vol.6, No.7 (2012a), pp.1093-1106.
- Srirat, J., Yamazaki, K., and Kitayama, S., Optimization of Segmented Blank Holder Shape and Its Variable Blank Holder Gap in Deep-Drawing Process, Journal of Advanced Mechanical Design, Systems, and Manufacturing, Vol.6, No.4 (2012b), pp.420-431.
- Sung, J. H., Kim, J. H., and Wagoner, R. H., A plastic constitutive equation incorporating strain, strain-rate, and temperature, International Journal of Plasticity, Vol.26, No.12 (2010), pp.1746-1771.
- Tian, S. X., Feng, Y. X., and Gao, Y. C., Design and application of a novel cone-shaped blank holder for precision stamping process, Procedia CIRP, Vol.27 (2015), pp.309-312.
- Wang, J., Goel, A., Yang, F., and Gau, J.T., Blank optimization for sheet metal forming using multi-step finite element simulations, The International Journal of Advanced Manufacturing Technology, Vol.40, No.7-8 (2009), pp.709-720.
- Yoon, J. W., Barlat, F., Dick, R. E., and Karabin, M. E., Prediction of six or eight ears in a drawn cup based on a new anisotropic yield function, International Journal of Plasticity, Vol.22, No.1 (2006), pp.174-193.
- Yoon, J. W., Dick, R. E., and Barlat, F., A new analytical theory for earing generated from anisotropic plasticity, International Journal of Plasticity, Vol.27, No.8 (2011), pp.1165-1184.
- Zang, S. L., Lee, M. G., Sun, L., Kim, J. H., Measurement of the Bauschinger behavior of sheet metals by three-point bending springback test with pre-strained strips, International Journal of Plasticity, Vol.59, (2014), pp.84-107.