Original

Micro- and Nanostructural Characteristics of Rat Masseter Muscle Enteses

Keitaro Arakawa^{1,2)}, Satoru Matsunaga^{2,3)}, Kunihiro Nojima^{1,2)}, Takayoshi Nakano⁴⁾,
Shinichi Abe³⁾, Masao Yoshinari²⁾ and Kenji Sueishi^{1,2)}

¹⁾ Department of Orthodontics, Tokyo Dental College, Tokyo, Japan

²⁾ Oral Health Science Center, Tokyo Dental College, Tokyo, Japan

³⁾ Department of Anatomy, Tokyo Dental College, Tokyo, Japan

⁴⁾ Division of Materials & Manufacturing Science, Graduate School of Engineering, Osaka University, Osaka, Japan

(Accepted for publication, September 28, 2019)

Abstract: The enteses of the masticatory muscles differ slightly from those of the trunk and limb muscles. However, the bones of the skull are subject to various functional pressures, including masticatory force, resulting in a complex relationship between bone structure and muscle function that remains to be fully elucidated. The present study aimed to clarify aspects of masseter muscle-tendon-bone morphological characteristics and local load environment through quantitative analysis of biological apatite (BAP) crystallite alignment and collagen fiber orientation together with histological examination of the enteses. Result of histological observation, the present findings show that, in the enteses of the masseter muscle in the first molar region, tendon attaches to bone via unmineralized fibrocartilage, while some tendon collagen fibers insert directly into the bone, running parallel to the muscle fibers. Furthermore, BAP crystallites in the same region show uniaxial preferential alignment at an angle that matches the insertion angle of the tendon fibers. Conversely, in the enteses of the masseter muscle in the third molar region, the tendon attaches to the bone via a layer of thickened periosteum and chondrocytes. As in the first molar region, the results of bone quality analysis in the third molar region showed BAP crystallite alignment parallel to the orientation of the tendon fibers. This indicates that the local mechanical environment generates differences in entesis morphology. The present study showed a greater degree of uniaxial BAP crystallite alignment in enteses with direct insertion rather than indirect tendon-bone attachment and the direction of alignment was parallel to the orientation of tendon fibers. These findings suggest that functional pressure from the masseter muscle greatly affects bone quality as well as the morphological characteristics of the entesis, specifically causing micro- and nanostructural anisotropy in the direction of resistance to the applied pressure.

Key words: Collagen fiber, Biological apatite (BAP) crystallite, Bone quality, Microbeam X-ray diffraction, SHG imaging, Enteses

Introduction

The tendons of the trunk and limb muscles attach to bones via enteses¹⁻³⁾. These attachment sites are broadly categorized as either fibrous enteses, composed of perforating mineralized collagen fibers, or fibrocartilaginous enteses, comprising a multitissue interface involving the following four tissues of tendon, unmineralized fibrocartilage, mineralized fibrocartilage, and bone⁴⁾. The composition, structure, and mechanical properties of these multitissue interfaces vary widely, creating spatial gradients that mediate load transfer between soft and hard tissues and minimize stress concentration⁵⁾. Muscle loading is extremely important for healthy entesis formation and suppression of muscle function greatly diminishes the biomechanical performance of the entesis⁶⁾.

Histological examination by Hems et al. revealed that the enteses of the masticatory muscles differ slightly from those of the trunk and limb muscles⁷⁾. Specifically, the masticatory muscles contain three types of entesis, including sites of direct tendon insertion into the bone. The authors concluded that these different types contribute to the unique bio-

mechanical function of the masticatory muscles, enabling them to work as an “angle and stretching brake”. However, the bones of the skull are subject to various functional pressures, including masticatory force, resulting in a complex relationship between bone structure and muscle function that remains to be fully elucidated. Clarification of the relationships between the micro- and nanostructural characteristics of the muscles, tendons, and bones in the maxillofacial area and the mechanical environment is required^{8,9)}.

The relevance of bone quality in addition to bone density with regard to bone strength was proposed National Institutes of Health Consensus Development Conference in 2000. Since then, studies on the relationship between bone structural characteristics and bone strength have focused on bone quality factors¹⁰⁾. Collagen fibers and biological apatite (BAP) crystallites have been identified as dominant bone quality factors that are resistant to tensile and compressive stress, respectively, on bone tissue^{11,12)}.

Biological apatite is a hexagonal, ionic crystal that has a highly anisotropic nanostructure with preferential alignment along the c axis in the loading direction¹³⁾. Using microbeam X-ray diffraction analysis, Nakano et al. quantitatively analyzed BAP crystallite alignment in animal trunk and limb bones, demonstrating a high correlation between

Correspondence to: Dr. Satoru Matsunaga, Department of Anatomy, Tokyo Dental College, 2-9-18 Kamamisaki-cho, Chiyoda-ku, Tokyo 101-0061, Japan; Tel: +81-3-6380-9592; Fax: +81-3-6380-9664; E-mail: matsuna@tdc.ac.jp

Figure 1. Reference points, plane and axes: point a; the lowest point in anterior thickening area of mandible. Point p; the lowest point in posterior thickening area of mandible; Mandibular plane passing through a-a' and p-p' lines; X-axis passing through the mid-point of a-a' and p-p'; Y-axis the vertical axis against the mandibular plane; Z-axis the vertical axis against the X-Y plane.

mechanical stress and BAp crystallite alignment^{14,15}. With regard to collagen fibers as a bone quality factor, ongoing research by Vashishth et al. has shown that collagen crosslinks are a factor in age-related reductions in bone quality¹⁶.

Meanwhile, Kawagoe et al. reported a relationship between bone strength and orientational anisotropy of collagen fibers for the masticatory muscles¹⁷. Quantitative analysis of the jaw bone, particularly at entheses, should enable accurate prediction of the effects of the masseter muscles on the load environment of the mandible.

The present study aimed to clarify aspects of masseter muscle-tendon-bone morphological characteristics and local load environment through quantitative analysis of BAp crystallite alignment and collagen fiber orientation together with histological examination of the entheses.

Materials and Methods

Specimens

The present study was approved by the Ethics Committee of Tokyo Dental College (Ethics Application No. 282807). Samples were prepared from the skulls of five 24-week-old male Wistar rats euthanized after deep anesthesia with ethyl ether.

Tissue slice preparation

To obtain suitable samples for bone quality analysis, the left skull was embedded in autopolymerizing acrylic resin and sagittally sectioned using a saw microtome (SP1600; Leica Microsystems Inc., Wetzlar, Germany) with a blade width of 300 μm . Samples were then sanded using wet/dry sandpaper of increasing grit (400, 800, and 1,200) to prepare thin, 200 μm slices. The right skull was fixed in 4% paraformaldehyde phosphate buffer solution and demineralized in 10% ethylenediamine-tetraacetic acid (EDTA) for 4 weeks. Using standard methods, samples were embedded in paraffin embedding and sliced about 5 μm thick in the coronal plane to enable observation of the masseter muscle entheses. Masson's trichrome staining were performed to observe the structural morphology of masseter muscle entheses in the first and third molar regions. And Toluidine blue staining were used to make the acidic mucus polysaccharide present in the cartilage metachromatic.

Second harmonic generation (SHG) imaging

SHG images were acquired using a multiphoton confocal microscop-

Figure 2. Regions of interest in the mandible comprised masseter muscle entheses. The cortical bone of each red circle was selected in first molar region (A) and third molar region (B) and measurements were performed. Left; Lingual side. Right; Buccal side.

py system (A1R+MP, Nikon Instech Co., Ltd., Tokyo, Japan) with an excitation laser (Mai Tai eHP, wavelengths: 690-1,040 nm; repetition rate: 80 MHz; pulse width: 70 fs; Spectra-Physics, CA, US) and a water-immersion objective lens (CFI75 Apo 25 $\times$ W MP, numerical aperture: 1.1; Nikon Instech Co., Ltd., Tokyo, Japan). The excitation wavelength for the observation of collagen fibers was 880 nm. Image acquisition, processing for orthogonal views and cropping were performed using NIS-Elements version 4.0 (Nikon Instech Co., Ltd., Tokyo, Japan). Brightness and contrast of some images were adjusted using look-up tables (LUTs) of this software by the same parameters among relevant images to facilitate visibility.

Figure 3. Masson's trichrome and toluidine blue staining of masseter muscle entheses in the first molar region. (A) Whole image of the craniofacial area in coronal section. Masson's trichrome staining; magnification: $\times 25$. (B, D) The periosteum was fragmented and aggregation of chondrocytes was observed at the tendon-bone interface in the enthesis. The tendon was attached to the periosteum without rupturing. (B: Masson's trichrome staining. D: toluidine blue staining. magnification: $\times 100$) (C, E) Thickened chondrocytes (dotted line circle) were observed on the bone surface in the enthesis (C: Masson's trichrome staining. E: toluidine blue staining. Magnification: $\times 200$) MA: masseter muscle. T: tongue. 1st Molar: first molar region.

Figure 4. Masson's trichrome and toluidine blue staining of masseter muscle entheses in the third molar region. (A) Muscle fibers could be seen covering the area from the lateral aspect to the base of the mandible, while thin tendons ran toward the cortical bone protuberance on the buccal side of the mandibular body. Masson's trichrome staining; magnification: $\times 25$. (B, D) The tendon of the masseter muscle was attached to the periosteum without rupturing. (B: Masson's trichrome staining. D: toluidine blue staining. Magnification: $\times 100$). (C, E) The tendon thickened chondrocytes were observed on the bone surface in the enthesis. (C: Masson's trichrome staining. E: toluidine blue staining. Magnification: $\times 200$). MA: masseter muscle. T: tongue. 3rd Molar: third molar region.

Figure 5. Coronal section in first molar region. (A) Hematoxylin and eosin staining. (B) Second harmonic generation imaging. The masseter muscle tendon in the first molar region comprised thick collagen fibers extending through the enthesis, some of which penetrated the cortical bone.

Figure 6. Coronal section in third molar region. (A) Hematoxylin and eosin staining. (B) Second harmonic generation imaging. In the vicinity of the enthesis, many collagen fibers inside the bone were observed running parallel to the orientation of the tendon.

Figure 7. Orientation of tendon fibers in relation to bone. (A) First molar region. (B) Third molar region. In the first and third molar regions, tendon fibers ran tangentially to the bone at 31.1° [standard deviation (SD), 4.6°] and 40.4° [SD, 3.5°], respectively.

Micro-computed tomography (micro-CT) imaging

Samples were examined using micro-computed tomography (micro-CT; HMX225 Actis4; Tesco Co., Tokyo, Japan) under the following imaging conditions: tube voltage, 140 kV; tube current, 100 μ A; matrix size, 512 $\times$ 512; magnification, $\times$ 2.5; slice width, 50 μ m; and slice pitch, 50 μ m. Three-dimensional reconstruction was performed using TRI/3D-BON software (RATOC System Engineering Co., Ltd., Tokyo, Japan).

BAP crystallite alignment

Quantitative analysis of BAP crystallite alignment was conducted using an optical curved imaging plate (IP) X-ray diffraction system (XRD; D/MAX RAPID2-CMF; Rigaku Co., Tokyo, Japan). Measurements were performed in reflection and transmission modes with Cu-K α as the radiation source at a tube voltage of 40 kV and tube current of 30 mA. Reference axes were established in X axis, Y axis, and Z axis for each sample (Fig. 1)^{18,19}. Regions of interest in the mandible comprised masseter muscle entheses (Fig. 2). The radiation site was determined using the light microscope of the XRD system (magnification, $\times$ 0.6–4.8), then an incident beam (diameter, 50 μ m) was applied. Using reflection mode in the X-axis direction and transmission mode in the Y-axis and Z-axis directions, the diffracted X-ray beam was detected using a curved IP based on the conditions described by Nakano *et al.*²⁰. The diffracted X-ray beam was detected as a diffraction ring on the IP. Using 2-dimensional data-processing software (Rigaku Co., Tokyo, Japan), X-ray diffraction intensity ratios were calculated for the two diffraction peaks corresponding to planes 002 and 310.

Statistical analysis

Mean values for the five samples for each measurement point were calculated and compared using Tukey's multiple comparison test. Significance was set at $P < 0.05$.

Results

Histological observation of entheses

The results of Masson's trichrome staining and toluidine blue staining are showed of a coronal section in the first molar region of 24-week-old Wistar rat skulls (Fig. 3). Thick masseter muscle tendons with fibers largely grouped into bundles could be seen directly integrating into the buccal cortical bone. In the enthesis, the periosteum was fragmented and aggregation of chondrocytes was observed at the tendon-bone interface (Fig. 3B–E). The results of Masson's trichrome staining and toluidine blue staining are showed of a coronal section in the third molar region of 24-week-old Wistar rat skulls (Fig. 4).

In the masseter muscle enthesis, muscle fibers could be seen covering the area from the lateral aspect to the base of the mandible, while thin tendons ran toward the cortical bone protuberance on the buccal side of the mandibular body (Fig. 4A). The tendon was attached to the periosteum without rupturing (Fig. 4B, D) and thickened chondrocytes were observed on the bone surface in the enthesis (Fig. 4C, E).

Orientalional anisotropy of collagen fibers

SHG images from the first molar region are showed in Fig. 5. The masseter muscle tendon in the first molar region comprised thick collagen fibers extending through the enthesis, some of which penetrated the cortical bone. As in the first molar region, collagen fibers in the third molar region ran toward the bone. However, these fibers were interrupted at the thickened periosteum. In the vicinity of the enthesis, many collagen fibers inside the bone were observed running parallel to the orientation of the tendon (Fig. 6). In the first and third molar regions, tendon

Figure 8. BAP crystallite alignment in masseter muscle entheses. In both the first and third molar regions, strong uniaxial preferential alignment was noted in the Y axis direction in the masseter muscle entheses.

fibers ran tangentially to the bone at 31.1° [standard deviation (SD), 4.6°] and 40.4° [SD, 3.5°], respectively (Fig. 7).

BAP crystallite alignment

The angles of preferential alignment of BAP crystals are showed in an enthesis in relation to tooth axis in the first and third molar regions (28° [SD, 10.95°] and 36° [SD, 8.94°], respectively). X-ray diffraction intensity ratios calculated for the three reference axes for quantitative analysis are showed in Figure 8. The intensity ratios for hydroxyapatite powder were 1.4 and 5.6 in reflection and transmission modes, respectively. In both the first and third molar regions, strong uniaxial preferential alignment was noted in the Y-axis direction in the masseter muscle entheses. Furthermore, X-ray diffraction intensity ratios in the Y-axis direction were significantly higher in the first compared to the third molar region.

Discussion

According to Huang *et al.*, as the superior digital flexor tendon develops before and then joins with the subsequently formed digital bone, the related entheses penetrate the periosteum²¹. Conversely, the entheses of many of the muscles in the trunk and limbs do not involve the periosteum, suggesting that these attachments are already formed at the stage of periosteal development²². The present findings also show that, in the entheses of the masseter muscle in the first molar region, tendon attaches to bone via unmineralized fibrocartilage, while some tendon collagen fibers insert directly into the bone, running parallel to the muscle fibers. Furthermore, BAP crystallites in the same region show uniaxial preferential alignment at an angle that matches the insertion angle of the tendon fibers. This suggests that both the anisotropy of the collagen fibers and BAP crystallite alignment confer high resistance in the direction of the masseter muscle tendon. As the masseter muscle in the first molar region is directly attached to the bone via the tendon, these structural characteristics may optimize bone quality to enable the high load generated by muscle contraction to be efficiently transmitted from tendon to bone²³.

Conversely, in the entheses of the masseter muscle in the third molar region, the tendon attaches to the bone via a layer of thickened periosteum and chondrocytes. Muscles with entheses that indirectly attach to the bone via the periosteum do not produce large functional pressures;

rather, they are responsible for precise movements²⁴). As in the first molar region, the results of bone quality analysis in the third molar region showed BAp crystallite alignment parallel to the orientation of the tendon fibers. However, the intensity ratio values were significantly lower. This indicates that the local mechanical environment generates differences in enthesis morphology.

Matsumoto et al. analyzed bone quality in human jaw bones and found uniaxial preferential alignment of BAp crystallites and high bone strength in the tooth axis direction in specific alveolar bone²⁵). Meanwhile, Nakano et al. demonstrated a strong positive correlation between bone quality factors and bone strength, indicating that the mechanical environment of entheses determines the orientation of the collagen fibers, which is linked to the preferential alignment of BAp crystallites. Changing the amount and direction of functional pressure from the muscles may thus affect not only bone density, but also bone density.

Acknowledgements

This study was supported by a research grant from the Japan Society for the Promotion of Science; contract grant number: 18K09643, 17K11808 and was partly supported by a grant of Multidisciplinary Research Center for Jaw Disease (MRCJD): Achieving Longevity and Sustainability by Comprehensive Reconstruction of Oral and Maxillofacial Functions.

Conflict of Interest

The authors have no COI exists.

References

- Benjamin M, Evans EJ and Copp L. The histology of tendon attachments to bone in man. *J Anat* 149: 89-100, 1986
- Holger P and Martin S. Histological evidence for muscle insertion in extant amniote femora: implications for muscle reconstruction in fossils. *J Anat* 222: 419-436, 2013
- Evans E J, Benjamin M and Pemberton DJ. Variations in the amount of calcified tissue at the attachments of the quadriceps tendon and patellar ligament in man. *J Anat* 174: 145-151, 1991
- Apostolakis J, Durant TJ, Dwyer CR, Russell RP, Weinreb JH, Alae F, Beitzel K, McCarthy MB, Cote MP and Mazzocca AD. The enthesis: a review of the tendon-to-bone insertion. *Muscles Ligaments Tendons J* 4: 33-42, 2014
- Thomopoulos S, Williams GR, Gimbel JA, Favata M and Soslowsky LJ. Variations of biomechanical, structural, and compositional properties along the tendon to bone insertion site. *J Orthop Res* 1: 13-19, 2003
- Schwartz AG, Lipner JH, Pasteris JD, Genin GM and Thomopoulos S. Muscle loading is necessary for the formation of a functional tendon enthesis. *Bone* 55: 44-51, 2013
- Hems T and Tillmann B. Tendon entheses of the human masticatory muscles. *Anat Embryol (Berl)* 202: 201-208, 2000
- Yamada K. Histological study on the migration mechanism of the attachment of the deep layer of the masseter muscle to the rat mandible during growth. *Jpn J Oral Biol* 27: 254-271, 1985
- Doreen A and Carla A. Histologic study of the attachment of muscle to the rat mandible. *Arch Oral Biol* 27: 519-527, 1982
- NIH consensus development panel on osteoporosis prevention, diagnosis, and therapy. Osteoporosis prevention, diagnosis, and therapy. *JAMA* 285, 785-795, 2001
- Sasaki N and Sudoh Y. X-ray pole figure analysis of apatite crystals and collagen molecules in bone. *Calcif Tissue Int* 60: 361-367, 1997
- Wang J, Ishimoto T and Nakano T. Unloading-induced degradation of the anisotropic arrangement of collagen/apatite in rat femurs. *Calcif Tissue Int* 100: 87-94, 2017
- Elliot JC. Structure and Chemistry of the Apatites and Other Calcium Orthophosphates. Amsterdam: Elsevier Science; 1994
- Jimbo R, Nakano T and Sawase T. Alignment of biological apatite c-axis under functional loading: a preliminary report. *Implant Dent* 25: 594-598, 2016
- Nakano T, Kaibara K, Ishimoto T, Tabata Y and Umakoshi Y. Biological apatite (BAp) crystallographic orientation and texture as a new index for assessing the microstructure and function of bone regenerated by tissue engineering. *Bone* 51: 741-747, 2012
- Vashishth D. The role of the collagen matrix in skeletal fragility. *Curr Osteoporosis Rep* 5: 62-66, 2007
- Benjamin M, Kumai T, Milz S, Boszczyk BM, Boszczyk AA and Ralphs JR. The skeletal attachment of tendons--tendon "entheses". *Comp Biochem Physiol A Mol Integr Physiol* 133: 931-945, 2002
- Xiao F, Hayashi H, Fujita T, Shirakura M, Tsuka Y, Fujii E, Tanne K and Tanimoto K. Role of articular disc in cartilaginous growth of the mandible in rats. *APOC* 7: 29-34, 2017
- Fujita T, Ohtani J, Shigekawa M, Kawata T, Kaku M, Kohno S, Tsutsui K, Tenjo K, Motokawa M, Tohma Y and Tanne K. Effects of Sex Hormone Disturbances on Craniofacial Growth in Newborn Mice. *J Dent Res* 83: 250-254, 2004
- Nakano T, Kaibara K, Tabata Y, Nagata N, Enomoto S, Marukawa E and Umakoshi Y. Unique alignment and texture of biological apatite crystallites in typical calcified tissues analyzed by microbeam X-ray diffractometer system. *Bone* 31: 479-487, 2002
- Huang AH, Riordan TJ, Wang L, Eyal S, Zelzer E, Brigande JV and Schweitzer R. Repositioning forelimb superficialis muscles: tendon attachment and muscle activity enable active relocation of functional myofibers. *Dev Cell* 26: 544-551, 2013
- Berendsen AD and Olsen BR. Bone development. *Bone* 80: 14-18, 2015
- Apostolakis J, Durant TJ, Dwyer CR, Russell RP, Weinreb JH, Alae F, Beitzel K, McCarthy MB, Cote MP and Mazzocca AD. The enthesis: a review of the tendon-to-bone insertion. *Muscles Ligaments Tendons J* 4: 333-342, 2014
- Lu HH and Thomopoulos S. Functional attachment of soft tissues to bone: development, healing, and tissue engineering. *Annu Rev Biomed Eng* 15: 201-226, 2013
- Matsumoto T, Matsunaga S, Morioka T, Nakano T, Yoshinari M and Yajima Y. Relationship between preferential alignment of biological apatite and Young's modulus at first molar in human mandible cortical bone. *J Hard Tissue Biol* 22: 163-170, 2013