IMPROVEMENT OF NEEDLE BAR IN TEXTILE MACHINE BY HITTING PROCESS

Kontawat Chottikampon (Kyoto Institute of Technology, Kyoto, Japan)

Suchalinee Mathurosemontri (Kyoto Institute of Technology, Kyoto, Japan)

Porakoch Sirisuwan (Kyoto Institute of Technology, Kyoto, Japan)

Yuqiu Yang (Donghua University, Shanghai, China)

Noriaki Kuwahara (Kyoto Institute of Technology, Kyoto, Japan)

Hiroyuki Hamada (Kyoto Institute of Technology, Kyoto, Japan)

Abstract

In this research, a needle bar was studied to approach the techniques and manufactures of this product by learning via the expert. Although the fixed of the pins on the brass bar is the only one step to make a needle bar, the fixed method is so complicate. It requires the fineness and high skill from manufacturer. The soldering process was used for fixed pins and brass bar together. However, the effect of heat transfer from soldering process on brass bar revealed the curve of specimen. The hitting technique was used to modify the curve. This technique is very useful. The curved of needle bar was improved and became too straight.

Introduction

From an experience and skill more than 30 years, the man in who is the owner of this business became to the expert in the needle bar fabrication. This specific part is the important component of a linking machine. Function of needle bar is used for help a seaminess. The fabric has been set on the pins of needle bar that will guild a needle of a sewing machine. That is convenience for the seaminess. This specific part was produced by man-made technique. All manufactures of the needle bar were determined by his intellect. The main process of this product is the setting of the pins on the niches of needle bar. He has chosen the soldering process to fix pins and needle bar together. However, the brass bar has an effect on the heat transfer and became to bend that led to the zigzag of the pins. Therefore, the expert overcame this trouble by using the hitting technique. The hitting process was operated under his feeling. It can say that the manufactures of this product were controlled by an experience of the expert.

Soldering process

The main structure of this product is a brass bar,

which has a size of 4.5x92x0.2 cm. There are the small niches that were gouged on the bar for putting In this research, the needle bar number 7 was used to study. The meaning of “number 7” is the amount of pin that can put in the niche within 1 inch in range (7 pin/inch). Pins and brass bar was held on together by a solder process. The soldering process in shown in figure1.

Fig.1 : Flow chart of soldering process

Hitting process

In general the pins that were soldered on the brass bar should be straight in the roll. But the effect of heat transfer from soldering process has an influence on the expansion of brass bar that lead to occurring of curve at the bar and pin roll [2]. Thus, the expert modified this curve by using a hitting technique. The hitting positions are shown in figure 2. The needle bar was hit 6 rounds. After finished 1 round, the expert would measure the needle bar and start to hit again until the pin roll became to straight.

Round 1

Round 2

Round 3

Round 4

Round 5

Round 6

Fig. 2 : Hitting position and the gap length before and after hitting

Effect of hitting process on gap length between pins

Gap length between pins was measured at 2 parts including base and tip of pins. As mentioned before, needle bar was hit with the different frequency of each round. That has an effect on gap length of pins. For the based position, the results reveal both of decreasing and increasing of gap length. The most values lean to the decreasing side. There is only round 3 that shows the decreasing of gap length at all hitting position as shown in figure 3.

Fig. 3 : The distance of gap length at based positions

For the measuring at tip point, it was found that the hitting led to the decreasing of gap length. At the hitting points, they show the high decreasing of gap length at the middle positions of needle bar. For example, at round 2, the decreasing of gap length at the first hitting position is around 2.7% and increases to 6.3 and 6.7 % at position 6 and 7, respectively. Whereas at the final

position the decreasing of gap length drops to 2.8%. However, at round 3-5 reveal the increasing of the tendencies as show in figure 4.

Fig. 4 : The distance of gap length at tip positions

Effect of hitting process on needle bar curved

Needle bar was modified the curved problem by hitting technique. The gap under the curve of needle bar was measured before and after the hitting process as show in figure 5

Fig.5 : Gap length under the needle bar curve

Conclusion

-Soldering process : The effect of heat transfer during the soldering process led to the curved of needle bar that affect the alignment of pins. The needle bar could not be usable if the pins did not align as a straight line. Thus, the expert improved the curve of needle bar by hitting process.

-Hitting process : Needle bar was hit at the several positions for modification the curve of needle bar. The effect of the hitting process cause of the decreasing of gap length at tip positions of pins. Whereas at based positions sparsely exhibited the increasing of gap length. However, the area under the curve obviously decreased even there still revealed a small gap.

References

W. J. Tomlinson, I. Collier, The mechanical properties and microstructures of copper and brass joint soldered with eutectic tin-bismuth solder. Journal of Materials, 22(5), 1835-39 (1987).

[2]Concise metals engineering data book, 1997, "ASM International", pp. 87-93.