Structure and Some Physical Properties of In_2O_3 Films Deposited on In_2O_3 SubstratesShigetoshi Muranaka^{☆1} and Toshihiko Shigematsu^{☆2}^{☆1}Faculty of Integrated Human Studies, Kyoto University, Kyoto 606. ^{☆2}Faculty of Science, Konan University, 8-9-1 Okamoto Higashinada-ku, Kobe 658.

Received October 8, 1997

SYNOPSIS

Indium oxide films were reactively deposited on the indium oxide substrates at 25~100°C. The influence of the substrate on the film structure and the physical properties was studied. The structure of the films was greatly dependent of the freshness of the substrate surface. Crystallized films could be deposited even at room temperature on the fresh substrates. On the air-exposed substrates, films were amorphous at room temperature, and partially crystallized at the higher substrate temperatures. The influence of the substrate on the electrical resistivity and optical transmission of the films was described. The effect of the heat-treatment of the air-exposed substrates on the film structure was also studied. Further, the contamination of the substrate surface was investigated by X-ray photoelectron spectroscopy. The results suggested that the surface of the substrates was refreshed by heating in vacuum at and above 300°C.

KEY WORDS

 In_2O_3 films, In_2O_3 substrates, reactive deposition, optical and electrical properties

1 Introduction

Extensive studies have been made to prepare indium oxide films because of application of transparent conductive electrodes. The films can be deposited by reactive evaporation. The structure of the films and the physical properties are greatly dependent of the deposition conditions and kinds of substrates. When glass substrates were used, amorphous or quasi-amorphous films were deposited at the substrate temperatures below 150°C, and films were crystallized at and above 150°C¹⁻⁵⁾. However, on CeO_2 substrates⁶⁾ and crystallite-nucleated substrates⁷⁾, the crystallization temperature of the films could be lowered to 60 and 100°C, respectively. The crystallinity of the films was also improved to some degree on CaO substrates at 100°C⁸⁾. The crystallized films displayed excellent light transparency and high electrical conductance, whereas amorphous films were opaque and had lower electrical conductance. We further studied the influence of In_2O_3 substrates on the structure of the films and the physical properties. The films were deposited on the fresh and the air-exposed substrates maintained between room temperature and 100°C. The results for the films deposited at room temperature have been briefly reported⁹⁾. The effect of heat-treatment of the air-exposed substrates on the film structure was also studied. Such studies are important to obtain the

clue to prepare the high quality films on the heat-sensitive materials at the low substrate temperatures.

2 Experimental Procedure

Films were deposited in a conventional high-vacuum chamber evacuated with an oil diffusion pump. Indium (purity: 99.999%) was evaporated from an alumina crucible by resistive-heating. The substrates were placed about 20cm from the evaporation source. In_2O_3 layers used as the substrates were reactively deposited on quartz glass heated to about 200°C. The thickness of the sublayer was about 100Å. The sublayers of this thickness were continuous taking a crystallized grain-like structure²⁾. The films were deposited on the fresh substrates and the substrates which were exposed to air for 30min. For deposition on the fresh substrates, the films were formed subsequently after the sublayers were prepared, without breaking the vacuum of the chamber. The deposition conditions of the films were as follows: oxygen pressure, 0.28Pa; substrate temperature, 25~100°C; deposition rate, 1Å/s; film thickness, 2000Å. For film deposition at room temperature, the substrates were kept below 30°C by water cooling. The structure of the films was studied by X-ray diffraction using $\text{CuK}\alpha$ radiation. The electrical resistivity of the films was measured by a four-point probe method. The optical transmission measurements

were made using a double-beam spectrophotometer. The contamination of the substrate surface was studied by X-ray photoelectron spectroscopy (XPS). The XPS spectra were taken with $\text{MgK}\alpha$ X-rays at the pressure below 10^{-7} Pa.

3 Results and Discussion

3.1 Films deposited on fresh substrates

Figure 1 shows the X-ray diffraction pattern for the films deposited at room temperature. The diffraction patterns of the films consisted of the well-defined In_2O_3 lines, indicating the crystallized films. Quite similar results were obtained for the films deposited at 60 and 100°C. Thus, the films were crystallized on the fresh substrates regardless of the substrate temperature. To authors' knowledge, this is the first time to prepare the crystallized films at room temperature without using ionized particles in the deposition process. The result for the films deposited at 25°C was well agreed with that for the films previously reported⁹⁾.

Figure 2 shows the optical transmission spectra for the films deposited at 25~100°C. The films deposited at 100°C were highly transparent with an average transmittance of above 80% in the visible light range. The transmittance of the films was decreased with decreasing substrate temperature, although the films were crystallized as well. The decrease in the transmittance will be due to incomplete oxidation of the films or excess In over stoichiometry (In_2O_3). The films will be less oxidized at lower substrate temperatures. Such a deviation from stoichiometry has also been observed for amorphous films deposited at room temperature²⁾. The results suggested that at room temperature, more transparent films will be deposited at higher oxygen pressures or at lower deposition rates. This is because the degree of film oxidation generally increases in the ratio of O_2 molecules to In atoms impinging onto the substrate.

The electrical resistivities for the films deposited at 25, 60 and 100°C were apparently 2.6×10^{-3} , 2.7×10^{-3} and $3.0 \times 10^{-3} \Omega\text{cm}$, respectively. Since the underlayers (the resistance, about $2\text{k}\Omega/\square$) also contributed to the electrical conductance, the actual resistivities of the films were slightly higher. However, the results suggested that the films were very conductive because of the crystallization of the films. The resistivity of the films was less sensitive to the substrate temperature compared to the optical transmission.

3.2 Films deposited on air-exposed substrates

Figure 3 shows the X-ray diffraction patterns for the films deposited at 25~100°C on the air-exposed substrates. The

Fig.1 X-ray diffraction pattern for films deposited at room temperature on fresh substrates.

Fig.2 Optical transmission spectra for films deposited on fresh substrates at different substrate temperatures: a, 25°C; b, 60°C; c, 100°C.

Fig.3 X-ray diffraction patterns for films deposited on air-exposed substrates at different substrate temperatures: a, 25°C; b, 60°C; c, 100°C.

diffraction patterns of the films deposited at room temperature indicated amorphous structure. The very weak (222) line contained in the diffraction patterns was ascribed mainly to the underlayers and possibly to trace of the crystallized part in the films. The result was well agreed with that for the films previously reported⁹⁾. The disordered structure of the films was again ascribed to contamination of the substrate surface with water molecules. The diffraction patterns of the films deposited at 60 and 100°C included the diffraction lines of In_2O_3 . The diffraction lines were stronger for the films deposited at the higher substrate temperature. However, the intensities of the diffraction lines were still reduced to below one third compared to those of the diffraction lines for the perfectly crystallized films. The results suggested that the films contained the amorphous phase in addition to the crystallized phase, and the fraction of the crystallized part in the films was increased at the higher substrate temperature. The deterioration of the film crystallinity on the air-exposed substrate was similarly ascribed to contamination of the substrate surface with H_2O .

Figure 4 shows the optical transmission spectra for the films deposited at 25~100°C. The transmittance was much reduced for the amorphous films deposited at room temperature. With partial crystallization of the films at the higher substrate temperatures, the transmittance of the films was increased. However, the average transmittance of the films was still lower by about 10% than that of the perfectly crystallized films deposited at 100°C. The decrease in the transmittance is due to the amorphous phase contained in the films.

The apparent resistance measured for the films deposited at 25°C was about $1.8\text{k}\Omega/\square$. However, the electrical conductance was dominantly due to the underlayers. The

Fig.4 Optical transmission spectra for films deposited on air-exposed substrates at different substrate temperatures: a, 25°C; b, 60°C; c, 100°C.

resistance of the films alone will be much higher because of the amorphous structure. The resistivities of the films deposited at 60 and 100°C were apparently about 4.2×10^{-3} and $2.8 \times 10^{-3} \Omega\text{cm}$, respectively. The values were decreased at the higher substrate temperatures on account of the partial crystallization of the film.

Figure 5 shows the X-ray diffraction patterns of the films deposited on the heat-treated substrates. Before deposition of the films, the air-exposed substrates were heated in vacuum for 30min. at temperatures between 100 and 400°C. The vacuum pressure was below $7 \times 10^{-4}\text{Pa}$. As indicated by the diffraction patterns, the films were perfectly crystallized on the substrates which were pre-heated at and above 300°C, whereas the films were still amorphous on the substrates pre-heated at and below 200°C. The films deposited on the substrates pre-heated at 250°C were only slightly crystallized. The results suggested that the surface of the air-exposed substrates was refreshed by heat treatment at and above 300°C in vacuum, that is, H_2O molecules were desorbed from the substrate.

The contamination of the substrate surface was studied by XPS. The substrates were heated in vacuum at 180, 260, 300 and 340°C. For the standard material, sputter-etched substrates about 800Å thick were also used. The sputter-etching of the substrates was made with Ar^+ ions of

Fig.5 X-ray diffraction patterns for films deposited at 25°C on heat-treated substrates. Before deposition of films, air-exposed substrates were heated in vacuum at various temperatures: a, 200°C; b, 250°C; c, 300°C.

about 0.9keV. This ion treatment gave the fresh surface for the substrates because more harsh sputter-etching of the substrates with Ar^+ ions of about 2.5keV did not alter the XPS spectra. Figure 6 shows the O1s spectra for the air-exposed substrates, the substrates heated at 180 and 300°C and the sputter-etched substrates. In3d spectra were insensitive to the surface contamination of the substrates.

Fig.6 O1s XPS spectra of substrates: a, air-exposed; b, heated at 180°C; c, heated at 300°C; d, sputter-etched.

The observed O1s spectra were asymmetric at the higher energy side. The spectra could be resolved into two Gaussian peaks. The peaks at the lower and the higher energies were denoted as O1s (I) and O1s (II), respectively. Table 1 shows the binding energies of the O1s (I) and O1s (II) peaks and their intensity ratios. The O1s (I) peak is a signal from In-O bonds. The value of the binding energy (529.9eV) was well agreed with that reported for In_2O_3 ^{10,11}. The O1s (II) peak was partially ascribed to H_2O or OH^- adsorbed on the substrate surface. The binding energy of the peak (531.9eV) corresponds to the value reported for the adsorbed H_2O or OH^- ¹⁰⁻¹². With an increase in heat-treated temperature upto about 300°C, the intensity of the O1s (II) peak was decreased to the level for the O1s (II) peak of the sputter-etched substrates. The results suggested that the water molecules adsorbed on the substrate surface were removed at and above 300°C. However, the origin of the O1s (II) peak which was still remained above 300°C is unexplainable at the present stage. It may arise from the oxygen concerning structural defects such as vacancies in In_2O_3 .

4 Summary

The influence of In_2O_3 substrates on the film structure and the physical properties was investigated. The films were crystallized on the fresh substrates regardless of the substrate temperature. On the air-exposed substrates, amorphous films were deposited at room temperature, and the films were partially crystallized at the higher substrate temperatures. The crystallized films deposited at 100°C on the fresh substrates displayed high electrical conductance and excellent light transparency. The light transmittance of the crystallized films was reduced at the lower substrate temperatures because of insufficient oxidation of the films. The amorphous films deposited on the air-exposed substrates at room temperature were opaque and have higher electrical conductance. With partial improvement of the film crystallinity, the transparency of the films was increased, and the electrical resistance was reduced. The effect of the heat treatment of the air-exposed substrates on the film structure was also investigated. The results suggested that the surface of the air-exposed substrates was refreshed by heat treatment in vacuum at and above 300°C. This was confirmed by the XPS analyses for the substrate surface.

References

- 1) I.Hamberg and C.G.Granqvist: J. Appl. Phys., 60

Table 1 Binding energies of O1s (I) and O1s (II) peaks and their intensity ratios for substrates heated at various temperatures and for sputter-etched substrate.

Substrate	Heating temp. (°C)	Binding energy(eV)		Intensity ratio O1s(II)/O1s(I) (%)
		O1s(I)	O1s(II)	
Heat-treated	unheated	529.9	531.9	43
	180	529.9	531.9	31
	240	529.9	531.7	23
	300	529.9	531.6	17
	340	529.9	531.6	18
Sputter-etched		529.9	531.6	17

- (1986)R.123.
- 2) S.Muranaka, Y.Bando and T.Takada: Thin Solid Films, 151(1987)355.
 - 3) T.Nagatomo, Y.Murata and O.Omoto: Thin Solid Films, 192(1990)17.
 - 4) S.Muranaka and N.Yamamoto: J. Jpn. Soc. Powder and Powder Met., 40(1993)718.
 - 5) S.Muranaka, H.Hirooka and Y.Bando: J. Mater. Chem., 3(1993)237.
 - 6) S.Muranaka and S.Matsuda: J. Jpn. Soc. Powder and Powder Met., 42(1995)532.
 - 7) S.Muranaka: Thin Solid Films, 221(1991)1.
 - 8) S.Muranaka: J. Jpn. Soc. Powder and Powder Met., 43(1996)134.
 - 9) S.Muranaka: J. Jpn. Soc. Powder and Powder Met., 43(1996)930.
 - 10) B.R.Natarajan, A.H.Eltoukhy, J.E.Greene and T.L.Barr: Thin Solid Films, 69(1980)217.
 - 11) T.L.Barr and Y.L.Liu: J. Phys. Chem. Solids, 50(1989) 657.
 - 12) S.J. Kerber, J.J.Bruckner, K.Wozniak, S.Seal, S. Hardcastle and T.L.Barr: J. Vac. Sci. Technol., A14(1996)1334.