Stabilized Wüstite Formed from Zn(II)- and Mn(II)-Wüstite below 575°C

T. SANO, Y. HOSOKAWA, H. AMANO, M. TSUJI, AND Y. TAMAURA

Research Center for Carbon Recycling & Utilization, Tokyo Institute of Technology,
Ookayama, Meguro-ku, Tokyo 152, Japan

Abstract— The transformation of the Zn(II)- and Mn(II)-wüstite into spinel-type compound was studied to investigate the effect of foreign cations (Zn(II), Mn(II) ions) on FeO-wüstite disproportionation into α -Fe and Fe_3O_4 below 575°C. In these transformation reactions, the Fe(III) ions in the Zn(II)- and Mn(II)-wüstites ($\text{Zn}^{2+}_x\text{Fe}^{2+}_y\text{Fe}^{3+}_z\text{O}$, $\text{Mn}^{2+}_x\text{Fe}^{2+}_y\text{Fe}^{3+}_z\text{O}$; $x+y+z<1$) form the spinel type structure in Ar gas at 500°C (Zn(II)-wüstite) and 450°C (Mn(II)-wüstite), but no α -Fe phase appeared, indicating that the presence of those foreign cations in the FeO-wüstite interferes with the disproportionation into α -Fe and Fe_3O_4 . No manganese oxides were formed from Mn(II)-wüstite at 450°C, while the ZnO was formed from the Zn(II)-wüstite. This difference came from the fact that the Mn(II) ion does not have a site preference and Zn(II) ion has a tetrahedral site preference.

I. INTRODUCTION

FeO-wüstite is a nonstoichiometric compound with NaCl-type structure and is decomposed into magnetite (Fe_3O_4 , spinel-type structure) and α -Fe by disproportionation at the temperatures below 575°C [1,2]. Replacement of the Fe(II) ions in the FeO-wüstite with foreign cations will cause a change in the crystal parameters. This change will bring about a different reaction from the disproportionation of the FeO-wüstite into α -Fe and Fe_3O_4 . However, effect of replacement with foreign cations on the disproportionation reaction is not well-understood as well as on its relationship with crystal parameters of the FeO-wüstite.

The purpose of the present paper is to clarify the effect of foreign metal ions (Zn(II), Mn(II)) on the disproportionation of the wüstites, and to understand the relationship of its replacement with the crystal parameters.

II. EXPERIMENTAL

Zn(II) ferrite was synthesized by air oxidation of the Fe(II)/Zn(II) mixed hydroxide suspension according to the previous reports (wet oxidation process) [3]. Zn(II)-wüstite was prepared by H_2 -reduction of the Zn(II) ferrite at 300°C for 4h.

Mn(II)-wüstite was synthesized by reducing the mixture of magnetite and MnO_2 with mole ratio of Mn:Fe=1:1 in a CO_2/H_2 mixed gas stream ($\text{CO}_2:\text{H}_2=2:1$ at room temperature) at 800°C for 3h. The synthesized Mn(II)-wüstite was quenched by moving the reactor into ice-water. The solid phase was identified by X-ray diffractometry (XRD) with $\text{FeK}\alpha$ radiation. The mole ratio of Fe^{2+} and Fe^{3+} in the product was determined by colorimetry using 2,2'-bipyridyl.

The samples were allowed to stand in an Ar gas stream at 500°C (Zn(II)-wüstite) or 450°C (Mn(II)-wüstite) in the tubular quartz reaction cell for 1-5h. After the heat-treatment, the sample was quenched by moving the reaction cell into a refrigerant of ice-water and stored

in a nitrogen atmosphere.

III. RESULTS AND DISCUSSION

A. Characterization of Zn(II)- and Mn(II)-Wüstite

In the XRD spectrum of the Zn(II)-wüstite synthesized by reducing the Zn(II) ferrite in a H_2 gas atmosphere at 300°C for 4h (Fig. 1(a)), the peaks of NaCl-type structure appeared along with the weak peaks of wurtzite structure (ZnO). No peaks of the spinel-type structure appeared in the spectrum. These results indicate that most of the Zn(II) ions in the Zn(II) ferrite formed the Zn(II)-wüstite. The lattice constant of the Zn(II)-wüstite was 0.4299 nm, which is larger than that of the FeO-wüstite ($\text{Fe}_{0.89}\text{O}$; $a_0=0.4292$ nm). The chemical composition of the Zn(II)-wüstite was determined to be $\text{Zn}^{2+}_{0.29}\text{Fe}^{2+}_{0.38}\text{Fe}^{3+}_{0.22}\text{O}$, indicating the cation deficiency and the Fe(III) content.

In the XRD patterns of the Mn(II)-wüstite, only the peaks of NaCl-type structure of the Mn(II)-wüstite appeared. The lattice constant, a_0 , was 0.4367 nm and the chemical composition was $(\text{Mn}_{0.50}\text{Fe}_{0.50})_{0.962}\text{O}$. The imbalance in the number of cation and anion due to the cation deficiency indicates that the Fe(II) ions were replaced with Fe(III) ions and that spinel-type cluster were formed in the Mn(II)-wüstite phase.

B. Effect of Zn(II) Ion on Disproportionation of FeO-Wüstite

In the XRD pattern of the solid products obtained by heating the Zn(II)-wüstite at 500°C in an Ar gas stream for 1h, small peaks of spinel-type compound appeared along with large peaks of Zn(II)-wüstite and ZnO (Fig. 1(b)). The lattice constant of the Zn(II)-wüstite in the pattern b is 0.4291 nm, which is smaller than that of the Zn(II)-wüstite before the heat-treatment (0.4299 nm). This suggests that a part of the Zn(II) ions in the Zn(II)-wüstite transferred into the ZnO phase and that the Zn(II) content of the Zn(II)-wüstite decreased. Although the heat-treatment time was made longer for 5h, no α -Fe

Fig. 1. XRD patterns of (a) the Zn(II)-wüstite obtained by reducing the Zn(II) ferrite in a H_2 gas stream at $300^\circ C$, (b) the Zn(II)-wüstite after the heat-treatment at $500^\circ C$ for 1h and (c) 5h, and (d) the products obtained by allowing Mn(II)-wüstite to stand in an Ar gas stream at $450^\circ C$ for 3h.

peaks appeared (Fig. 1(c)). The peak intensities of the magnetite and ZnO, which had been appended for 1h heat-treatment, only slightly increased. The lattice constant of the Zn(II)-wüstite was 0.4290 nm, which is very close to the lattice constant (0.4291 nm) of the Zn(II)-wüstite heated at $500^\circ C$ for 1h. These results suggest that the Zn(II)-wüstite would not be decomposed completely into α -Fe and spinel-type compound by a further heat-treatment over 5h at $500^\circ C$.

The lattice constant of the Zn(II)-wüstite after the heat-treatment (0.4290 nm) is smaller than that of the active FeO-wüstite (0.4322 nm) which was obtained by heating the FeO-wüstite at $500^\circ C$. This suggests that the Zn(II)-wüstite contained a larger amount of Fe(III) ion, which decreases the lattice constant of the wüstite structure, than the active FeO-wüstite. This is probably due to the Zn(II) ion in the Zn(II)-wüstite, which may stabilize the existence of the Fe(III) ions in the Zn(II)-wüstite. Since the Zn(II) ion has tetrahedral site preference in the spinel-type structure, a small amount of Zn(II) ions may occupy the tetrahedral sites in the Zn(II)-wüstite. The Zn(II) ion in the tetrahedral site would expand the spacing among the oxide ions surrounding the Zn(II) ion. Simultaneously, cation vacancies would be formed in the octahedral site

and the vacancy in the octahedral site would shorten the spacing among the oxide ions neighboring to the vacancy. Thus the Zn(II) ion in the tetrahedral site may distort the crystal structure of the wüstite. This distortion of the oxide ion arrangement may reduce the formation Gibbs energy of the Zn(II)-wüstite. This may be the reason why small amounts of Zn(II) ions interfere with the disproportionation of Zn(II)-wüstite.

C. Effect of Mn(II) Ion On Disproportionation of FeO-Wüstite

Fig. 1(d) show the XRD spectrum of the solid products obtained by heating the Mn(II)-wüstite in an Ar gas stream at $450^\circ C$ for 3h. Small peaks of the spinel-type structure appeared along with peaks of the Mn(II)-wüstite, but no peaks of manganese oxides nor α -Fe appeared. This result is quite different from the case of the Zn(II)-wüstite in which the Zn(II) oxide was formed from the Zn(II)-wüstite (Fig. 1b and c). The reason for this difference is considered as follows. The Mn(II) ion has no site preference to either tetrahedral or octahedral site, but the Zn(II) ion, tetrahedral site preference. This suggests that the Zn(II) ions in the octahedral site of the Zn(II)-wüstite could be stabilized by being moved into the tetrahedral sites of ZnO (wurtzite structure), which would be the driving force for the formation of ZnO during heating the Zn(II)-wüstite. On the other hand, the Mn(II) ions were stable in the Mn(II)-wüstite during heating the Mn(II)-wüstite, due to its no site preference.

The Mn(II)-wüstite did not decompose into α -iron and Mn(II) ferrite below $575^\circ C$ where FeO-wüstite decomposes into α -iron and magnetite. This suggests that the Mn(II) ion stabilized the wüstite structure. The reason is considered as follows. Since the Mn(II) ion is larger than the Fe(II) ion in the octahedral site, the Mn(II) ion expanded the spacing between oxide ions. Therefore, anion repulsion would become weaker with an increase in the Mn(II) content and the Gibbs energy of formation of Mn(II)-wüstite would be smaller. The difference between the Gibbs energy of formation of the Mn(II)-wüstite and the Mn(II) ferrite is considered to be too small to compensate the Gibbs energy from α -iron formation from the Mn(II)-wüstite. As a consequence, the Mn(II)-wüstite was stable and did not disproportionate into Mn(II) ferrite and α -iron.

REFERENCES

- [1] S. Stolen, R. Glockner and F. Gronvold, *Thermochimica Acta*, vol. 256, pp. 91-98, 1995.
- [2] L. Broussard, *J. Phys. Chem.*, vol. 73, pp. 1848-1853, 1969.
- [3] M. Tabata, K. Akanuma, Y. Togawa, M. Tsuji and Y. Tamaura, *J. Chem. Soc. Faraday Trans.*, vol. 90 [8], pp. 1171-1175, 1994.