Fig. 3 Relationship between crack extension and fatigue cycles

the crack extension rate for each values of R as a function of stress intensity factor range, i.e. $\Delta K = K_{\max} - K_{\min}$. Here, the data points with arrows imply those specimens for which no crack more than $10\mu\text{m}$ were observed to extend in each stress intensity factor range after loading of 10^5 cycles. It is found in Fig. 4 that da/dN depends strongly on R . The solid lines in the figure were obtained by fitting the data points for each stress intensity factor range to the equation

$$da/dN = C'(\Delta K)^{n'} \quad (\text{m/cycle}), \quad (2)$$

here, C' and n' are constants. Results of the calculation of C' and n' are summarized in Table 2, where it is seen that both C' and n' increase as R increases.

2. Threshold Stress Intensity Factor Range

Here, the threshold stress intensity factor ΔK_{th} is defined as the range below which no crack larger than $10\mu\text{m}$ are observed after 10^5 cyclic loading. The range is represented as the points with arrows in Fig. 4. In the actual experiment, after a crack extension was observed at a given ΔK , the load was lowered stepwise until no crack extension could be observed after

Fig. 4 Plots of crack extension rate as function of stress intensity factor range

Table 2 Values of C' and n' in $da/dN = C'(\Delta K)^{n'}$ for various R -values

R -values	C'	n'
0.0	7.19×10^{-5}	20.8
0.3	1.03×10^{-2}	17.1
0.5	1.71×10^3	25.5
0.65	3.57×10^{23}	54.0
0.8	5.95×10^{25}	41.7

loading to 10^5 cycles in the condition that R was constant. From the minimum upper load determined in this manner ΔK_{th} was calculated using Eq. (1). The values of ΔK_{th} are listed in Table 3 for various R 's examined here.

Table 3 Values of threshold intensity factor range, ΔK_{th}

R	0.0	0.30	0.50	0.65	0.80
ΔK_{th} (MPa $\sqrt{m}$)	0.610	0.441	0.352	0.238	0.149
	0.632	0.452	0.370	0.238	0.155
	0.645	0.461	0.375	0.245	0.155
	0.659	0.471	0.384	0.251	0.160
		0.482			
Mean	0.637	0.461	0.370	0.243	0.155
	± 0.021	± 0.016	± 0.014	± 0.006	± 0.005

IV. DISCUSSION

1. Equation Expressing Crack Extension Rate

Marshall & Priddle⁽⁴⁾ proposed a formula to represent the rate from the results obtained for two kinds of graphites;

$$da/dN = C(\Delta K - \Delta K_{th})^n \quad (\text{m/cycle}). \quad (3)$$

Crack extension rate which was obtained here for IG-11 graphite is analyzed in Fig. 5 using Eq. (3) for all the values of R examined in the present experiment.

As a result, a single line was obtained as

$$da/dN = (\Delta K - \Delta K_{th})^{5.7}, \quad (4)$$

here, an appropriate value of ΔK_{th} was determined by the way mentioned in preceding chapter.

However, some difference is still observed between the rearranged data of $R=0.0$ and 0.8 . This is believed to result from the fact that for low values of R , da/dN is dependent on ΔK whereas it depends almost only on

Fig. 5 Plots of crack extension rate da/dN as function of stress intensity factor range $\Delta K - \Delta K_{th}$ rearranged according to Eq. (3)

K_{max} for high values of R . This might mean that fracture mode changes with increasing R . This results shows that crack extension rate of IG-11 graphite is larger than that of graphite A tested by Marshall & Priddle. It seems that the reason for this difference is that graphite A contains much larger pores than IG-11 graphite and these pores arrest crack to blunt the extending crack tip.

It is well known that fatigue life of material could be predicted by integration of Eq. (2). However, it is not available to predict fatigue life of VHTR's graphite components with Eq. (4) for all of stress ratio conditions. Because Eq. (4) overestimates crack extension rate da/dN for R -values less than 0.5.

2. R-effect on Threshold Stress Intensity Factor Range

Figure 6 shows the relationship between R

Fig. 6 Plots of threshold stress intensity factor range as function of R and ΔK_{th} or R and $\Delta K_{th}/\Delta K_{tho}$.

The solid line was obtained by fitting the data to the following equation :

$$\Delta K_{th}/\Delta K_{tho} = (1-R)^A, \quad (5)$$

where ΔK_{tho} is ΔK_{th} at $R=0$ and A a constant which was calculated as 0.89 in the present case. Since $\Delta K = K_{max}(1-R)$, from Eq. (5)

$$\Delta K_{th}/\Delta K_{tho} = K_{max \cdot th}(1-R)/K_{max \cdot tho}, \quad (6)$$

here, $K_{max \cdot th}$ and $K_{max \cdot tho}$ are thresholds of the maximum stress intensity factor in the conditions that $R=R$ and $R=0$, respectively, if $A=1$, from Eq. (6)

$$K_{max \cdot th} = K_{max \cdot tho}. \quad (7)$$

Crack extension rate would be independent of R and dependent only on K_{max} , i.e. $da/dN = f(K_{max})$, provided that the condition specified by Eq. (7) be satisfied. In the case of IG-11 graphite for which $A=0.89$ and 1, the crack extension depends strongly on K_{max} . This suggests that the fracture of the material is well characterized by the cleavage fracture model.

Photograph 1 shows an example of scanning electron microscopic observation of the fracture surface of IG-11 graphite on which one can observe a lot of flakes. This fact might be considered to indicate that the main fracture mode of the graphite is cleavage fracture.

CRACK EXTENSION DIRECTION

Photo. 1 Scanning electron micrograph of fracture surface of IG-11 graphite

V. CONCLUSION

Crack extension rate da/dN of a fine-grained isotropic nuclear graphite IG-11 was measured for various R values ranging 0~0.8 where $R = K_{min}/K_{max}$.

Conclusions derived are :

- (1) For a given value of R , crack extension rate da/dN can be expressed as

$$da/dN = C(\Delta K)^n \quad (\text{m/cycle}),$$

here, ΔK is a stress intensity factor ranges, i.e. $\Delta K = K_{max} - K_{min}$, and C and n are constant and strongly dependent on R value respectively.

- (2) Threshold stress intensity factor range ΔK_{th} which was defined as the point below which no crack extension more than 10 μm was observed after loadings of 10^5 cycles as related with R -values as

$$\Delta K_{th}/\Delta K_{tho} = (1-R)^{0.89}.$$

—REFERENCES—

- (1) PARIS, D. C., et al.: *J. Basic Eng. Trans.*, ASEM Ser. B, 93, 1190 (1971).
- (2) KRESNIL, M., et al.: *Eng. Frac. Mech.*, 4, 77 (1972).
- (3) MILLER, M. S., et al.: *ASTM STP* 738, 1190 (1981).
- (4) MARSHALL, P., et al.: *Carbon* 11, 541 (1973).
- (5) KAKUI, H., OKU, T.: *J. Nucl. Mater.*, 137, 124 (1986).
- (6) ISHIYAMA, S., OKU, T., ETO, M.: *J. At. Energy Soc. Jpn.*, (in Japanese), 28[10], 966 (1986).

Kinetics of Reduction of Np(V) by Hydroxylammonium Chloride in Perchloric Acid Solution

Yasushi INOUE, Osamu TOCHIYAMA and Ichiro KOSAKA

*Department of Nuclear Engineering, Faculty of Engineering,
Tohoku University**

Received August 27, 1986

The kinetics of the reaction between Np(V) and hydroxylammonium chloride in perchloric acid solution was studied at 70°C. In perchloric acid solutions from 1.0 to 1.5 mol·dm⁻³, the reaction rate is described by

$$-d[\text{Np(V)}]/dt = k[\text{Np(V)}][\text{NH}_2\text{OHCl}]^{1.6}[\text{H}^+]^{2.1},$$

where the rate constant $k = (6.7 \pm 0.3) \times 10^{-2} \text{ mol}^{-3.7} \text{ dm}^{11.1} \text{ min}^{-1}$. Detailed studies of the dependence of the rate on the concentrations of hydroxylammonium ion and chloride ion showed that the reaction is much accelerated by chloride ion.

KEYWORDS: actinoid, chloride ions, hydroxylamine, hydroxylammonium chloride, neptunium, neptunyl ions, Purex process, reaction kinetics, redox reaction

I. INTRODUCTION

Neptunium has attracted special interest recently in the technology of the nuclear fuel cycle because of the potential radiological hazard of the long-life isotope ²³⁷Np⁽¹⁾⁽²⁾.

Since Np in solutions behaves differently according to its oxidation state, it is very important to study its oxidation-reduction (redox) reactions. The redox reactions of light actinoids are generally characterized by the formation of stable oxygenated cations of the general type MO₂⁺ and MO₂²⁺ in their higher oxidation states. As a result, redox reactions involving MO₂²⁺/M⁴⁺ or MO₂⁺/M⁴⁺ couples are considered to proceed far more slowly than those involving M⁴⁺/M³⁺ or MO₂²⁺/MO₂⁺, because the former require the breaking or formation of metal-oxygen bonds in addition to the electron transfer⁽³⁾⁽⁴⁾.

Among the four oxidation states of Np Np(V) is the most stable in acid solutions. Thus, the reactions involving NpO₂⁺/Np⁴⁺ couple are especially important since their slow kinetics eventually affect the behavior of Np in many practical situations.

Hydroxylamine is an important reducing agent for Pu in the processing of nuclear fuel because it would not add extraneous, non-volatile components to the wastes. Since hydroxylamine is usually available in a form of

hydroxylammonium salts and the processing of nuclear fuel (Purex process) is conducted in nitric acid media, considerable studies^{(5)~(9)} have been made by using hydroxylammonium nitrate as a reducing agent. The reduction in nitric acid media, however, is subject to complications by the destruction of hydroxylamine by nitrous acid and the oxidation of Np(V) by nitric acid catalyzed by nitrous acid⁽¹⁰⁾.

The present study is an attempt to obtain fundamental data on the rate of reduction of Np(V) to Np(IV) with hydroxylammonium chloride in perchloric acid media, in the hope of avoiding the occurrence of complicated reactions inherent to nitrate media. Although this system is of no practical use in the processing of nuclear fuel, the comparison between this and the nitrate media would provide valuable information on the fundamental aspects of the redox reaction of Np.

II. EXPERIMENTAL

1. ²³⁷Np Solution

Neptunium was obtained from Radiochemical Centre, Amersham, as ²³⁷NpO₂, and purified by solvent extraction with TTA (2-thenoyl-trifluoroacetone)⁽¹¹⁾. A small amount of Fe(II) remained in the ²³⁷Np solution was removed by repeated solvent extraction with MIBK (4-methyl-2-pentanone) from HCl solution. The

* Aramaki, Sendai-shi 980.

radioactive purity of the ^{237}Np solution was checked by α -spectrometry and the chemical purity by spot test with $\text{K}_4\text{Fe}(\text{CN})_6$ ⁽¹²⁾. Finally, the solution was fumed with HClO_4 to remove all organics and chlorides. The concentration of Np in this stock solution was determined by radiometric assay with a 2π gas-flow counter (Aloka Model FC-1E).

The Np(VI) solutions for rate measurement were prepared as follows: A portion of the stock solution was heated and evaporated nearly to dryness to give moist salt. The salt was then dissolved and diluted with an appropriate amount of standardized HClO_4 , NaClO_4 and HCl solutions to give Np(VI) in desired acid and chloride concentrations, and ionic strength. Separate experiments showed that fuming HClO_4 quantitatively oxidized neptunium to the hexavalent state.

2. Reducing Agent

The stock solution of hydroxylammonium chloride was prepared by dissolving a weighed amount of analytical-reagent grade NH_3OHCl with an appropriate amount of standardized HClO_4 .

When the concentrations of hydroxylammonium and chloride ions were to be changed independently, hydroxylammonium perchlorate was used since the use of hydroxylammonium chloride gives the combined effect of these ions. The stock solution of hydroxylammonium perchlorate was prepared as follows. The solution of $\text{Ba}(\text{ClO}_4)_2$ was added to that of $(\text{NH}_3\text{OH})_2\text{SO}_4$ to precipitate BaSO_4 , and the precipitate was filtered off from the solution. The filtrate was then passed through a cation-exchange column of Dowex 50W-X8 (obtained from Bio-Rad Laboratories, Ltd.) in hydrogen form. The concentration of $\text{NH}_3\text{OHClO}_4$ was determined by the method of Raschig^{(13)~(15)}.

3. Procedure

The acid solutions ($[\text{H}^+] = 1 \sim 1.5 \text{ mol} \cdot \text{dm}^{-3}$) of Np(VI) ($2 \sim 4 \times 10^{-3} \text{ mol} \cdot \text{dm}^{-3}$) and the reducing agent ($0.8 \sim 1.2 \text{ mol} \cdot \text{dm}^{-3}$) were separately placed in stoppered glass tubes and allowed to stand for 30 min at $70 \pm 1^\circ\text{C}$ in a thermostated aluminium mold ("Heating Block" supplied by Yamato K.K.). This rather high temperature was selected because of the ex-

tremely slow rate of reaction at room temperature. After the reaction was started by mixing these solutions, aliquots of the solution were taken out at proper intervals and quenched with water to stop the reaction. Absorption spectra were then measured with a Hitachi EPS-3T recording spectrophotometer with an optical cell (1-cm light path). The concentration of Np(V) was determined from the absorbance at 975 nm, which is due primarily to Np(V). Slight contribution of Np(IV) to the absorption at this wavelength was estimated from the absorbance at 955 nm, which is assigned to Np(IV), and subtracted from the observed value. The absorption spectra were confirmed to be independent of the chloride-ion concentration and acidity in the conditions studied.

III. RESULTS

1. Stoichiometry

No Np(VI) was detected during the whole experiment. Hence, it is obvious that Np(VI) is completely reduced to Np(V) immediately after the addition of the reducing agent in the conditions used in the present experiment. Separate experiments showed that no reduction of Np(V) occurred by chloride ions without the reducing agent. Although the redox potentials of $\text{NpO}_2^+/\text{Np}^{4+}$, $\text{Np}^{4+}/\text{Np}^{3+}$, $\text{NH}_3\text{OH}^+/\text{N}_2$ and $\text{NH}_3\text{OH}^+/\text{N}_2\text{O}$ indicate a possibility of the reduction of Np(V) to Np(III), the absorption spectra showed no evidence of the formation of Np(III) under the conditions studied.

From these observations and by analogy with the reaction of Np with hydroxylammonium ion in nitric acid media⁽⁷⁾, it can be assumed that the reaction is represented by the following overall stoichiometric equation :

In the presence of an excess of Np(V), NH_3OH^+ might not be oxidized to nitrogen :

Since all the kinetic experiments were conducted in the presence of more than hundredfold excess of the reductant, reaction (2) was assumed

to contribute negligibly as compared with reaction (1). The reaction products other than Np(IV) were not identified nor determined because of the experimental difficulty.

2. Kinetics of Reaction

In order to obtain the rate equation, the effects of the concentration of hydroxylammonium chloride and the acidity were studied by varying the initial concentration of each component. The experimental results are shown in Figs. 1 and 2 in terms of the plots of $\log([Np(V)]/[Np(V)]_0)$ against time, where the symbols in brackets with subscript "0" denote the initial concentrations, while those without subscript the concentrations at time t . For these runs, the ionic strength (I) was not maintained constant and varied from 1.3 to 2.5 $\text{mol}\cdot\text{dm}^{-3}$. The linear relationship in Figs. 1 and 2 indicates that the reaction rate is first-order with respect to $[Np(V)]$ under these conditions.

$$-d[Np(V)]/dt = k_0[Np(V)], \quad (3)$$

where k_0 is the apparent first-order rate constant. When the concentration of the reductant or hydrogen ion is low, the plots deviate from the first-order relationship with respect to $[Np(V)]$. A reason for these deviations may be the contribution of the disproportionation reaction since its reaction rate is second-order

with respect to $[Np(V)]$. However, the rate of disproportionation is too slow to contribute significantly under these conditions⁽¹⁶⁾⁽¹⁷⁾. In any case, the reduction of Np(V) is considered to proceed mainly through the reaction which is first order with respect to $[Np(V)]$, and the deviation is considered to originate from side reactions. We, therefore, focused our attention on this first-order reaction. The mechanism of the reaction deviating from the first-order dependence with respect to $[Np(V)]$ was not investigated further more.

To determine the order of the reaction with respect to $[H^+]$ and $[NH_3OHCl]$, $\log k_0$'s obtained from the initial rates were plotted as a function of $\log[H^+]_0$ and $\log[NH_3OHCl]_0$, as are shown in Figs. 3 and 4. Linear dependence was obtained under the conditions where the first-order relationship held with respect to $[Np(V)]$. From these results, the rate expression is given by

$$-d[Np(V)]/dt = k[Np(V)][NH_3OHCl]_0^{1.6}[H^+]_0^{2.1}, \quad (4)$$

where the rate constant is,

$$k = (6.7 \pm 0.3) \times 10^{-2} \text{ mol}^{-3.7} \text{ dm}^{11.1} \text{ min}^{-1},$$

under the conditions,

$$[NH_3OHCl]_0 = 0.80 \sim 1.20 \text{ mol}\cdot\text{dm}^{-3},$$

Fig. 1 Influence of concentration of NH_3OHCl on rate of reaction

Fig. 2 Influence of acidity on rate of reaction

$$[\text{H}^+] = 1.01 \sim 1.52 \text{ mol} \cdot \text{dm}^{-3},$$

$$[\text{Np(V)}] = 2 \times 10^{-4} \sim 4 \times 10^{-3} \text{ mol} \cdot \text{dm}^{-3},$$

Conditions: Same as in Fig. 1.

Fig. 3 Dependence of initial rate on concentration of NH_3OHCl

IV. DISCUSSION

Koltunov *et al.*⁽⁷⁾ have measured the rate of the reaction of NpO_2^+ with NH_3OH^+ in nitric acid solutions. The reaction rate was

$$\begin{aligned} -d[\text{Np(V)}]/dt \\ = k[\text{Np(V)}][\text{NH}_3\text{OH}^+][\text{H}^+]^{1.65}, \end{aligned} \quad (5)$$

where the rate constant is

$$k = (4.54 \pm 0.09) \times 10^{-2} \text{ mol}^{-2.65} \text{ dm}^{7.95} \text{ min}^{-1}$$

at 92°C and ionic strength $I = 4 \text{ mol} \cdot \text{dm}^{-3}$. To explain the rate equation (5), they considered the participation of protonated forms of Np(V) ions, $\text{NpO}_2\text{H}^{2+}$ and $\text{NpO}_2\text{H}_2^{3+}$, in the rate-determining steps.

at 70°C .

Increase of the rate of the reaction with hydrogen-ion concentration is consistent with the general view of the kinetics of the reduction of actinoid oxo-ions accompanied by a change in the structure⁽³⁾.

Conditions: Same as in Fig. 2.

Fig. 4 Dependence of initial rate on acidity

Comparing with their results obtained in nitric acid solutions, the rate expression (4) obtained in the present study has higher order of the reaction with respect to reductant and hydrogen-ion concentrations. Moreover, by taking into account the difference in the temperature, the rate of the reaction observed in the present study is much faster than that in nitric acid solutions. The difference implies the possibility of the contribution of the reoxidation of Np^{4+} in nitric acid media or the participation of chloride ion in the rate-determining step of the reaction in the present study. Equation (4), however, does not suffice to describe the detail of the reaction rate, since it was obtained by the use of hydroxylammonium chloride which gave the simultaneous change of the concentrations of hydroxylammonium ion and chloride ion.

In order to examine the dependence of the rate on the concentrations of chloride ion and hydroxylammonium ion separately, hydroxylammonium perchlorate was used instead of hydroxylammonium chloride. Figure 5 shows the rate of reduction under the conditions of constant hydroxylammonium-but varying chlo-

ride-ion concentration. The values of $\log k_0$

Fig. 5 Influence of concentration of Cl^- on rate of reaction at $[\text{NH}_3\text{OH}^+] = 0.91 \text{ mol} \cdot \text{dm}^{-3}$

Figures 7 and 8 show the dependence of the rate on hydroxylammonium-ion concentration at constant chloride-ion concentration. The result indicates that the 1.6th-order dependence of the reaction with respect to NH_3OHCl in

Fig. 7 Influence of concentration of NH_3OH^+ on rate of reaction at $[\text{Cl}^-] = 1.18 \text{ mol} \cdot \text{dm}^{-3}$

obtained from these data are plotted against $\log[\text{Cl}^-]$ in Fig. 6, which reveals the 0.65th-order dependence of the reaction with respect to chloride-ion concentration. Apparently, the chloride ion considerably accelerates the reaction of Np(V) with hydroxylammonium ion.

Conditions: Same as in Fig. 5.

Fig. 6 Dependence of initial rate on concentration of Cl^- at $[\text{NH}_3\text{OH}^+] = 0.91 \text{ mol} \cdot \text{dm}^{-3}$

Eq. (4) is the combined effect of the hydroxylammonium ion and chloride ion. It should be noted that the rate levels off with the increase of $[\text{NH}_3\text{OH}^+]$. This indicates that the rate-determining step changes from the reactions related to NH_3OH^+ to those irrelevant to this ion as its concentration increases.

From the experimental results, the mechanism

Conditions: Same as in Fig. 7.

Fig. 8 Dependence of initial rate on concentration of NH_3OH^+ at $[\text{Cl}^-] = 1.18 \text{ mol} \cdot \text{dm}^{-3}$

of the interaction of hydroxylammonium chloride and Np(V) can be represented by a set of reactions

These equations are similar to those proposed by Koltunov *et al.*⁽⁷⁾ for nitrate media (Eqs. (6)~(11)) except that the rate-determining steps represented by Eqs. (6) and (7) are replaced by reactions (13) and (14) involving chloride ions.

Since the order of reaction with respect to hydrogen-ion concentration is close to 2 in this work, the pathway involving $\text{NpO}_2\text{H}_2^{2+}$ is neglected unlike Koltunov's case. Equation (12) represents the protonation of NpO_2^+ or the replacement of O^{2-} in NpO_2^+ by H_2O . This equilibrium is presumed to be rapidly established by considering the specific rate constant obtained by Rabideau⁽¹⁸⁾ (0.31 s^{-1}) of the oxygen exchange reaction between NpO_2^+ and H_2O in $1 \text{ mol} \cdot \text{dm}^{-3} \text{ HClO}_4$ at 23°C .

Equation (13) represents the replacement of H_2O by Cl^- . Although there is no direct confirmation of the presence of NpOCl_2^+ , it is likely that the formation of this species facilitates the nucleophilic attack of the nitrogen in hydroxylammonium since the coulombic repulsive force is smaller than the reaction (7).

Assuming that the concentration of NpOCl_2^+ is kept constant at the steady-state condition, the rate equation can be expressed by the following equation:

$$-d[\text{Np(V)}]/dt = k_3 K_1 [\text{NpO}_2] [\text{H}^+]^2 [\text{Cl}^-] / \{1 + k_{-2}/(k_3 [\text{NH}_3\text{OH}^+])\}. \quad (16)$$

Although Eq. (16) explains qualitatively well the dependence of the rate on the experimental

factors, it does not exactly explain the 0.65th-dependence of the rate on the chloride-ion concentration. The mechanism of the reaction may be more complicated than that postulated here, since interactions between chloride ion and Np, and chloride ion and the reductant, which were not examined because of experimental difficulty, may possibly occur in reality. Moreover, since the conditions adopted in the present experiment were limited to a narrow range due to the slow rate of the reaction, the mechanism discussed above is effective only under limited conditions.

In conclusion, the acceleration of the rate by chloride ion observed in the present experiment suggests the importance of the kinetic studies, which are designed to examine the effect of coexisting substances, such as uranium and fission products, in order to obtain the fundamental and technological information about the reaction of neptunium.

—REFERENCES—

- (1) THOMPSON, R.: *Radiat. Res.*, **90**, 1 (1982).
- (2) REES, J. H., *et al.*: *Nucl. Energy*, **22**, 423 (1983).
- (3) KOLTUNOV, V. S., *et al.*: *Radiokhimiya*, **27**, 90 (1985).
- (4) NEWTON, T. W.: The kinetics of the oxidation-reduction reactions of U, Np, Pu and Am in aqueous solutions, TID-26506, (1975).
- (5) SHILOV, V. P., *et al.*: *Radiokhimiya*, **17**, 564 (1975).
- (6) KOLTUNOV, V. S., *et al.*: *ibid.*, **19**, 611 (1977).
- (7) *idem*: *ibid.*, **19**, 620 (1977).
- (8) EL-NAGGAR, H. A., *et al.*: *Radiochim. Acta*, **31**, 51 (1982).
- (9) SZE, Y.-K., *et al.*: *Nucl. Technol.*, **63**, 431 (1983).
- (10) BENEDICT, M., *et al.*: "Nuclear Chemical Engineering", (2nd ed.), p. 487; p. 542 (1981), McGraw-Hill, New York, and the references cited therein.
- (11) MOORE, F. L.: *Anal. Chem.*, **29**, 941 (1957).
- (12) FEIGL, F.: "Spot Test", (5th ed.), p. 161 (1958), Elsevier.
- (13) BRAY, W. C., *et al.*: *J. Am. Chem. Soc.*, **41**, 1363 (1919).
- (14) ABE, S., *et al.*: *Sci. Rep. Res. Inst. Tohoku Univ.*, Ser. A, **7**, 524 (1955).
- (15) KOLASA, T., *et al.*: *Talanta*, **21**, 845 (1974).
- (16) KOLTUNOV, V. S., *et al.*: *Radiokhimiya*, **17**, 560 (1975).
- (17) KOLTUNOV, V. S., *et al.*: *Russ. J. Phys. Chem.*, **48**, 495 (1974).
- (18) RABIDEAU, S. W.: *J. Phys. Chem.*, **67**, 2655 (1963).