部分熔融 Y - B a - C u - O 繊維の臨界電流密度

Tomoko GOTO, Asaichi KAWANAKA*, Takeshi HAYAKAWA, Ken-i-chi SAKAI and Masato NIWA

Department of Materials Science and Technology, Nagoya Institute of Technology,

Gokiso-cho, Showa-ku, Nagoya, 466 JAPAN

Tel:81-52-732-2111 Fax:81-52-741-4099

*Nitivy Co.Ltd.

300 Zenzaemon, Fujieda, Shizuoka, 426 JAPAN

TEL:81-546-35-2450 Fax:81-463-59-5078

(Received 9, October 1991 Accepted 28, November 1991)

ABSTRACT

The contribution of the $Y_2Ba_1Cu_1O_5$ (211) phase and the effect of Pt addition on the critical current density (J_c) of the partial-melted Y-Ba-Cu-O filaments produced by suspension spinning and solution spinning are investigated. The J_c of the filament increases by adding the Pt element, whereas the J_c decreases with increasing the Y-rich region from the stoichiometric composition of $Y_1Ba_2Cu_3O_x$.

Key words : Partially-melted Y-Ba-Cu-O filament, solution spinning, suspension spinning, platinum addition

1. INTRODUCTION

We have studied the preparation of superconducting oxide of long filaments by using a textile fiber spinning technology for the precursor of the oxide, and a high J_c value of more than 10^4 A/cm² at 77 K and 0 T was attained for the suspension-spun and solution spun Y-Ba-Cu-O filament by using melt growth process.^{1,2} However the reproducibility of the J_c of the partial-melted filament was very poor as compared with the sintered filament. It was reported in the QMG processed materials that the 211 particles can be regarded as working for the J_c increase³ and the platinum-added sample exhibited a high J_c .⁴ In this paper the effect of the starting composition changing from the stoichiometry of

Y:Ba:Cu=1:2:3 toward the 211-rich region and Pt addition on the J_c of the partial-melted Y-Ba-Cu-O filaments produced by suspension spinning and solution spinning is described.

2. EXPERIMENTAL

2.2. suspension spinning

Appropriate amounts of Y_2O_3 , $BaCO_3$ and CuO (99.9% pure) were mixed into the composition Y:Ba:Cu=1:2:3, 1.2:2.1:3.1 and 1.4:2.2:3.2, ground, and calcined at 900 °C for 24 h and then an amount of 0, 0.5 wt. %, and 1 wt. % PtO_2 was added. The powder was melted in a platinum crucible at 1400 °C for 900 s. The molten oxides were rapid-quenched by soaking in liquid nitrogen. Then the oxide was pulverized. The resultant powder was suspended in a mixed

polyvinyl alcohol (PVA) solution of dimethyl sulfoxide and hexamethyl phosphoric triamide. The viscous suspension was extruded as a filament into a precipitating medium of methyl alcohol and coiled on a winding drum. The filament with a diameter of 250 μm was fabricated in a length of well over 10m and was heated under various conditions in flowing oxygen.

2.2 solution spinning

Long filaments were prepared by dry spinning with a starting homogeneous aqueous solution of Y, Ba and Cu acetates. An aqueous solution of PH = 4.3 was prepared in advance by dissolving PVA, propionic acid, 2-hydroxy isobutyric acid and/or 0.5 wt. % hydrogen hexachloroplatinate hexahydrate. The mixture of the acetates, in which the atom ratio of Y:Ba:Cu was adjusted to 1:2:3, 1.2:2:3 and 1.5:2.25:3.25 was dissolved in the solution. The resultant solution was concentrated and deaerated to obtain a stable, viscous, homogeneous spinning dope. The dope was extruded as a filament into a hot air zone and coiled on a winding drum. The as-drawn filament with a diameter of 250 μm was heated at 150 $^{\circ}\text{C}$ for 1h and 500 $^{\circ}\text{C}$ for 1h in air to remove volatile components. A partial melting was investigated in various heating conditions in flowing oxygen.

The electrical resistivity (ρ) of the heated filament was measured by a standard four-probe method. Silver paint was used to connect gold sputtered parts of the filament with Ag electrodes 50 μm in diameter. The specimen temperature was measured using calibrated chromel-gold + 0.07 % iron thermocouple. The transport J_c measurement was performed at 77 K, 0 T with criterion of 1 $\mu\text{V}/\text{cm}$.

3. RESULTS AND DISCUSSION

3.1. Filaments by suspension spinning

The partial-melting of various compositions of Y:Ba:Cu = 1:2:3, 1.2:2:3 and 1.4: 2.2: 3.2 filament produced by

suspension spinning was examined. Although the maximum J_c value more than $10^4 \text{ A}/\text{cm}^2$ at 77 K, 0 T was observed for the Y:Ba:Cu=1.2:2:3 filament,¹ the J_c of the filament heated at same heating condition was sometimes the order of $4000 \text{ A}/\text{cm}^2$ at 77 K, 0T. Maximum J_c value for the filament with the composition of Y:Ba:Cu=1:2:3 and 1.4:2.2:3.2 was observed at $3000 \text{ A}/\text{cm}^2$ and $1500 \text{ A}/\text{cm}^2$ at 77 K and 0 T, respectively. The maximum J_c was obtained with a 50 mol% excess of the 211 particle on the bulk QMG processed materials and the 211 particles can be regarded as working for the J_c increase due to the reduction in crack³ or in increasing pinning force.⁴ For the present fine filament with diameter of 250 μm , it is considered that 211 particle may reduce the current path as well as work for the J_c increase and optimum amount of 211 particle becomes to be smaller than that for the bulk QMG materials.

The suspension spun $\text{Y}_{1.2}\text{Ba}_{2.1}\text{Cu}_{3.1}\text{O}_x$ filaments containing 0.5 and 1 wt. % PtO_2 were partially melted at various temperatures ranging from 1080 $^{\circ}\text{C}$ to 1160 $^{\circ}\text{C}$ for 20 min and were cooled to 1000 $^{\circ}\text{C}$. After 1 h, the samples were cooled at the rate of 10 $^{\circ}\text{C}/\text{h}$ to 950 $^{\circ}\text{C}$ and then furnace cooled. The materials were then annealed in oxygen at 600 $^{\circ}\text{C}$ for 16 h and subsequently cooled slowly to room temperature. Figure 1 shows the relation between the J_c of the filament and the partial-melting temperature. Although the maximum J_c for the filament without Pt was as low as $2000 \text{ A}/\text{cm}^2$, the J_c is increased by adding Pt element and the J_c of $8000 \text{ A}/\text{cm}^2$, and more than $7000 \text{ A}/\text{cm}^2$ (the filament was burn out by applying more than 3 A) was attained for the filament containing the 0.5 wt.% PtO_2 and 1 wt.% PtO_2 , respectively.

The filament exhibited superconductivity at a T_c of 86 K from the temperature dependence of the electrical resistivity, and a diamagnetic response due to the

Fig.1. Relation between J_c at 77 K and O_T of the filament and partially-melted temperature.

Fig.2. The polished and etched surface on the longitudinal cross-section of the filament containing PtO_2 with high J_c .

Fig.3. X-ray diffraction pattern taken by a flat cassette camera of the partially-melted filament with PtO_2 .

Meissner effect below 91 K was observed. The normal resistivity value such as $0.22 \text{ m}\Omega\cdot\text{cm}$ was relatively low as compared with the value of $4 \text{ m}\Omega\cdot\text{cm}$ for a partial-melted filament without PtO_2 .⁴

Figure 2 shows the polished and etched surface on the longitudinal cross-section of the filaments. The sample shows a very dense and well aligned structure consisting of plate like grains. It was reported for the partial-melted filament with high J_c that the filament had a well-aligned texture and the matrix was sometimes cut off by the bulk grain with different orientation.¹ However such bulk grains were not observed for the present filament containing PtO_2 .

An X-ray diffraction powder pattern of the filament containing PtO_2 showed that the filament was a mixed phase of 123, 211, CuO and $BaCuO_2$. An X-ray transmission Laue pattern of the partially-melted filament with high J_c containing PtO_2 was taken by a flat cassette camera to examine the orientation of the crystals. Figure 3 shows the representative X-ray Laue patterns of the filament. The distance from the sample to the film was 33 mm and Cu radiation was used. The data for determination of the fiber axis using the X-ray diffraction pattern of the filament were examined and $[100]$ and $[010]$ fiber texture were deduced for the filament. The fiber axis appeared to coincide with the direction perpendicular to the c -axis of the orthorhombic phase in the superconducting layer. Such crystallographic alignment should be beneficial for the flow of supercurrent in this severely anisotropic layer compound. Fine laue pattern was not obtained for the filament without PtO_2 due to the coarse grain.

Platinum is considered to enhance the nucleation of 211 which forms by the peritectic reaction between Y_2O_3 and liquid phase and could produce finely dispersed 211 inclusions in 123 matrix. When the sample

contains fine 211 precipitates, a strain field is created in the vicinity of every 211 precipitates, which favorably disperses stress and reduces the stress concentration and hence prevent crack formation.⁵ On the present filament a finer filament can be produced by adding platinum.

3.2 Filament by solution spinning

Three kinds of filaments with a composition of Y:Ba:Cu = 1:2:3 (A), 1.2:2:3 (B) and 1.5 : 2.25: 3.25 (C) were spun by solution spinning. The filaments were heated at 150 °C for 1 h and 500 °C for 1 h in air to remove volatile components and then a partial melt growth process was applied to enhance the J_c of the filaments. The optimum heating conditions were dependent on a composition and diameter of the filament. For example, filament A was partially-melted at 1030 °C for 15 min and was cooled to 930 °C at a rate of 100 °C/h subjected to slow cooling to 830 °C at a cooling rate of 30 °C/h and then furnace-cooled in flowing oxygen.⁴ A diameter of filament A was reduced to about 60 μ m, in spite of starting from the as-drawn filament of 250 μ m in diameter. Filaments B and C were partially-melted under the same condition of filament A. However the filament did not show the superconductivity at more than 77 K. Filament B was partially-melted at 1000 °C for 15 min and was cooled to 930 °C at the rate of 100 °C for 15 min and was cooled to 930 °C at the rate of 100 °C/h. After 1 h, the filament was slow-cooled to 830 °C at a cooling rate of 30 °C/h and then furnace-cooled in flowing oxygen. Filament C was partially-melted at 1000 °C for 1 h and was cooled as same as for filament B. The maximum transport J_c at 77 K and 0 T of the filaments was 17000 A/cm², 7300 A/cm² and 3200 A/cm² for filaments A, B and C, respectively. As the ratio of 211 phase increases, the J_c of the filament decreases. As the filament was very thin, the excess 211 particle may

reduce the current path and did not result in a increasing J_c .

The fractured texture of filament A was coarser than that for filament B. and no cracking was observed for the filament B. The 211 particle can be regarded as working for the reduction in cracks.

The effect of Pt addition on melt-processed filament by solution spinning was also examined. A higher J_c of 4200 A/cm² at 77 K, 0 T was observed for the filament containing 0.5 wt. % Pt salt as compared with the J_c of 1400 A/cm² at 77 K, 0 T for filament without Pt salt under same heating condition. A further optimization of the melt-processed condition is now progress.

4. CONCLUSION

The effect of the excess 211 phase and Pt addition on the J_c of the partial-melted Y-Ba-Cu-O filaments produced by suspension spinning and solution spinning was examined. The J_c of the filament increases by adding the Pt element, whereas the J_c decreases with increasing the 211 phase.

ACKNOWLEDGMENT

This work was partly supported by a Grant-in-Aid for Scientific Research on Chemistry of New Superconductors for the Ministry of Education, Science and Culture (No.03211216).

REFERENCES

- ¹T. Goto and Y. Kino, Jpn. J. Appl. Phys. 29, L2030(1990).
- ²T. Goto and T. Sugishita, Jpn. J. Appl. Phys. 30, L997(1991).
- ³M. Tanaka et al., Proc. 3rd Int. Symp. Superconductivity ISS'90 Sendai 1990 (Springer Verlag, Tokyo, 1991), p.721.
- ⁴M. Morita et al., Jpn. J. Appl. Phys. 30, L813(1991).
- ⁵M. Murakami et al., Cryogenics 30, 390(1990).

***The 2nd Tokai University
International Workshop
on
SUPERCONDUCTIVITY
(TUIWS)***

October 9-12, 1991

**Tokai University Pacific Center
2241 Kapiolani Blvd. Honolulu, Hawaii
(Phone: 808-973-4100 Fax: 808-973-4107)**

CONFERENCE ORGANIZERS

Organizing Committee (Tokai University)

Chair; Tatsuro MATSUMAE
(President of Tokai University)
Sonosuke KATORI
Shoji YOSHIDA
Kimikazu MATSUYAMA
Norio MATSUMAE
Yoshio MIHARA
Hajime YANO
Takashi MATSUMOTO
Toru HIRAYAMA
Mamoru KAWAKAMI

Conference Organizers

Chair; Sadao NAKAJIMA
Co-Chair; Shoji TANAKA
Co-Chair; Kyoji TACHIKAWA
Mamoru KAWAKAMI
Hideomi KOINUMA

Program Committee

Chair; Tadashi SHIRAISHI
Hideomi KOINUMA
Kazumasa TOGANO
Naoto NAGAOSA
Yoshitake NISHI
Yuh SHIOHARA

Secretariat

Chair; Tadashi SHIRAISHI
Ichiro NAKADA
Shusuke YOMO
Yasunari KURIHARA
Tetsunobu TAKAYAMA
Minoru HAYAMA
Masaaki IGARASHI