INFLUENCE OF ROOT IRREGULARITY ON FATIGUE STRENGTH OF PARTIALLY-PENETRATED LONGITUDINAL WELDS

By Chitoshi MIKI*, Fumio NISHINO**, Toshimi SASAKI***
and Takeshi MORI****

1. INTRODUCTION

Partially-penetrated longitudinal weldings are often used for assembling box-section members. In the previous studies^{1)~3)}, it was shown that weld defects such as blowholes existed at the root of this joint and these defects decreased fatigue strength of the joint. In the case that root gap of this joint becomes wide, some melted weld metal spills down into the root gap of the joint. After the welding is completed, the weld metal stays in the root gap as if it is hanging-down from the root. In the pilot members for Ohnaruto Bridge, hanging-downs remained when root gap was wider than 0.6 mm⁴⁾ (Fig. 1). This root irregularity causes stress concentration and may

Fig. 1 Depth of weld penetration for various root gaps⁴⁾.

reduce the fatigue strength.

The main objective of this study is to examine the influence of this root-irregularity on the fatigue strength of this joint and to clarify the properties of initiation and propagation of fatigue crack experimentally. Fracture mechanics analysis of fatigue crack propagation is also carried out to predict the fatigue life of this joint.

2. SPECIMEN AND TESTING METHOD

The material used is 600 MPa class quenched and tempered steel. Mechanical properties and chemical compositions of the steel are shown in Table 1. Plates of 620 mm in length, 120 mm in width and 17 mm in thickness were welded longitudinally with the root gaps of 0, 0.5, 1.0 and 2.0 mm. Prior to regular welds, the welds for sealing the root had been done by CO₂ arc welding process. The longitudinal welds were placed by automatic submerged arc welding process. Then specimens were cut out from these welded plates. Fig. 2 shows the configuration and dimensions of specimens. Specimen made as 0, 0.5, 1.0 and 2.0 mm of root gaps are called as G0, G0.5, G1 and G2 specimen, respectively. Due to the weld shrinkage, actual root gaps of G0, G0.5, G1 and G2 specimens become 0, 0~0.1, 0.6 and 1.4~1.5 mm after weldings. In G0

Table 1 Mechanical properties and chemical compositions.

Mechanical Properties			Chemical Compositions					
yield point (MPa)	tensile strength (MPa)	elongation (%)	C ×100	Si ×100	Mn ×100	P ×1 000	Cu ×1 000	Ceq ×100
560	650	36	15	24	133	21	6	38

* Member of JSCE, Dr. of Eng., Associate Professor, Dept. of Civil Engineering, Tokyo Institute of Technology

** Member of JSCE, Ph. D., Dr. of Eng., Professor, Dept. of Civil Engineering, University of Tokyo

*** Member of JSCE, Research Associate, Dept. of Civil Engineering, University of Tokyo

**** Member of JSCE, M. Eng., Research Associate, Dept. of Civil Engineering, Tokyo Institute of Technology

Fig. 2 Configuration and dimensions of specimen.

and G1 specimens, no hanging-downs of weld metal are observed. Hanging-downs of weld metal are observed in G1 and G2 specimens. G2 specimens contain remarkable hanging-downs of weld metal.

The measured value of welding residual stress was about 180 MPa in tension at the center of specimen.

Fatigue tests were performed by using Amsler-type and servo-type testing machines of 500 kN in dynamic capacities. Fatigue loadings were repeated-tension of 20~30 MPa in minimum stress. Load waveform was sinusoidal and its frequency was 2~10 Hz.

3. TEST RESULTS

(1) Fatigue strength

Fig. 3 shows the relation between stress range S_r and fatigue life to failure N_f . Fatigue strengths of G0 and G0.5 specimens are almost equal and they are significantly higher than those of G1 and G2 specimens. Fatigue strength of G1 specimen is slightly higher than that of G2 specimen. The Honshu-Shinkoku Bridge Authority recently adopted the design allowable stress range for the corner weld⁵⁾ as shown in Fig. 3. All present test results are above this line. S_r - N_f relations for welded joints with large blowholes and without blowholes obtained in previous study²⁾ are also shown in Fig. 3. The dimensions of specimens are equal to those in this study and the steel used is the same grade. The average of large blowhole is 3.0 mm wide and 4.4 mm long. Fatigue test results of G2 specimens are plotted

Fig. 3 Results of fatigue tests.

above the S_r - N_f line for large-blowhole specimens and test results of G0 and G0.5 specimens are located above the S_r - N_f line for no-blowhole specimens. Therefore, the influence of hanging-downs of weld metal on fatigue strength is about the same degree as that of large blowholes in previous study.

(2) Initiation of Fatigue Crack

After fatigue tests, several specimens were opened along the weld line to observe the degree of irregularity at the weld root and fatigue cracking. Photo 1 shows the these exposed surfaces.

In G0 and G0.5 specimens, no weld metal hang down into the root gap of the joint, and no fatigue crack is observed. In G1 and G2 specimens, many inherent partially propagating fatigue cracks are observed. These cracks initiate and propagate from the concave portions of hanging-downs at which stress concentration is high.

The degree of stress concentration at the concave portion is depends on the depth of hanging-down and the radius of concave point. In all observed concave points, the shape is very sharp and its radius is nearly equal to zero. The depth of the hanging-down of weld metal was measured and the results are shown as histograms in Fig. 4. Hatched portion and dotted portion in Fig. 4 indicate that partially propagating cracks were found at the both side and one side of the hanging-down, respectively. Hollow portion shows the hanging-downs with no cracks. In

Photo 1 Condition of root face and partially propagating crack.

Fig. 7 Predicted S_r-N_f relations and test results.

(3) The diameter of final crack is equal to 90% of specimen-thickness.

(4) For the relation between the rate of fatigue crack propagation da/dN and stress intensity factor range ΔK , equation (2) is employed⁶⁾.

$$da/dN = 5.47 \times 10^{-12} (\Delta K^{3.0} - 2.5^{3.0}) \dots \dots (2)$$

$$da/dN: \text{m/cycle}, \Delta K: \text{MPa} \sqrt{\text{m}}$$

Predicted life for various sizes of initial defects (a_i) and test results are compared in Fig. 7. In this figure, broken lines indicate predicted S_r-N_f relations for G1 and G2 specimens. These predicted lines are close to the experimental results. Therefore, it is valid that initial defect is assumed to be penny-shaped crack having a diameter equal to the width of root gap.

5. CONCLUSIONS

The results obtained in this study are as follows.

(1) Fatigue strengths of joints with no root irregularities are considerably higher than those of joints containing hanging-downs of weld metal. As the root gaps of joints become wide, hanging-downs of weld metal become remarkable and fatigue strengths decrease.

(2) Fatigue crack originates at the one corner of root gap in the concave portion of hanging-downs, and propagates rapidly along the surface of weld metal at the root gap. Then, this crack grows to become penny-shaped crack.

(3) In the joints with hanging-downs of weld

metal, fatigue cracks initiate and start to propagate at the early stage of life.

(4) In the joints with hanging-downs of weld metal, a large number of partially propagating fatigue cracks are observed at the concave portion of hanging-downs.

(5) Fatigue life of this joint can be predicted by using the fracture mechanics concepts. For this purpose, initial defect is regarded as a penny-shaped crack having a diameter equal to the width of root gap. Predicted stress range-fatigue life curves are close to the experimental results.

6. ACKNOWLEDGEMENT

The authors express their gratitude to Dr. Atsushi Okukawa of Honshu-Shikoku Bridge Authority for his valuable suggestion and to Mr. Takao Narumiya of Miyaji Iron Works for the fabrication of specimens.

REFERENCES

- 1) Nishimura, T., J. Tajima, A. Okukawa and C. Miki: Fatigue Strength of Longitudinal Single-Bevel-Groove Welded Members, Proceedings of JSCE, No. 291, pp. 27~40, Oct. 1979.
- 2) Miki, C., F. Nishino, Y. Hirabayashi and H. Ohga: Fatigue Strength of Longitudinal Welded Joints Containing Blowholes, Proceedings of JSCE, No. 325, pp. 155~166, Sept. 1982.
- 3) Miki, C., J. Tajima, K. Asahi and H. Takenouchi: Fatigue of Large-Size Partial Penetrated Longitudinal Butt Welds, Proceedings of JSCE, No. 322, pp. 143~156, June 1982.
- 4) Technical Committee for the Construction of Honshu-Shikoku Bridges, Kaiyoh Kakyō Chōsakai: Technical Report for the Construction of Stiffened Truss of Ohnaruto Bridge, 1982.
- 5) Matsuzaki, Y., H. Shimokawa and K. Murakami: Fatigue Design of the Honshu-Shikoku Bridges in Japan, IABSE Colloquium Lausanne 1982, pp. 497~502, 1982.
- 6) Miki, C., F. Nishino and Y. Hirabayashi: Fatigue Crack Growth in the Corner Weld of Box-Section Bridge Truss Chord, IABSE Colloquium Lausanne 1982, pp. 345~352, 1982.

(Received January 25, 1983)