High Pressure Phase Transition of CrSb_2

H. Takizawa, K. Uheda, T. Endo, and M. Shimada[†]*Department of Molecular Chemistry and Engineering, Tohoku University, Sendai 980-77, Japan*[†]*Institute for Advanced Materials Processing, Tohoku University, Sendai 980-77, Japan*

A new high-pressure phase of CrSb_2 has been synthesized from the marcasite-type ambient pressure phase by high-pressure/temperature treatment above 5.5 GPa. The crystal structure of the high-pressure phase is body-centered tetragonal, which is assigned as CuAl_2 -type structure. The bond nature in the high-pressure phase is metallic, in contrast to the mixed ionic and covalent character in the marcasite-type phase. The phase transition, marcasite-type to CuAl_2 -type, accompanies 11% volume decrease and a change of d-electron character from localized to itinerant.

[high-pressure synthesis, phase transition, marcasite-type, CuAl_2 -type, pnictides]

1. Introduction

Transition metal dichalcogenides and dipnictides (TX_2) with the pyrite, marcasite, and arsenopyrite-type structures have been widely discussed on their structural relationship and chemical bonding schemes. The common features of these closely related compounds are the formation of X-X dimer (dumb-bells) and the mixed ionic and covalent character of the chemical bonds [1, 2]. The X-X bond distances in these compounds are nearly equal to sum of the single bond tetrahedral covalent radii. Transition metal atoms are in T^{2+} (dichalcogenides) or T^{3+} (dipnictides) valency states and octahedrally coordinated by six chalcogen or pnictogen atoms.

Two types of pressure-induced phase transitions, marcasite (or arsenopyrite) to pyrite and pyrite to marcasite structures, were reported in this family. The former was found in FeSe_2 , FeTe_2 , CoTe_2 , CuSe_2 , NiP_2 , NiAs_2 and described to be due to the effective packing of TX_6 octahedra [3, 4]. The latter case was observed in high-pressure X-ray diffraction study of MnS_2 and MnTe_2 [5-7]. The 15-18% volume decrease at the transition suggest a high-spin to low-spin transition of Mn^{2+} [6].

This paper describes a new type of phase transition in this family, marcasite to CuAl_2 -type, which has been found in CrSb_2 . High-pressure form of CrSb_2 was metastably obtained by quenching from 7-7.7 GPa and 600-700°C. The structural analysis and electrical and magnetic measurements reveals that the transition accompanies a change of d-electron character from localized to itinerant.

2. Experimental

Stoichiometric mixture of chromium and antimony powders was heated at 700°C for 168 h in an evacuated silica tube and quenched to room temperature. The marcasite-type (low-pressure form) sample thus obtained was ground, pressed into pellet, and subjected to high-pressure/temperature condition using the belt-type high-pressure equipment. The detailed cell assemblage of the belt-type equipment is shown in Fig.1. High-pressure/temperature treatments were carried out at 3-7.7 GPa and 400-700°C for 30 min and then the sample was quenched to room temperature prior to releasing the applied pressure. Phase identification of the recovered sample was performed by powder X-ray diffraction analysis. The crystal structure of high-pressure form was refined by Rietveld analysis of the powder X-ray

Fig.1. The cell assemblage of the belt-type high-pressure equipment.

diffraction data using the RIETAN program [8]. The magnetic measurements were carried out by a magnetic torsion balance in the temperature range 77-300 K.

3. Results and Discussion

Figure 2 shows the X-ray diffraction patterns of products quenched from 600°C at various pressures. The detailed X-ray

Fig.2. The X-ray powder diffraction patterns of CrSb_2 quenched from 600°C at various pressures; open circle: high-pressure form, closed circle: low-pressure form.

diffraction study of quenched samples revealed that the crystal structure of the sample treated below 5 GPa was low pressure marcasite-type, while a new modification of CrSb_2 coexisted with the low-pressure form in the samples treated above 5.5 GPa. Single phase of this high-pressure form was obtained after treatments at 7-7.7 GPa and 600-700°C.

The high-pressure form is metastable at ambient condition and transforms to low-pressure marcasite-type structure by heating above 300°C at atmospheric pressure.

The X-ray diffraction data of the high-pressure form was completely indexed on a tetragonal unit cell with lattice parameters of $a=6.49 \text{ \AA}$ and $c=5.74 \text{ \AA}$. From the Rietveld analysis, the crystal structure was refined to be body-centered tetragonal CuAl_2 -type with the lattice parameters $a=6.4913(3) \text{ \AA}$ and $c=5.7440(4) \text{ \AA}$. The final refinement gave the R-factors of $R_1=5.37\%$ and $R_F=4.01\%$.

The crystallographic parameters of the high-pressure form (CuAl_2 -type) are given in Table 1. The crystal structure is shown in Fig.3.

The high-pressure form of CrSb_2 is isostructural with TiSb_2 and VSb_2 [9]. At ambient pressure, only two compounds, TiSb_2 and VSb_2 , are known to crystallize into CuAl_2 -type structure in transition metal diantimonides family. The occurrence of the CuAl_2 -type in TiSb_2 and VSb_2 is considered to be due to the relatively large size of the transition metal atom as compared with the other group transition elements [9].

The interatomic distances in high-pressure CrSb_2 are listed in Table 2. The local environments of Cr atoms in both low-pressure (marcasite-type) and high-pressure (CuAl_2 -type) structures are shown in Fig.4.

In contrast to the octahedral coordination of Cr atoms in the low-pressure form, each Cr atom is surrounded by 8 Sb atoms at equidistance and additionally 2 Cr atoms (10-fold coordination)

Table 1. Crystallographic parameters of CrSb_2 (high-pressure form).

Space group: $I4/mcm$ (No. 140) $a=6.4913(3)\text{\AA}$, $c=5.7440(4)\text{\AA}$						
Atom	Site	Occ.	x	y	z	$B (\text{\AA}^2)$
Cr	4a	1.0	0.0	0.0	0.25	0.7(3)
Sb	8h	1.0	0.1587(5)	0.6587	0.0	0.2(1)

final R-factors: $R_1 = 5.37\%$, $R_F = 4.01\%$, $S = 1.3773$

Fig.3. The crystal structure of CrSb_2 (high-pressure form).

Table 2. Interatomic Distances in CrSb_2 (high-pressure form).

Cr - Cr	2.8720(2) $\text{\AA}$	$\times 2$
Cr - Sb	2.8339(14)	$\times 8$
Sb - Sb	2.914(9)	$\times 1$
	3.325(5)	$\times 2$
	3.455(2)	$\times 4$
	3.535(4)	$\times 4$

Fig. 4. The local environments of chromium atoms in CrSb_2 .

in the high-pressure form. As seen in Fig.4, Cr-Cr-Cr linear chains are formed along the c-axis. The Cr-Sb distance in the high-pressure form is $2.834 \text{ \AA}$. This value is longer than that of the low-pressure form and nearly equal to sum of the metallic radii. According to the literature [1], the average Cr-Sb distance in the low-pressure marcasite-type, in which the bond nature is believed to be mixed ionic and covalent character, is $2.708 \text{ \AA}$. The bonding scheme in the marcasite-type phase is explained as $\text{Cr}^{4+}(\text{Sb}_2)^{4-}$. The higher coordination number of Cr atom, the longer Cr-Sb bond distance, and the formation of Cr-Cr bond indicate the metallic bond character in the high-pressure form.

There is still a possibility of the formation of Sb-Sb dimer in the high-pressure form. It is somewhat difficult to estimate the nature of Sb-Sb bond. The nearest Sb-Sb distance in CrSb_2 (high-pressure form) is $2.914 \text{ \AA}$, while the value is $2.84 \text{ \AA}$ [1] in the low-pressure form. In fact, Sb-Sb dimeric bonds are believed to exist in isostructural TiSb_2 and VSb_2 [9]. The Sb-Sb bond distances in TiSb_2 and VSb_2 are $2.840 \text{ \AA}$ and $2.892 \text{ \AA}$, respectively [9]. These values are comparable with those of other TSb_2 family (2.82 - $2.88 \text{ \AA}$) with the pyrite, marcasite, and arsenopyrite-type structures [1]. However, it should be noticed that the Sb-Sb distance in CrSb_2 (high-pressure form) is the longest value among the transition metal diantimonides family [1, 9]. This fact suggests that the covalent character of Sb-Sb bond in the low-pressure form is weakened through the phase transition and the metallic bond character appears in the high-pressure form.

From the structural consideration discussed above, it is concluded that the phase transition of CrSb_2 , low-pressure marcasite-type to high-pressure CuAl_2 -type, accompanies a change in bond nature from the mixed ionic and covalent character to the metallic character. The transition accompanies 11% volume

Fig. 5. High-pressure phase transitions of transition metal dichalcogenides and dipnictides, TX₂, with the pyrite, marcasite, and arsenopyrite-type family.

decrease.

The low-pressure form of CrSb₂ is an antiferromagnetic semiconductor with the Néel temperature of 275 K [2, 10]. A high-spin 3d² electron configuration for Cr was proposed. In contrast, the electrical and the magnetic measurements revealed that the high-pressure form exhibited metallic conductivity and itinerant electron ferromagnetic behavior with the Curie temperature of 160 K, *i.e.*, the localized character of the low-pressure form changed to itinerant in the high-pressure form.

Figure 5 summarizes the high-pressure phase transitions in transition metal dichalcogenides and dipnictides with the pyrite, marcasite, and arsenopyrite structures. The marcasite-type to CuAl₂-type transition, found in CrSb₂, represents a new transition scheme in this family, that is, nonmetal-metal transition associated with the change in bond nature. This suggests possible synthesis of new metallic compounds in this family by applying high-pressure technique.

Acknowledgments

This work has been supported in part by a Grant-in-Aid for Scientific Research (B)(2) (No. 09450238) from the Ministry of Education, Science, Sports, and Culture, Japan.

References

- [1] G. Brostigen and A. Kjekshus, *Acta Chem. Scand.*, **24**, 2993 (1970).
- [2] H. Holseth and A. Kjekshus, *Acta Chem. Scand.*, **24**, 3309 (1970).
- [3] T. A. Bither, C. T. Prewitt, J. L. Gilson, P. E. Bierstedt, R. B. Flippin, and H. S. Young, *Solid State Communications*, **4**, 533 (1966).
- [4] P. C. Donohue, T. A. Bither, and H. S. Young, *Inorg. Chem.*, **7**, 998 (1968).
- [5] H. Fjellvåg, A. Kjekshus, T. Chattopadhyay, H. D. Hochheimer, W. Hönle, and H. G. Von Schnering, *Phys. Lett.*, **112A**, 411 (1985).
- [6] T. Chattopadhyay and H. G. Von Schnering, *J. Phys. Chem. Solids*, **46**, 113 (1985).
- [7] H. Fjellvåg, W. A. Grosshans, W. Hönle, and A. Kjekshus, *J. Magn. Magn. Mater.*, **145**, 118 (1995).
- [8] F. Izumi, in *"The Rietveld Method"* (R. A. Young, Ed.), chap.13, Oxford University Press, Oxford, 1993.
- [9] J. D. Donaldson, A. Kjekshus, D. G. Nicholson and T. Rakke, *J. Less-Common Metals*, **41**, 255 (1975).
- [10] A. Kjekshus, P. G. Peterzens, T. Rakke, and A. F. Andersen, *Acta Chem. Scand.*, **A33**, 469 (1979).