Pressure Effect on Yb_4As_3 and Its Related Compounds

H. Aoki, A. Ochiai*, Y. Seino*, H. Kobayashi, T. Kamimura, T. Suzuki, H. Takahashi[†], N. Takeshita[§] and N. Môri[§]

Physics Department, Tohoku University, Sendai 980-77, Japan

**Department of Material Science and Technology, Niigata University, Niigata 950-21, Japan*

[†]College of Humanities and Science, Nihon University, Setagayaku, Tokyo 156, Japan

[§]ISSP, University of Tokyo, Minatoku, Tokyo 106, Japan

Transport properties of P- and Sb-doped Yb_4As_3 were measured. The electrical resistivity measurement of $\text{Yb}_4(\text{As}_{0.88}\text{Sb}_{0.12})_3$ under various pressure up to 8 GPa was performed. These results were compared with that of pure Yb_4As_3 under high pressure. The substitution effect of Sb is very similar to the pressure effect, however, there is a big difference between them. This similarity strongly suggests that the mobility of the electron is much smaller compared to that of the hole. [pressure effect, Yb_4As_3 , $\text{Yb}_4(\text{As}_{1-x}\text{Sb}_x)_3$, $\text{Yb}_4(\text{As}_{1-x}\text{P}_x)_3$]

1. Introduction

Mixed valence compound Yb_4As_3 with anti- Th_3P_4 structure has attracted much attention of many researchers due to its anomalous physical properties. Around 300 K Yb_4As_3 shows a charge ordering of Yb^{3+} and Yb^{2+} ions accompanied by a structural phase transition shrinking slightly along $\langle 111 \rangle$ direction. Above the phase transition temperature (T_C) the system is considered to be in the thermal valence fluctuating state. In the low temperature phase, characteristic behavior such as a large γ -value of 205 mJ/molK² and T^2 dependence in the electrical resistivity and a plateau around 20 K in the magnetic susceptibility is observed. These results seem to indicate that this compound is a typical heavy fermion compound [1]. However low carrier concentration suggested by the resistivity of the order of m Ω cm and the large Hall coefficient isn't enough to make a Kondo singlet state. So it is difficult to explain that a heavy-fermion-like behavior in this compound by usual Kondo mechanism. So, main interest of this compound is how to interpret it.

Recently neutron measurements on Yb_4As_3 were done by Kohgi *et al.* [2]. They found direct evidence of the arrangement of Yb^{3+} ions along $\langle 111 \rangle$ direction, and further antiferromagnetic spin excitations on its chain. These results make us imagine another origin of the heavy-fermion-like behavior. Actually, calculation using one-dimensional antiferromagnetic Heisenberg model could well reproduce the large γ -value and the plateau of the magnetic susceptibility. Therefore, next question is what is the role of the carrier and how the carrier affects on the heavy-fermion-like behavior.

To clarify the role of the carrier, it is the best way to change the carrier concentration.

In Yb pnictides with anti- Th_3P_4 structure, there is a tendency that mean valence of Yb ions decreases down to almost 2 in Yb_4Bi_3 with increasing the weight of pnictogen. In other words, the hole concentration increases with the increase of the weight of pnictogen. In Yb_4As_3 , a mean valence of Yb ions is close to 2.25. If the valence is exactly equal to 2.25, then the system should be a semimetal or semiconductor. Yb_4As_3 seems to be close to such a situation because of the large resistivity and Hall coefficient.

Therefore, by replacing As with Sb or P, the carrier concentration could be changed. For this purpose, $\text{Yb}_4(\text{As}_{1-x}\text{Sb}_x)_3$ and $\text{Yb}_4(\text{As}_{1-x}\text{P}_x)_3$ are investigated.

Another way to change the carrier concentration is the pressure effect which is especially effective for a low carrier concentration system. Môri *et al.* studied transport properties of pure Yb_4As_3 under high pressure [3,4]. By applying pressure up to 1.2 GPa, the electrical resistivity, the Hall coefficient and T_C decrease. These results indicate the increase of the hole concentration and the subsequent larger screening effect by the pressure. They estimated the mobility of the hole using the resistivity and the Hall coefficient on the assumption of the one band model. To be surprisingly, obtained mobility is independent of the pressure. This result strongly indicates that the hole conduction is always dominant and the hole concentration increases by the pressure. However this interpretation seems to be unusual. The increase of the hole concentration is equal to the increase of Yb^{2+} ions. Therefore this interpretation leads to the increase of Yb^{2+} with the larger ionic radius by the pressure. Actually, the contrary experimental result was obtained by the L_{III} absorption measurement under high pressure, which clearly shows the increase of Yb^{3+} ions by the pressure. By applying pressure over 1.2 GPa, the electrical resistivity further decreases and the transition seems to smear out just above 8 GPa.

To clarify the pressure effect on Yb_4As_3 , it is necessary to reexamine how the pressure affects this system and to compare it with the substitution effect.

2. Sample Preparation and Experimental

Crystal growth of P- or Sb-doped Yb_4As_3 was performed using the same method as that of pure Yb_4As_3 [1]. Lattice constants of these compounds increase and decrease by the doping of Sb and P, respectively. A content of P or Sb was determined by Vegard's law using lattice constants of pure Yb_4Sb_3 , Yb_4As_3 and Yb_4P_3 .

The electrical resistivity under the pressure up to 8 GPa and that at the normal pressure were measured using the conventional four-terminal method. The pressure was generated in cubic anvil apparatus [5] with a 1:1 mixture of Flourinert FC-70 and FC-77 as

a pressure transmitting medium. In order to achieve hydrostatic conditions, the measurements were carried out at fixed pressure with variable temperature between 4.2 and 300 K, the applied pressure changed at room temperature after each low temperature run. The pressure was calibrated using the superconducting transition temperature of Pb.

3. Results and Discussion

In Fig. 1 and 2, the temperature dependence of the electrical resistivities and the Hall coefficients of Sb-doped Yb_4As_3 systems are shown. With Sb content, both of the electrical resistivity and the Hall coefficient become smaller. T_C also goes down reflecting the increase of the screening effect due to the increase of the carrier concentration. Around Sb content of 29%, the transition seems to smear out similar to pure Yb_4As_3 under high pressure of 8 GPa.

Fig. 1. The temperature dependence of the electrical resistivities of the Sb-doped Yb_4As_3 system.

Fig. 2. The temperature dependence of the Hall coefficients of the Sb-doped Yb_4As_3 system.

So, the Sb-doping causes almost the same effect on the transport properties as the pressure, although it expands the lattice constant, corresponding to the negative pressure.

In Fig. 3 and 4, the transport properties of P-doped systems are shown. The P-doped system behaves like a semiconductor. Although the P-doping gives the same effect as the pressure concerning the lattice constant, the transport properties goes to opposite direction. So, the effect of the P-doping obeys the tendency of Yb pnictides with anti- Th_3P_4 structure as described before.

Fig. 3. The electrical resistivities of $\text{Yb}_4(\text{As}_{1-x}\text{P}_x)_3$ system.

Fig. 4. The temperature dependence of the Hall coefficients of $\text{Yb}_4(\text{As}_{0.6}\text{P}_{0.4})_3$ and Yb_4As_3 .

To compare the pressure effect with the substitution effect, it is necessary to investigate the pressure effect on the doped system. In Fig. 5, the electrical resistivities of $\text{Yb}_4(\text{As}_{0.88}\text{Sb}_{0.12})_3$ under various pressure up to 8 GPa are shown. By applying pressure the electrical resistivity decreases in the same way as Yb_4As_3 . The transition smear out between 6 and 8 GPa. So the critical pressure

is forced to be lower by the doping of Sb, compared to that of pure Yb_4As_3 . From this result the doping of Sb seems to behave as same way as the pressure effect, too.

Fig. 5. The temperature dependence of resistivity of $\text{Yb}_4(\text{As}_{0.88}\text{Sb}_{0.12})_3$ under various pressure.

In many aspects the substitution effect of Sb seems to be similar to the pressure effect on pure Yb_4As_3 concerning the transport properties, however, there is a big difference concerning the lattice constant between them as mentioned before. It should be briefly investigated how the substitution of Sb affects the band structure of Yb_4As_3 as pointed out by Suga *et al.* in PES study [6].

As the introduction of Sb expands the distance between Yb ions, the bottom of the conduction band made mostly 5d of Yb ions may be shifted up by the 0th approximation. On the other hand, it is a little bit complex how the valence band made of mostly *p*-character of As or Sb behaves. Judging from the transport properties, the top of the valence band may be shifted up perhaps due to the larger ionic radius of Sb. Such behavior of the valence band is consistent with the tendency of Yb pnictides with anti- Th_3P_4 structure. Therefore in the Sb-doped system, the relative position of the top of the valence band to the 4*f*-level may be shifted up, leading to the high hole concentration. The electron concentration may be too low to affect on the transport properties.

In the meantime, the pressure expands both of the conduction and valence band. So, both of the electron and hole concentration increase by the pressure. The increase of only the hole concentration is absolutely neglected, as Yb^{3+} ions increase with the pressure as seen in the L_{III} absorption measurement. The increase of Yb^{3+} is equivalent to the increase of the electron. So, Yb_4As_3 under the pressure should behave as a semimetal, however, as stated before the hole conduction is always dominant. Further it is very similar to that of the Sb-doped system.

By comparison of the pressure and Sb-substitution effect, it

may be concluded that in Yb_4As_3 the mobility of the electron is too small to affect on the transport properties. Concerning this, recent band calculation done by Harima is interesting [7]. According to its result, the conduction band of Yb_4As_3 under the charge ordered state is rather one dimensional. So, the electron is rather hardly to move compared to the hole.

In the P-doped system, although the bottom of the conduction band may be shifted down, the top of the valence band may be much further shifted down. Consequently a small energy gap is established. The reason why only the hole conduction is observed even in this situation seems to be due to the small mobility of the electron as same way as pure Yb_4As_3 under high pressure.

4. Conclusion

The transport properties of the Sb- and P-doped Yb_4As_3 and the pressure effect on $\text{Yb}_4(\text{As}_{0.88}\text{Sb}_{0.12})_3$ were investigated. The similarity of the pressure and substitution effect strongly suggests smaller mobility of the electron compared to the hole.

Acknowledgments

One of the authors (H. Aoki) is supported by the Research Fellowships of the Japan Society for the Promotion of Science for Young Scientists.

References

- [1] A. Ochiai, T. Suzuki, and T. Kasuya, *J. Phys. Soc. Jpn.*, **59**, 4129 (1990).
- [2] M. Kohgi, K. Iwasa, A. Ochiai, T. Suzuki, J. -M. Mignot, B. Gillon, A. Gukasov, J. Schweizer, K. Kakurai, M. Nishi, A. Dönni, and T. Osakabe, *Physica B*, **230-232**, 638 (1997).
- [3] Y. Okunuki, N. Môri, A. Ochiai, Y. Haga and T. Suzuki, *J. Phys. Soc. Jpn.*, **64**, 533 (1995).
- [4] N. Môri, H. Takahashi, Y. Sekine, A. Ochiai, Y. Haga, T. Suzuki, T. Kashiwakura, S. Nakai, and M. Nomura, *Physica B*, **230-232**, 630 (1997).
- [5] N. Môri, Y. Okayama, H. Takahashi, Y. Haga and T. Suzuki, *Jpn. J. Appl. Phys. Ser. 8*, 182 (1993).
- [6] S. Suga, A. Ochiai, T. Suzuki, T. Matsushita, H. Harada, A. Kimura, M. Tsunekawa, T. Muro, H. Daimon, S. Imada, H. Namatame, M. Taniguchi, H. Ishii, T. Miyahara, T. Hanyu, A. Sekiyama, and A. Fujimori, *to be published*.
- [7] H. Harima, *to be published*.