Oxygen under High Pressure - Temperature Dependence of Electrical Resistance

K. Shimizu^{a,b}, M. I. Erements^{b,c}, K. Suhara^a, and K. Amaya^{a,b,d}

^a Department of Material Physics, Faculty of Engineering Science, Osaka University, Toyonaka, Osaka 560, Japan

^b CREST, Japan Science and Technology Corporation (JST)

^c On leave from Institute of Spectroscopy, Russian Academy of Science, Troitsk, Moscow Region

^d Research Group for Quantum Condensed Matter Systems, Japan Atomic Energy Research Institute

We have measured electrical resistance of oxygen under high pressures up to 120 GPa and at temperatures down to 45 mK. With increasing pressure, the resistivity of oxygen was found to decrease rapidly and reached 0.3 ohm x cm at 95 ± 5 GPa that was still comparable to that of semiconductor. We present measurements of the temperature dependence of electrical resistance of oxygen to observe the metallic behavior in the temperature dependence. The temperature dependence of resistance clearly changes its slope of dR/dT at around 90 GPa. The critical pressure is in agreement with previous reports for the metallization. We found an abrupt drop of resistance which may indicate superconducting transition of metallic oxygen at pressures above 98 GPa with $T_c \sim 0.6$ K. This is confirmed by the magnetic field dependence of the resistance drop.

[diatomic molecule, insulator-metal transition, electrical resistance, low temperature, superconductivity]

1. Introduction

Oxygen (O_2) is known as a rather unique magnetic molecule which shows the antiferromagnetism at low temperature. This diatomic molecule is also expected to undergo an insulator-metal transition in its highly compressed condition. In fact, optical reflection measurement¹⁾ suggested the pressure-induced

metallization of oxygen at 90 ± 10 GPa from an increase of near-infrared reflectivity. X-ray diffraction study²⁾ reported a new high pressure phase (ζ) which is regarded as the metal phase of oxygen at pressures above 96 GPa. In this paper, we measured the temperature dependence of electrical resistance of oxygen up to 120 GPa and down to 45 mK in order to observe clearly the insulator-metal transition.

2. Experimental

A diamond anvil cell (DAC) made of nonmagnetic Be-Cu alloy was used to generate pressures with a pair of 1/3 carat synthetic diamonds of the top surface diameter of 100 μm and beveled angles of 7 degrees from a culet diameter of 300 μm . The sample chamber of 50 μm -hole was prepared at the center of prepressed Al_2O_3 gasket. Thin platinum films were placed between the anvil and gasket for using electrical probes. The arrangement of sample, electrodes and the insulation layer in DAC is shown in Fig. 1. DAC was placed in a chamber of the liquid nitrogen cryostat equipped with a pressure loading mechanism. After filled up the chamber with enough volume of liquid oxygen with a purity of 99.9%, DAC was squeezed up to several GPa's and warmed up

Fig.1. Arrangement of sample and electrode on the insulated gasket in DAC. S:sample (oxygen), E:electrode, I:insulator, M:gasket, D:diamond.

Fig.2. Photo-micrograph of sample and electrodes observed through the diamond. These photos are obtained from the experiments of Ref. 3.

to room temperature for further compression. Resistance was measured by 4-terminal method with a small ac measuring current of 1 μA or less to minimize a heating by the current. The isolation of those electrodes from the metal gasket was confirmed above 200 M Ω with additional electrode welded on the metal gasket (not shown in the figure) during all experimental processes. The pressure was determined by the R1 line of ruby chips placed in the sample chamber at both room temperature and 77 K. The pressure at low temperatures was found to change during cooling from 300 K to 77 K but within 5 % and expected not to change below 77 K. After pressure determination, the cell was warmed up again and directly connected to the mixing chamber of a $^3\text{He}/^4\text{He}$ dilution refrigerator. The temperature was measured by a germanium resistance thermometer on the body of DAC. The sample temperature is expected to be close to that of DAC as the sample has negligible small heat capacity and platinum electrodes have good thermal conductivity.

Fig.3. Electrical resistance of oxygen as a function of pressure at room temperature. (Ref. 3)

3. Results

Figure 2 shows the photomicrographs of the sample and electrodes observed through the diamond during compression at room temperature. With increasing pressure, opaque black oxygen (30 GPa) gradually became bright and some reflection was seen at the highest pressure (~90 GPa). Actually, the resistance also became a measurable value of several M Ω 's at around 60 GPa and showed a rapid decrease in further compressions as shown in Fig 3. The resistivity is estimated from the geometry of the sample of 50 μm x 50 μm x 5 μm . However, the value of resistivity even at the highest pressure of 95 ± 5 GPa is 0.3 Ωcm which is too large for an evidence of metallization and is almost equal to that of a semiconductor.

In order to confirm the metallization and to study the electrical character of this 'conductive' oxygen, the resistance of a function of pressure is measured from 300 K to 45 mK. Figure 4 shows the relative resistance from the resistance divided by that of 300 K, as a function of temperature at 55, 72, 98 and 115 GPa. At

Fig.4. Relative resistance ($R/R_{T=300}$) as a function of pressure of oxygen at several pressures.

pressures below 98 GPa, the temperature dependence of resistance behaves as that of a semiconductor where the slope decreases with increasing pressure. At 98 GPa, the resistance becomes almost temperature independent. The curve between temperature of 70 and 300 K shows unusual shape but may be caused by a pressure changing during cooling. Finally, the slope of the resistance clearly changes to positive which indicates the metallization of oxygen. This measurement of the temperature dependence reveals the critical pressure is around 98 GPa which is comparable with previous reports.^{1,2)} The examinations at lower temperatures show tendency of slight increase of the resistivity below 60 K and 20 K at 98 GPa and 115 GPa respectively. This may suggest that the ζ -oxygen at these pressures are not still usual metal. The origin of the increments of the resistance is still unknown. However, these increments are also observed in the case of solid iodine⁴⁾ and bromine⁵⁾ at around the pressure of the pressure-induced metallic-molecular phase.

The most striking is the observation of an abrupt drop of resistance which may indicate superconducting transition at and below temperature of 0.6 K. Figure 5 shows the measurement of

Fig.5. Resistivity of oxygen as a function of temperature at 120 GPa. Inset shows the magnetic field dependence of the transition.

magnetic field dependence of the drop. The drop is suppressed and disappears by the applied magnetic field. This is the evidence for the superconductivity. The residual resistance below 0.3 K at 120 GPa is considered to the pressure distribution in the sample chamber. Further confirmation of the superconductivity by the detection of the Meissner effect is now going on. The present results may also give evidence of absence of magnetism of metallic oxygen down to observed mK region.

References

- 1) S. Desgreniers, Y. K. Vohra, and A. L. Ruoff, *J. Phys. Chem.* **94**, 1117- 1122 (1990).
- 2) Y. Akahama, H. Kawamura, D. Hausermann, M. Hanfland, and O. Shimomura, *Phys. Rev. Lett.*, **74**, 4690-4693 (1995).
- 3) K. Shimizu, K. Suhara, K. Amaya and S. Endo, *J. Phys. Soc. Jpn.* **65**, 1527-1528 (1996).
- 4) K. Shimizu, T. Yamauchi, N. Tamitani, N. Takeshita, M. Ishizuka, K. Amaya and S. Endo, *J. Superconductivity* **7**, 921(1994).
- 5) K. Shimizu, K. Amaya and S. Endo, *Proceedings of the joint XV AIRAPT and XXXIII EHPRG International Conference (Warsaw, 1995)* p. 498.