Analysis of Rolling of Bars by the Energy Method using Finite Element Division*

By Kazutake KOMORI**, Kazunori KATO*** and Tadao MUROTA****

In the field of bar rolling, many experimental researches have been performed, and various empirical formulas are proposed. But there are few analytical approaches to this subject, because the flow of material in bar rolling is complicated in comparison with that in sheet rolling and it is not easy to determine the three-dimensional kinematically admissible velocity fields.

Recently, we have proposed a new energy method using finite element division. In this paper, this method is described in application to bar rolling. First, technique of finite element division is suggested in order that we can apply the method to any type of rolling in which central region of material is reduced earlier than the other part. Second, the influence of degree of freedom of velocity fields on rolling properties is discussed, and an appropriate velocity field is proposed. Finally, this method is applied to the analysis of flow of material in two types of bar rolling, square-diamond pass and round-oval pass, and reasonable results are obtained.

Key Words : Plasticity, Forming, Energy Method, FEM, Rolling, Three dimensional Deformation

1. Introduction

In the field of bar rolling, many experimental researches have been performed and various empirical formulas are proposed.⁽¹⁾⁻⁽³⁾ However, theoretical approaches are necessary for understanding the influence of rolling conditions on rolling properties clearly. An analysis of bar rolling was done by Yanagimoto⁽⁴⁾ by the slab method, but it can be applied only to the rolling of a rather thin material because its deformation is assumed to be uniform in thickness direction. In bar rolling, the reduction of height, the projected length of roll-material contact arc, and circumferential roll velocity vary in width direction. So, it is not easy to obtain an appropriate velocity field in the usual energy method.⁽⁵⁾ Recently, we have proposed a new energy method using finite element division to analyze the steady state of a three-dimensional deformation effectively.⁽⁶⁾ In this paper, this method is described in application to bar rolling. The technique of finite element division, which we propose in this paper, may be applied to other types of rolling in which the central part of a material comes to contact with roll surfaces earlier than the other part does.

2. Method of Analysis

2.1 Fundamental equations

Caliber rolling of a bar is considered. In Fig.1, square-diamond pass is shown. Coordinate axes are taken with the origin at the midpoint of the entry cross section as shown in Fig.1. The axes X, Y and Z are the directions of length, width and thickness, respectively.

The variational principle about rigid plastic solids is expressed as follows:⁽⁷⁾

$$2T\omega \leq \Phi$$

$$\Phi = \int_V \sqrt{3} k \dot{\epsilon}_{eq} dV + \int_{\Gamma} k \Delta v_k^k d\Gamma^k + \int_{S_c} \tau_f \Delta v_k^k dS_c + Q_B v_B^k - Q_F v_F^k \dots \dots \dots (1)$$

where

T : true torque of upper and lower rolls
 ω : angular velocity of upper and lower rolls

Q_F, Q_B : back and front tension

v_F^k, v_B^k : velocities of material at entry and exit cross sections

τ_f : frictional stress on roll surface

V : volume of material in plastic solid

Fig.1 Coordinates and notations (square-diamond pass)
(a) Entry cross section
(b) Longitudinal section
(c) Exit cross section

* Received 23rd June, 1984.

** Research fellow, Faculty of Engineering, Tokyo Institute of Technology, 2-12-1, Ookayama, Meguro-ku, Tokyo.

*** Associate Professor, T.I.T.

**** Professor, T.I.T.

S_c : contact surface with rolls
 Γ^* : interface on which discontinuity of tangential velocity arises
 k : suffix indicating kinematically admissible velocity fields
 k : shearing yield stress
 Δv_k^* : amount of discontinuity of velocity
 $\dot{\epsilon}_{eq}^k$: equivalent plastic strain rate
 Material is assumed to be a rigid plastic Mises' solid.

2.2 Method of analysis

The method of analysis is explained in the previous paper,⁽⁶⁾ so brief description is made in this paper. Plastic deformation region is divided into finite elements in a similar way to that of FEM. And the actual velocity field is expressed as the summation of several admissible fundamental velocity fields, which are given beforehand.

$$v = \sum_{i=1}^q a_i v^{(i)} \quad (a_i: \text{unknown coefficient} \dots \dots \dots (2))$$

Here, $v^{(i)}$ is a velocity vector, which is composed of X, Y, Z components of velocities at all nodal points, so the number of the total components is $3N$ (N : number of nodes), q is the number of fundamental velocity fields. Then Φ in Eq.(1) is expressed as $\Phi(v)$. Coefficients a_i in Eq.(2) are determined by the condition of minimizing the functional in Eq.(1). The procedure of analysis is shown in Fig.2.

2.3 Finite element division

According to an experiment made by the authors using plasticine (experimental method is given in reference(8)), the deformation between the roll contact surfaces and the deformation near the free side surface differ widely from each other, so interface between elements should be taken such as to coincide with the boundary of contact surface in the situation that rather a small number of elements are used.

Plastic deformation region is divided into two regions: the region between the roll contact surfaces (I) and the region near the free side surface (II), as shown in Fig.3(a). The finite element division in the region (I) is as follows.

Fig.2 Procedure of analysis

We use the normal finite element division in Fig.3(b) in the analysis of flat rolling. We can modify this division to one in Fig.3(c). Next we introduce a special element to express the singular deformation in the neighborhood of boundary of contact surface. A normal hexahedral element is shown in Fig.3(d). The line segment "cd" in contact with roll surface is moved to "ba", which is located on the free side surface (see Fig.3(e)). If such modification is done, with respect to all line segments along the division line 22', the line 22' moves up to the line 33' in Fig.3(a). Similar modification is made concerning other division lines, such as 11'. Then we obtain element division shown in Fig.1(c).

The region (II) is divided uniformly in the length and the thickness directions.

2.4 Procedure of introducing admissible velocity fields

We must prepare many kinematically admissible velocity fields as the fundamental velocity fields beforehand, but this is not so easy usually. So two components of velocity (X and Z components) are assumed and the third component (Y component) is calculated numerically from the equation of volume constancy.

In the previous paper,⁽⁶⁾ velocity in width direction V_y is determined such as to satisfy the condition of volume constancy at the center of each element, but this method cannot be applied, if the finite element division is irregular. In this paper, V_y is determined such as to minimize the summation of square of volumetric strain rate.

Squares of volumetric strain rate are considered at eight Gauss points in each hexahedral isoparametric element. And V_y is determined such as to minimize the summation of square volumetric strain rate in each group of elements where grouping is done by lines 11', 22' --- in Fig.3(a). Velocity in thickness direction V_z on the roll contact surface is determined with consideration of the boundary condition.

Fig.3 Procedure of finite element division (plane figure)

The boundary conditions of velocity are expressed as follows.

$$\left. \begin{aligned} v_x|_{x=0} &= v_B \\ v_x|_{x=l} &= v_F \\ v_z|_{z=h} &= \frac{\partial h}{\partial x} v_x|_{x=h} + \frac{\partial h}{\partial y} v_y|_{z=h} \end{aligned} \right\} \dots\dots\dots (3)$$

3. Discussion of Fundamental Velocity Fields in Bar Rolling

3.1 Definition of rolling conditions and rolling properties

Non-dimensional variables are defined in the rolling to the square-diamond pass and round-oval pass as follows(see Fig.4). The suffix B denotes entrance, and the suffix F denotes exit. In Fig.4, dotted lines denote material shape before rolling, solid lines denote material shape after rolling, fine lines denote caliber shape, and in this analysis, caliber shape of "oval" is circle.

(i) Variables concerning rolling conditions

Reduction: $r = (h_B - h_F)/h_B$

Roll radius: R/h_B

Height/width ratio of caliber: h_F/b_K

(ii) Variables concerning rolling properties

Width spread: $w = (b_F - b_B)/b_B$

Reduction of area: $(S_B - S_F)/S_B$

Filling ratio: b_F/b_K

Mean gradient of free side surface: $\tan \theta_F$

Torque: $T^* = \Phi / (R \omega \cdot 4 S_B \cdot \sqrt{3} k)$

Fraction of friction loss: Φ_F / Φ

(Frictional energy rate: $\Phi_F = \int_{S_F} \tau_F \Delta v^2 dS$)

Neutral point: x_N/l

(x_N : no sliding point in XZ plane)

Forward slip: $\xi = (v_F - U)/U$

(v_F : material velocity at the exit

U : roll velocity in XZ plane)

Warping of cross section after rolling, which is perpendicular to X axis before rolling, is expressed as follows (see Fig.4(c),(d)).

Warping of section along thickness: u_h/h_F

Warping of section along width: u_b/b_F

3.2 Definition of fundamental velocity fields

To analyze effectively, it is important to make the fundamental velocity fields as few as possible. So how much the analytical results change with an increase in the number of fundamental velocity fields is examined. This is done concerning square-diamond pass under the condition in Table 1. Considering the results in the previous paper⁽⁹⁾, finite element division shown in Fig.1 is used, where one fourth of a billet is expressed for symmetry.

3.3 Fundamental velocity fields

Several cases of different combinations of fundamental velocity fields are examined. Number of fundamental velocity fields means degree of freedom of the velocity field representing the deformation under consideration and it corresponds to q in Eq.(2).

3.3.1 Velocity field of $q=3$ (fundamental velocity fields for whole region)

The following three velocity fields $V_x^{(1)}, V_x^{(2)}, V_x^{(3)}$ will be introduced with reference to the velocity field in flat rolling of a bar.

$$v_x^{(1)} = \frac{h_B}{h(y=0)} U \dots\dots\dots (4)$$

$$v_x^{(2)} = U \dots\dots\dots (5)$$

$$v_x^{(3)} = \left(1 - \frac{x}{l}\right)^2 \left\{ \frac{h_B}{h(y=0)} - 1 \right\} U \dots\dots\dots (6)$$

V_y and V_z are determined under the condition as follows: For any cross section perpendicular to X axis, V_y is independent of Z, V_z changes linearly in thickness direction. $\dot{E}_y$ and $\dot{E}_z$ are assumed to be continuous across the boundary of regions (I) and (II), and to be constant in the region (II).

Table 1 Standard rolling condition

Roll radius	$R/h_B = 10$
Reduction	$r = 0.25$
Height/width ratio of caliber	$h_F/b_K = 0.6$
Friction ratio	$m = 1$

Fig.4 Definitions of notations

(a) Square-diamond pass

(b) Round-oval pass

(c) Warping of section along thickness

(d) Warping of section along width

3.3.2 Velocity field of $q=7$ (fundamental velocity fields in the region (II))

The region (II) is shown in Fig.5(a) (refer to Fig.3(a)), where the area ABED is a side free surface, and the area ACFD is the boundary surface between regions (I) and (II). Nodal points in region (II) are divided into two groups: nodal points on the area ABFD and those on the area ACFD. For each group of nodal points, V_x is given as follows.

$$v_x^{(i)} = \frac{x}{l} \left(\frac{x}{l} - 1 \right)^2 U, \quad i=4,5 \dots \dots \dots (7)$$

And V_z is given as follows.

$$v_z^{(i)} = \frac{\partial h}{\partial x} \frac{z}{h} U, \quad i=6,7 \dots \dots \dots (8)$$

3.3.3 Velocity field of $q=25$ (fundamental velocity fields for region (I))

For the purpose of representing the warping of section along thickness, the following type of a fundamental velocity field is introduced for each cross section (for example, AA' in Fig.5(c)) except the cross section at the exit,

$$\left. \begin{aligned} v_x^{(i)} &= \left(\frac{z^2}{h_b^2} - \frac{h^2}{3h_b^2} \right) U \\ v_z^{(i)} &= \frac{2}{3} \frac{h^2}{h_b^2} \frac{\partial h}{\partial x} \frac{z}{h} U \end{aligned} \right\} \dots \dots \dots (9)$$

$i=8 \sim 13$

And concerning the warping of section along width, a fundamental velocity field is given with respect to each cross section except the exit one,

$$\left. \begin{aligned} v_x^{(i)} &= \left(\frac{y^2}{b^2} - 1 \right) U, \quad v_z^{(i)} = \left(\frac{y^2}{b^2} - 1 \right) \frac{\partial h}{\partial x} \frac{z}{h} U \end{aligned} \right\}$$

$i=14 \sim 19$

$(b=b(x) : \text{contact width}) \dots \dots \dots (10)$

Also to consider the barreling of side free surface, a fundamental velocity field is given with respect to each cross section except the exit one,

$$\left. \begin{aligned} v_x^{(i)} &= 0, \quad v_z^{(i)} = \left(\frac{z}{h} - \frac{z^3}{h^3} \right) U \end{aligned} \right\} \dots \dots \dots (11)$$

$i=20 \sim 25$

Fig.5 Method of giving fundamental velocity fields

3.3.4 Velocity field of $q=29$ (fundamental velocity fields for the nodes near the point "a" in Fig.5(c))

Figure 5(c) is a plane figure of the whole region, and Fig.5(b) is an XZ plane near the entrance. The node 10 is located near the node 5. Concerning the nodes 6-10, three velocity fields expressed by Eq.(9)-(11) are introduced as fundamental velocity fields ($i=26-28$). And, velocity field in which V_z changes linearly is given as a fundamental velocity field ($i=29$) with respect to nodes 1-5.

3.3.5 Velocity field of $q=36$ (fundamental velocity fields for the nodes near the points "b" and "c" in Fig.5(c))

Arrangement of nodes near the point "b" in the section AA' in Fig.5(c) is similar to that near the point 'a'. So velocity fields, which are given in 3.3.4, will be used as fundamental velocity fields concerning the nodes near the point "b" ($i=30-33$).

Concerning the nodes near the point "c" - nodes 11-15 in Fig.5(c), velocity fields given by Eq.(9)-(11) are used as fundamental velocity fields ($i=34-36$).

3.3.6 Velocity field of $q=43$ (fundamental velocity fields for the nodes near the points "d" and "e" in Fig.5(c))

Concerning the nodes near the point "d", velocity fields similar to those concerning "a" are introduced ($i=37-40$), and concerning those of "e", velocity fields similar to those of "c" are used ($i=41-43$).

3.3.7 Velocity field of $q=50$ (fundamental velocity fields for the nodes near the points "f" and "g" in Fig.5(c))

Concerning the nodes near the point "f", velocity fields concerning that of "a" are given ($i=44-47$), and concerning that of "g", velocity fields concerning that of "c" are given ($i=48-50$).

Fig.6 Effect of number of fundamental velocity fields

3.4 Results of using various combinations of fundamental velocity fields

Results of using of various fundamental velocity fields in 3.3, are shown in Fig.6. Rolling condition is shown in Table 1.

According to Fig.6, results do not change so much, when degree of freedom becomes greater than 36 in 3.3.5. Consequently, the velocity field in 3.3.5 is found to be the most effective, so we use this in the following.

4. Results

4.1 Results for square-diamond pass

Results for square-diamond pass are obtained by using the velocity fields in 3.3.5. Standard rolling condition is adopted (refer to in Table 1).

Fig.7 Effect of roll radius (square-diamond pass)

4.1.1 Effect of roll radius

Effect of roll radius is shown in Fig.7. Results are plotted by "o".

As roll radius increases, width spread increases (Fig.(a)), filling ratio increases (Fig.(b)) and reduction of area decreases (Fig.(c)). The reason is assumed as follows: as roll radius increases, projected length of roll-material contact arc increases, then elongation in the length direction is restrained and width spread is promoted. This tendency is also observed in the case of flat rolling of a bar. Mean gradient of free side surface decreases (Fig.(d)). In Fig.(a), experimental expression by Shinokura⁽³⁾, which is derived from experiments about hot rolling of steel, is supplemented. The authors' results are in good agreement with the experimental ones. The locations of the neutral point and the forward slip are shown in Fig.(e) and (f), respectively. Warping of section along thickness increases (Fig.(g)) and fraction of friction loss also increases (Fig.(i)). This is related to the increase of the projected length of roll-material contact arc. Warping of section along width does not change so much (Fig.(h)). Torque is shown in Figure(j).

4.1.2 Effect of height/width ratio of caliber

Effect of height/width ratio of caliber is shown in Fig.8. As height/width ratio of caliber increases, width spread increases gradually (Fig.(a)) and filling ratio increases (Fig.(b)). Reduction of area increases (Fig.(c)). This is because the elongation along the length direction is promoted because of the decrease in area of caliber. Fraction of friction loss increases (Fig.(d)).

Fig.8 Effect of height/width ratio of caliber (square-diamond pass)

Fig.9 Effect of friction factor
(square-diamond pass)

Fig.10 Finite element division
(round-oval pass)

Fig.11 Effect of roll radius
(round-oval pass)

4.1.3 Effect of friction ratio

Effect of friction ratio is shown in Fig.9. As friction ratio increases, width spread increases (Fig.(a)). This tendency is also recognized in the case of flat rolling of a bar. Fraction of friction loss increases (Fig.(b)).

4.2 Results for round-oval pass

The shape of caliber of oval is a curved surface. So, the number of elements in width direction must be increased. And it is set at 5. The finite element division is shown in Fig.10, so that the boundary of contact surface may be divided almost equally. Standard rolling condition in Table 1 is adopted.

4.2.1 Effect of roll radius

Effect of roll radius is shown in Fig.11. The trend of rolling properties in round-oval pass is almost the same as that in square-diamond pass (Fig.(7)). Comparison of Fig.11(a) with Fig.7(a) shows that width spread in round-oval pass is greater than that in square-diamond pass under the approximately same rolling condition except the shape of caliber and material (Table 1).

4.2.2 Effect of height/width ratio of caliber

Effect of height/width ratio of caliber is shown in Fig.12. The trend of rolling properties in round-oval pass is almost the same as that in square-diamond pass (Fig.(8)). Comparing Fig.12(c) with Fig.8(c), reduction of area in round oval pass is almost the same as that in square-diamond pass under the same rolling condition.

Fig.12 Effect of height/width ratio of
caliber (round-oval pass)

4.2.3 Effect of friction ratio

Effect of friction ratio is shown in Fig.13. The trend of rolling properties in round-oval pass is almost the same as that in square-diamond pass (Fig.9). Comparing of Fig.13(b) with Fig.9(b), fraction of friction loss in round-oval pass is greater than that in square-diamond pass. This is attributed to a difference in the magnitude of the projected contact area.

4.3 Discussion of deformation

Distribution of equivalent strain rates under standard rolling condition is shown in Fig.14 and Fig.15.

In Fig.14, equivalent strain rate is small near the roll contact surface, except in the part near the entry. This result is confirmed by the slip line field of plane strain rolling. Further, it coincides with the experiment with use of plasticine.⁽⁸⁾

In Fig.15, equivalent strain rate is small near the roll contact surface and near the free side surface. This distribution agrees with the result by the slip line field of plane strain compression of a block.

Fig.13 Effect of friction factor (round-oval pass)

Fig.14 Distribution of equivalent strain rates in longitudinal section
(a) Square-diamond pass
(b) Round-oval pass

Fig.15 Distribution of equivalent strain rates in cross section
(a) Square-diamond pass
(b) Round-oval pass

Coefficients a_4 and a_5 in Eq.(7) are negative in all the rolling conditions. This means that deformation in the region (II) always occurs later than that in the region (I).

5. Conclusions

Analysis of caliber rolling of bars was done by combination of the energy method with the rigid plastic FEM with the following results:

- (i) A method of finite element division is proposed and it is applied to some types of rolling in which central region of material is reduced earlier than the other part.
- (ii) Several different combinations of fundamental velocity fields were examined, and the velocity field in 3.3.5 (degree of freedom is 36) was found to be the most effective one.
- (iii) Analysis of caliber rolling of bars was done about square-diamond pass and round-oval pass, and rolling properties were obtained with respect to fundamental rolling conditions. Results were found to be reasonable from comparison with the experimental ones. Distribution of strain rates well agrees with experimental one. This proves that the present solution is much improved one in comparison with that of the usual energy method.

References

- (1) Yanagimoto, S., J. Japan Tech. Plast., 5-40 (1964), 315 (in Japanese)
- (2) Saito, Y., J. Iron and Steel Inst. Japan, 63-12 (1977), 1819 (in Japanese)
- (3) Shinikura, T., et al., J. Appl. Metalworking, 2-2 (1982), 94
- (4) Yanagimoto, S., Trans. JSME, 28-190 (1962), 637 (in Japanese)
- (5) Kato, K., et al., J. Japan Tech. Plast., 21-231 (1980), 359 (in Japanese)
- (6) Kato, K., et al., Bull. JSME, 29-251 (1986)
- (7) Kudo, H., Theory of Plasticity, (1968), Morikita Pub. Co., (in Japanese)
- (8) Kato, K., et al., J. Japan Tech. Plast., 24-268 (1983), 471 (in Japanese)