Cell Sheet Formation Utilizing Cell Adhesion Control and Analysis of its Functionality

正 ○オケヨ ケネディ (東大) 非 大政 直也 (東大)
 非 黒澤 修 (東大) 正 小穴 英廣 (東大) 正 鷲津 正夫 (東大)

Kennedy O. Okeyo, Graduate School of Engineering, University of Tokyo, Hongo 7-3-1, Bunkyo-ku, Tokyo
 Naoya Omasa, Graduate School of Engineering Science, University of Tokyo
 Shu Kurosawa, Graduate School of Engineering Science, University of Tokyo
 Hidehiro Oana, Graduate School of Engineering Science, University of Tokyo
 Masao Washizu, Graduate School of Engineering Science, University of Tokyo

Key words : Tissue Engineering, Cell Sheet, Open Mesh Scaffold, Adhesion Control

1. Introduction

Cell sheet technology has recently emerged as a powerful alternative approach for generating sheets of live cells as biomaterials for tissue regeneration without a scaffold [1]. It has been applied in the regeneration of cornea, heart, kidney etc. [2]. To generate cell sheets, typically cells are first grown to confluence on a culture dish coated with thermo-responsive or photo-responsive polymers (smart polymers). Then, the polymer-coated surface is thermally or optically stimulated to detach cells as intact cell sheets [1]. A major advantage of this method is that cell sheets can be harvested with little damage to cell-cell adhesion, as opposed to enzymatic methods such as trypsin treatment which leads to cell sheet damage by destabilizing cell-cell contact. Nevertheless, several drawbacks can also be pointed out; one being that smart polymers can only be used with certain adherent cell types that can respond to changing surface properties of the polymer upon thermal or optical stimulation. Another problem is that cell sheet shrinkage occurs during harvesting, leading to loss of function [3].

As an alternative approach, this study proposes a novel system for cell sheet generation which employs an ultra-thin open mesh scaffold suspended in a culture medium such that cell attachment is only restricted to the narrow strands of the scaffold. By keeping the mesh size much larger ($> 50 \mu\text{m}$), and the width of mesh strands much narrower ($< 10 \mu\text{m}$) compared with the size of a single cell, we demonstrate that cells can be induced to form a monolayer cell sheet on a meshed scaffold. The greatest advantage of this method is that cell sheet formation occurs by cell-cell adhesion and self-assembly over the open meshes due to limited substrate adhesion. Thus, cell sheets with greater cell-cell adhesion and hence less shrinkage can be generated.

2. Experimental procedures

A $2 \mu\text{m}$ -thick open mesh scaffold was microfabricated by photolithography using SU-8 (a negative photoresist), according to the procedures illustrated in Fig. 1. Briefly, SU-8 was spincoated on a silicon wafer that had been pre-coated beforehand with 2% gelatin to form a sacrificial layer. After UV exposure through a photomask and etching in SU-8 developer, the highly flexible meshed scaffold was recovered by immersion in hot water to dissolve the sacrificial gelatin layer. Lamination with kapton tape ($100 \mu\text{m}$ thick) was performed before gelatin dissolution for easy handling. In this study, we used a meshed scaffold with a mesh width of $5 \mu\text{m}$ and a mesh size (pitch) of $200 \mu\text{m}$.

Fig. 1 Fabrication procedures for a meshed scaffold

Fig.2 Procedures for cell seeding on a meshed scaffold

Next, the fabricated meshed scaffold was set suspended in a culture medium as shown in Fig. 2b(b-1). Spacers ($500 \mu\text{m}$ in height) were used to raise the meshed scaffold off the bottom of a culture dish such that cells were completely out of contact with the dish bottom. This ensures that cells can only attach to the narrow strands of the mesh scaffold. Finally, as illustrated in Fig. 2b (2-4), TIG120 cells, mouse embryonic fibroblasts (MEFs) and mouse embryonic stem cells (mESs) were seeded onto a circular meshed scaffold with a diameter of 4 mm at a density of $5,000 \text{ cells/cm}^2$ and left to grow in an incubator (37°C , $5\% \text{ CO}_2$).

3. Results and Discussion

Since an open mesh scaffold was used, most cells would fall off to the dish bottom during seeding. However, some cells remained attached on the narrow mesh strands, mainly at the intersection points because the probability of attachment at such positions is

Fig. 3 Formation process and cytoskeleton labeling of cell sheet on a meshed scaffold. **A:** day 2, **B:** day 7, **C:** day15, and **D:** day 22 after initial cell seeding. **E:** Bright field image and **F:** fluorescent image of the same position of an epithelial cell sheet. Images E and F were acquired after cell fixation and actin cytoskeleton labeling. Color code: Actin (green), nuclei (blue), mesh stands (white).

high. It is noteworthy that the scaffold is suspended in a culture medium such that cells that remain attached on the scaffold have no choice but to rely on the narrow (5 μm) strands for support.

Figure 3 shows images of TIG120 cells at different stages of epithelial cell sheet formation on a triangular open mesh scaffold. After culturing for 2 days, cells that had remained attached on the mesh, primarily at the points of intersection, began to elongate and migrate over the mesh (Fig. 3A). As proliferation and migration proceeded, the surface of the scaffold gradually became covered by a monolayer of cells (Fig. 3B). The layer became compact with time as the density of cells increased (Fig. 3C), resulting in the formation of a dense and highly compacted cell sheet after 2-3 weeks (Fig. 3D). Once formed, sheets could be maintained for over 100 days by routine medium exchange.

The result of fixed-cell actin cytoskeleton labeling is shown in Figs. 3E and F. The bright field image in Fig. 3E shows that cell sheet remained intact even after the rigorous procedures of cell fixation and actin labeling, including fixation for 15 minutes in 4% formaldehyde and permeabilization in 1% Triton X for 10 minutes followed by incubation with Alexa 488 phalloidin for 40 minutes. As shown in Fig. 3F, a uniformly distributed actin cytoskeleton network was observed in fixed cell sheets, suggesting that the cytoskeleton provided the mechanical strength that kept the cell sheets intact. Actin cytoskeleton is known to maintain cell-cell interconnectivity via cadherin [4], and we hypothesize that such a property may be more enhanced in this case where cells have to rely more on their own contact to remain on the suspended meshed scaffold than on the support from the substrate.

Continued observation revealed that cell division occurred even after 45 days of cell culture, when cells had reached confluence on the scaffold. At this point, cells would appear like in Fig. 3D, and showed very little migration (data not shown). Considering that cells cultured on a dish or similar substrates typically stop division after reaching confluence due to contact inhibition, the fact that cell division continued in the case of culture on a meshed scaffold

even after confluence was reached points to the unique advantage of the proposed scaffold method. In other words, the suspended scaffold ensures that non-viable cells that can no longer sustain cell-cell adhesion naturally fall off to the bottom, creating space for further cell division. Hence, in this case, cell sheets are mainly composed of viable cells capable of maintaining cell-cell contact.

As expected, the duration to cell sheet formation was highly influenced by the density of cells during seeding, with cell sheets forming much faster (within 1 week) when cell density was high ($> 10^6$ cells/mL) and taking longer when density was low ($< 10^4$ cells/mL). Sometimes a complete coverage of the scaffold did not occur when cell density was significantly low or when the passage number (PN) of cells was very high (PN >20 for TIG120 cells used in this case). We recommend using low PN cells and seeding at a relatively high density for faster cell sheet formation. Indeed, fast replicating cells such as mES cells could form a sheet in less than 2 days (results not shown). In addition, the size and shape of mesh were also found to have significant influence on the speed of cell sheet formation, with cell sheets forming much faster on triangular meshes, and much slower on square and hexagonal meshes.

4. Conclusion

This study has outlined a novel method for cell sheet formation using a thin meshed membrane suspended in culture medium as a scaffold for initial cell attachment. The processes for epithelial cell sheet formation have been elaborated on, and the result of cytoskeleton labeling presented. Future works includes cell sheet lamination and characterization of intercellular boundaries. Use of a biodegradable material instead of SU-8 is also being considered.

5. References

- [1] Okano et al., J Biomed Mater Res. 27 (1993):1243–1251.
- [2] J. Yang et al., Biomaterials 28 (2007): 5033–5043T.
- [3] Canavan et al., J. Biomed. Mat. Res. Part A 75A (2005): 1-13.
- [4] Vasioukhin et al., Cell 100 (2000): 209–219.