研 究 報 文

漂白クラフトパルプ及び古紙パルプのオゾン処理

東京農工大学 農学部 山本 諭
 富士ゼロックス株式会社 メディア研究開発部 古賀 千鶴, 細村 弘義
 東京農工大学 農学部 岡山 隆之

Ozone Treatments of Bleached Kraft Pulp and Waste Paper

Satoshi Yamamoto

Faculty of Agriculture, Tokyo University of Agriculture and Technology

Ghizuru Koga and Hiroyoshi Hosomura

Media R&D, Fuji Xerox/Supply Business Company

Takayuki Okayama

Faculty of Agriculture, Tokyo University of Agriculture and Technology

山本 諭

古賀千鶴

細村弘義

岡山隆之

Commercial bleached kraft pulps were treated by ozone. Changes in the total halogen and ethanol extractable organic halogen of these pulps as well as brightness, viscosity and the water retention value were investigated during the ozone treatment. The effects of the ozone treatment on the total halogen and ethanol extractable organic halogen of the waste paper were also studied using toner-printed copy paper.

The ozone treatments of the chlorine-bleached pulps and the waste copy paper were carried out at a 4 % (or 30%) pulp consistency and at 10°C for 5, 10 and 20 min., respectively.

The total halogen and the ethanol extractable organic halogen of the chlorine-bleached pulps were much higher than those of the elemental chlorine-free pulps. The ozone treatment substantially reduced both the total halogen and the ethanol extractable organic halogen of the chlorine-bleached pulps. The ozone-treated pulps from the waste copy paper resulted in a lower total halogen compared with the usual deinked pulp.

The hardwood bleached pulp with a lower brightness showed some increase in brightness after the ozone treatment. Although the pulp viscosity significantly decreased during the ozone treatment, the strength properties of the handsheet from the ozone-treated pulps were slightly changed.

Keywords : Ozone treatment, Chlorine-bleached pulps, Total halogen, Extractable organic halogen, Viscosity, Brightness, Tensile strength
分類 : R₁ クラフトパルプ, R₂ 古紙パルプ, K₁ 塩素処理

1. Introduction

There is a concern about the environment due to organic chlorine compounds¹⁾ exhausted from the KP bleaching process as one of the environmental topics which the pulp and paper industries have to overcome. To solve this issue, the process which disposes of drain by a closed system and adopts the pulp bleaching process without using chlorine has received much attention. The introduction of the ECF (elemental chlorine free) and TCF (totally chlorine free) bleaching is already being utilized in Europe and America, and the use of the chlorine type bleach in the bleaching process tends to be suppressed. Recently, the conversion to the ECF bleaching is being rapidly advanced in our country. On the other hand, the occurrence of dioxin in the garbage incineration treatment in Japan has become a big social issue, and the improvement plan which aims at the European and American level is being quickly adopted. Currently, the proportion of the paper garbage in the burnable waste for incineration treatment done at a waste incineration plant, etc., is significantly high, and this tendency is quite high in cities where many offices are concentrated. It has been confirmed that the organic chlorine compound remains in the bleached pulp and the paper product when a chlorine-type bleaching agent is used for the bleaching process^{2/3)}, and it is postulated that it will be included in a lot of paper products as a chlorine compound. Accordingly, the possibility of producing chlorinated dioxin when the paper article is incinerated cannot be ignored. There is a requirement to decrease the chlorine compound in the chlorine-type bleached pulp or the paper product based on such a concern.

In this study, we report the results of investigating the quantitative changes in the chlorine compound included in the pulp and the efficacy of decreasing it using an ozone treatment on the chlorine-type bleached pulp and the fine quality grade wastepaper pulp. Moreover, ozone is a multipurpose material suitable for the oxidation, sterilization, bleaching, and deo-

dorization, etc., due to its strong oxidizability, and in the past, many studies concerning the effect of the bleaching has been carried out in the pulp and paper field. However, there are relatively few examples of using it as a method of decreasing the chlorine compound in the bleached pulp or the treatment of the wastepaper pulp.

2. Experimental

2.1 Samples

Nine kinds of bleached kraft pulp, which were tested in this experiment, are shown in Table 1. N-1, L-1, and L-3 are the pulp which utilized the chlorine (C) step in the bleaching sequence, and the other pulps are bleached by the ECF sequence.

2.2 Measurement of total halogen (TX) and ethanol extractable organic halogen (EOX)

Total halogens (hereafter abbreviated as TX) and the ethanol extractable organic halogens (hereafter abbreviated as EOX) were adopted as an index of the amount of the chlorine compound in the pulp used in this study. The TX was measured according to the total chlorine measurement method in ISO 11480. The EOX was measured as follows : The sample was extracted for two hours with ethanol, and after the extracted solution was filtered and diluted, it was adjusted with nitric acid to pH=2. The organic substance included in the extracted solution was then absorbed on activated carbon, and after the activated

Table 1 Pulp samples

Samples No.	Types of pulp
N-1	Chlorine bleached
N-2	Softwood BKP ECF
N-3	ECF
L-1	Chlorine bleached
L-2	ECF
L-3	Chlorine bleached
L-4	Hardwood BKP ECF
L-5	ECF
L-6	ECF

carbon was washed with potassium nitrate aqueous solution to remove the inorganic ions, it was burnt. The amount of generated HCl was measured⁴⁾.

2.3 Ozone treatment

Fig. 1 shows an outline of the method used for the ozone treatment of the samples. After 60 grams of the oven dried sample were disintegrated for 20 minutes at a 4 % pulp consistency, it was put in the reaction vessel of the ozone treatment apparatus which uses a rotary evaporator at the same concentration, and the vessel was then rotated. The ozone treatment was done by introducing the ozone gas, which was generated using an ozonizer. The ozone treatment was done under the following conditions : the flow rate of the raw material oxygen was 1.5 L/min, about a 105 grams/m³ ozone concentration, a 10°C treatment temperature, and 5 minutes, 10 minutes, and 20 minutes (however, 5 minutes and 10 minutes for N-1) as the treatment times. The unreacted ozone after the treatment was absorbed by potassium iodide. Afterwards, the ozone consumption was calculated using the titration method. The sample after the ozone treatment was washed with 3 liters of hot water on filter paper in a Buchner funnel. Moreover, as for the L-3 sample, which had the highest TX and EOX values, the ozone treatment experiment of a 30% pulp consistency was done separately by dehydrating the pulp slurry after disintegration on the Buchner funnel. In this case, the fluff pulp was prepared beforehand using the blender so that it uniformly reacts with the ozone⁵⁾.

2.4 Properties of pulp and handsheet

The freeness, ISO brightness, and limiting viscosity number of the pulp sample using the cupri-ethylene-

diamine solution method were measured based on the JIS (Japanese Industrial Standard). Moreover, the water retention value of the pulp sample was measured based on the JAPAN TAPPI pulp and paper testing method No. 26. The handsheet was prepared from each pulp sample based on the JIS method, and the physical properties of the sheet such as sheet density, tensile strength, tearing resistance and light scattering coefficient, etc., were measured.

2.5 Ozone treatment of fine quality grade waste-paper pulp

Color copying is done using the neutral commercial PPC paper, and this was used as a fine quality grade waste paper sample. After the waste paper sample was disintegrated and the ozone treatment was done, the deinking chemicals were added based on the JAPAN TAPPI pulp and paper testing method No. 39 and matured, then the deinking by flotation and washing was done. The ozone treatment was carried out under the condition of a 4 % pulp consistency, 10°C treatment temperature, and 5-minute treatment time. The TX, EOX, and the ink particle count and the residual ink area by image analysis were measured for the handsheets which had been prepared with the pulp.

3. Results and discussion

3.1 Measurement of chlorine compound of pulp sample

Fig. 2 shows the measurement results of the TX and EOX in each pulp sample. In this experiment, the TX and EOX values of the bleached pulp made from hardwood as the raw material were higher than those of

Fig. 1 Ozone treatment

Fig. 2 Total halogen and ethanol extractable organic halogen of pulp samples

softwood, and it turned out that the pulp, which used the chlorine stage for the bleaching sequence, has very high TX and EOX values. Moreover, the ratio of EOX to TX was higher than that of the softwood bleached pulp in the hardwood bleached pulp, and the tendency was particularly remarkable in the pulp which included the chlorine stage. Each pulp sample of N-1, L-1, and L-3, which were treated by the bleaching sequence including the chlorine stage, was then subjected to ozone treatment, and the quantitative change in the chlorine compound in the pulp examined.

3.2 Decrease in chlorine compound in bleached pulp by ozone treatment

Fig. 3 shows the measurement results of the ozone consumption for the L-3 sample to which the ozone treatment was done at a 30% pulp consistency and that for three kinds of pulp to which the treatment

Fig. 3 Changes in ozone consumption during ozone treatments

*LC and HC denote samples treated with 4 and 30% pulp consistency, respectively

was done at a 4% pulp consistency. Here, the ozone consumption indicates the ratio of the amount of ozone consumption for each oven dried mass of the pulp. The ozone consumption increased almost linearly as the treatment time increased. Moreover, when the pulp consistency during the ozone treatment increased from 4% to 30%, the ozone consumption increased, and it was clarified that the ozone reacts more efficiently with the pulp. The reason for this phenomenon is considered as follows: When the pulp consistency decreases, the liquid phase (water) becomes thick, and the diffusion rate of ozone from the liquid phase to the solid phase (pulp) becomes slower⁶⁾, and much of the ozone gas is removed from the system without coming in contact or reacting with the pulp.

Fig. 4 and Fig. 5 show the changes in the TX and EOX in the pulp according to the ozone treatment time, respectively, when three kinds of pulp samples were subjected to the ozone treatment for a 4% pulp

Fig. 4 Effect of ozone treatment on total halogen of pulps bleached with chlorine

Fig. 5 Effect of ozone treatment on EOX of pulps bleached with chlorine

consistency. Both the TX and EOX of the washing treated hardwood sample decreased compared with those of the untreated sample. The reason for this is considered that some portion of chlorine compound was washed with a large amount of water that is used in the washing and the handsheet making process. Moreover, by ozone treating the washing treated sample, it became possible to further decrease the values of TX and EOX in the pulp. For instance, by carrying out the ozone treatment for ten minutes to the L-3 pulp sample, which includes a large amount of the

chlorine compound, the TX of the washing treated sample decreased from 660 to 570 ppm and the EOX decreased from 130 to 97 ppm. When the ozone treatment time was lengthened, the decrease in TX and EOX was further promoted.

Fig.6 and Fig.7 show the comparisons of the change in TX and EOX for sample L-3 by the ozone treatments between the 4 % and 30% pulp consistencies, respectively. The TX and EOX after the ten-minute ozone treatment could be decreased by 80 ppm and 16 ppm, respectively, by increasing the pulp con-

Fig.6 Effects of ozone treatment at 4 % and 30% pulp consistency on total halogen of L-3

Fig.7 Effects of ozone treatment at 4 % and 30% pulp consistency on EOX of L-3

Table 2 Pulp properties of samples

Sample	Freeness (CSF ml)	W. R. V. (%)	Limiting viscosity number (ml/g)
N- 1 LC Washed O ₃ tr., 5 min. O ₃ tr., 10 min.	685	112	820
	682	110	740
	687	110	621
L- 1 LC Washed O ₃ tr., 5 min. O ₃ tr., 10 min. O ₃ tr., 20 min.	651	106	755
	666	109	711
	661	113	646
	669	107	400
L- 3 LC Washed O ₃ tr., 5 min. O ₃ tr., 10 min. O ₃ tr., 20 min.	624	115	755
	635	118	662
	636	114	676
	601	91	522
L- 3 HC Washed O ₃ tr., 5 min. O ₃ tr., 10 min. O ₃ tr., 20 min.	620	107	734
	628	111	582
	616	108	425
	617	109	397

sistency of the ozone treatment from 4 % to 30%. This corresponds well to the result of the previous ozone consumption. That is, it is considered that the chlorine compound in the pulp could be decomposed and removed because the ozone efficiently contacted the pulp and reacted when the pulp consistency increased. Consequently, studying of the mixing method, etc., during the ozone treatment is required to improve the contact of ozone with the pulp.

3.3 Effect of ozone treatment on pulp properties

Table 2 shows the measurement results concerning the pulp properties. The limiting viscosity number of the pulp sample by the cupri-ethylene-diamine method, which became an index of cellulose polymerization, decreased as the ozone treatment time increased, and the level of the decrease was particularly remarkable for the sample treated at a 30% pulp consistency. On the other hand, as for the freeness of the hardwood pulp, though the tendencies which slightly increased by the ozone treatment were generally observed, the freeness of the L-3 sample significantly decreased when the treatment was for 20 minutes. As for the water retention value of the hardwood pulp, though the tendency which once increased by the ozone treatment was observed, but when the treat-

ment time became long, a big decrease like that for the L-3 sample was observed. On the other hand, the change in the water retention value by the ozone treatment of softwood pulp was small.

Moreover, the brightness was increased due to ozone treatment of the L-3 sample, which had the pulp brightness of about 83%, and in particular, a remarkable improvement was observed in the treatment at a 30% pulp consistency (Fig. 8). However, the tendency of a decreasing brightness by the ozone treatment was observed for the L-1 sample, which

Fig. 8 Effect of ozone treatment on ISO brightness of pulps bleached with chlorine

Table 3 Sheet properties of samples

Sample	Density (g/cm ³)	Tensile index (N·m/g)	Tear index (mN·m ² /g)	Light scattering coefficient (cm ² /g)	
N- 1 LC	Washed	0.63	36.2	25.3	342
	O ₃ tr., 5 min.	0.60	34.3	24.8	368
	O ₃ tr., 10 min.	0.60	34.8	21.8	371
L- 1 LC	Washed	0.59	25.5	9.78	392
	O ₃ tr., 5 min.	0.55	21.1	6.72	436
	O ₃ tr., 10 min.	0.58	25.1	8.40	395
	O ₃ tr., 20 min.	0.55	20.3	6.50	423
L- 3 LC	Washed	0.62	30.3	8.53	417
	O ₃ tr., 5 min.	0.59	23.1	7.13	481
	O ₃ tr., 10 min.	0.63	29.3	8.05	402
	O ₃ tr., 20 min.	0.64	31.9	8.04	418
L- 3 HC	Washed	0.61	24.0	5.69	435
	O ₃ tr., 5 min.	0.64	29.2	7.24	406
	O ₃ tr., 10 min.	0.65	29.7	7.38	413
	O ₃ tr., 20 min.	0.63	27.4	6.39	427

has a brightness of 90% or more. Consequently, it has been clarified that the effect of improving the brightness of pulp by the ozone treatment is limited to the pulp with a brightness of 90% or less.

3.4 Effect of ozone treatment on physical properties of handsheet

Table 3 shows the measurement results concerning the physical properties of the handsheets. As for hardwood pulp, when the pulp consistency is about 4 % during the ozone treatment, the tensile index of the sheet tended to increase as the ozone treatment time was extended though it once decreased at the beginning of the treatment.

However, when the pulp consistency is about 30%, it turned out that the tensile index of the sheet increased with the increase in the ozone treatment time. On the other hand, a change was hardly observed in the tensile index of the sheet for the ozone treatment of the softwood pulp. By the way, the reason why the tensile index of washed original pulp at a 30% pulp consistency was lower than the 4 % case is that the fluff pulp was prepared before the ozone treatment. The change in the sheet strength by the ozone treatment was similar in the tear index, and corresponded to the sheet density and the light scattering coefficient results. From the result of the light scattering coefficient of the sheet, when the pulp consistency is 4 %, it is postulated that the bonded area recovers again by a ten minute or more treatment though the bonded area between the fibers decreased by ozone treatment at the beginning. On the other hand, when the pulp consistency is 30%, it is postulated that the bonded area between the fibers increased by extending the ozone treatment time. In the ozone bleaching,

there is a report⁷⁾ that the strength properties was retained even if the viscosity of the pulp significantly decreased due to the bleaching process. Also in this experiment, the ozone treatment did not become a factor decreasing the sheet strength in spite of the fact that the limiting viscosity number of the pulp significantly decreased by the treatment.

3.5 Ozone treatment of fine quality grade waste paper

Table 4 shows the change in the TX and EOX by the deinking treatment of the fine quality grade waste paper which is printed using a color toner. When the deinking treatment was done after the ozone treatment was carried out for five minutes at a 4 % pulp consistency, the TX and EOX included in the waste-paper pulp was slightly decreased compared with the case treated only by the usual deinking. There is a possibility to decrease the chlorine compound in the wastepaper pulp by further adjusting the ozone treat-

Fig.9 Changes in residual ink area and ink particle count per mm² during deinking with or without ozone treatment

Table 4 Total halogen and ethanol extractable organic halogen of recycled pulps from color-copied paper

	TX (ppm)	EOX (ppm)
Blank	1,000	61
Before deinking	410	42
After deinking	380	38
After deinking with ozone tr.,*	350	36

*Deinked sample treated for 5 min. with 4% pulp consistency.

ment conditions. Figure 9 shows the measurement results of the ink particle count and the residual ink area on the handsheet by image analysis. Due to the ozone treatment, the ink particle count and the residual ink area decreased and the deinking capability of the fine quality grade waste paper was improved. This result coincides with the report⁸⁾ concerning the deinking of the waste paper which utilizes the ozone treatment.

4. Conclusions

The ozone treatment experiment was done using chlorine bleached pulp and fine quality grade waste-paper pulp to investigate the quantitative changes in the chlorine compound included in the pulp, and to decreasing it. In conclusion, the following results have been obtained.

(1) A large amount of chlorine compounds remained in the chlorine-bleached pulp compared with the ECF bleached pulp, and the tendency was particularly remarkable in the hardwood pulp.

(2) The amount of the organic chlorine compound in the pulp decreased by ozone treating the chlorine-bleached pulp.

(3) The amount of the chlorine compound decreased by raising the concentration of the pulp during the ozone treatment. In this case, the tendency of

improving in the brightness and increasing the sheet strength was observed.

(4) The ozone treatment has enabled us to promote the deinking of waste paper from offices and to decrease the amount of chlorine compounds in the pulp.

Acknowledgement

The loan of the ozonizer by Ishikawajima-Harima Heavy Industries Co. Ltd. is gratefully acknowledged.

References

- 1) D. W. Reeve, P. F. Earl : Pulp & Paper Canada 90 (4) T 128 (1989)
- 2) D. W. Reeve : Tappi J. 74 (2) 123 (1991)
- 3) D. W. Reeve : Tappi J. 75 (2) 63 (1992)
- 4) Zensaku Abe, Pierre O. Ljungquist, Filipe de Sousa, Knut P. Kringstad : Mokuzai Gakkaishi 39 (10) 1169 (1993)
- 5) A. A. Chapman, K. L. Nguyen, R. A. Cook : J. of Pulp and Paper Science 25 (7) 264 (1999)
- 6) C. Shuerch, Z. Osawa : Japan Tappi Journal 21 (1) 13 (1967)
- 7) Kengo Magara, Isao Takano, Shuji Hosoya : Japan Tappi Journal 51 (12) 110 (1997)
- 8) Hiroyuki Yamaguchi, Tokiya Yaguchi : Japan Tappi Journal 50 (8) 105 (1996)

(received : '00.8.22)

漂白クラフトパルプ及び古紙パルプのオゾン処理

東京農工大学 農学部 山本 諭
 富士ゼロックス株式会社 メディア研究開発部 古賀 千鶴、細村 弘義
 東京農工大学 農学部 岡山 隆之

近年、クラフトパルプ漂白工程から排出される有機塩素化合物の環境への影響が指摘され、塩素系漂白剤の使用を抑制する傾向にある。しかし、これらの有機塩素化合物は、漂白パルプ並びに紙製品中に残存することが確認されており、紙製品が紙ごみとして焼却処分されることを考えると、低減の必要がある。本研究では、市販の塩素漂白パルプ並びにカラーコピーされた上質系古紙パルプをオゾン処理し、塩素化合物量の指標として全ハロゲン (TX) 及びエタノール抽出有機ハロゲン (EOX) を、また、パルプ及びシートの性質として ISO 白色度、銅エチレンジアミン法による極限粘度数、保水度、引張強さなどを測定した。

オゾン処理はオゾンをパルプスラリーと接触させることにより行い、処理温度 10℃、処理時間を 5, 10, 20 分とし、処理時のパルプ濃度は 4 %, 30 % とした。塩素漂白パルプ中の TX 及び EOX の量は ECF 漂白パルプに比べて大きかったが、オゾン処理を施すことによってその量を低減できた。上質系古紙パルプにおいても、通常の脱インキパルプに比べ、オゾン処理を施したパルプの方が TX, EOX ともに低い値を得た。オゾン処理によって、広葉樹漂白パルプの白色度は大きく向上したが、白色度 90 % 以上のパルプの場合には低下する傾向を示した。また、パルプの極限粘度数はオゾン処理によって大幅に低下したが、手すきシートの強度特性に及ぼす影響は小さかった。

(本文 90 ページ)

フーリエ変換と相互相関法による紙の異同識別法 (第 2 報)

—市販 PPC 用紙への適用—

王子製紙株式会社 新技術研究所 篠崎 真
 警視庁 科学捜査研究所 宮田 隼
 東京大学大学院 農学生命科学研究科 中山 智仁、江前 敏晴

紙の異同識別を非破壊で行う方法として前報で画像解析を利用する方法を提唱した。すなわち、紙の光透過画像に対してフーリエ変換を施してワイヤーマークなどの周期性を特徴として抽出し、そのパワースペクトル (以下 PS と略す) の類似度を相互相関法によって定量化することによって紙の異同識別を行う方法である。

前報においては紙に周期を与える要因をモデル的にワイヤーのみに注目し、市販の実機用ワイヤー片を用いて調製した手すき紙を試料とした。今回はその実地応用例として市販 PPC 用紙への適用を試みた。

市販の 12 銘柄の化学パルプ製 PPC 用紙を用いて、原則として 1 銘柄につき 4 枚の紙片の各 3 箇所、計 12 箇所に対して光透過画像の FFT を施した。その 12 枚の PS を単純平均したものをもその銘柄の代表的な画像、すなわち参照ファイルとし、参照ファイルの群をデータベースとした。

また試料ファイルとしては、参照ファイルと同一の 12 銘柄から 1 枚ずつ別の紙片をとり、それぞれの 3 箇所を FFT 処理しその 3 枚の PS を単純平均し各試料ファイルとした。

異同識別のアルゴリズムとしては前報と同じ相互相関法を採用した。類似度の計算の際に長波長成分のパワー値が短波長成分に比較してきわめて大きいことを考慮して 1.63 mm 以上の波長のパワーをすべて 0 とした。