研 究 報 文

リサイクル処理によるパルプ繊維の結晶化度及び再膨潤能力の変化

東京大学大学院 農学生命科学研究科生物材料科学専攻製紙科学研究室 カンタヤースウォン ソムワン*
江前敏晴, 磯貝 明, 尾鍋史彦

Changes in Crystallinity and Re-swelling Capability of Pulp Fibers by Recycling Treatment

*Khantayanuwong Somwang**,

Toshiharu Enomae, Akira Isogai and Fumihiko Onabe

Paper Science Laboratory, Department of Biomaterial Sciences,
Graduate School of Agricultural and Life Sciences, The University
of Tokyo, Japan

* Present address : Faculty of Forestry, Kasetsart University,
Bangkok, Thailand

カンタヤースウォン ソムワン

江前敏晴

磯貝 明

尾鍋史彦

An integrated technique was purposed for clarifying changes in amounts of amorphous and crystalline regions of fibers as well as for estimating possibility of their irreversible conversion due to recycling treatment. The crystallinity of fibers in handsheets was moderately changed by the recycling treatment as observed by X-ray diffractometry. Because major part of fibers consisting of the stable crystalline region which was hardly affected by the recycling treatment, the change in crystallinity possibly stemmed from a slight increase in crystallinity of amorphous region of fibers during recycling. The decrease in the amount of the amorphous region by the recycling treatment, which affects the water adsorbability of fibers, was indirectly detected by differential scanning calorimetry. Because of the lack of re-opening of recycled fiber lumens in a wet state, the amount of bound water adsorbed to fiber wall substantially influenced the re-swelling capability of recycled fibers. The loss in re-swelling capability of wet recycled fibers was consistent with sub-morphological changes of fiber wall possibly due to the decrease in the amount of the amorphous region. In this study, FT-Raman spectroscopy could not detect the effect of recycling treatment on changes in amounts of amorphous and crystalline regions of fibers.

Keywords : Amorphous region, Crystallinity, Recycling treatment, Re-swelling capability

分類 : Y₂ 材木化学, G₁ 古紙一般, A₂ 木材の特性 (組織学的性質, 化学的性質)

1. Introduction

Microfibrils in bleached chemical pulp fibers consist of two regions of cellulose: crystalline and amorphous¹⁻³⁾. The crystalline region is normally very stable with highly ordered cellulose molecules hardly accessed by water molecules. On the other hand, water molecules could access and adsorb to the amorphous region consisting of less-ordered cellulose molecules. Because a trace amount of adsorbed water on the surface of crystalline region is almost negligible, the amount of adsorbed water in fibers, which is also called "bound water", almost totally relies on accessible sorption sites of amorphous region¹⁾. Therefore, determination of the amount of amorphous region of fibers can be conducted by differential scanning calorimetry (DSC) that is commonly used for determining the amount of bound water in fibers^{1,4)}. For a study focusing on the crystalline region of fibers, one of the methods typically used is X-ray diffractometry^{3,5,6)}. This method can be used for determining ratios of crystalline region as a crystallinity index that is basically proportional to the peak intensity ratio of reflected X-ray, which is derived from the 200 plane, for the crystalline region to that for the total regions.

As the advantages of these methods are specifically characterized by measurement of either the amount of amorphous or crystalline region, it seems to be doubtful about using them separately for determining changes in amounts of both the regions and discussing their irreversible conversion due to recycling treatment. Though some researchers⁷⁾ stated the possibility of FT-Raman spectroscopy to detect and distinguish the proportional changes in amounts of amorphous and crystalline regions in cellulosic materials conditioned by some chemical and biochemical treatments, it has rarely been applied to study a stepwise effect of recycling treatment on changes in amounts of both the regions of fibers as in a case of DSC.

Therefore, it is the purpose of the present paper to provide an integrated technique of DSC, FT-Raman spectroscopy, and X-Ray diffractometry, which are possibly useful to clarify changes in amounts of amor-

phous and crystalline regions of fibers including their irreversible conversion due to the recycling treatment. Furthermore, because the re-swelling capability of dried fibers seems to be caused by two phenomena, i.e. the displacement of morphological features in fibers and sub-morphological swelling caused by bound water⁸⁾, the effect of recycling treatment on re-swelling capability of fibers which is probably related to the amount of bound water in fibers is also demonstrated.

2. Materials and methods

Handsheets R0 were made from a virgin hardwood bleached kraft pulp beaten to a freeness of 480 ml/CSF (Canadian Standard Freeness), according to TAPPI test methods. As a model of paper recycling process⁹⁾, some of them were treated in a well-ventilated electric oven at 105°C for 24 hours and then soaked in de-ionized water for 24 hours before disintegration for making handsheets R1 (recycled once).

This procedure is called "recycling treatment" hereafter. The recycling treatment was repeated for one, two and three more cycles to produce handsheets R2, R3 and R4 from some of handsheets R1, respectively. Every handsheet was conditioned at 23°C and 50% relative humidity for two months, according to Japanese Industrial Standards (JIS). The amount of bound water and crystallinity were determined by using a differential scanning calorimeter (Pyris 1, Perkin Elmer Instrument Inc., USA) and an X-ray diffractometer with Cu K α radiation (RINT 2000, Rigaku, Japan), respectively, with six replications for sheets chosen randomly from conditioned handsheets R0-R4. Small pieces of the rest of handsheets R0-R4 were soaked in de-ionized water for 24 hours and then disintegrated to fiber slurries for determining the aspect ratio of wet single fibers by using a confocal laser-scanning microscope (LSM 510, Carl Zeiss Jena GmbH, Germany). Seventy single fibers were observed for each fiber slurry¹⁰⁾. FT-Raman spectroscopy (Magna-IR 860 equipped with Raman accessory, Nicolet Instrument Co., USA) was also attempted for determining changes in amounts of amorphous and crystalline re-

gions of fibers in the handsheets.

3. Results and discussion

The pattern of X-ray diffraction of a handsheet, as shown in Fig. 1, was used for calculating a crystallinity index following the empirical method of Segal et al⁶⁾. As can be seen in Fig. 2, the crystallinity indices of

Fig. 1 Calculation method for X-ray crystallinity index by using the empirical method of Segal et al⁶⁾.

Fig. 2 Effect of the recycling treatment on crystallinity index of fibers in the handsheets. A pair of bars denotes a range of 95% confidence level.

handsheets appear to be moderately changed by the recycling treatment. This result indicates that the crystalline region of cellulose, which is major part of bleached kraft pulp fibers^{1,11,12)}, in the handsheets was quite stable and hardly affected by the recycling treatment. The moderate change in crystallinity index of fibers in the handsheets was possibly reflected by some changes of amorphous region of fibers as the remarkable change in structure of amorphous region of natural cellulose untreated with any chemicals is probably influenced easily by the recycling treatment. As demonstrated in the research of Isogai et al.³⁾, the regenerated amorphous cellulose, which is stable under aqueous conditions as the amorphous region in cellulosic materials, can be changed in its structure to be higher crystallinity and possessed lower water accessibility by irreversible hydrogen bonds formation due to hydrothermal and dry thermal treatments, respectively. Matsuda et al¹³⁾ also confirmed that heat treatment promoted hardwood bleached kraft pulp fibers lower water accessibility with the increased irreversible hydrogen bonds in some part of amorphous region in the fibers. These increased irreversible hydrogen bonds are suggested to be a cause for sub-morphological changes of fiber wall^{8,14)}. Therefore, some part of the amorphous region of fibers in the present study could possibly be also distorted to lose in their water adsorbability, i.e. due to irreversible hydrogen bonds formation, by the thermal condition in the recycling treatment. This part of the amorphous region lost in water adsorbability is named as "distorted amorphous region" hereafter.

Fig. 3 demonstrates the noticeable changes in broad endothermic peak areas of handsheets, which were measured by using DSC, due to the recycling treatment. The endothermic peak area attributed to the heat of dehydration of bound water (ΔH) of handsheets was calculated based on dried weight of samples following the procedure suggested by Bertran and Dale¹⁾. According to our previous research⁹⁾, the same recycling treatment performed in this study gave handsheets with constant and fairly small amounts of fines content. The negligible loss in carbohydrates of kraft pulp fibers during recycling is also credible¹⁵⁾. Therefore, the change in ΔH values considerably relied on the change in the amount of bound

Fig. 3 DSC patterns of bound water of fibers in the handsheets.

Fig. 4 Effect of the recycling treatment on ΔH values of fibers in the handsheets. A pair of bars denotes a range of 95% confidence level.

water adsorbed to fibers in the handsheets. Fig. 4 shows the decrease in ΔH values of fibers in the handsheets was affected by the recycling treatment. As can be seen, even though the ΔH value of R0-fibers was not statistically different from that of recycled fibers, the ΔH value of the recycled fibers was significantly decreased when they were recycled for three more times from R1 to R4-cycle. This result possibly demonstrates that the inferior adsorbability

of water of recycled fibers was influenced by irreversible hydrogen bonds of distorted amorphous region in the fibers which were increasingly formed remarkably through the heating stage of the recycling treatment^{3,13)}.

Even though the decrease in ΔH values represented mostly the increase in the amount of distorted amorphous region of fibers that was induced by the heating stage of the recycling treatment, the good relationship between the crystallinity index and the ΔH value was still in an agreement as demonstrated in Fig. 5. As can be seen, the fibers with high values of crystallinity index have low values of ΔH , i.e. they also have low water adsorbability possibly by increasing in crystallinity of the amorphous region. The increase in crystallinity of amorphous region in the fibers was possible during recycling because the hydrothermal condition was possibly induced, during the initial stage of heating in the recycling treatment, with the moisture content of fibers mostly consisted of bound water adsorbed to the amorphous region³⁾. However, this phenomenon was likely to cause the crystallinity index of fibers in the handsheets to change very slightly by the recycling treatment, which was hardly determined by conventional X-ray diffractometry, as shown in Figs. 1 and 2.

Figs. 6, 7 and 8 represent the measurement method, the mean values, and the frequency distribution of the

Fig. 5 Relationship between crystallinity indices and ΔH values of fibers in the handsheets.

Fig. 6 Measurement of aspect ratio of wet single fiber by using a confocal laser-scanning micrograph.

Fig. 7 Effect of the recycling treatment on aspect ratio of wet single fibers. A pair of bars denotes a range of 95% confidence level.

aspect ratio of wet single fibers, respectively. Because fully swollen wet fibers with almost completely round cross-sections gave the values of aspect ratio close to 1.00, most of the wet R0-fibers were more swollen than those of the wet recycled ones. Moreover, most of the wet recycled fibers were also irreversibly collapsed after the first recycling time. This phenomenon was similar to the result in our previous research⁹⁾ in which recycling treatment was conducted for the same kind of chemical pulp fibers. Therefore, the re-swelling capability of wet recycled fibers considerably depended on their cell wall swelling because of the lack of re-opening ability of their lumens.

Fig. 9 demonstrates the relationship between the ΔH value and the value of the aspect ratio. As can be

Fig. 8 Distribution of aspect ratio of wet single fibers affected by the recycling treatment.

Fig. 9 Relationship between aspect ratios and ΔH values of fibers.

seen, at low ΔH values, i.e. small amounts of bound water were adsorbed to fibers, the fibers had a less swelling capability. Because wet fibers could be swelling when the internal strain relaxation of cellulose microfibrils in fiber wall is caused by introducing water molecules to the amorphous region¹⁰⁾, this result confirms that the re-swelling capability of recycled fibers collapsed even in the wet state relied strongly on the amount of bound water adsorbed to their cell wall. In other words, the loss in re-swelling capability of recycled fibers was consistent with the loss in the amount of bound water adsorbed to their cell wall, which was

possibly caused by the increase in crystallinity and distorted part of amorphous region, as is known as sub-morphological changes of fiber wall⁶⁾. In fact, the increase in crystallinity and distorted part of amorphous region certainly reduced the amount of the amorphous region which could be adsorbed by water molecules. As a result, both the ΔH value and the value of aspect ratio could reflect highly sensitively the changes in physical features of fibers affected by the recycling treatment. This finding is proved by the fact that there were certain differences demonstrated significantly among the recycled fibers with both the parameters as shown in Figs. 4 and 7. Especially for the DSC, it could probably show that the recycling treatment gave the fibers more uniformity as statistical confidence levels of the ΔH values were gradually narrowed with recycling times, as also demonstrated in Fig. 4. The evaluation method of X-ray diffractometry seems to be lacking in sensitivity of this phenomenon as previously mentioned above and shown in Figs. 1 and 2.

Fig. 10 shows the intensity and pattern of FT-Raman spectrum of R0-fibers were similar to those of FT-Raman spectrum of R4-fibers. Because changes in intensity of FT-Raman spectrum at 900 and 1098 cm^{-1} represent changes in amounts of amorphous and crystalline regions, respectively⁷⁾, therefore, the FT-

Fig. 10 Similarity between FT-Raman spectrum of R0-fibers and that of R4-fibers.

Raman spectroscopy was found not suitable for determining the change in the ratio of amorphous and crystalline regions in the fibers affected by the recycling treatment. This is possibly caused by the fact that the ratio was not statistically different between R0- and R4-fibers, as shown in Figs. 2 and 4, and not caused by changes in chemical aspects of fibers due to the recycling treatment. Moreover, a possible cause for the similarity of the two FT-Raman spectra is that the sample preparation and treatments in the present study were different from those in others' research.

4. Conclusion

The crystallinity index of fibers in the handsheets was moderately changed by the recycling treatment. This phenomenon is suggestively caused by some part of amorphous region of fibers in the handsheets was slightly changed to be higher crystallinity during recycling. Because of the lack of re-opening of recycled fiber lumens in the wet state, the amount of bound water adsorbed to fiber wall substantially influenced the re-swelling capability of recycled fibers. The loss in re-swelling capability of recycled fibers was consistent with the loss in the amount of bound water adsorbed to their cell wall, which was possibly caused by the loss in the amount of the amorphous region which could be adsorbed by water molecules, as is known as sub-morphological changes of fiber wall. Only the DSC and the measurement of the aspect ratio of wet single fibers could sensitively determine the changes in physical features of fibers affected by the recycling treatment. The FT-Raman spectroscopy was found not suitable for determining the effect of recycling treatment on the changes in amounts of amorphous and crystalline regions of fibers.

Acknowledgements

The authors are indebted to Professor Shigenori Kuga and Mr Yasutomo Noishiki, Department of Biomaterial Sciences, Graduate School of Agricultural and Life Sciences, The University of Tokyo, for their useful advices on the DSC operation.

References

- 1) Bertran M. S. and Dale B. E. : J. Appl. Polym. Sci. 32 4241-4253 (1986)
- 2) Young R. A. : Cellulose-Structure, modification

- and hydrolysis, eds. by Young R. A. and Rowell R. M., John Wiley and Sons, New York, 1986, Chapter 6
- 3) Isogai A., Akishima Y., Onabe F. and Usuda M. : Sen-i Gakkaishi 47 (11) 573-579 (1991)
- 4) Nakamura K., Hatakeyama T. and Hatakeyama H. : Text. Res. J. 51 (9) 607-613 (1981)
- 5) Isogai A. and Usuda M. : Sen-i Gakkaishi 46 (8) 62-67 (1990)
- 6) Segal L., Creely J. J., Martin Jr. A. E. and Conrad C. M. : Text. Res. J. 29 (10) 786-794 (1959)
- 7) Stewart D., Wilson H. M., Hendra P. J. and Morrison I. M. : J. Agric. Food Chem. 43 2219-2225 (1995)
- 8) Weise U. and Paulapuro H. : J. Pulp Pap. Sci. 25 (5) 163-166 (1999)
- 9) Somwang K., Enomae T. and Onabe F. : Japan Tappi J. 56 (2) 239-245 (2002)
- 10) Nakamura K., Hatakeyama T. and Hatakeyama H. : Text. Res. J. 53 (11) 682-688 (1983)
- 11) Kolseth P. and Ruvo A. D. : Paper structure and properties, eds. by Bristow J. A. and Kolseth P., Marcel Dekker Inc., New York, 1986, Chapter 1
- 12) Scallan A. M. and Tigerstrom A. C. : J. Pulp Pap. Sci. 18 (5) J 188-J 192 (1992)
- 13) Matsuda Y., Isogai A. and Onabe F. : J. Pulp Pap. Sci. 20 (11) J 323-J 327 (1994)
- 14) Lindstrom T. : Paper structure and properties, eds. by Bristow J. A. and Kolseth P., Marcel Dekker Inc., New York, 1986, Chapter 5
- 15) Ackermann C., Gottsching L. and Pakarinen H. : Papermaking science and technology : Recycled fiber and deinking, eds. by Gottsching L. and Pakarinen H., Fapet Oy, Helsinki, 2000, Chapter 10

(accepted : '01.8.27)

てコメの最大の輸出業者であるスーン・ファ・セン財閥がユーカリの植樹から紙パルプ産業に乗り出し、最大の生産能力を誇るアドバンス・アグロ社をスタートさせたことで業界は大きく変わった。すなわち、非木材ベースからユーカリベースの近代的な紙パルプ産業に形質が変わったのである。そして、タイ国の紙生産総量は年産 365 万トンとなり、これは需要量の 200 万トンを凌駕するところとなった。言い換えれば、タイ国は新聞用紙など一部の種類を除けば、全体的には紙の輸出国となっているのである。タイはアジア通貨危機の時、一時的に経済不況に襲われたが、日本よりも速くこの不況を脱しつつある。最後に、日本の紙パルプ企業のタイ国進出例として、天満製紙、阿波製紙、王子製紙の海外活動について言及した。

(本文 78 ページ)

OM, SEM, EPMA による観察及び分析のための紙の断面作製技法

(2) SEM, EPMA 用断面作製技法

濱田 忠平

前稿の光学顕微鏡用に引き続き、本稿では SEM, EPMA 用の断面作製技法について述べる。SEM, EPMA では通常はバルク試料を取り扱うため、OM のように包埋して薄い切片を作製する必要はないが、切片作製後包埋剤を除去しないとコントラストのある鮮明な像が得られない。したがって OM の場合には最も一般的なエポキシ樹脂は脱包埋が困難なため、あまり適当ではなく、また包埋処理や脱包埋処理中に紙の成分や印刷インキなどが溶出したり、変質するが多い。そこで包埋せずに紙層構造の変化をできるだけ少なくする切断法が試みられた。この中で筆者らの確立した 2 枚の塩化ビニル板の間に試料をはさんで切断する方法によれば、包埋せずに大部分の紙の良好な切断面を作製することができ、サブミクロンの領域での紙の断面の観察や分析が比較的簡単にできるようになった。しかし含浸加工用原紙、ティシュペーパーなどの非常にかさ高な試料や薄くて凹凸の著しい試料には不適当で、またより高倍率の観察や分析には微小部分の脱落などが発生しやすい欠点があった。

最近、収束イオンビーム (FIB) を使用した新しい手法がこの分野に導入され、無包埋でより精度の高い紙の断面の作製ができるようになった。しかしこの方法は装置が非常に高価なため、より普及させるためにはより安価な装置の出現が望まれる。

(本文 85 ページ)

リサイクル処理によるパルプ繊維の結晶化度及び再膨潤能力の変化

東京大学大学院 農学生命科学研究科生物材料科学専攻製紙科学研究室

カンタヤヌウォン ソムワン, 江前敏晴, 磯貝 明, 尾鍋史彦

各種分析技術を総合的に用いることによって、リサイクル処理による非晶及び結晶領域量の変化を明らかにし、同時にそれらが不可逆的に転換する可能性を評価した。X 線回折法で観察されるように、リサイクル処理によって繊維の結晶化度は幾分変化した。繊維の大部分は、リサイクル処理による影響をほとんど受けない安定した結晶領域からできているので、結晶化度の変化は、おそらくリサイクル中に非晶領域がわずかに結晶化することに起因するのであろう。リサイクル処理による非晶領域量の減少は、繊維の水分吸着能力に影響するが、これが示差走査熱量計によって間接的に検出された。リサイクル繊維のルーメンは、湿潤状態でも潰れたままであり開くことは少ないので、繊維壁に吸着する結合水の量は、リサイクル繊維の再膨潤能力に多大な影響を与えていることがわかった。湿潤リサイクル繊維の再膨潤能力の低下は、非晶領域量の減少によると考えられる、形態変化には現れないような繊維壁の微小

な変化に対応していた。本研究では、フーリエ変換ラマン分光法によって、リサイクル処理が繊維の結晶及び非晶領域量の変化に与える影響を決定することはできなかった。

(本文 103 ページ)

高速抄紙に適した歩留まりシステム

日本製紙株式会社 技術研究所 上條 康幸, 宮西 孝則

凝結剤と凝集剤を組み合わせたデュアルシステムに関して、光度分散分析器 (PDA) と動的濾水度測定装置 (DDA) を用いて、凝集性や濾水性について検討を行なった。

その結果、凝集剤を単独で使用するシングルポリマーシステムと比較して濾水性、ファインの再凝集性が優れている結果が得られた。これは初めに添加される凝結剤がファイン表面上に存在するアニオン性部位の電荷を中和して (サイト・ブロッキング効果)、後から添加する凝集剤のファイン表面での吸着形態の変化を抑制するためであると考えられる。またデュアルシステムは、先に添加する凝結剤が、繊維表面を中和する役割を果たしているが、時間の経過に伴い、ファイン細孔内への拡散などによりカチオン電荷を失う。従って凝結剤と凝集剤の添加間隔を短くするほど薬品の添加効果が高められる。

紙質について検討を行なったところ、DDA で得られる濾水時間とシート透気度には相関が認められた。濾水性が向上するほど紙層内に細かい細孔が形成され、濾水性が向上するほどシートの透気度が低下する結果が得られた。地合の悪化が認められないことから、この歩留まりシステムを用いることにより印刷適性の優れた紙を抄造できる可能性が示唆される。

以上の結果より、シングルポリマーシステムと比較してデュアルシステムは凝集性、濾水性に優れており、紙料に対するせん断力が高い高速抄紙に対応する歩留まりシステムであると考えられる。

(本文 110 ページ)