Surface Analysis of Silica Gel Particles After Mechanical Dry Coating with Magnesium Stearate[†]

Laurence Galet^{1*}, Yamina Ouabbas², Alain Chamayou¹, Philippe Grosseau², Michel Baron¹, Gérard Thomas²

Ecole des Mines d'Albi-Carmaux¹

Ecole Nationale Supérieure des Mines de Saint Etienne²

Abstract

A dry coating technique has been used to change the surface properties of silica gel particles ($d_{50}=55\mu\text{m}$) by coating with different mass ratios of magnesium stearate - MgSt_2 ($d_{50}=4.6\mu\text{m}$): 1%, 5%, 15% and 30%. The dry coating experiments were performed using a "Hybridizer, a high-speed dry impact blending coater", manufactured by Nara Machinery (Japan). The surface morphology of the uncoated and coated silica gel particles was observed by environmental scanning electron microscopy (ESEM). The images show that a greater MgSt_2 coverage was observed on the surface of silica gel as the MgSt_2 mass ratio is increased. In addition, atomic force microscopy (AFM) analysis revealed how this coating process makes possible a discrete and uniform dispersion of the MgSt_2 particles. AFM studies were carried out with a scanning probe microscope Multimode Nanoscope IIIA (Digital Instruments/Veeco Metrology Group).

Keywords: AFM phase imaging, adhesion force, dry coating, silica, magnesium stearate

1. Introduction

Dry particle coating to change the surface properties of powders is very important in many industries. Typical applications include, but are not limited, to flowability, wettability (hydrophobic/hydrophilic properties), solubility, dispersibility, flavour, shape, electrostatic, optical, electric, magnetic, etc. In dry particle coating processes, materials with relatively large particle size (host particles; 1-500 μm) are mechanically coated with fine particles (guest particles; 0.1-50 μm) in order to create new functionality or to improve their initial characteristics¹⁾. Since the size of the guest particles are so small, van der Waals interactions are strong enough to keep them firmly attached to the host particles. Thus, either a discrete or continuous coating of guest particles can be achieved depending on a variety of operating conditions includ-

ing processing time, rotation speed, weight fraction of guest to host particles and particle properties²⁾. **Fig. 1** below is a simple schematic illustrating the process of dry particle coating.

Over the last few years, we have performed experimental investigations of applications of the dry coating technique to study the effect of mechanical dry coating on the surface properties of powders. Our recent work is related to the modification of the flowability and the wettability properties of silica gel particles coated with different weight ratios of magnesium stearate by using a high energy impact coater Hybridizer from Nara Machinery³⁾ and a high shear mixer Cyclomix from Hosokawa⁴⁾. For example, the flowability of the silica gel powder was significantly decreased after treatment in the Cyclomix mixer with 15% of MgSt_2 . Moreover, it has been found that the coating by hydrophobic MgSt_2 in the Cyclomix can reduce the high affinity between silica gel and water after treatment with 5% and 15% of MgSt_2 . In those papers, it has been demonstrated that a dry particle coating technique can be used to modify the properties of silica gel powder by coating with small quantities of hydrophobic magnesium stearate in both the Hybridizer and the Cyclomix. The more uniform

[†] Accepted: September 23, 2010

¹ Centre RAPSODEE, UMR CNRS 2392
Campus Jarlard 81013 Albi Cedex 9, France

² Centre SPIN - LPMG - UMR CNRS 5148
158 Cours Fauriel 42023 Saint-Etienne Cedex 2, France

* Corresponding author

E-mail: laurence.galet@mines-albi.fr

TEL: +33 5 63 49 32 35 FAX: +33 5 63 49 30 25

Fig. 1 Schematic principle of dry coating.

coating has been obtained after treatment in the Hybridizer device.

In this paper, we report an investigation of the surface analysis of the coated silica gel particles using atomic force microscopy in tapping mode (TM-AFM) and contact mode (CM-AFM). The TM-AFM method, based on the measurements of the oscillations of a cantilever probe in contact on the sample, has been used for several years to characterize the surface topography of particles. In particular, phase contrast images are related to characterize the attractive and repulsive probe sample interactions⁵⁾, the sample surface components⁶⁾ and the morphology of composite particles⁷⁾. The CM-AFM method consists in using a colloidal probe fixed on the cantilever to quantify the adhesion force between the particles. As an example, Kani et al report an interesting study on the silica-mica adhesion force as a function on the presence of impurities on the silica particles⁸⁾. Meincken et al. report a relationship between contact angle analysis and adhesive forces measurements by the AFM technique in a study of the surface hydrophobicity of polyurethane coatings⁹⁾. This technique has been also used to characterize the adhesion properties of pharmaceutical carriers¹⁰⁾. In our case, we performed AFM phase-contrast and adhesion forces measurements to characterize the surface of silica particles as a function of the magnesium stearate

mass ratio (1 to 30%).

2. Experimental

2.1 Powders

Silica gel powder supplied by Merck and usually used for filling chromatography columns has been chosen as host particles for dry coating (Silica gel 60, 0.040-0.063 mm). The volume distribution of silica gel shows a population of large particles with median diameter (d_{50}) of about 55 μm . Hydrophobic magnesium stearate (MgSt₂) supplied by Chimiray is used as guest particles. The MgSt₂ is a fine, white, greasy and cohesive powder widely used in pharmaceutical formulation as a lubricant. A wider size distribution is observed for MgSt₂ particles. The size of MgSt₂ particles varies between 20 μm to less than 1 μm with a median diameter (d_{50}) of about 4.6 μm . The main properties of host and guest particles are reported in the **Table 1**.

2.2 Coating process

The hybridization system (HB, type NHS-0; Nara Machinery Co.), a high-speed dry impact blending coater, has been used to make the silica gel-MgSt₂ composite particles. The reactor consists in a very high-speed rotating rotor with six blades, a stator and a powder re-circulation circuit. The coating chamber

Table1 Properties of host and guest particles

Particles	Size (d_{50}) (μm) (Mastersizer 2000)	Solid density (g/cm^3) (Helium Pycnometer)	Specific surface area (SBET (m^2/g))	Pore Volume (cm^3/g)
Silica gel	55 (D_{host})	2.07 (ρ_{host})	475	0.69
MgSt	5 (d_{guest})	1.04 (ρ_{guest})	7.7	0.02

is surrounded with a jacket in which coolant is circulated¹⁾. The coating process can be summarized as follows: the powder mixture (host and guest particles) is subjected to high impaction and dispersion due to collisions with blades and the walls of the device and continuously re-circulates in the machine through the cycle tube. Particle coating is achieved due to the embedding or filming of the guest particles onto the host particles by high impaction forces and friction heat. Since the rotor of the hybridizer can rotate from 5000 to 16000 rpm, very short processing time is required to achieve coating. The operating conditions used in experiments are 4800 rpm for 5 min. The preparation of the coated particles is described in detail in previous papers 3, 4). Coating experiments have been carried out with 1%, 5%, 15% and 30% of mass fraction of guest MgSt₂ particles.

2.3 Particles characterization

The uncoated and coated silica gel particles were examined by environmental scanning electron microscopy (ESEM) to study the surface morphology and the covering by the MgSt₂ particles (XL 30 Philips). The ESEM images reveal that greater MgSt₂ coverage is observed on the surface of silica gel particles as the percentage of MgSt₂ is increased (Fig. 2). Additional investigations were done to analyse the surface atomic composition of the coated particles by X-ray spectroscopy confirming the presence of magnesium atoms when analysis is performed on a black spot¹¹⁾. At 15%, the surface coverage of the MgSt₂ is intense but seems discrete.

Thermal analysis was used to measure the MgSt₂ mass fraction after treatment (TG-DSC 11 Setaram). Samples are analyzed under nitrogen gas, from 20° C to 600° C, with a ramp of 5° C/min. Fig. 3 and 4 show the heat flow, the mass lost and the differential mass lost as a function of the temperature diagram for pure silica gel and MgSt₂, respectively. We observe that the silica gel particles have a main first mass loss of about 4-5% near 100° C, due to dehydration, and a second near of 2% 400-600° C, probably due to a thermal

decomposition. The MgSt₂ has a first small mass loss near 100° C due to dehydration and a main mass loss of 85-90% between 250° C and 450° C due to a thermal degradation. This mass loss can be used to quantify the MgSt₂ in the powder mixtures.

TG-DSC experiments have been performed on silica gel-MgSt₂ mixtures made by manual mixing (1%, 3%, 15%, 30% and 50% mass ratios). The loss of mass obtained between 250° C and 600° C as a function of the MgSt₂ ratio is reported in the Fig. 5. This result is the mean of two measurements. The results show a very good relation between the AGT-DSC mass loss (%) as a function of the MgSt₂ ratio (%). The linear relation obtained with a high correlation coefficient has been used to calculate the real composition of the coated particles after processing in the reactor with a precision of less than ± 1%.

AFM measurements were made with a Multimode Nanoscope IIIA from Veeco Metrology Group. In tapping mode, the cantilever is driven to oscillate. Height, amplitude and phase images were simultaneously recorded for each sample. Beyond the standard height imaging, the phase contrast mode is quite efficient to exhibit the main surface property differences between de silica gel and MgSt₂.

The amplitude and the frequency of the oscillations change when the tip scans on a surface. TM-AFM images are produced by imaging the oscillating contacts of the tip with the sample surface: height and amplitude images give information on the sample surface topography and phase images give information on the atomic surface composition (interaction tip-surface). The TM-AFM measurements were performed with a MPP 11100 Silcon phosphorus doped silicium tip with a spring constant of 40 N/m. Large surface scale of surface sample has been scanned: from 250×250nm² to 5×5nm², for silica gel and silica gel-MgSt₂ coated particles (1%, 5% and 15% MgSt₂ mass ratio).

In contact mode AFM, the tip scans the sample in close contact with the surface. The force between the tip and the surface sample is measured as the

Fig. 2 ESEM images of silica gel and MgSt₂-silica gel coated particles.

Fig. 3 TG-DSC diagrams for silica gel.

Fig. 4 TG-DSC diagrams for MgSt₂.

Fig. 5 Experimental relation between the TG-DSC mass loss (from 250°C to 600°C) and the mass ratio of MgSt₂.

distance, by maintaining a constant deflection. To examine the mechanism of interaction between silica gel and MgSt_2 particles, the CM-AFM measurements were performed with a NP silicon nitride tip with a spring constant of 0.32 N/m on which a MgSt_2 particle was glued under optical microscope. The adhesion forces were measured between the MgSt_2 particles attached on the end of the cantilever and the different samples of uncoated and coated particles with 1% to 30% MgSt_2 mass ratio. For each sample 450 force curves were obtained. The presence of the magnesium stearate particle on the tip was checked after each series of measurements.

Influence of the coating on the surface property of the silica gel particles was also studied. The sessile drop method was used to study the wettability of the different samples. We report the contact angle value of a water drop (10 ml) deposited on different particulate systems: pure silica gel, pure MgSt_2 and coated particles. The method performed is described in details in previous papers^{3,4}.

3. Results and Discussion

The real concentration of the MgSt_2 after coating is calculated from the TG-DSC measurements and the calibration straight line shows in **Fig. 5**. The results are reported in the **Fig. 6**. This loss of MgSt_2 , due to a deposit of MgSt_2 on the coating chamber surface, varies as a function of the introduced MgSt_2 mass ratio. That is from 30% for the sample containing initially 30% of MgSt_2 in the mixture, to 40% for the sample

containing initially 5% MgSt_2 in the mixture.

The phase imaging TM-AFM characterisations of the samples are reported in **Fig. 7**. Concerning the MgSt_2 , the amplitude image reveals an irregular surface topography. The phase contrast image shows various levels of phase contrast (black and white areas), which can reach 50° . The silica gel particles have a more regular surface topography, formed by spherical micro beads (about 100 to 600 nm) and a low phase contrast only due to the topography (from 0° to 10°). The analyses of the silica- MgSt_2 coated particles clearly reveal a modification of the surface due to the presence of the magnesium stearate, even at 1% of MgSt_2 introduced. With a MgSt_2 initial mass ratio of 15%, both the amplitude and the phase contrast images evolve into the pure MgSt_2 images. For the coated particles, the part of the image characterized by high phase angles can be attributed to the presence of MgSt_2 layers on the surface of silica gel.

The contact mode analyses bring some pertinent information about the silica gel covering by the magnesium stearate. **Fig. 8** gives an adhesion force-displacement curve for the pure products. The force measured between a particle of MgSt_2 fixed onto the AFM tip is about 10 nN for the pure silica gel particle. That is near 120 nN for the MgSt_2 - MgSt_2 , revealing a high interaction.

The adhesion force distributions for the different particulate systems are reported in the **Fig. 9**. These distributions were obtained from 450 measurements of each particulate system. This force varies proportionally to the quantity of MgSt_2 introduced and

Fig. 6 Real mass fraction of MgSt_2 after the coating process calculates from the mass loss.

Fig. 7 TM-AFM images of MgSt_2 , silica gel and silica coated with 1% and 15 % initial mass ratios of MgSt_2 ($2 \times 2 \mu\text{m}^2$).

Fig. 8 Force curves F (N/m) as a function of the distance z (μm) measured with MgSt_2 stuck on the tip for pure silica gel and pure MgSt_2 .

Fig. 9 CM-AFM adhesion force distribution obtained with 450 analyses for different particulate systems.

confirms the increasing presence of the MgSt_2 on the silica gel surface when the mass ratio increases. For the coated particles, the number of high adhesion forces increased as the mass ratio of MgSt_2 increases. The mean adhesion force between the MgSt_2 particles attached on the end of the cantilever and the MgSt_2 sample (68 nN) was stronger than for the silica gel sample (8 nN). The large distribution of the adhesion forces confirm the discrete deposition of the MgSt_2 particles onto the surface silica gel particles as observed by the ESEM images.

The mean adhesion force calculated from the 450 measurements for each system is reported in the **Table 2**. The results show an increasing of the mean value of the force as a function of the increasing of the MgSt_2 concentration. The mean adhesion force seems to evolve progressively to the mean value of the pure MgSt_2 (**Fig. 10**). This no linear evolution could be due to a random distribution of the MgSt_2 particles on the silica gel surface.

The affinity of water is evaluated by the behaviour of a water drop deposited on the particulate systems. The initial contact angle values are reported in **Table 3**. The **Fig. 11** shows the evolution of the contact angle as a function of the MgSt_2 ratio. We observe a increasing of the contact angle of the water drop as the presence of the MgSt_2 on the silica gel surface. This result is of course in agreement with the hydrophobicity of this compound. However, even with a low content of MgSt_2 , the contact angle measured is significantly modified: 70° and 110° for 0.1% and

1.1% MgSt_2 respectively. The surface property of the silica gel particles is modified by dry coating even with a very low ratio of MgSt_2 . This result reveal that at the water drop scale, a very few presence of MgSt_2 is enough to modify the hydrophilic property of the silica gel.

4. Conclusion

Dry particle coating can be used to create new generation materials with altered properties or new functionalities. This treatment creates a discrete or a continuous coating of fine particles on the surface of the large particle surface. In this study a Nara Hybridizer has been used as a dry coating device for the coating of silica gel particles with different mass ratios of MgSt_2 particles. ESEM observations show that MgSt_2 particles form a discrete coating onto the surface silica gel particles. The MgSt_2 surface coverage increases and the surface becomes more and more uniform as the mass ratio of MgSt_2 is increased. In addition to ESEM observations, AFM images and distributions curves of adhesion forces confirm the distribution of MgSt_2 in discrete layers onto the silica gel surface. The mean adhesion force obtained for the different particulate systems reveal a no linear evolution to the adhesion force measured for the pure MgSt_2 . From these results, we are currently working on the development of a distribution model of MgSt_2 particles onto the surface of silica gel based on the adhesion force results. The sessile drop method re-

Table 2 Mean adhesion force (nN) for different particulate systems

Sample	Mean adhesion force (nN)
Pure silica gel	8
Silica gel + 2.95 % MgSt	13
Silica gel + 9.93 % MgSt	23
Silica gel + 21.51 % MgSt	35
Pure MgSt	68

Table 3 Contact angle measurements (°) for different particulate systems

Sample	Contact angle (°)
Pure silica gel	15 ± 3
0.1 %	70 ± 7
1.1 %	110 ± 5
3.0 %	112 ± 5
9.9 %	116 ± 3
Pure MgSt	125 ± 6

Fig. 10 Mean adhesion force (nN) as a function of the sample MgSt₂ concentration.

Fig. 11 Contact angle measurements (°) as a function of the sample MgSt₂ concentration.

veals that a discrete deposition of the MgSt₂ allows a real modification of the hydrophilicity of the silica gel. Less than 3% of MgSt₂ is enough to increase the contact angle near the value of the pure MgSt₂. This additional approach confirms the efficiency of the dry coating technique to design some new composite systems with controlled end use properties.

Acknowledgements

The authors would like to acknowledge Sylvie Delconfetto for the TG-DSC measurements and Christine Rolland for the ESEM images.

Nomenclature

AFM	Atomic Force Microscopy
CM-AFM	Contact Mode Atomic Force Microscopy
ESEM	Environmental Scanning Electron Microscopy
MgSt₂	Magnesium Stearate
TM-AFM	Tapping Mode Atomic Force Microscopy

References

- 1) Yoshihara, I. and Pieper, W. (1999): Hybridization – Technology for surface modification of powders without binders, *Swiss Pharma.*, 21, 6.
- 2) Pfeffer, R., Dave, R., Dongguang, N. W. and Ramakhan, M. (2001): Synthesis of engineered particulates with tailored properties using dry particle coating, *Powder Technology*, 117, pp.40-67.
- 3) Ouabbas, Y. , Chamayou, A., Galet, L., Baron, M., Thomas, G., Grosseau, P. and Guilhot, B. (2008): Surface modification of silica particles by dry-coating: Characterization and powder ageing, *Powder Technology*, in press.
- 4) Ouabbas, Y., Dodds, J.A., Galet, L., Chamayou, A. and Baron, M. (2008): Particle-particle coating in a cyclomix impact mixer, *Powder Technology*, in press.
- 5) Chen, X., Roberts, C.J., Zhang, J., Davies, M.C. and Tendler, S.J.B. (2002): Phase contrast and attraction-repulsion transition in tapping mode atomic force microscopy, *Surface Science*, 519, pp. L593-598.
- 6) Danesh, A., Chen, X., Davies, M.C., Roberts, C.J., Sanders, G.H.W., Tendler, S.J.B. Williams, P.M. and Wilkins, M.J. (2002): *Langmuir*, 16, pp. 866-870.
- 7) Gun'Ko, V.M. et al. (2006): Composite powders with titania grafted onto modified fumed silica, *Powder Technology*, 164, pp. 153-167.
- 8) Kani, T., Tamonoki, M., Suzuki, T., Tsukada, M. and Kamiya, H. (2007): Influence on the surface-adhered nanoparticles and nanoporous structure on particle-particle interaction of silica, *Powder Technology*, 176, pp. 99-107.
- 9) Meincken, M., Klash, A., Saboa, S. and Sanderson, R.D. (2006): Influence of the viscosity and the substrate on the surface hydrophobicity of polyurethane coatings, *Applied Surface Science*, 253, pp. 805-809.
- 10) Louey, M., Mulvaney, P. and Stewart, P.J. (2001): Characterization of adhesional properties of lactose carriers using atomic force microscopy, *Journal of Pharmaceutical and Biomedical analysis*, 25, pp. 559-567.
- 11) Ouabbas, Y. (2008): Procédés mécaniques d'élaboration à sec de particules composites à propriétés d'usage contrôlées – Caractérisation et stabilité d'un gel de silice, PhD Thesis, Ecole Nationale Supérieure des Mines de Saint-Etienne, N° 467GP.

Author's short biography

Laurence Galet

Dr Laurence Galet received her Biological Engineering Engineer degree in 1991 and her PhD in Chemical Engineering in 1997 from the University of Technology of Compiègne.

She joined the Ecole des Mines d' Albi, France in 1998 and developed the solids-liquids interaction area. Her research interest in the Rapsodee Center-CNRS FRE 3213 are directed towards Chemical Engineering and the wettability assessment of particulates solids and their dispersion in liquid media.

She was awarded in 2009 "Chevalier" in the national "Ordre des Palmes Académiques", France.