The Influence of the Die-Exit Upon the Properties of Drawn Wires*

By Hiroshi Tanaka** and Makoto Sato**

If the drawing direction of the wire is not aligned with the axis of the die-hole, the wire has to be continuously bent over the die-exit. The authors' intention was to find out what influences the deflection (the angle α between the die-axis and the drawing direction) had on the properties of the wires drawn as described above. Copper and aluminium wires were used. It was determined that if α was more than 5° , hard copper wire decreased in strength, while aluminium wire became stronger. In all cases, the free looping diameter (the diameter of the wire-loop which results after the wire was drawn and thrown on the floor) sharply decreases if α was increased more than 5° , causing the wire to pile up very tightly on to the take-up drum.

(Received September 26, 1960)

1. Introduction

The general shop practice is to give some rounding or what is called "back relief angle" to the wire drawing die-exit. This is mostly determined by experience, and is regarded as important measure for insuring the easy inspection of the die-hole, preventing a knifing effect of the exit on the work, as well as for the ready regrinding of the die.

It is to be noted, however, that the wire is more or less rubbed or bent continuously over the die-exit. In other words, the axis of the die-hole is not coincidental to the drawing direction, and such an operation as to insure the perfect alignment is almost impossible, that is, the drawing direction is slightly deflected from the die-axis, deliberately or otherwise.

In the case of high speed fine wire drawing, if the foundation of the machine is not firm enough, the wire suffers from whipping which in turn causes additional deflection and it becomes more and more complicated. When drawing steel wire as well as wires of non-ferrous metals of high elasticities, the wires are sometimes drawn obliquely to facilitate the easy winding of the wire onto the drawing drums (spool, coil, etc.) as the wires acquire a natural looping tendency, and the wires themselves are prone to suffer various influences by the shapes of the die-exits.

The authors studied the mechanical properties of copper and aluminium wires after drawing through varying die-exits and with various deflections, and also studied the degree of loopings which result along the drawn wires.

2. Experimental Procedure

On the basis of experimental difficulties in which dies are made with varying exits with consistent accuracy at the remaining portions, the authors started their study with tools which are depicted in Fig. 1. (a) and (c) in Fig. 1 show the present procedures and

correspond to the actual dies (b) and (d) respectively. In (a) the wire is being drawn with α in deflection, through a die having exit-rounding r in radius, which in this case, is the radius of a cylinder (steel pin), and in (c), the wire is being drawn through a die having β in back relief, and is deflected by α . The trapezoid in (c) is a steel pillow uniform in cross section.

Fig. 1 Comparison of the use of dies in the experimental method and in actual dies.

α = angle of deflection
 β = back relief

The principal difference between the experimental and actual dies is that the former has the flat contour on which the wire is to be bent, the latter, however, has a concave contour, and both types are more or less at variance with each other. Thus, the influence of r was studied by (a), and the knifing effect of the die-exit was studied by (c).

The dies used in the following experiments are all WC, being 6° in die-taper, and a small roundness at the die-exits. In experiment (a), $r=0.65, 1.0, 2.0, 4.0$ and 6.0 mm (steel pins), and in experiment (c), $\beta=30, 75, 125$ and 180° steel pieces were used. The wires used for drawing were soft copper, hard copper of 1.2 mm in diameter, and soft aluminium of 2.3 mm in diameter, the lubricant used was rape-seed oil, and the drawing speed was 3 m/min.

As the materials were drawn with α to the die-axis, the cross section of the drawn wires became oblique, but it was also found that they were almost circular when α is less than 10° . After drawing,

** The Nikko Copper Works of The Furukawa Electric Co., Ltd.

* Given at the B Lecture Meeting of the 35th Tokyo Meeting of The Nippon Kinzoku Gakkai (Japan Institute of Metals) in 1955.

tensile strength, elongation, number of bend, twisting value were determined for all the wires mentioned above. The gauge length for the tensile strength specimen was 100mm, and the area of the cross section was calculated from the weight and specific gravity of the specimen. The bend radius was $r=2$ mm, and the number of bending unit was taken when the wire was bent 90° to each side without failure. The twisting value was determined from the 75mm gauge length wire.

3. The Effect of r on the Properties of the Wires.

Fig. 2 shows the results when soft copper wires were drawn from 1.2 to 1.1mm in diameter. β is 180° throughout and the free diameter of the bundle before drawn is 120mm in diameter. The values indicated in the figures were the mean of 3 tests.

When the wires were drawn straight ($\alpha=0$), their tensile strengths increased as are shown in the figure from the original 26.3 to 32.9 kg/mm². But if the

Fig. 2 The effects of r on the properties of soft Cu wire.

The wire after it was drawn and let free, acquires a looping tendency. This comes partly from the tendency of the wire to restore its original bundle form ever after being drawn and from the continuous bending of the wire at the die-exit by pulling it with some deflection (α). If α is great, the wire presses on the drum tightly, and if it is small, the wire springs back and becomes loose on the drum.

Such a relationship as above is of importance especially in the wire drawing shop, and the authors

Fig. 3 The effect of r and α on the tensile strength of soft Cu wire.

Fig. 4 The effects of r on the properties of hard Cu wire.

measured the free diameter of the bundle (the diameter of the bundle after its binder is removed) with the mechanical properties already mentioned.

wires were drawn with $\alpha=10$ to 20° , their tensile strengths decreased slightly and their elongations increased irrespective of the values of r . When α

was increased further, the tensile strengths of the wires again increased, and their elongations decreased.

The free-looping diameter of the predrawn wire was 120 mm in diameter, and became 750 mm after it was drawn without deflection ($\alpha=0$), showing the effect of straightening by the die, but when it was drawn between $\alpha=10$ to 20° , the free diameter was extremely reduced, and was more or less increased when α was increased beyond that value.

Let us consider the effect of r . The value of r

Figs. 5 and 6 show the results obtained when hard aluminium wires were drawn from 2.29 to 1.97 mm diameter with varying r , namely, $r=0, 0.65, 1.0, 2.0, 4.0$ and 6.0 mm. The strength of the wires, in contrast with that of the copper wires, seemed to increase with an increase in α . The effect of α was also found in this case.

4. The Effects of β

Fig. 7 shows the effects of the back relief angle β

Fig. 5 The effects of r on the properties of hard Al wire.

seemingly had no effect on the properties of the wires. Fig. 3, was derived from rearranging the values in Fig. 1, and it may be found that the effect of r is not as important as that of α .

Fig. 4 shows the results obtained for the hard drawn copper wires. The looping diameter of 190 mm before drawing was increased by passing it through the die from 1.2 to 1.1 mm diameter with $\alpha=0$ to 650 mm, and was sharply decreased when α was increased to more than 10° . The tensile strength of the wire before drawing was 49.8 kg/mm^2 , and was not increased beyond this value even after it was drawn without deflection, because it was nearly the maximum attainable strength for the hard drawn wire. With increasing values of α , the strength was gradually decreased, and when α became 30° , the tensile strength became 47 kg/mm^2 , and the elongation was adversely increased. The strength, in contrast with that of annealed wire, was not increased

on annealed copper wires. In actual practice, some roundings are often given to the die edges; for the present experiment, however, no roundings were made.

As shown in Fig. 7, α is always more influential. In Fig. 8, the tensile strengths are compared in all cases.

Figs. 9 and 10 show the results obtained for the hard copper wires with practically the same tendency as in the previous experiments.

It has been found by other experiments, that the

Fig. 6 The effect of r and α on the tensile strength of hard Al wire.

again even when α became extremely high. As in the former case, the effect of r was small, and that of α was predominant.

Fig. 7 The effects of back-relief angle β on the properties of soft Cu wire.

wire, no matter under what varying conditions it was drawn, had almost the same properties when it was finally annealed at about 450°C . This fact would

suggest that the wire does not internally suffer any visible defects by the drawing conditions mentioned above.

Fig. 8 The effect of β and α on the tensile strength of soft Cu wire.

Fig. 9 The effects of back relief angle β on the properties of hard Cu wire.

Fig. 10 The effect of β and α on the tensile strength of hard Cu wire.

5. Considerations on the Effects of α and r .

Let xx' in Fig. 11 be the wire being drawn, P the simple drawing force and P' the drawing force required for drawing the wire over the steel pin r in

diameter, making α to the die-axis, then we have,

$$P' = P e^{\mu \alpha}$$

where e is the base value of the natural logarithm

Fig. 11

and μ is the coefficient of friction between the wire and the pin. The heat due to frictional work on the pin by drawing the wire 1 in length may be $P'1 - P1$, which can be affected by α and not by r .

By increasing the value α , the heat developed by frictional work will also increase, and the self-annealing effect or the softening effect of the wire will be more marked (if softening be at all justified in this manner), if the softening effect is more influential than the hardening effect of the wire due to the work on the pin.

The authors are not convinced, at present, of whether or not the heat developed by working is accountable for all the phenomena mentioned above.

6. Conclusion

By pulling the wire through a die with some deflection α to the die-axis, the wire after passing through the die acquire a certain looping tendency. Marked decrease of the diameter of the free looping occurs when α is increased beyond 5° , whereby the wire becomes more or less soft. When α is increased to more than 10° , the cross section of the wire becomes elliptic, and unfavourable surface finish.

The free diameter of the drawn wire should be similar to that of the take-up drum, and the regulation for this is to set α within 5° . The shape of the die-exit, in the experiments, did not evince any notable effect, however, it ought have some rounding in order to guarantee the wire to be excellent surface finish.

Further, no paper on this kind of subject was published in the past. However, in spring of 1954, Dr. Tetsuya Arizumi reported at the meeting of the Japan Institute of Metals that on drawing Ni-Mn 4.5% wires at various deflection angles, it could be inferred from the determination of electrical resistance, no harmful effects were given to the wires when drawn at deflection angles of up to $\alpha = 4^\circ$.