LETTERS TO THE EDITOR

A Method for Determining the Solid-Liquid Interface Shape during the Czochralski Growth of Copper Crystals

(Received April 25, 1972)

It has been reported for semiconductor crystals (germanium^{(1)~(3)}, silicon⁽⁴⁾) and oxide crystals (garnet⁽⁵⁾, ruby⁽⁵⁾, tellurium dioxide⁽⁶⁾) that, when the crystals were grown with a curved solid-liquid interface, thermal strains are generated near the interface and many dislocations are introduced into the crystals. Moreover, it has been shown experimentally and theoretically that the interface shape varies with growth conditions^{(7)~(8)}. Two methods were mainly used for determining the interface shape during the Czochralski crystal growth. In the case of semiconductor crystals, it is possible to dope the melt at a given instant during the crystal growth with an activator of opposite electrical polarity. Such doping has been known to be very effective in that the conversion of polarity takes place almost all-over the interface which can be shown up by selective etching. On the other hand, the solid-liquid interface can be exposed by pulling up quickly a crystal from the melt during the crystal growth. This method has been mainly used for the oxide crystals, though the details of its experimental condition were not given.

In this note, the application of the quick pulling-up method to a copper crystal is reported. Figure 1 shows the Czochralski furnace equipped with an attachment for pulling up quickly the crystal from the melt. This attachment is so devised as to separate quickly the crystal (8) from the melt (9) by the action of a spring (2) when the trigger (6) is pulled with a copper wire (5) from the outside of the furnace. The spring used is a helical stainless spring of which the spring constant is 6.9 N/cm and the acceleration when the crystal is separated from the melt can be controlled by a change of the compression distance of the spring. The copper (99.999%) crystals of 14~20 mm diameter to be examined were grown at a speed of 1 mm/min and a crucible rotation rate of 3 rpm in an atmosphere of argon.

The macrophotographs of the underside of copper crystals separated quickly from the melt under various conditions are shown in Photo. 1. At first, in Photo. 1 (a), it is shown that the liquid drop remains hanging

Fig. 1 The Czochralski furnace equipped with an attachment for observing a solid-liquid interface during crystal growth.

1: Water-cooled shaft 2: Spring 3: Stopper
4: Spring casing 5: Copper wire 6: Trigger
7: Seed holder 8: Crystal 9: Melt 10: Opaque silica radiation shield 11: Graphite heater 12: Graphite crucible.

partly on a crystal when the crystal is separated from the melt at the pulling speed of 18.7 cm/min without using the spring. When a crystal is separated from the melt at the acceleration $\sim 2000^{\dagger}$ cm/sec² with the spring, a thin liquid layer adheres to the crystal and constitutes a pocky structure wholly or locally, as shown in Photo. 1 (b) and (c). But such an adherence of a

- (1) E. Billig : Proc. Roy. Soc., A 235 (1956), 37.
- (2) I. G. Cressel and J. A. Powell : *Progress in Semiconductors*, vol. 2, Heywood, London, (1957), p. 139.
- (3) F. D. Rosi : RCA Rev., 19 (1959), 349.
- (4) M. G. Milvidskii and B. I. Golovin : Soviet Physics-Solid State, 4 (1961), 737.
- (5) B. Cockayne, M. Chesswas and D. B. Gasson : J. Materials Science, 4 (1969), 450.

- (6) N. Miyazawa and Y. Iwasaki : Japan. J. Appl. Phys., 9 (1970), 441.
 - (7) T. Arizumi and N. Kobayashi : Japan. J. Appl. Phys., 8 (1969), 1091.
 - (8) N. Kobayashi and T. Arizumi : Japan. J. Appl. Phys., 9 (1970), 361, 1255.
- [†] calculated value

Photo. 1 Macrophotographs of the underside of copper crystals separated quickly from the melt. (a) At the pulling speed of 18.7 cm/min, without using the spring. (b) and (c) At the acceleration $\sim 2000^\dagger \text{cm/sec}^2$ with the spring. (d) At the acceleration $\sim 5000^\dagger \text{cm/sec}^2$ with the spring.

thin liquid layer can be completely avoided and a smooth exposed surface is obtained as shown in Photo. 1 (d), when the acceleration at an instant of separation from the melt with the spring is increased to $\sim 5000^\dagger \text{cm/sec}^2$.

From the above-mentioned results, it is confirmed that the solid-liquid interface can be really exposed

when a crystal is separated from the melt at the acceleration as large as $5000^\dagger \text{cm/sec}^2$.

By Tetsuo Inoue*, Jiro Watanabe**
and Mikio Yamamoto*

*The Research Institute for Iron, Steel and Other Metals,
Tohoku University, Sendai, Japan.

**Department of Metallurgy, Akita University, Akita, Japan.

† calculated value