Directional Solidification of René 80

By Y. G. Nakagawa*, A. Ohtomo* and Y. Saiga*

Directional solidification (DS) of a nickel-base superalloy, René 80, was studied from the viewpoint of its possible engineering applications in the future. Its feasibility was examined in terms of the alloy's castability in DS and the resultant mechanical properties. Experimental fabrication of turbine blades in actual size was made by the "Power Down" method and excellent DS castability for this alloy was confirmed by easy mold production and high speed processing rates. The tensile strength increased approximately by 10~15% while the creep rupture life was extended by 2~4 times. In conclusion René 80 was found to be markedly benefited by DS.

(Received February 7, 1975)

I. Introduction

It is a well established fact that directionally solidified (DS) castings having a columnar or single crystal structure would bring a number of new characteristics in high temperature performance of nickel⁽¹⁾⁽²⁾ and cobalt⁽³⁾ base superalloys as demonstrated by a series of investigations of DS Mar-M200 and its application to gas turbine components^{(4)~(8)}. These previous studies indicate that in every case the ductility improvement, thermal shock resistance, and fatigue life extension are promised by directional solidification (DS) processing, but improvements in high temperature strength measured in tensile strength and the creep rupture life are not always ensured⁽⁹⁾. The strength improvement, if any, is given to a different extent for different alloys, and there seems no indirect way of knowing the degree of improvement from the composition of an alloy although the amount of elements to contribute the intrinsic (bulk) strength is considered to be important⁽¹⁾. Therefore, it is necessary to examine experimentally the importance of directional solidification in its engineering application to a particular alloy interested.

The other critical factor involved in the application of directional solidification is "DS castability" of the alloy since it determines the main portion of overall cost. DS castability implies here the mold wall reactivity with molten

metals and the necessary processing time to obtain sound DS castings. Because the relationship between alloy's chemistry and its castability has not been well understood even for conventional castings, and castability markedly differs from alloy to alloy, the experimental establishment of an adequate shell mold structure and G (thermal gradient)/ R (solidification rate) ratio is required for an individual alloy to examine the DS castability, where much severer conditions have to be met.

At the present, the authors firmly believe that because of distinct DS characteristics, accumulation of DS property data is desired so as to present "DS supplement" to each specification of all superalloys for the benefit of future engine designers. In the present study as an effort to generate DS data, feasibility of applying DS to a nickel base superalloy, René 80, with chemical composition specified in Table 1, was evaluated in terms of engineering factors described above. René 80 was chosen as a representative blade alloy in the René family for which DS informations is particularly lacking⁽¹⁰⁾. The alloys for which improved DS properties have been already known are, for instance, Mar-M200, B1900 and IN100⁽¹⁾ which have relatively poor hot corrosion resistance, while alloys with improved hot corrosion resistance have relatively low intrinsic strength and no significant effects by DS may be expected. In this respect René 80 has a well balanced chemical composition and possesses superior hot corrosion resistance and good creep strength caused by a large amount of intrinsic hardeners⁽¹¹⁾. The castability of René 80 to produce thin airfoils

* Metallurgy Department, Ishikawajima-Harima Heavy Industries Co., Ltd., Tokyo 135-91, Japan.

Table 1 Specification of chemical composition of René 80.

C	Mn	Si	S	Cr	Ti	B	Al	W	Mo
0.15~0.19	≤0.20	≤0.20	≤0.015	13.70~14.30	4.80~5.20	0.010~0.020	2.80~3.20	3.70~4.30	3.70~4.30
W+Mo	Co	Fe	Zr	Ni					
≥7.70	9.00~10.00	≤0.20	0.02~0.10	BAL.					

using DS technology has been examined in experimental facilities by the so-called "Power Down" method. Also examined are resultant high temperature properties of DS René 80 in comparison of conventional castings so that an overall engineering evaluation for DS application to this particular alloy can be made.

II. Experimental

1. DS casting

DS casting of airfoils (T-64 blade) were produced by the "Power Down" method, the details of which have been described in various papers⁽⁵⁾⁽⁶⁾. Mold heaters capable to preheat DS mold up to 1600°C were prepared by winding 50 mm diameter by 250 mm long alumina tubes with two independently controlled tantalum heating coils. To minimize radial heat flow to the outer side, the heating elements were shielded by an alumina tube and a few layers of hollow cylinders out of molybdenum and stainless steel (Fig. 1). The conventional method of alumina-zirconia investment shell mold preparation is found to be applicable for directional casting of René 80. The inner wall surface had to be furnished by the powder with much higher alumina content to prevent the penetration of liquid metal during a prolonged period. The mold was heated up above 1400°C and vacuum-melted master ingot was poured into the mold. When a steep temperature gradient was established between molten metal and the copper chill plate, the solidification was performed by controlling the heater input according to temperature readings monitored at a number of locations of the mold wall. The DS at various solidification rates was tried and resultant temperature gradients in liquid phase

Fig. 1 Mold heater and mold assembly.

G_L , and solid phase G_s were obtained from the cooling curves.

2. Mechanical test

A number of DS rods were machined to prepare specimens in the shape shown in Fig. 2 for high temperature tensile tests and creep rupture tests. Most of the specimens were taken from the rods solidified at a DS rate 15~20 cm/hr, which was the possible maximum DS velocity for the production of T-64 airfoil with sound columnar structure using the present equipment. After machining the specimens were heat-treated according to the following specification required for conventional René 80 castings. 1220°C for 2 hr, then argon gas quenching to room temperature (RT). 1095°C for 4 hr, then argon gas quenching to RT.

1050°C for 4 hr, then furnace cooling to 650°C in 1 hr, argon gas quenching to RT. 845°C for 16 hr, then argon gas cooling to RT. The tensile tests were carried out in air with a strain rate of approximately 0.05/min. The elongation, strain rate and 0.2% strain were determined by a clip gage driven by extension meter bars clamped onto the end flanges of the specimens. All creep rupture tests were conducted in air and the applied stresses and test temperatures which were the same as those to give 50, 100, and 500 hr average rupture time for conventionally cast René 80. The creep strain was measured by extension meter bars coupled with the LVDT system.

III. Result

Visual inspections of DS airfoils were performed after sand blasting. The DS castings were found to be very free from foreign objects, mostly various oxides particles, constituent of mold. Macrostructure was examined by etching in a solution of hydrochloric acid and hydrogen peroxide to make a columnar grain alignment visible as seen in Photo. 1. The maximum allowance of orientation divergence is said to be a few degrees, and all successfully cast blades in the present program showed grain alignment well within this criterion. At various locations of DS blades, microstructures were also examined. It was concluded that shrinkage porosity and

Photo. 1 DS turbine blade castings in the macroetched condition.

Fig. 2 DS specimen used for tensile and creep rupture test (mm).

Fig. 3(a) Tensile and yield strength of DS René 80.

(b) Tensile elongation and reduction of area of DS René 80.

Table 2 Result of high temperature tensile test for DS René 80.

T.P.	Cast	R (cm/hr)	Temp. (°C)	σ_B (kg/mm ²)	YS (kg/mm ²)	ρ (%)	RA (%)	Condition
1	DS	17.5	RT	105.4	85.8	10.6	19.0	HT
2	DS	17.5	650	117.6	81.3	10.6	19.0	HT
3	DS	17.5	760	115.5	88.4	9.7	16.0	HT
4	DS	17.5	870	85.7	70.7	24.6	33.3	HT
5	DS	37.5	870	74.9	51.3	16.3	30.6	HT
6	DS	17.5	870	65.5	57.2	24.0	33.3	As cast
7	CC	—	870	76.5	54.8	12.6	15.1	HT
8	CC	—	870	76.8	54.6	12.3	15.0	HT
9	DS	17.5	980	48.1	39.4	20.7	46.2	HT

R: Solidification velocity, Temp.: Test temperature, CC: Conventional casting, σ_B : Tensile strength, YS: 0.2% offset yield strength, ρ : Elongation, RA: Reduction of area, HT: Heat treated.

Table 3 Results of creep rupture test for DS René 80.

T.P.	Cast	R (cm/hr)	Temp. (°C)	Stress (kg/mm ²)	ρ (%)	RA (%)	<i>tr</i>	Condition
1	DS	17.5	760	63.0	16.2	33.3	474	HT
2	DS	17.5	872	37.8	29.3	43.8	162.5	HT
3	DS	17.5	872	35.0	21.6	36.0	276.5	HT
4	DS	17.5	872	27.3	—	—	> 1430	HT
5	DS	37.5	982	19.4	38.6	56.5	45	HT
6	DS	37.5	982	19.4	9.7	29.2	54.3	HT
7	DS	16.2	982	19.4	17.0	36.2	50.3	HT
8	DS	17.5	982	19.4	26.7	62.0	44.3	As cast
9	CC	—	982	19.4	6.8	8.2	29.5	HT
10	CC	—	982	19.4	7.1	10.1	48.1	HT
11	DS	14.0	982	16.8	9.7	30.3	176.8	HT
12	DS	17.5	982	12.6	4.0	29.8	882.3	HT

micro-inclusions were minimized by DS processing. Tensile strength, 0.2% proof stress, elongation, and reduction of area measured for DS René 80 are listed in Table 2, and the results are plotted in Fig. 3(a) and (b), where the average values for conventionally cast René 80 are also included. The results of creep rupture tests at 982, 872 and 760°C are summarized in Table 3 and are shown in Fig. 4, together with the average values for conventional castings.

IV. Discussion

Since the formation of stray crystals in undirectionally solidified materials depends on constitutional supercooling induced by a

Fig. 4 Degree of improvement in creep rupture time by DS as compared with conventional casting.

combination of R and G_l , the evaluation of casting structures (equiaxed or columnar) is normally made on the bases of G_l/R ratio where R is the solidification velocity. As Shown in Table 4, R is closely related to G_l , while G_s remains fairly constant in the power down method. In order to make sound casting structures, G_l/R was limited to be more than unity and the allowable maximum R obtained was 18 cm/hr.

which readily leads to a conclusion that a narrower melting temperature range, $\Delta T (= T_l - T_s)$, is favorable for DS, and alloys with large ΔT tend to nucleate stray crystals. This conclusion should be applicable to a quasi-binary γ - γ' systems in superalloys of complex chemistry. Other possible danger to give defects in DS castings originates from a convective jet stream of eutectic fluid to solidify at the last stage

Table 4 Estimated values, t , G_l , G_s , R and G_l/R for directionally solidified T64 blades.

Casting	t (hr)	G_l (°C/cm)	G_s (°C/cm)	R (cm/hr)	G_l/R (°Chr/cm ²)	Structure
DST64Z1	0.4	23.4	25.0	15	1.56	Columnar
DST64Z2	0.33	20.0	25.0	18	1.1	Columnar
DST64Z3	0.25	15.8	26.7	24	0.66	Columnar, Slight Divergence
DST64Z4	0.1	10.0	21.6	60	0.16	Defective

t : Solidification time for casting, G_l : Temperature gradient in liquid part, G_s : Temperature gradient in solid part, R : Solidification rate.

Considering the relatively low temperature gradient available to the present equipment, the maximum velocity is considerably high and hence indicates excellent DS castability of René 80. Since a much steeper temperature gradient can be realized by the High Rate Solidification or Liquid Metal Cooling process⁽¹²⁾, much faster solidification should be achieved in a plant at which the critical processing velocity is said to be a few inches per hour⁽¹³⁾.

The critical value of G/R under which constitutional supercooling is developed in the liquid ahead of an advancing planar interface in a binary alloy is given by the equation⁽¹⁴⁾,

$$G/R = \frac{mCo}{D} \frac{1 - Ko}{Ko} \quad (1)$$

where Co , m , Ko , and D are the average concentration of the solute, the slope of the liquidus in the phase diagram, the distribution coefficient of solute, and the diffusion constant of solute in liquid, respectively. The equation may be changed to correlate with the temperature difference between liquidus (T_l) and solidus (T_s) at Co as,

$$G/R \approx \frac{T_l - T_s}{D} \quad (2)$$

in the system. The investigations of the defect, appeared as "freckles", suggested that alloys with large ΔT , and with high aluminum or tungsten content are prone to form more freckles⁽¹⁵⁾⁽¹⁶⁾. Table 5 shows a comparison of T_l , T_s , ΔT , and aluminum and tungsten contents of René 80 with those of various alloys. Since no critical G/R values are available for the alloys, no precise evaluation can be made at this stage, but a possible indication in Table 5 is that IN100 may have worst DS castability because of the large melting temperature range and the large amount of the total γ' formers (10.2 wt %). As for other alloys, except B1900, γ' formers are approximately at the same level (7~8 %). The aluminum content is maximum in B1900 and minimum in René 80. Mar-M200 with relatively large ΔT and a large amount of tungsten was reported to suffer freckle formation⁽¹⁵⁾. The other factor, possibly more important from the practical point of view, is the difference in the melting point of the alloy which determines the necessary degree of superheating for the cast molten metal in contact with the ceramic mold wall for a prolonged time. Thus the melting point can be a direct measure for deciding how stable molds should be in terms of the mold wall reaction and of maintaining dimensional precision.

Table 5 DS castability determinative element.

Alloy	Melting temperature			Chemical composition (wt %)									
	(°C)			γ' Formers					Other major elements				
	T_l	T_s	ΔT	Cb	Ta	Ti	Al	W	Co	Mo	Cr	C	Ni
René 80	1320	1280	40	—	—	5.0	3.0	4.0	9.5	4.0	14.0	0.17	Bal.
IN 100	1340	1265	75	—	—	4.7	5.5	—	15.0	3.0	10.0	0.18	Bal.
Mar-M200	1370	1315	55	1.0	—	2.0	5.0	12.5	10.0	—	9.0	0.15	Bal.
BI900	1300	1270	30	—	4.0	1.0	6.0	—	10.0	6.0	8.0	0.10	Bal.

Through the various experiences encountered in the present study such as molding, necessary processing time and thin part castability, René 80 was found to be highly adequate for DS casting by reason of the moderate melting temperature range and the minimum amount of aluminum.

As shown in Fig. 3(a) and (b), the tensile strength and yield strength of DS René 80 are improved by 10~15% in the temperature range of 600~980°C as compared with those of the conventional castings. The ductility measured in elongation and the reduction of area also increase significantly at all the test temperatures including room temperature. However, the minimum improvement is observed for the specimen whose tensile strength is maximum. In Table 2 the results of a DS specimen solidified at a faster rate 40 cm/hr is included. This specimen showed no improvements in tensile and yield strengths but maintained approximately the same values as conventionally cast René 80, while its ductility improvement is comparable to the specimens solidified at a lower rate.

DS effectively extends the rupture life of René 80 at all the test temperatures. At 982°C no significant effect is observed at a higher stress (19 kg/mm²), but as the applied stress decreases, the rupture life extends approximately 1.8 times. At 870°C DS specimens show threefold improvement in rupture life at all stress levels. The creep strains were monitored during the creep tests, and the results were compared with those of the conventional castings. It was found that at 980°C the life time improvement in DS specimens resulted mainly from the extended third creep stage but not from the second stage where no appreciable difference in the minimum creep rate was observed. At 760°C, however, the

improvement was due largely to the extended second stage with the strain rate reduced by approximately 1/7 (7×10^{-5} cm/cm/hr for DS).

As suggested in the extensive studies on DS poly- or single crystals of Mar-M200^{(1,7)(1,8)}, the improvements in ductility and strength for DS materials are mainly induced by the directional alignment of crystal orientation and the absence of grain boundaries perpendicular to the principal stress direction. The latter is particularly effective to promote the longer third stage since boundaries serve as major sites of void (crack) nucleation and linking. At 980°C (above $0.6 T_m$, where T_m is the melting point of the alloy), since the deformation is likely activated by the vacancy diffusion and thus is insensitive to crystal orientation, the minimum strain rate is not much different between DS and the conventional castings. A significant difference in strain rate at 760°C ($\approx 0.6 T_m$) is caused by the orientational dependence of the available number of active slip systems. For nickel base superalloys, the principal solidification direction in DS is parallel to [001] which gives the most remarkable resistance for high temperature deformation.

The importance of the heat treatments for the high temperature strength of DS René 80 can be understood from Table 2 where the ultimate tensile strength, σ_b , of the as-cast DS specimen is shown to be considerably smaller than that of the specimens subjected to the heat treatment. In view of the fact that heat treatments effectively control the intrinsic strength of the alloy, the choice of the most appropriate heat treatment for DS René 80 remains as a very important subject in the future.

Good internal qualities of DS parts are thought to be another major reason for the mechanical improvement as Hot Isostatic

Pressure⁽¹⁹⁾ process was developed for this purpose. When one considers that microporosity and micro-inclusions are the main factors to determine the rejection rates of conventional castings, the good internal quality naturally free from these defects is regarded as one of the greatest advantages for DS processing.

V. Summary

Feasibility of engineering application of DS to René 80 was demonstrated in the present investigation. Excellent DS castability of the alloy was confirmed by easy mold fabrication and the high speed processing rate. The tensile strength increased by 10~15% while two-fold extension of creep rupture life was obtained for DS specimens. In conclusion René 80 has proved to be one of the existing superalloys which are remarkably benefited by DS.

Acknowledgments

The authors are especially indebted to Dr. T. Nishigori for his stimulating discussions on the present topic and his technical assistance.

REFERENCES

- (1) B. J. Pearcey and B. E. Terkelsen: Trans. Met. Soc. AIME, **239** (1967), 1143.
- (2) C. H. Lund: Foundry Trade J., **5** (1970), 815.
- (3) R. F. Vandermousen et al.: Cobalt 1, (1974), 6.
- (4) B. J. Pearcey and F. L. Versnyder: SAE J., **74** (1966), 84.
- (5) F. L. VerSnyder and B. J. Pearcey: J. of Aircraft, **3** No. 5 (1966), 390.
- (6) F. L. VerSnyder, R. B. Barrow, B. J. Pearcey and L. W. Sink: Modern Castings, **50** No. 12 (1967), 360.
- (7) B. J. Pearcey and F. L. VerSnyder: ASE paper 66055, **75** (1967), 247.
- (8) F. L. VerSnyder and M. E. Shank: Mater. Sci. Eng., **6** (1970), 213.
- (9) D. A. Woodford and J. J. Frawley: Met. Trans., **5** (1974), 2005.
- (10) L. P. Jainke: J. of Metal, **10** (1973), 15.
- (11) E. W. Ross: Metals Progress, **99**, No. 3 (1971), 93.
- (12) M. Gell, C. P. Sullivan and L. F. VenSnyder: Solidification Technology, Proc. of 1st Army Mat. Tech. Conf., (1972), p. 141.
- (13) B. H. Kear, P & W Aircraft: Private Communication.
- (14) B. Chalmers: *Principals of Solidification*, John Wiley & Sons, Inc., (1964), 158.
- (15) A. F. Giamei and B. H. Kear: Met. Trans., **1** (1970), 2185.
- (16) S. M. Copley and et al.: Met. Trans., **1** (1970), 2193.
- (17) F. L. VerSnyder and B. J. Pearcey: SAEJ., **74** (1966), 36.
- (18) B. H. Kear and B. J. Pearcey: Trans. Met. Soc. AIME, **239** (1967), 1209.
- (19) G. E. Wasielewski and N. R. Lindblad: *Superalloys Processing*, Proc. of 2nd Intern. Conf. (1972), Sect. D.