LETTER TO THE EDITOR

The Effect of Zinc Addition on the Mechanical Properties of Ni_3Al

Keywords: intermetallic compound, Ni_3Al , nickel-aluminum-zinc, nickel alloy, ternary alloy, ternary phase diagram, flow stress, phase stability, zinc addition

The positive temperature dependence of strength of L_{12} intermetallic compounds is affected remarkably by ternary additions, as has been reported by Suzuki *et al.*⁽¹⁾⁽²⁾ The ternary addition influences the electron atom ratio and the atomic radius ratio in the compound and consequently changes the phase stabilities of L_{12} phase with respect to other GCP (geometrically close-packed) phases, which are closely related to the thermally activated cross slip mechanism and hence to the anomalous increase in strength with temperature⁽³⁾⁽⁴⁾.

In commercial nickel base superalloys, various kinds of alloying elements are partitioned into γ and γ' (Ni_3Al) phases. For the alloy design to develop the high performance alloys, it is desirable to know the individual effect of alloying elements on the strength and the phase stability in γ' . In order to test whether the phase stability concept is valid or not in Ni_3Al , the substitution of B-subgroup elements, which is of little practical use, is actually suitable for the change in electron atom ratio in Ni_3Al , because the valence of B-subgroup elements is strictly defined. The present authors have found that the addition of B-subgroup elements to Ni_3Al and Ni_3Ga enhances the positive temperature dependence of strength in order of the group number; $3\text{B}(\text{Ga}, \text{In}) < 4\text{B}(\text{Si}, \text{Ge}, \text{Sn}) < 5\text{B}(\text{Sb})$ ⁽⁵⁾. As a natural consequence, it has been expected that the addition of 2B-subgroup elements should weaken the positive temperature dependence of strength of Ni_3Al . The conventional melt and cast method, however, can not be used for alloy preparation, when one of the components, such as Zn, has relatively high vapor pressure. The purpose of this paper is to confirm the effect of Zn, one of the 2B-subgroup elements, on the substitution behavior and the temperature dependence of strength of Ni_3Al .

For the constitutional examination the melting method in a sealed silica tube, which was employed in nickel alloys containing zinc by Pearson and Thompson⁽⁶⁾, was adopted and for compression test the hot press method. Raw materials were carbonyl nickel powders of 4 to 7 μm in size having a purity of 99.9%, zinc powders of 2 to 5 μm in size having a purity of 99.9% and NiAl intermetallic compound powders (Cerac Inc.) of 150 μm on an average in size containing impurities less than 0.5%. Hot press was done, in an argon atmosphere, at 1173 K for 21.6 ks under 4.5 MPa in an alumina dies. All the alloys obtained were homogenized at 1223 K for 605 ks in a small vacuum silica capsule. The weight loss during homogenizing was less than 0.1% in extreme cases. Optical microscopy and X-ray analysis were made for the constitution of the phase

diagram. Compression test was done by an Instron-type testing machine using specimens with a dimension of $3 \times 3 \times 6 \text{ mm}^3$ at a strain rate of $1.4 \times 10^{-4} \text{ s}^{-1}$ in a flowing argon atmosphere. The chemical compositions of the three alloys for compression test obtained by hot press are 74.6 at%Ni–25.4 at%Al, 73.9 at%Ni–22.3 at%Al–3.21 at%Zn and 73.8 at%Ni–19.6 at%Al–5.91 at%Zn. Every alloy has a grain size of about 30 μm and a porosity of 7 vol% at most, irrespective of Zn content.

The nickel corner of Ni–Al–Zn phase diagram at 1123 K obtained in this study is shown in Fig. 1. The Ni–Ga–Zn phase diagram reported by Bhan and Schubert⁽⁷⁾ is helpful in constructing the diagram, because in many respects the behavior in Ni_3Al is analogous to that in Ni_3Ga ⁽⁸⁾. The site preference of Zn being for Al-site in Ni_3Al can be confirmed by the direction of solubility lobe in the ternary region. This substitution behavior is the same as in the case of other B-subgroup elements⁽⁹⁾. The maximum solubility of Zn in Ni_3Al at 1123 K is estimated to be 6 at%.

With increasing Zn content the positive temperature dependence of strength of Ni_3Al becomes weaker and appears to be lost at 6 at% Zn, as shown in Fig. 2. In this figure, data of a cast Ni_3Al , taken from a previous work⁽⁴⁾, are also shown as a reference. The strength level of the sintered Ni_3Al is much greater, for example, by a factor of seven at 77 K, than that of the cast Ni_3Al . To make a comparison between the two alloys produced by the different methods, the grain boundary strengthening due to fine grains, the dispersion strengthening by oxide particles and the softening by dispersed voids should be considered.

The grain size of sintered alloys is much finer than that of cast alloys of 300 to 400 μm . Fortunately Oya *et al.*⁽¹⁰⁾ have studied the effect of grain size on the strength of Ni_3Al and Ni_3Si and reported the temperature dependence of the coefficient k_y in the Hall-Petch relation, $\sigma = \sigma_0 + k_y d^{-1/2}$. Utilizing the values of k_y the temperature dependence of σ_0 of the sintered Ni_3Al and $\text{Ni}_3(\text{Al}, \text{Zn})$ can be estimated, as shown in Fig. 3. After excluding the effect of grain size, the 0.2% flow stress of the sintered alloy is still greater by about 290 MPa, independent of temperature, than that of the cast one. The dispersion hardening by oxides should be a main cause of the increment of 290 MPa in the sintered alloy. The sintered alloys contain a significant amount of fine oxides. It has been reported frequently that the dispersion strengthening by oxides is independent of temperature. A typical example is reported in the work by Wilcox and Jaffe⁽¹¹⁾ in TDNi with 2.3% ThO_2 . The decrement of strength by pores is

Fig. 1 The proposed Ni-Al-Zn phase diagram at 1123 K.

Fig. 2 Temperature dependence of the 0.2% flow stress for sintered $\text{Ni}_3(\text{Al, Zn})$, with the data of cast Ni_3Al .

Fig. 3 Temperature dependence of the modified 0.2% flow stress for Ni_3Al and $\text{Ni}_3(\text{Al, Zn})$. The effect of grain size is excluded by the previous result⁽¹⁰⁾ on the temperature dependence of k_y in Hall-Petch relation.

Fig. 4 Logarithmic plots of the stress increment vs reciprocal temperature for Ni_3Al and $\text{Ni}_3(\text{Al, Zn})$, where half symbols mean interpolated values. σ_H is the net stress increment by the thermally activated cross slip⁽¹⁾⁽²⁾⁽⁴⁾.

estimated to be 7%, if the rule of mixture between pores and substance could be applied. The effect of pores on strength is here negligibly small in contrast with those of grain size and oxide dispersion.

After excluding both the increments of strength due to the effects of grain size and oxide dispersion from the 0.2% flow stress shown in Fig. 2, Arrhenius plots for the anomalous increase in strength are obtained, as shown in Fig. 4. The beelines of the cast binary Ni_3Al and the sintered one are parallel, showing the propriety of the above procedure to draw the characteristic behavior from the data of sintered Ni_3Al . The slope of beelines becomes steeper with increasing Zn content, indicating the increase of the activation constant. This fact confirms that the addition of Zn, 2B-subgroup element, weakens the positive temperature dependence of strength in Ni_3Al , as has been expected.

REFERENCES

- (1) T. Suzuki, Y. Oya and D. M. Wee: *Acta Met.*, **28** (1980), 301.
- (2) T. Suzuki and Y. Oya: *J. Mater. Sci.*, **16** (1981), 2737.
- (3) D. M. Wee and T. Suzuki: *Trans. JIM*, **20** (1979), 634.
- (4) D. M. Wee, O. Noguchi, Y. Oya and T. Suzuki: *Trans. JIM*, **21** (1980), 237.
- (5) S. Ochiai, M. Yodogawa, Y. Mishima and T. Suzuki: to be published.
- (6) W. B. Pearson and L. T. Thompson: *Canad. J. Phys.*, **35** (1957), 349.
- (7) S. Bhan and K. Schubert: *J. Less-Common Metals*, **17** (1969), 73.
- (8) O. Noguchi, Y. Oya and T. Suzuki: *Met. Trans.*, **12A** (1981), 1647.
- (9) S. Ochiai, Y. Oya and T. Suzuki: *Acta Met.*, **32** (1984), 289.
- (10) Y. Oya, Y. Mishima, K. Yamada and T. Suzuki: *J. Iron Steel Inst. Japan*, **15** (1984), 1870.
- (11) B. A. Wilcox and R. I. Jaffe: 1st Int. Conf. on Strength of Metals and Alloys, Supplement Trans. JIM, **9** (1968), 575.

Y. Kuriki*, S. Ochiai**, M. Yodogawa***
and T. Suzuki***

* Graduate Student, Tokyo Institute of Technology. Now at Technical Research Center, Nippon Kokan K.K., Minami-Watarida, Kawasaki-ku, Kawasaki 210, Japan.

** Graduate Student, Tokyo Institute of Technology. Now at Nagaoka Technological University, Kamitomioka, Nagaoka 949-54, Japan.

*** Research Laboratory of Precision Machinery and Electronics, Tokyo Institute of Technology, Nagatsuta, Midori-ku, Yokohama 227, Japan.

(Received September 3, 1984)