Mössbauer Effect of Metastable bcc and fcc Fe-Cu Alloys Produced by Vapor Quenching

By Kenji Sumiyama*, Tsutomu Yoshitake** and Yoji Nakamura*

Mössbauer spectra were obtained at 4.2 K and 290 K for the metastable bcc and fcc phases of sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys. For $x=0-0.4$ (the bcc phase region), a ferromagnetic sextet was observed at both 4.2 K and 290 K. The halfwidths of spectra are narrow and the average hyperfine field slightly decreases with increasing x . For $x=0.6-1.0$ (the fcc phase region), a sextet with very broad halfwidths was observed at 4.2 K. The average hyperfine field is smaller than that of the bcc alloys and gradually decreases with increasing x . At 290 K, where the fcc alloys are paramagnetic, a broad quadrupole splitting is detected, which can be decomposed into several contributions of Fe atoms with different numbers of nearest neighbor Fe atoms.

(Received, October 23, 1984)

Keywords: iron-copper alloys, metastable crystalline alloys, sputtering, vapor quenching, Mössbauer effect

I. Introduction

X-ray diffraction and the magnetization of sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys have already been reported in previous papers⁽¹⁾⁻⁽³⁾. By sputtering, single bcc alloys are obtained for $x < 0.4$, while single fcc alloys for $x > 0.6$. With increasing x , the lattice constant slightly increases in the bcc alloys, whereas it decreases in the fcc alloys. The characteristic magnetic properties of the sputtered Fe-Cu alloys are summarized as follows⁽³⁾. A bcc alloy with $x=0-0.4$ is a ferromagnet whose Curie temperature drops from 1000 K to 750 K with increasing x . An fcc alloy is also a ferromagnet whose Curie temperature is about 320 K for $x=0.58$ and goes down sharply with increasing x to 0 K around $x=0.92$. The magnetic moment of the $\text{Fe}_{1-x}\text{Cu}_x$ alloys monotonically decreases with increasing x . For the bcc alloys, it slightly deviates upwards from the simple dilution law, while for the fcc alloys it deviates downwards from the simple dilution law.

In contrast to the extensive Mössbauer studies of both ultimate concentration regions

of bulk Fe-Cu alloys⁽⁴⁾, the present paper deals with experimental results of the Mössbauer effect of the high concentration $\text{Fe}_{1-x}\text{Cu}_x$ alloys produced by sputtering and shows the microscopic characteristics of these metastable alloys.

II. Experimental Procedures and Results

The samples were prepared on polyimide film substrates by a conventional rf sputtering method as described in the previous paper⁽³⁾. The Mössbauer effect measurements were carried out at 4.2 K and 290 K by a constant acceleration type spectrometer using a ^{57}Co source doped in Cu.

Figure 1 shows the Mössbauer spectra at 290 K for the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys with $x < 0.6$. A ferromagnetic sextet is predominant in the single bcc alloys with $x < 0.4$, whose Curie temperatures are much higher than room temperature⁽³⁾. A central peak attributable to an fcc phase, whose Curie temperature is comparable to or lower than room temperature, appears for $x > 0.45$ ⁽³⁾. For bcc alloys, the sextet is relatively sharp, i.e., the outer lines do not show a well-resolved fine structure, in contrast to many other Fe alloys with nonmagnetic solute elements⁽⁵⁾⁽⁶⁾. This feature resembles those observed for solid

* Department of Metal Science and Technology, Kyoto University, Kyoto 606, Japan.

** Graduate Student, Kyoto University, Kyoto 606. Present address: Central Research Laboratory, Nippon Electric Co., Ltd., Kawasaki 213, Japan.

Fig. 1 Mössbauer spectra at 290 K for the single bcc and bcc-fcc mixed phases in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys ($0 < x < 0.6$). The solid curves indicate the calculated spectra fitted to the hyperfine field distributions shown in Fig. 2. The velocity scale is relative to $\alpha\text{-Fe}$ at room temperature.

quenched and thermally evaporated Fe-Cu alloys with dilute Cu concentrations⁽⁷⁾⁻⁽⁹⁾. The slight increase in the halfwidth with increasing x is ascribed to a distribution of hyperfine fields and electric field gradients caused by a wide variety of local atomic environments around the resonance Fe atom.

Each spectrum was fitted by a superposition of sets of six Lorentzians with different Zeemann splittings, leading to a hyperfine field distribution⁽¹⁰⁾. Here, the halfwidth of each Lorentzian was about 0.25 mm/s in the present experiments and the smoothing factor was chosen to be about 50⁽¹⁰⁾, whereas the isomer shift and the intensity ratio of the second and fifth peaks to the others were adjusted to get the best fittings in the analysis. The contribution of the electric field gradient was neglected, because the principal axis of the electric field

Fig. 2 Hyperfine field distribution at 290 K for the single bcc and bcc-fcc mixed phases in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys ($0 < x < 0.6$).

gradient randomly aligns against the principal axis of the magnetic hyperfine field. Figure 2 shows hyperfine field distribution curves obtained at 290 K for $x < 0.6$. With increasing x , the main peak position shifts slightly to the lower hyperfine field side, and at the same time the low field side shoulder grows continuously. A small zero field peak appears as the fcc phase coexists.

It is worthwhile to note the concentration dependence of the intensities of the second and fifth peaks (see Fig. 1). These intensities become weaker with increasing x , i.e., the intensity ratios of the six lines are about 3:1:1:1:1:3 for $0 < x < 0.2$, about 3:0.9:1:1:0.9:3 for $0.2 < x < 0.35$ and about 3:0.7:1:1:0.7:3 for $0.35 < x < 0.42$, respectively. The similar behavior has been observed for the sputtered Fe-Mn and Fe-Ni alloys, suggesting that a

perpendicular magnetic anisotropy in the bcc Fe alloys is enhanced near the bcc-fcc phase boundary⁽¹¹⁾⁽²²⁾. However, it is incompatible with the results for the thermally evaporated Fe-Cu alloys, where the relative intensity ratios of nearly 3:4:1:1:4:3 indicate that the magnetization lies in the plane of films⁽⁸⁾⁽⁹⁾. One of the possible origins of the perpendicular magnetic anisotropy is a shape anisotropy, because the sputtered alloy films reveal a columnar type crystal growth perpendicular to the film plane⁽¹³⁾.

The Mössbauer spectra of the bcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys at 4.2 K exhibit similar characteristics as those observed at 290 K. However, the average value of hyperfine field is larger and its distribution is narrower in comparison with those at 290 K.

The fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys are also ferro-

magnetic at low temperatures, and the Mössbauer spectra of these alloys at 4.2 K shown in Fig. 3 reveal a very broad sextet. The line broadening is also ascribed to a distribution of hyperfine fields, as shown in Fig. 4. The main broad peak slightly shifts to the lower hyperfine field side with increasing x , whereas the low field components are detectable for all of the fcc alloys.

The average hyperfine field, $\bar{H}_{\text{hf}}$, estimated for the bcc and fcc phases of the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys is plotted against x in Fig. 5. Here, for the bcc-fcc mixed alloys with $x=0.43-0.50$, $\bar{H}_{\text{hf}}$ at 290 K of the bcc phase was estimated as an average of hyperfine field components higher than 12 MA/m (150 kOe) in Fig. 2. In the bcc alloys, $\bar{H}_{\text{hf}}$ at 4.2 K decreases slightly with increasing x , being compatible with a gradual decrease of the average

Fig. 3 Mössbauer spectra at 4.2 K for the fcc phase in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys ($0.6 < x < 1.0$). The solid curves indicate the spectra fitted to the hyperfine field distribution shown in Fig. 4. The velocity scale is relative to α -Fe at room temperature.

Fig. 4 Hyperfine field distribution at 4.2 K for the fcc phase in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys ($0.6 < x < 1.0$). Hyperfine field components A, B and C are explained in the text.

Fig. 5 Concentration dependence of the average hyperfine field, $\bar{H}_{hf}$, for the bcc and fcc phases in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys. ■: at 4.2 K and ●: at 290 K for the single phases. ○: at 290 K for the bcc phase in the bcc-fcc mixed alloys (see the text).

magnetic moment for the bcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys as a function of x ⁽³⁾. $\bar{H}_{hf}$ of the fcc alloys at 4.2 K is smaller than those of the bcc alloys, and it gradually decreases with increasing x , in contrast to the sharp concentration dependence of magnetic moment of Fe atoms in the fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys⁽³⁾.

The paramagnetic Mössbauer spectra at 290 K for the fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys with $x > 0.6$, plotted on an expanded velocity-scale in Fig. 6, reveal a very broad asymmetric doublet. This may be ascribed to distributions of quadrupole splitting, QS , and isomer shift, IS , in the fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys.

For bulk fcc Fe-Cu with a few at% Fe, the variation of Mössbauer spectra with annealing has been interpreted in terms of the precipitation process from a supersaturated Fe solution⁽⁴⁾, where all of the nearest neighbor atoms surrounding a resonance Fe atom are Cu, to γ -Fe precipitates with large dimensions, where all of them are Fe atoms. The absolute value of QS is the largest for the Fe atom with one nearest neighbor Fe atom, and it decreases with the increase in the number of nearest neighbor Fe atoms⁽⁴⁾. Isolated Fe atoms in the solution and γ -Fe precipitates exhibit single resonance lines with $IS=0.22$ and -0.09 mm/s relative to α -Fe, respectively⁽⁴⁾. IS ranges from a positive to negative value; the change in IS is nearly inversely-proportional to the number of nearest neighbor Fe atoms⁽⁴⁾.

Fig. 6 Mössbauer spectra at 290 K for the sputtered fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys. The full lines represent the fitted curve for each spectrum, and the individual spectral components, L, M and S. The fitting parameters are given in Table 1. The velocity scale is relative to α -Fe at room temperature.

For the lack of clear structures in the Mössbauer spectra at 290 K of the sputtered fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys, we simply fitted the observed spectrum to three components, a singlet, S, and two doublets, L and M, using a least square minimization program. The singlet and two doublets were constructed from one Lorentzian and two Lorentzians, where the values of IS , QS and the intensity ratios of three components were fitting parameters. Since resonance Fe atoms having different numbers of nearest neighbor Fe atoms and lattice defects in the sputtered alloys give rise to line broadenings in the spectra of these components⁽⁴⁾, halfwidths were chosen to

be 0.27, 0.29 and 0.31 mm/s for the components, L, M and S, respectively, as trials. Considering the results of analyses for Mössbauer spectra in Cu-Fe alloys⁽¹⁴⁾⁻⁽¹⁶⁾, these three components can be interpreted as follows:

(1) The doublet, L, is ascribed to resonance Fe atoms surrounded by one or two nearest neighbor Fe atoms.

(2) The doublet, M, is attributable to resonance Fe atoms surrounded by three to five nearest neighbor Fe atoms.

(3) The singlet, S, is due mainly to resonance Fe atoms surrounded by more than five nearest neighbor Fe atoms. It also contains minor contributions from isolated Fe atoms and γ -Fe atoms, as will be discussed later.

The fitted curves are shown by the solid curves in Fig. 6 along with the individual components, L, M and S. As listed in Table 1, the parameters of components, L and M, determined from the fitting procedures, are not sensitive to the alloy concentration, x , and they are consistent with the sets of parameters used to fit the spectra of solid-quenched and ion-implanted Cu-Fe alloys⁽¹⁴⁾⁽¹⁶⁾. On the other hand, the isomer shift of the component S increases with increasing x . This may be due partly to the contribution of the isolated Fe atoms, which have the large IS value of 0.22 mm/s⁽⁴⁾⁽¹⁶⁾. The fractional contribution of each component to the spectra, plotted against x in Fig. 7, shows a gradual concentration dependence.

Fig. 7 Variations of fractional contributions of spectral components L, M and S for the sputtered fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys (L, M and S are explained in the text). The closed symbols indicate the results estimated from the least square fitting to the experimental spectra, while the dotted lines indicate the results on the assumption of random Fe atom distribution in the fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys. The open symbols indicate the fractional numbers of Fe atoms whose hyperfine field ranges from 6 MA/m (80 kOe) to 16 MA/m (200 kOe) in Fig. 4.

Table 1. Mössbauer parameters for the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys at 290 K.

	Doublet: L		Doublet: M		Singlet: S
	IS (mm/s)	QS (mm/s)	IS (mm/s)	QS (mm/s)	IS (mm/s)
0.67	0.12 ± 0.04	0.50 ± 0.02	0.05 ± 0.04	0.33 ± 0.02	0.00 ± 0.04
0.70	0.14 ± 0.04	0.51 ± 0.02	0.06 ± 0.04	0.33 ± 0.02	0.02 ± 0.04
0.73	0.16 ± 0.04	0.60 ± 0.02	0.06 ± 0.04	0.32 ± 0.02	0.01 ± 0.04
0.78	0.19 ± 0.04	0.53 ± 0.02	0.12 ± 0.04	0.31 ± 0.02	0.08 ± 0.04
0.81	0.17 ± 0.04	0.57 ± 0.02	0.13 ± 0.04	0.29 ± 0.02	0.08 ± 0.04
0.83	0.14 ± 0.04	0.60 ± 0.02	0.12 ± 0.04	0.35 ± 0.02	0.09 ± 0.04
0.85	0.16 ± 0.04	0.56 ± 0.02	0.11 ± 0.04	0.32 ± 0.02	0.07 ± 0.04

Column headings are: IS , isomer shift in mm/s relative to α -Fe at room temperature. QS , quadrupole splitting in mm/s. (L, M and S are explained in the text).

III. Discussion

1. The bcc Fe_{1-x}Cu_x alloys

The bcc alloys with $x < 0.42^{(3)}$ exhibit relatively sharp magnetic hyperfine patterns with no well-resolved satellite structure. This suggests that a Cu atom behaves similarly to Ni or Co solute in an Fe matrix which causes no pronounced satellite line in the spectra⁽⁵⁾⁻⁽⁷⁾. In Fig. 8, the reduced hyperfine fields $h(x, T) = \bar{H}_{\text{hf}}(x, T) / \bar{H}_{\text{hf}}(0, T)$ at 4.2 K and 290 K are plotted against x for the sputtered bcc Fe_{1-x}Cu_x alloys together with those obtained by other experimental studies⁽⁸⁾⁽⁹⁾⁽¹⁷⁾⁽¹⁸⁾. At 290 K, $h(x, T)$ of the present sputtered alloys decreases linearly with increasing x and deviates downwards from the straight line extrapolated from the results for the solid quenched Fe_{1-x}Cu_x alloys with $x < 0.03^{(17)}$, while it deviates upwards from an empirical relation for Fe alloys with non-magnetic elements, $h(x, T) = 1 - 0.42x$, at $T = 290$ K⁽¹⁸⁾. At 4.2 K, $h(x, T)$ is less sensitive to x , as compared with that at 290 K. For ther-

Fig. 8. Reduced average hyperfine field, $h(x, T)$, of bcc Fe_{1-x}Cu_x alloys as a function of Cu concentration, x , where $h(x, T) = \bar{H}_{\text{hf}}(x, T) / \bar{H}_{\text{hf}}(0, T)$. ■ and ●: the sputtered alloys at 4.2 K and 290 K, respectively. ▽ and △: the thermally evaporated alloys at 77 K and 295 K⁽⁸⁾⁽⁹⁾. The open circles and the dashed line indicate the experimental results and the linearly extrapolated one for bulk bcc Fe_{1-x}Cu_x alloys⁽⁷⁾. The dash-dotted line indicates $h(x, T) = 1 - 0.42x$ ⁽¹⁸⁾.

mally evaporated Fe_{1-x}Cu_x alloys, the concentration-insensitive behavior of $h(x, T)$ was ascribed to the clustering or precipitation of Cu atoms during sample preparations, which reduces the average number of Cu atoms in the local environment of Fe atoms as compared with a random distribution⁽⁸⁾⁽⁹⁾. Though the immiscibility between Fe and Cu in the equilibrium state⁽³⁾ may not be suppressed completely even by the sputtering method, electron microscopic and electron diffraction studies of the present sputtered alloys showed no evidence of Cu clusters or precipitates. A preliminary NMR study of the bcc phase of sputtered Fe_{1-x}Cu_x alloys with $x = 0.35$ also gave no detectable signal indicating pure Cu metals. These results imply that the present bcc Fe_{1-x}Cu_x alloys hardly contain any well-defined Cu segregation.

2. The fcc Fe_{1-x}Cu_x alloys

The local arrangement of Fe atoms in fcc Fe_{1-x}Cu_x alloys can be examined by the analysis of Mössbauer spectra at 290 K, because the paramagnetic fcc Fe-Cu alloys exhibit the quadrupole splitting, QS , which is determined mainly by the short range atomic configuration around the central ⁵⁷Fe atom. Assuming the same dependence of QS and IS on the number of nearest neighbor Fe atoms, as have been done for the bulk fcc Fe-Cu alloys with dilute Fe⁽¹⁶⁾, we estimate the fractional contributions of three components, L, M, and S for the random fcc Fe_{1-x}Cu_x alloys. As shown in Fig. 7, they markedly depend on x in contrast to the gradual variations of three components with x , as analyzed for the present sputtered alloys. This suggests that the local arrangement of Fe atoms is not perfectly random in the present sputtered Fe_{1-x}Cu_x alloys.

At low temperatures, isolated Fe atoms in Cu matrices carry magnetic moments except in the ultimately dilute Kondo alloys⁽⁴⁾⁽¹⁴⁾⁽¹⁹⁾. Since their magnetic moments couple each other and randomly align via long range RKKY interactions, the isolated Fe atoms show a small hyperfine field of about 5.6 MA/m (70 kOe)⁽⁴⁾⁽¹⁴⁾. As the first nearest neighbor Fe atom pairs ferromagnetically couple each other, Fe atoms with one nearest neighbor Fe atom show

a hyperfine field, H_{hf} , of about 11 MA/m (140 kOe), Fe atoms with two nearest neighbor Fe atoms show H_{hf} of about 16 MA/m (200 kOe) and Fe atoms with three or four nearest neighbor Fe atoms show H_{hf} of 16.8–20 MA/m (210–250 kOe)⁽¹⁴⁾⁽¹⁹⁾⁽²⁰⁾. On the other hand, Fe atoms in the γ -Fe precipitates carry very small magnetic moments, which align antiferromagnetically and show H_{hf} of about 2 MA/m (25 kOe)⁽⁴⁾⁽¹⁹⁾⁽²⁰⁾. In this context, the hyperfine field distribution curve in Fig. 4 may be interpreted as follows. The component, A, ranging from 6.4 MA/m (80 kOe) to 16 MA/m (200 kOe) may be ascribed to Fe atoms with one or two nearest neighbor Fe atoms. As shown in Fig. 7, the fractional number of these Fe atoms gradually changes with increasing x , being in rough agreement with the concentration dependence in the fractional contribution of the component L. The component, B, ranging from 16 MA/m (200 kOe) to 30 MA/m (380 kOe) may be attributable to Fe atoms with more than two nearest neighbor Fe atoms. The component, C, lower than 6 MA/m (80 kOe) can be ascribed to γ -Fe-like and isolated Fe atoms⁽⁴⁾⁽¹⁴⁾⁽²⁰⁾⁽²¹⁾. However, it is very weak. This indicates that the numbers of γ -Fe-like and isolated Fe atoms are quite small. Thus, the sum of fractional numbers of the components, B and C, roughly agrees with the sum of the contributions of M and S shown in Fig. 7. The contribution of α -Fe clusters, which should exhibit a hyperfine field of about 27 MA/m (340 kOe)⁽⁴⁾⁽¹⁴⁾⁽¹⁹⁾⁽²⁰⁾, is not clearly discriminated in the present spectra except for $x=0.61$, i.e., a maximum of the hyperfine field distribution curve is located around 27 MA/m (340 kOe) for $x=0.61$, possibly indicating the existence of small α -Fe particles which could not be detected by X-ray diffraction experiments.

The average hyperfine field, $\bar{H}_{\text{hf}}$, of fcc $\text{Fe}_{1-x}\text{Cu}_x$ alloys is lower than those of the fcc Fe-Ag and Fe-Au alloys at 4.2 K⁽²⁾⁽²²⁾⁽²³⁾, being in accordance with the results of magnetization measurements⁽³⁾: The magnetic moment of Fe atoms in the fcc Fe-Cu alloys is much smaller than those in the fcc Fe-Ag and Fe-Au alloys⁽³⁾⁽²³⁾⁽²⁴⁾. These features can be ascribed to smaller lattice constants of fcc Fe-Cu alloys compared with those of the fcc Fe-Ag and Fe-

Au alloys⁽³⁾⁽²³⁾, because the magnetic moment of Fe atoms becomes larger as the interatomic distance between Fe atoms increases⁽³⁾⁽²⁵⁾⁻⁽²⁷⁾. Moreover, the gradual concentration dependence of $\bar{H}_{\text{hf}}$ is incompatible with the sharp concentration dependence of the magnetic moment of Fe atoms in the sputtered $\text{Fe}_{1-x}\text{Cu}_x$ alloys. These aspects are partly ascribed to a spin-glass-like magnetic ordering, as was observed in thermally evaporated Fe-Cu alloys with dilute Fe concentrations⁽²⁸⁾.

Acknowledgements

The authors wish to thank Dr. M. Shiga for valuable suggestion in the analysis of Mössbauer spectra. They are also indebted to Mr. K. Yoshimura for the NMR measurements of the sputtered bcc Fe-Cu alloy. This work was supported partially by a Grant-in-Aid for Scientific Research given by the Ministry of Education, Science and Culture of Japan.

REFERENCES

- (1) K. Sumiyama and Y. Nakamura: J. Magn. Magn. Mat., **35** (1983), 219.
- (2) K. Sumiyama and Y. Nakamura: Physica Status Solidi, (a)**81**, (1984), K109.
- (3) K. Sumiyama, T. Yoshitake and Y. Nakamura: J. Phys. Soc. Japan, **53** (1984), 3160.
- (4) U. Gonser and M. Ron: *Applications of Mössbauer Spectroscopy II*, ed. by R. L. Cohen, Academic Press, New York, (1980), p. 281 and references quoted therein.
- (5) G. K. Wertheim, V. Jaccarino, J. H. Wernick and D. N. E. Buchanan: Phys. Rev. Lett. **12** (1964), 24.
- (6) S. K. Lahiri, D. Chandra, L. H. Schwartz and M. E. Fine: Trans. Met. Soc. AIME, **245** (1969), 1865.
- (7) I. Vincze and A. T. Aldred: Solid State Commun., **17** (1975), 639.
- (8) W. Keune, J. Lauer, D. L. Williamson: J. Physique, **35** (1974), C6-473.
- (9) J. Lauer, W. Keune, U. Gonser and D. L. Williamson: J. Magn. Magn. Mat., **7** (1978), 75.
- (10) J. Hesse and A. Rubartsch: J. Phys. E: Sci. Instrum., **7** (1974), 526.
- (11) K. Sumiyama, M. Kadono and Y. Nakamura: Trans. JIM, **22** (1981), 686.
- (12) K. Sumiyama, M. Kadono and Y. Nakamura: Trans. JIM, **24** (1983), 190.
- (13) H. Fujimori and N. S. Kazama: Sci. Rep. RITU A-27 (1977), 177.
- (14) B. Window: Phil. Mag., **26** (1972), 681.
- (15) G. Longworth and R. Jain: J. Phys. F: Metal Phys., **8** (1978), 351.
- (16) P. E. Clark, J. M. Cadogan, M. J. Yazghi and S. J.

- Campbell: J. Phys. F: Metal Phys., **9** (1979), 379.
- (17) I. Vincze and I. A. Campbell: J. Phys. F: Metal Phys., **3** (1973), 647.
- (18) M. B. Sterns: Phys. Rev., **B6** (1972), 3326.
- (19) S. J. Campbell, P. E. Clark and T. J. Hicks: J. Phys. F: Metal Phys., **6** (1976), 249.
- (20) S. J. Campbell and P. E. Clark: J. Phys. F: Metal Phys., **4** (1974), 1073.
- (21) Y. Nakamura, Y. Hamakawa and M. Shiga: *Proc. Int. Conf. on The Applications of The Mössbauer Effect*, Indian National Science Academy, (1982), p. 250.
- (22) B. Window: Phys. Rev., **B6** (1972), 2013.
- (23) N. Kataoka, K. Sumiyama and Y. Nakamura: J. Phys. F: Metal Phys., **15** (1985), No. 6.
- (24) W. Felsch: Z. Angew. Physik, **29** (1970), 217.
- (25) R. J. Weiss: Proc. Phys. Soc., **82** (1963), 281.
- (26) M. Shiga: Solid State Commun., **10** (1972), 1233.
- (27) O. K. Andersen, J. Madsen, U. K. Poulsen, O. Jepsen and J. Kollar: Physica, **86-88B** (1977), 249.
- (28) G. Zibold and D. Korn: J. Magn. Magn. Mat., **9** (1978), 34.
-