High Temperature Oxidation of the Austenitic Fe-9Al-30Mn-1.0C and Duplex Fe-10Al-29Mn-0.4C Alloys

By S. C. Tjong*

The oxidation behaviors of the austenitic Fe-8.7Al-29.7Mn-1.04C and duplex Fe-10Al-29Mn-0.4C alloys in air at elevated temperatures have been investigated by the X-ray diffraction and metallographic techniques. The results showed that the oxide nodules were formed on the surface of both alloys at 1073 and 1273 K during the early stage of oxidation. These oxide nodules grew and eventually coalesced to form continuous duplex scales. The composition and structure of the duplex scales depended on the oxidation temperature and alloy composition. For the duplex Fe-10Al-29Mn-0.4C alloy oxidized in air at 1073 K for 259.2 ks (72 h), the duplex scales consisted of an outer $(\text{FeMn})_2\text{O}_3$ layer and an inner $\alpha\text{-Al}_2\text{O}_3$ layer at the oxide-alloy interface. However, oxidation of the duplex Fe-10Al-29Mn-0.4C alloy at 1273 K for 259.2 ks led to the formation of an external $(\text{FeMn})_3\text{O}_4$ and an inner $\alpha\text{-Al}_2\text{O}_3$ layers with some internal oxides precipitated within the austenitic phase. Furthermore, the SEM micrographs showed that the oxide growth pits were formed on the austenitic Fe-8.7Al-29.7Mn-1.04C alloy after exposure in air at 1273 K for 259.2 ks. However, oxide pyramids were observed to grow on this alloy as the temperature was increased to 1473 K.

(Received November 6, 1986)

Keywords: oxidation, iron-aluminum-manganese-carbon alloy, duplex alloy, oxide nodule, oxide pyramid

I. Introduction

The Fe-Al-Mn-C alloys have attracted considerable attention recently in the possibilities of developing these alloys as substitutes for conventional stainless steels in many applications. The Fe-Al-Mn-C alloys are anticipated to possess good corrosion resistance in both aqueous and gaseous environments. The oxidation and corrosion resistance of Fe-Al-Mn-C alloys are derived from the aluminum content. The aqueous corrosion properties of the Fe-Al-Mn-C alloys have been extensively investigated by the author⁽¹⁾⁻⁽⁴⁾. Tjong reported that the austenitic Fe-8.7Al-29.7Mn-1.04C alloy passivated with difficulty in sulphuric acid solution and showed no passivation behavior in slightly basic solutions. This alloy only passivated in aqueous solutions with pH ranged from 5.5 to 6.10⁽²⁾. Furthermore, the solution treated and aged Fe-8.7Al-29.7Mn-1.04C alloy were also found to be susceptible

to hydrogen embrittlement⁽³⁾⁽⁴⁾. On the other hand, some Fe-Al-Mn alloys have been reported to exhibit excellent oxidation resistance up to temperatures of 1373 K⁽⁵⁾.

The high temperature oxidation resistance of the Fe-Al-Mn alloys is usually related to the contents of the alloying elements. Jackson and Wallwork⁽⁶⁾ reported that the ferritic Fe-(5-10)%Mn-(6-10)%Al was the most oxidation resistant alloy. However, Sauer *et al.*⁽⁷⁾ reported that the Fe-32Mn-7.5Al-0.6C alloys containing 1-2% Si have good oxidation resistance up to 1123 K. The purpose of this paper is to study the effects of the carbon content on the morphological development of the oxide scales formed on the austenitic Fe-8.7Al-29.7Mn-1.04C and duplex Fe-10Al-29Mn-0.4C alloys in air at elevated temperatures.

II. Experimental

The austenitic Fe-8.7Al-29.7Mn-1.04C and duplex Fe-10Al-29Mn-0.4C alloys (where the composition is given in mass%) were prepared by melting high purity iron, manganese and

* Institute of Materials Science & Engineering, National Sun Yat-Sen University, Kaohsiung, Taiwan, Rep. of China.

aluminum in a laboratory induction furnace. The melts were then cast into the steel molds. Each cast ingot was hot-forged at 1473 K into a billet. The billet was homogenized at 1373 K for 43.2 ks, air cooled and subsequently cold rolled to 2 mm thick plates. These plates were further vacuum annealed at 1323 K for 7.2 ks and immediately quenched into water upon removal from the furnace.

The sample coupons with dimensions of about 5 mm × 4 mm × 2 mm were cut from the plates and mechanically polished in steps down to 600 SiC grit. Prior to the oxidation test, each specimen was cleaned in an ultrasonic cleaner, rinsed in methanol, and air dried. The specimen was subsequently positioned inside the furnace.

The oxidation kinetics were carried out in air at 1273 K using a Netzsch 409 thermobalance in combination with a Netzsch model 414 data acquisition system and a Hewlett Packard model 86B personal computer. The sensitivity of the microbalance was 50 μ g.

The surface morphologies and transverse sections of the oxide scales formed on the alloys investigated were examined by a JEOL model JSM-35 scanning electron microscope equipped with an energy dispersive X-ray analyser (EDAX) system. The EDAX were used to determined distributions of elements in the various oxide phases. The structure of the oxide scales were further determined with a Rigaku X-ray diffractometer equipped with a Mo-K α

radiation. The specimens for metallographic cross-section examinations were prepared by mounting the oxidized specimens in epoxy resin. The mounted specimens were polished with successively finer grades of alumina down to 0.05 μ m.

III. Results and Discussion

Figure 1 shows the X-ray diffraction pattern of the oxides formed on the duplex Fe-10Al-29Mn-0.4C alloy at 1073 K for 259.2 ks. The oxides are identified as Mn₂O₃, α -Fe₂O₃ and α -Al₂O₃. The SEM micrograph of the surface layer of these oxides are shown in Fig. 2. It can be seen that the oxides formed on the duplex alloy exhibit a nodular structure. The metallographic cross-section of a oxide nodule and its respective X-ray images are shown in Fig. 3 (a)–(d). X-ray images revealed that typical double layered scales were formed on the duplex alloy. The outer layer was highly enriched in manganese and iron. The inner layer was depleted of manganese, iron, and enriched only in aluminum. On the basis of these results, it appears that the outer region of the nodule consists of a solid solution phase (FeMn)₂O₃. A continuous healing layer of α -Al₂O₃ is formed at the nodule-alloy interface. Jackson and Wallwork⁽⁸⁾ reported that the oxide scales formed on the binary iron-manganese alloys at elevated temperatures composed predominantly of solid solution

Fig. 1 The X-ray diffraction pattern for the oxides formed on the Fe-10Al-29Mn-0.4C alloy in air at 1073 K for 259.2 ks.

Fig. 2 SEM micrograph showing the surface morphology of the oxides formed on the Fe-10Al-29Mn-0.4C alloy in air at 1073 K for 259.2 ks.

phases of the type (FeMn)O, (FeMn)₃O₄ and (FeMn)₂O₃. However, the addition of aluminum to the iron-manganese alloys prevents formation of the oxides FeO and MnO. This is

due to the formation of α -Al₂O₃ oxide with much lower dissociation pressures at the oxide-alloy interface⁽⁶⁾.

Figure 4(a) shows the cross-sectional microstructure of the duplex alloy oxidized at 1273 K for 3.6 ks. It is obvious that several oxide nodules are formed within the austenitic phase of the duplex Fe-10Al-29Mn-0.4C alloy during the early stage of oxidation. The corresponding elemental distributions in the oxide nodules are shown in Fig. 4(b)–(d). These X-ray images show that iron and manganese are uniformly distributed within the nodules whereas aluminum is enriched at the nodule-alloy interface. However, as the oxidation time is increased to 259.2 ks, the oxide nodules tend to coalesce and eventually overgrow the entire specimen surface (Fig. 5). Furthermore, some internal oxides are observed to be precipitated in the austenitic phase of the duplex alloy after long exposure in air for 259.2 ks.

Figure 6 shows the X-ray diffraction pattern

Fig. 3 The microstructure and X-ray images of the cross-section of an oxide nodule formed on the Fe-10Al-29Mn-0.4C alloy in air at 1073 K for 259.2 ks. (a) SEM image, (b) Fe X-ray image, (c) Mn X-ray image and (d) Al X-ray image.

Fig. 4 The microstructure and X-ray maps of the cross-section of the oxide nodules formed on the Fe-10Al-29Mn-0.4C alloy in air at 1273 K for 3.6 ks. (a) Backscattered electron image, (b) Fe X-ray image, (c) Mn X-ray image and (d) Al X-ray image.

Fig. 5 SEM micrograph of the cross-section of the oxide scales formed on the Fe-10Al-29Mn-0.4C alloy in air at 1273 K for 259.2 ks.

of the oxide scales formed on the duplex alloy at 1273 K for 259.2 ks. As can be seen that the oxide scales predominantly composed of

Fe_3O_4 , Mn_3O_4 and $\alpha\text{-Al}_2\text{O}_3$. A higher magnification of the metallographic cross-section and X-ray images of the oxide scales are shown in Fig. 7 (a)–(d). The outer scale is found to be enriched in iron. Aluminum is again enriched at the oxide-alloy interface and at the outer layer of the internal oxides. According to these determinations, the thick outer oxide scale consist of a solid solution of $(\text{FeMn})_3\text{O}_4$ phase. The alumina is only formed at the oxide-alloy interface and the internal oxide-alloy interface.

Based on Wagner's secondary getter theory, the addition of an element with an oxygen sensitivity between that for iron and aluminum should prevent nodule growth⁽⁹⁾⁽¹⁰⁾. The free energy of formation of the chromium oxide (Cr_2O_3) is between that of the oxides of iron and aluminum, and consequently the formation of oxide nodule on the Fe-Al alloys is suppressed⁽¹¹⁾. The free energy of formation of MnO is close to that for Cr_2O_3 , and the addition of manganese to Fe-Al alloys is expected to suppress nodule growth. However, Tomaszewicz and Wallwork reported that

Fig. 6 The X-ray diffraction pattern for the oxide scales formed on the Fe-10Al-29Mn-0.4C alloy in air at 1273 K for 259.2 ks.

manganese contributed little to the oxidation resistance and even adversely affected certain oxidation parameters. The addition of manganese to Fe-4Al alloy promoted the growth and coalescence of iron oxide nodules⁽¹¹⁾. The present work is consistent with the above report and shows that the addition of manganese to Fe-10Al alloy favors formation of the oxide nodules.

Figure 8 (a)–(d) show the microstructure and X-ray maps of the cross-section of the oxide scales formed on the austenitic Fe-8.7Al-29.7Mn-1.04C alloy in air at 1073 K for 259.2 ks. The oxide scales were identified by X-ray diffraction as Mn_2O_3 , $\alpha\text{-Fe}_2\text{O}_3$ and $\alpha\text{-Al}_2\text{O}_3$. Oxidation of the austenitic Fe-8.7Al-29.7Mn-1.04C alloy at 1073 K gave rise to a similar two layered scales structure. The X-ray cross-sectional examination for the austenitic alloy revealed that the outer layer was enriched in manganese with the incorporation of small amount of iron in this outer region. Thus, the outer layer was probably composed of $(\text{FeMn})_2\text{O}_3$. In addition, the oxide nodules which were formed during the initial stage of oxidation finally coalesced to form a continuous $(\text{FeMn})_2\text{O}_3$ external layer.

Figure 9 (a) and (b) show typical mass gain versus time curves for the oxidation of austenitic Fe-8.7Al-29.7Mn-1.04C and duplex Fe-10Al-29Mn-0.4C alloy in air at 1273 K.

It is apparent that the austenitic Fe-8.7Al-29.7Mn-1.04C alloy exhibits much faster oxidation rate compared with the duplex alloy. It is likely that the higher aluminum concentration of the duplex alloy enables a more effective Al_2O_3 layer to develop more rapidly. Jackson and Wallwork indicated that the austenitic phase of the duplex Fe-Al-Mn alloys containing no carbon addition is detrimental to the oxidation resistance as it promoted the breakdown of alumina scales⁽⁶⁾. Carbon is well known as a austenite stabilizer and the addition of this element to Fe-8.7Al-29.7Mn alloy up to 1% leads to the formation of a single austenitic structure. For the Fe-10Al-29Mn alloy containing 0.4% carbon, the microstructure of the alloy consists of a duplex ($\alpha + \gamma$) phases. It has been reported that carbon does not contribute to oxidation resistance in a high temperature oxidizing environment. A high carbon Fe-Mn-Al-C alloy has good oxidation resistance only below 1273 K⁽⁷⁾⁽¹²⁾. In the present work, the oxidation kinetics results show that the duplex Fe-10Al-29Mn-0.4C alloy has a much lower oxidation rate than the austenitic Fe-8.7Al-29.7Mn-1.04C alloy. Therefore, the addition of carbon to the Fe-Al-Mn alloy up to 1% is believed to have detrimental effect on the high temperature oxidation resistance.

Figure 10 (a) and (b) show the surface morphologies of the oxide scales formed on

Fig. 7 A higher magnification of the microstructure and X-ray images of the oxide scales formed on the Fe-10Al-29Mn-0.4C alloy in air at 1273 K for 259.2 ks. (a) SEM image, (b) Fe X-ray image, (c) Mn X-ray image and (d) Al X-ray image.

the Fe-8.7Al-29.7Mn-1.04C alloy at 1273 K and 1473 K for 259.2 ks. It is obvious from Fig. 10(a) that the oxide scales formed on the Fe-8.7Al-29.7Mn-1.04C alloy at 1273 K exhibits dislocation pit morphology. On the other hand, the oxidation of this alloy at 1473 K results in the growth of the oxide pyramids. A schematic diagram of the structure of oxide pyramid is shown in Fig. 10(c).

Rapp and his co-workers⁽¹³⁾⁻⁽¹⁵⁾ have observed the growth of oxide scales on metals (Cu, Fe, Ni) in a hot-stage environmental scan-

ning electron microscope. They reported that the scales on pure metals exhibit irregular growth morphologies, i.e., whiskers, pyramids and pits. The appearance of these oxide growth morphologies is depended on the oxidation temperatures. At low temperatures, the oxide whiskers grow predominantly by surface diffusion of cations along a tunnel centered on a cored of a screw dislocation or a bundle of dislocations. These dislocations are formed by oxidation growth stresses or are inherited from the metal substrate through epitaxial relation-

Fig. 8 The microscopic section and the characteristic X-ray images of the austenitic Fe-8.7Al-29.7Mn-1.04C alloy exposed in air at 1273 K for 259.2 ks. (a) SEM image, (b) backscattered electron image, (c) Fe X-ray image and (d) Mn X-ray image.

ships. Further lateral whisker growth occurs via lattice diffusion. As the temperature increases, lattice diffusion becomes more significant so the lateral growth leads to the formation of a pyramid. However, at sufficiently high temperatures, only the oxide growth pits are observed. Growth pits are formed at the oxide/gas interface at the emergence of a screw dislocation. The intersection of a screw dislocation with a surface provides ledges for the extension of the oxide lattice⁽¹³⁾⁽¹⁴⁾. Pits are formed during oxide growth in order to minimize the sum of dislocation line tension

and surface energy⁽¹⁶⁾. The present work confirms the existence of the oxide growth pits and pyramids in a Fe-8.7Al-29.7Mn-1.04C alloy. The oxide growth pits are observed to grow on this alloy at a lower oxidation temperature (1273 K) whilst these pits are observed at a higher oxidation temperature (1473 K) for iron oxidation⁽¹⁴⁾.

IV. Summary

(1) Addition of manganese to the Fe-Al-Mn-C alloys promotes formation, growth,

Fig. 9 Oxidation behavior of the (a) duplex Fe-10Al-29Mn-0.4C alloy and (b) austenitic Fe-8.7Al-29.7Mn-1.04C alloy exposed in air at 1273 K.

and coalescence of the oxide nodules.

(2) Oxide growth pits are observed in the austenitic Fe-8.7Al-29.7Mn-1.04C alloy after exposure in air at 1273 K for 259.2 ks. However, oxide pyramids are observed to grow on this alloy as the oxidation temperature is increased to 1473 K.

Acknowledgments

This work was supported by the National Science Council of ROC through Grant no. NSC 74-0201-E110-01. The author would also like to thank Prof. C. M. Wan of National Tsing Hua University for providing the alloys investigated.

REFERENCES

- (1) S. C. Tjong: *J. Mater. Sci.*, **21** (1986), 1166.
- (2) S. C. Tjong: *Surf. Coatings Technol.*, **28** (1986), 181.
- (3) S. C. Tjong and C. S. Wu: *Mater. Sci. Eng.*, **80** (1986), 203.
- (4) S. C. Tjong: *Werks. U. Korros.*, **37** (1986), 444.
- (5) R. Wang, M. J. Straszheim and R. A. Rapp: *Oxid. Met.*, **21** (1984), 71.
- (6) P. R. S. Jackson and G. R. Wallwork: *Oxid. Met.*, **21** (1984), 135.
- (7) J. P. Sauer, R. A. Rapp and J. P. Hirth: *Oxid. Met.*, **18** (1982), 285.

Fig. 10 Scanning electron micrographs of the surface oxide of Fe-8.7Al-29.7Mn-1.04C alloy oxidized in air for 259.2 ks at (a) 1273 K and (b) 1473 K. (c) Schematic diagram of the structure of oxide pyramid as shown in (b).

- (8) P. R. S. Jackson and G. R. Wallwork: *Oxid. Met.*, **20** (1983), 1.
- (9) C. Wagner: *Corros. Sci.*, **5** (1965), 751.
- (10) W. E. Boggs: *J. Electrochem. Soc.*, **118** (1971), 906.
- (11) P. Tomaszewicz and G. R. Wallwork: *High Temperature Corrosion*, NACE-6, Houston, (1981), p. 258.
- (12) J. C. Garcia, N. Rosas and R. J. Rioja: *Metal Prog.*, **117** (1982), 47.
- (13) G. M. Raynaud and R. A. Rapp: *Oxid. Met.*, **21** (1984), 89.
- (14) T. L. Jungling and R. A. Rapp: *Metall. Trans.*, **15A** (1984), 2231.
- (15) R. A. Rapp: *Metall. Trans.*, **15B** (1984), 195.
- (16) F. C. Franck: *Acta Cryst.*, **4** (1951), 497.