LETTERS TO THE EDITORS

Electrolytic Hydrogen Charging in Niobium Single Crystals

(Received June 1, 1967)

The interaction of niobium metal with hydrogen gas has been studied by many workers. X-ray examinations^{(1)~(5)} and microscopic observations^{(3)~(6)} have been carried out on the niobium metal reacted with hydrogen gas at higher temperatures above 200°C. In these experiments, contamination with impurities (nitrogen and oxygen) has been hardly avoidable^{(2)~(6)} during hydrogen gas charging. The present study was, therefore, undertaken to clarify the effect of hydrogen addition by an electrolytic charging technique on the impurity contamination and on the microstructure of Nb-H alloys^{(6)~(8)}.

Specimens were cut out from the single crystal bars (5 mm ϕ $\times$ 100 mm) produced by electron bombardment melting. After conventional metallographic polishing, the specimens were annealed at 1000°C in a vacuum of 1×10^{-6} mmHg to homogenize the surface condition. Laue's back reflection photographs of the specimens

were taken to determine the crystallographic orientation.

Hydrogen was introduced by the electrolytic charging method using a niobium single crystal as a cathode and a platinum wire as an anode. The specimen was set at the center of a glass frame around which a platinum wire was coiled. Charging was carried out in a 0.2 N-H₂SO₄ solution at 40°C and the current density was about 0.1 A/cm².

Photo. 1 Section of the specimen charged for 10 hr. ($\times 50$)
a: Surface region with hydride.
b: Intermediate region with plate-like hydride.
c: Core region.

Photo. 2 Structure of intermediate region. Observed surface inclines a few degrees from the (110) plane and traces of hydride are intersecting at right angle. ($\times 500$)

Photo. 3 Structure of intermediate region. Observed surface is close to the (111) plane and triangular traces of hydrides are observed. ($\times 500$)

- (1) C. Wainwright, A. J. Cook and B. E. Hopkins: *J. Less-common Metals*, 6 (1964), 362.
- (2) R. J. Walter and W. T. Chandler: *Trans. AIME*, 233 (1965), 762.
- (3) S. Komjathy: *J. Less-common Metals*, 2 (1960), 466.
- (4) H. W. Paxton, J. M. Sheehan and W. J. Babyak: *Trans. AIME*, 215 (1959), 725.
- (5) G. C. Rauch, R. M. Rose and J. Wulff: *J. Less-common Metals*, 8 (1965), 99.
- (6) Y. Sasaki, H. Kimura and S. Uehara: *J. Japan Inst. Metals*, 31 (1967), 401.
- (7) Y. Sasaki: *Proc. of Memorial Lecture Meeting on 10th Anniversary of Found. of National Research Inst. for Metals*, (1966), 150~151.
- (8) Y. Sasaki and M. Amano: *Preprint of Japan Inst. Metals, Spring Meeting, Apr. (1967), 67~68.*

After charging, the specimens were analyzed chemically and examined metallographically with the longitudinal and the transverse sections. The analysis of hydrogen and impurities was performed by an inert gas carrier method and a vacuum fusion gas analysis

method, respectively.

The hydrogen concentration in the surface region of the specimens is about 48 ± 2 at% which corresponds to that⁽²⁾ in niobium hydride, whereas the hydrogen concentration in the core region of the specimens is about 1 at%. This indicates an inhomogeneous distribution of hydrogen in the sections. Nitrogen and oxygen picked up during the process are less than 20 ppm which is within the error of chemical analysis.

The typical microstructure of the section of the specimen charged for 10 hr is shown in Photo. 1. The heterogeneous distribution of hydrides is observed. The sectional structure can be divided into three regions; the surface region with hydride, the intermediate region with plate-like hydride and the core region. In the surface region, several cracks are observed as shown in Photo. 1. The cracks might have been formed by the stress resulting from the volume change during the phase transformation from niobium to hydride. In the intermediate region, the plates of hydride are intersecting each other as shown in Photos. 2 and 3. In Photo. 2, the observed surface inclines a

few degrees from (110) and the plate-like hydrides align along $\langle 1\bar{1}0 \rangle$ and $\langle 001 \rangle$. The former is the precipitates on the (001) matrix plane perpendicular to the observed surface. The latter is the precipitates on the (010) and (100) planes with an angle of about 45° from the observed surface. Triangular traces of hydrides aligned on the three {100} planes are observed in the (111) specimen as shown in Photo. 3. From these observations, it is found that the plate-like hydride in the intermediate region aligns on the {100} matrix plane, and this is consistent with the previous finding⁽²⁾⁽⁴⁾ in the alloys prepared by gas reaction.

It is certain that electrolytic charging is a satisfactory method for introducing hydrogen without the impurity contamination. It will be expected that the high purity niobium hydride can be obtained by the electrolytic hydrogen charging method under an optimum condition.

By Yasuo Sasaki* and Muneyuki Amano*

*National Research Institute for Metals, Tokyo, Japan.