Thermodynamic Properties of Mercury-Indium Liquid Alloys

By Yasuhiro Okajima* and Mitsuo Shimoji*

Using a dew point method, the vapour pressure of mercury over mercury-indium liquid alloys has been measured. The partial and integral molar excess free energies, excess entropies and excess enthalpies of this system have been determined. The experimental results were discussed in terms of the metallic solution theories.

(Received March 25, 1968)

I. Introduction

The measurement of vapour pressure is one of the most direct methods for the determination of activity. When one component of a system is much more volatile than the other, the dew point method developed by Hargraves⁽¹⁾ is suitable for partial pressure measurements. In this paper it is reported that thermodynamic studies on mercury-indium liquid alloys in the temperature range from 150° to 250°C were made by

the dew point method. Mercury melts at -38.9°C and boils at 356.6°C, while indium has a virtually negligible vapour pressure in this temperature range. The calorimetric measurements of this system have been made by Kleppa and Kaplan⁽²⁾, and Kleppa⁽³⁾. Hultgren et al.⁽⁴⁾ reported the free energies in the atomic fraction of indium $X_{\text{In}} < 0.5$, which are selected from

* Department of Chemistry, Faculty of Science, Hokkaido University, Sapporo, Japan.

(1) R. Hargraves : J. Inst. Metals, **64** (1939), 115.

(2) O. J. Kleppa and M. Kaplan : J. Chem. Phys., **61** (1957), 1120.

(3) O. J. Kleppa : Acta Met., **8** (1960), 435.

(4) R. Hultgren, R. L. Orr, P. D. Anderson and K. K. Kelley : *Selected Values of Thermodynamic Properties of Metals and Alloys*, Wiley, (1963).

the data of the e.m.f. measurements at 20°C by Sundén⁽⁵⁾. After our experiments were finished, thermodynamic properties of this system in the temperature range from 284° to 423°C were reported by Predel and Rothacker⁽⁶⁾. However, the temperature in their measurement is higher than that in the authors' experiment.

II. Experimental

The apparatus, illustrated in Fig. 1, was similar to that of Birchenall and Cheng⁽⁷⁾. The pyrex furnace, which was heated by three resistance windings, was designed to provide an adequate length of the hot zone for the alloy portion of the specimen tube and a variable temperature gradient leading to the cold zone. The hot zone of the furnace was thermostatically regulated within $\pm 0.5^\circ\text{C}$ by a temperature controller with a chromel-alumel thermocouple, D, and another chromel-alumel thermocouple, C, was used for the temperature measurement. The latter were calibrated against the boiling point of water and the melting points of tin and bismuth. A stainless steel spacer was constructed to diminish heat losses and to facilitate the positioning of the specimen tube in the furnace.

Fig. 1 Experimental apparatus. A, B, C, Chromel-Alumel thermocouples; D Control thermocouple; E Stainless steel spacer; F Specimen tube; G Brick disc; H Sample boat; I Ag Block; J Auxiliary heater; K light; L Telescope; 1, 2, 3 Furnace windings.

The alloy to be studied was prepared from pure mercury and indium (99.999%) in the sample boat placed in the specimen tube which was sealed under a vacuum of 10^{-5} mmHg. Wound about the cold zone was an auxiliary heater, the temperature of which could rapidly be changed by adjusting variable resistances connected in series with it. The specimen tube placed in the spacer was inserted in the furnace with the cold zone observable along the cross-arms using a cathetometric telescope. The thermocouple for temperature measurement, A, was positioned at the expected point of condensation.

The temperature gradient in the furnace was checked by a thermocouple, B, to prevent it from falling below

the temperature recorded by a thermocouple, A. On beginning a run, the temperature of the cold zone of the specimen tube was lowered until droplets of mercury condensed. These were evaporated by raising the temperature of the auxiliary heater and recondensed by lowering the temperature of the heater. The cycle was repeated several times until the difference between condensation and evaporation temperatures became within $\pm 0.5^\circ\text{C}$. An assortment of the different temperatures was designed to eliminate the possible systematic errors and to confirm an equilibrium state of the alloys tested.

III. Results and Discussion

In the dew point method the equilibrium vapour pressure of mercury for the alloy, P_{Hg} at the measuring temperature, T_{H} , is equal to the equilibrium vapour pressure of pure mercury, P_{Hg}° , at the cold temperature, T_{C} . According to Kubaschewski⁽⁸⁾, the vapour pressure of pure mercury is represented by the equation,

$$\log P_{\text{Hg}}^\circ (\text{mmHg}) = 10.355 - (3305/T) - 0.795 \log T. \quad (1)$$

Then the vapour pressure for the alloy, P_{Hg} , can be calculated by the relation,

$$\log P_{\text{Hg}} (\text{mmHg}) [T_{\text{H}}] = 10.355 - (3305/T_{\text{C}}) - 0.795 \log T_{\text{C}}. \quad (2)$$

The activity curves of mercury in the mercury-indium system at 160° and 240°C and that of indium at 160°C are shown in Fig. 2, the latter being obtained by a graphical integration of the Gibbs-Duhem equation⁽⁹⁾. The activities of mercury at 160° and 240°C are not contradictory to those obtained by Predel and Rothacker⁽⁵⁾ at 284°C. The activities of mercury

Fig. 2 The activity curves in the liquid Hg-In alloys — 160°C, --- 240°C, — — Predel and Rothacker (284°C)

(5) N. Sundén : *Z. Elektrochem.*, **57** (1953), 100.

(6) B. Predel and D. Rothacker : *Acta Met.*, **15** (1967), 135.

(7) C. E. Birchenall and C. H. Cheng : *J. Metals*, **185** (1949), 428.

(8) O. Kubaschewsky and E. L. Evans : *Metallurgical Thermochemistry*, London Pergamon Press, (1955).

(9) L. S. Darken and R. W. Gurry : *Physical Chemistry of Metals*, McGraw-Hill, (1956).

Table 1 Thermodynamic properties of the liquid Hg-In system

X_{In}	$\bar{H}_{\text{Hg}}^E$	$\bar{H}_{\text{In}}^E$	$\bar{H}_{\text{Hg}}^{E*}$	$\bar{S}_{\text{Hg}}^E$	$\bar{S}_{\text{In}}^E$	$\bar{G}_{\text{Hg}}^E$	$\bar{G}_{\text{In}}^E$	$\bar{G}_{\text{Hg}}^{E\dagger}$	$\bar{G}_{\text{Hg}}^{E**}$
	cal/g·atom			cal/g·atom·deg.		cal/g·atom (at 160°C)			
0.1	-23	-1765	-20	-0.004	-0.27	-20	-1650	-20	-20
0.2	-85	-1400	-85	-0.009	-0.27	-81	-1290	-40	-80
0.3	-195	-1070	-195	-0.02	-0.23	-184	-970	-180	-180
0.4	-360	-770	-360	-0.073	-0.09	-329	-730	-320	-315
0.5	-570	-505	-575	-0.23	-0.01	-474	-500	-470	-470
0.6	-840	-295	-835	-0.29	+0.05	-717	-320	-700	—
0.7	-1120	-140	-1120	-0.31	+0.08	-985	-180	-950	—
0.8	-1365	-50	-1370	-0.22	+0.07	-1285	-80	-1210	—
0.9	-1605	-10	-1615	-0.13	+0.02	-1570	-20	-1550	—

* O. J. Kleppa⁽³⁾, ** Hultgren et al.⁽⁴⁾, † B. Predel and D. Rothacker⁽⁶⁾

and indium show negative deviations from Raoult's law in the whole concentration range. Least square analysis of the data demonstrates that the temperature dependence of the activity can be represented analytically by

$$\log a_{\text{Hg}} = A + B/T, \quad (3)$$

where A and B are empirical constants. The partial molar entropies and enthalpies of mixing are related to these empirical equations, i.e. $\Delta S_{\text{Hg}} = -4.576A$ cal/deg·g·atom and $\Delta H_{\text{Hg}} = 4.576B$ cal/g·atom, respectively.

The thermodynamic properties of alloys are summarized in Table 1. The values for partial molar excess enthalpy obtained by the authors are in agreement with those determined calorimetrically by Kleppa⁽³⁾. The values for partial molar excess free energy obtained by the authors are not greatly different from those extrapolated from the data of Predel and Rothacker⁽⁶⁾ even in the indium-rich region.

The molar free energy of mixing, ΔG , excess free energy, G^E , and excess enthalpy, H^E , are illustrated in Fig. 3. This system shows the large negative excess free energy, the greater part of which is due to the excess enthalpy. The molar entropy of mixing, ΔS , and excess entropy, S^E , are also given in Fig. 3. No significant discrepancy was found between the molar entropy obtained by the authors and those by Predel and Rothacker⁽⁶⁾ in spite of the difference in the temperatures experimented. In Fig. 4 are shown the ratio of the integral excess enthalpy to $X_{\text{In}}X_{\text{Hg}}$, which is expressed in the concentration range $0 < X_{\text{In}} < 0.5$ by the following equation:

$$H^E/X_{\text{In}}X_{\text{Hg}} = -2180 \text{ cal/g·atom}. \quad (4)$$

In the indium rich solution, the concentration dependence tends to be sub-regular⁽¹⁰⁾. These large negative excess enthalpy may be due to the charge transfer from indium to mercury atoms⁽¹¹⁾⁽¹²⁾.

From the point of view of the solution theory the excess entropy of binary mixtures consists of three factors;

(1) the ordering effect, usually called the "quasi-chemical" approximation⁽¹³⁾, i.e., the contribution of

Fig. 3 Molar quantities in the liquid Hg-In system at 160°C

Fig. 4 Ratio of excess enthalpy to $X_{\text{In}}X_{\text{Hg}}$ vs. composition of In

(10) H. K. Hardy : Acta Met., 1 (1953), 202.

(11) M. Shimoji : J. Phys. Soc. Japan, 14 (1959), 1525.

(12) J. H. O. Varley : Phil. Mag., 45 (1954), 887.

(13) E. A. Guggenheim : Mixtures, London, Oxford Univ. Press, (1952).

excess entropy due to non-randomness is

$$S_{\text{order}}^E = -X^2(1-X)^2 \omega^2 / z R T^2$$

where ω is the interchange energy, and z is the coordination number.

(2) the effect of volume change by alloying at a constant pressure and temperature, which is calculated according to the Scatchard formula⁽¹⁴⁾,

$$S_{\text{vol}}^E \simeq \alpha V^E / \beta,$$

where V^E is the excess volume, α is the thermal expansion coefficient, and β is the isothermal compressibility.

(3) the effect of change in vibrational frequency of an atom which is caused by unlike atoms occupying the nearest neighbour sites.

The excess entropies due to the effects (1) and (2), S_{order}^E and S_{vol}^E , are calculated using the present experimental enthalpy values as well as the density data of Klappa and Kaplan⁽²⁾. Table 2 shows a comparison of theoretical and experimental excess entropies. The $S_{\text{av.pot.}}^E$ is calculated on the basis of Prigogine's average potential model⁽¹⁵⁾, which takes into account of the effects (2) and (3). The average potential model is valid in the mercury-rich range,

(14) G. Scatchard: *Trans. Faraday Soc.*, **33** (1937), 160.

(15) I. Prigogine: *The Molecular Theory of Solutions*, Amsterdam, North-Holland, (1957).

Table 2. Excess entropies in the liquid Hg-In system

X_{In}	$S_{\text{exp.}}^E$	S_{order}^E	S_{vol}^E	$S_{\text{av.pot.}}^E$
	cal/g·atom·deg.			
0.1	-0.03	-0.01	-0.11	-0.05
0.2	-0.06	-0.04	-0.18	-0.08
0.3	-0.08	-0.07	-0.23	-0.10
0.4	-0.08	-0.10	-0.25	-0.15
0.5	-0.12	-0.11	-0.24	-0.16
0.6	-0.09	-0.10	-0.22	-0.15
0.7	-0.03	-0.07	-0.19	-0.14
0.8	+0.02	-0.03	-0.14	-0.13
0.9	+0.01	-0.01	-0.08	-0.08

while the values calculated from the Scatchard formula are too high.

IV. Conclusion

The thermodynamic properties of mercury-indium liquid alloys were studied by means of the dew point method. The activities of mercury and those of indium in the temperature range from 150° to 250°C show negative deviations from Raoult's law in the whole concentration range. The excess entropy can be interpreted in terms of Prigogine's average potential model, and the excess enthalpy may be due to the charge transfer from indium to mercury atoms.