オキシステアリン酸の分子間水素結合に関する研究 (第1~2報)

(昭和35年3月28日受理)

中島 磯吉・外山 修之†

(第1報) 10-オキシステアリン酸

結晶状態にある10-オキシステアリン酸がIRスペクトルのOH伸縮振動領域に示す水素結合している水酸基の吸収はメチルエステルに変えても大きい変化がないことから、水酸基は隣接分子の水酸基と水素結合をつくって、脂脂肪酸炭素鎖と直角方向に長鎖状に連なっていると推定された。また10-オキシステアリン酸とステアリン酸の種々の比率の混合物を融解急冷してえた混晶のIRスペクトルから水素結合している水酸基を定量し、その量がオキシステアリン酸濃度の2乗に比例することから上の推定が確かめられた。

1 緒 言

オキシステアリン酸は一般の脂肪酸と異なる種々の特質を有するため、潤滑油添加剤としてしばしば使用されている。一般にオキシ脂肪酸の示す特性は分子内にある水酸基がつくる分子間水素結合に基因するところが大きいと考えられるが、まだその結合の方式に関する知見は推定の域をでない。天然にえられるオキシ脂肪酸としてはヒマシ油中のリシノール酸が代表的なものであって、その水添によってえられる12-オキシステアリン酸とともに現在潤滑油添加剤として広く使用されている。一方、最近簡便な合成法¹⁾が確立された10-オキシステアリン酸およびその異性体、ならびにポリオキシステアリン酸も種々の目的に使用することが試みられている。いずれの場合にもこれらオキシ脂肪酸の性質を決定する重要な要素として分子間水素結合が存在すると考えられる。

通常分子間水素結合のIRスペクトルによる研究手段は、無極性溶媒に試料を溶解し、次第に薄めていくことによって変化する吸収帯を見るのであるが、オキシステアリン酸は一般に溶解度が低く、分子間水素結合が、IRスペクトルで測定できる濃度範囲の溶液がえにくい。また実際に潤滑油添加剤として使用する場合には相当に高濃度であり、特に金属面と接触する液相の部分では、多くの場合脂肪酸分子は集合して液相内部とは異なる規則的配置をとる²⁾ため結晶状態に近いと考えてよい³⁾。したがってオキシ脂肪酸の分子間水素結合を研究するために結晶状態における知見をえることが重要と考えられる。

脂肪酸が融解状態にある場合でも各分子は脂肪酸炭素鎖の方向には平行性がよくたもたれているという性質があるから⁴⁾、本研究ではオキシステアリン酸とステアリン酸との混融急冷物について主として実験した。

2 実 験

2.1 試 料

10-オキシステアリン酸はSwernらの方法¹⁾によって過塩素酸

触媒下で純オレイン酸にギ酸を作用させて合成したものでリン片状結晶としてえられた。mp 82.0°~82.2°C (文献値 81.5°~82.5°C), アセチル価 161 (計算値 163.8)。メチルエステル, mp 54.0°C (文献値 54.1°C)。ステアリン酸は市販品を再結晶によって精製したもので mp 69.4°C (文献値 69.6°C)。混融急冷試料はこれらステアリン酸および10-オキシステアリン酸両者をはかり取って混合し、ガラスザラ上で融解し、かきまぜながら急冷し、さらにこの操作を数回くりかえして融点およびIRスペクトルが一定になったことを確かめた。

2.2 IR スペクトル

IRスペクトルはPerkin-Elmer 21型分光光度計、塩化ナトリウムプリズムを使って1500~3800 cm⁻¹の範囲を測定した。3400 cm⁻¹付近にある水の吸収をさけるため主としてNujol mull法を用いたが2500~3000 cm⁻¹の範囲は臭化カリウム錠剤法によった。図1は10-オキシステアリン酸およびそのメチルエステルのIRスペクトルを示す。水酸基による吸収は3290~3380 cm⁻¹に現われ、酸、メチルエステルいずれも同図に示すとおりOH伸縮振動領域における吸収にはほとんど差がない。

—: 10-オキシステアリン酸
: 10-オキシステアリン酸メチル
 図1 10-オキシステアリン酸とその
 メチルエステルのIRスペクトル

図2 10-オキシステアリン酸(51%)とステアリン酸の混融急冷物のIRスペクトル

† 名古屋大学工学部応用化学教室, 名古屋市千種区

- 1) D. Swern, H. B. Knight, R. E. Koos, *J. Am. Chem. Soc.* **75**, 6212 (1953); S. P. Fore, W. G. Bickford, *J. Org. Chem.* **24**, 920 (1959).
- 2) H. A. Smith, R. M. McGill, *J. Phys. Chem.* **61**, 1025 (1957); H. A. Smith, T. Fort, Jr., *ibid.* **62**, 519 (1958).
- 3) J. A. Chapman, D. Tabor, *Proc. Roy. Soc. A* **242**, 96 (1957).
- 4) R. W. Morrow, *Phys. Rev.* **31**, 10 (1928).

混融急冷試料の IR スペクトルの例を図 2 に示した。 3300cm^{-1} 付近の吸収が急激に減少し、同時に 3640cm^{-1} 付近に遊離の水酸基の吸収と考えられる吸収が現われる。

混融急冷試料中の水素結合している水酸基の定量は 1700cm^{-1} の $\text{C}=\text{O}$ の伸縮振動による吸収が混合両成分について共通であるから、この吸収強度を基準とし、試料の 3290 および 3380cm^{-1} の吸収をそれぞれベースライン法によって 100% 10-オキシステアリン酸試料との比較値から計算した。定量結果は図 3 に示したが、両吸収波数からの定量値の間にはほとんど差がなく一括して示した。

図 3 水素結合水酸基定量結果

同図における直線は水素結合している水酸基量が 10-オキシステアリン酸量に比例すると考えた場合の理論吸収量、曲線は 10-オキシステアリン酸量の 2 乗に比例すると考えた場合の理論量を示す。実測値はあきらかに 2 乗の曲線に近い吸収量を示している。

2.3 X 線回折測定

装置はノレルコ型のガイガーフレックス(理学電機製)を使用し Ni フィルターによる $\text{CuK}\alpha$ 線を用いて主として長面間隔だけを測定した。図 4 は 100% 10-オキシステアリン酸からえられた回折線図で、図 5 は種々の混合比の混融急冷試料からえられた図を示す。混合比の変化にかかわらず回折線の位置に移動がないのは、これら両物質が近似した長面間隔を持ち、しかも結晶構造も類似しているためと考えられる。また Martin⁵⁾, Chapman⁶⁾, Lampe⁷⁾ らによって長鎖状炭素化合物が結晶状態で副格子内でのメチレン基の振動におよぼす隣接分子間相互作用の影響を示すとして解釈された 720cm^{-1} 付近の IR スペクトルも、両化合物と

図 4 10-オキシステアリン酸の X 線回折図

A: 51%, B: 23%, C: 9% 10-オキシステアリン酸

図 5 10-オキシステアリン酸混融急冷物の X 線回折図

もに大体近似し上のように推論できると考えたが、これらの吸収については別に報告する。ステアリン酸の第 2 次回折線に相当する線が 10-オキシステアリン酸で消失しているのは π の位相差に相当する位置にある水酸基のつくる回折面からでてくる逆位相の回折線の影響と考えられる。10-オキシステアリン酸の長面間隔として $41.6\text{\AA}$ の数値がえられた。

2.4 混融急冷物の融点

混融急冷物の融点を微量融点測定装置(島津製)で測定した結果を図 6 に示す。とけ始めと終りとの温度差が短かく、両成分が均一によく混合していることを示すと考えられる。Swern⁸⁾ が種々の位置に不飽和結合を持つオクタデセン酸およびそれらから合成したジオキシステアリン酸の混合物の融点と X 線回折の研究から、X 線的に均一な相をつくる混合物の場合には融解温度の範囲が狭く、二つの相が独立に共存している場合には融解温度範囲が広いという結果をえているのと類似の事実と考えられる。

図 6 10-オキシステアリン酸混融急冷物の融点

3 実験結果の考察

OH 伸縮振動による赤外線吸収が水素結合の有無によって吸収

5) J. M. Martin, *Spectrochim. Acta* 12, 12 (1958).

6) D. Chapman, *J. Chem. Soc.* 1957, 4489.

7) G. R. Lampe, *Kolloid Z.* 182, 140 (1959).

8) D. Swern, L. P. Witnauer, J. B. Brown, *J. Am. Oil Chemists Soc.* 32, 539 (1955).

領域が異なることは広く認められているが、Smith ら⁹⁾および Coburn ら¹⁰⁾は水酸基相互の間で水素結合をつくった場合その結合方式によりつぎのように吸収波長に差が現われることを確認した。

図1の10-オキシステアリン酸の水酸基の吸収波長からみると、結晶状態における炭素鎖の中間にある水酸基は隣接分子の水酸基と水素結合をつくり、さらにそれが長鎖状に連なっている図7に示した模型がえられる。もしこの10-オキシステアリン酸が水酸基のないステアリン酸と自由に入りまじった混晶をつくった場合、これを炭素鎖方向から見たときのモデルとして図8を考えると、水素結合ができるためには水酸基が結合しうる隣接位置に10-オキシステアリン酸分子がなければならないため、全体としての水素結合している水酸基の量は混合試料中のオキシ脂肪酸の濃度の2乗に比例して増減を示すと考えられ、図3に示した定量結果はよくこの推定にあてはまる。しかしそのためには混融急冷物が微視的にもよく混合していることが必要条件であるが図5の混融急冷物のX線回折図型が濃度の変化にかかわらず変化しないことはその裏付けとなる。結局10-オキシステアリン酸は図7の模型に示したように、水酸基は隣接分子の水酸基と長鎖状に連なる水素結合をつくる結晶構造を持ち、ステアリン酸より融点が高い原因の一部を説明するものと考えられる。

終りに本報告に関して御校閲くださされ、御教示いただいた本学武内次夫教授に御礼申し上げる。また測定にさいし御協力いた

- 9) F. A. Smith, E. C. Creitz, *J. Research Natl. Bur. Standards* **48**, 145 (1951).
 10) W. C. Coburn, Jr., E. Grunwald, *J. Am. Chem. Soc.* **80**, 1318 (1958).

(第2報)¹⁾ D-12-オキシステアリン酸

D-12-オキシステアリン酸の水酸基の伸縮振動によるIR吸収はOH...OH型水素結合をしている水酸基の吸収領域よりはるかに低振動数側に現われ、プロトン受容体としてさらに電気陰性度の高いカルボキシル基が当然考えられる。ステアリン酸との混融急冷試料による水素結合している水酸基の定量結果はD-12-オキシステアリン酸の濃度に比例し、混融物は混晶をつくっていないと考えられ、これは結晶構造がステアリン酸と異なるためであろうと推定され、また混融急冷試料のX線回折、その他の方法によりこの推定が確認された。

1 緒 言

D-12-オキシステアリン酸は他の種々の脂肪酸と異なり、種々の溶媒中から再結晶をする場合、長鎖脂肪酸特有のリン片状結晶として析出しないで、多くの場合塊状になって分離するか、または無極性溶媒の場合にはしばしばゲル状になってかたまる場合が多い。これはD-12-オキシステアリン酸の持つ水酸基がつくる分子間水素結合が原因となって特殊な結晶構造をつくり、その構造が三次元的に発達しやすいことが原因となっているものと考えられる。

図7 10-オキシステアリン酸結晶構造模型図

図8 10-オキシステアリン酸混晶模型図

いた鉄道技術研究所河野通郎、青山芳夫両技師に厚く感謝する。
 (1958年11月、油脂討論会(一部)講演)

D-12-オキシステアリン酸およびその誘導体を潤滑目的に使用する場合、この物質の持つ独自の構造粘性が有用な役割をはたしているのであるが、それらの性質を支配していると考えられる分子間水素結合に関する知見はO'Connor ら²⁾がその可能性を推定したにとどまり、基礎的な研究がまだなされていない。本研究ではD-12-オキシステアリン酸の結晶状態における分子間水素結合の方式とその結果考えられる結晶構造をIRスペクトルおよびX線回折の測定結果から考察した。

2) R. T. O'Connor, C. H. Mack, E. F. Dupré, W. G. Bickford, *J. Org. Chem.* **18**, 686 (1953).

1) 前報(第1報), 中島, 外山, 日化 **81**, 1472 (1960).

nium salts at the room temperature. The products are readily soluble in water and their aqueous solutions possess cationoid surface active properties.

VII. Reactions of Grignard Reagents with Triphosphonitrilic Chloride (pp. 1457~1459)

The reactions of triphosphonitrilic chloride with grignard reagents prepared from alkyl and aryl halide are described. Replacement of chlorine atom of triphosphonitrilic chloride by alkyl or aryl group and the properties of the products are discussed. The yield of the products was not good. The products were crystalline substances of high melting point (above 300°C) or viscous and undistillable liquids.

Kogakuin University; Shinjuku-ku, Tokyo, Japan

Nippon Kagaku Zasshi, 81, 1459~1465 (1960)

Polarographic Study of Nicotinic Acid Derivatives. II. Reduction Waves of some 3-carbamoyl-1-alkylpyridinium halides

by Jun-ichi NAKAYA

Polarographic reduction has been examined of several 3-carbamoyl-1-alkylpyridinium halides (alkyl=methyl, propyl, benzyl, halogen=Cl, I), which are considered to be model compounds of coenzyme(I). They give one or two well defined diffusion controlled waves which cover the pH range 3.8~10.3. Half wave potential of the first wave of them is independent of pH (from 3.8 to 10.3), whereas that of the second wave depends upon pH (from 8.9 to 10.3). At pH 8.9 the reduction proceed through two processes, both of which are one-electronic. It has been confirmed by controlled potential electrolysis and by ultraviolet spectrum that the polarographic reduction of 3-carbamoyl-1-benzylpyridinium chloride gives *N*-benzyl-*o*-dihydronicotinamide at pH 8.9, whereas the chemical reduction gives the *p*-compound. An evidence has also been shown that highly stable semiquinones are formed in the polarographic reduction.

Department of General Chemistry, University of Osaka Prefecture; Sakai-shi, Osaka, Japan

Nippon Kagaku Zasshi, 81, 1465~1470 (1960)

Styrene Derivatives. VIII. The Reaction of β -Bromostyrene with Formaldehyde in Acidic Media—Configurations of 4-Phenyl-5-bromo-1,3-dioxanes and their Derivatives

by Akira TERADA

The reaction of β -bromostyrene with paraformaldehyde in an acidic medium gave, besides a small amount of $C_{10}H_{11}BrO_2$ (II), m.p. 75~76°C as a by-product, 4-phenyl-5-bromo-1,3-dioxane(I), b.p. 120~123°C/3 mmHg. (A. Terada, *Nippon Kagaku Zasshi*, 81, 606 (1960)). By the amination of (I), *dl*-threo-4-phenyl-5-amino-1,3-dioxane (III), HCl salt (IV), m.p. 222°~222.5°C, dichloroacetamide(V), m.p. 111.5°C, acetamide(VI), m.p. 103.5~104.5°C, and benzamide(VII), m.p. 93.5~94.5°C, was produced with Walden inversion. The acetolysis of (VI) and (VII) with acetic anhydride using zinc chloride as a catalyst followed by hydrolysis in an alkaline medium gave *dl*-threo-1-phenyl-2-acetamido-1,3-propanediol and *dl*-threo-1-phenyl-2-benzamido-1,3-propanediol respectively. The acetolysis of (I) with acetic anhydride-acetic acid using sulfuric acid as a catalyst followed by

hydrolysis in a dilute sulfuric acid-acetone solution gave *dl*-erythro-1-phenyl-2-bromo-1,3-propanediol, m.p. 62.5~63.5°C, which proved that (I) was *dl*-erythro-4-phenyl-5-bromo-1,3-dioxane. This result leads to a conclusion that the mode of the addition of formaldehyde to *trans*- β -bromostyrene is a *cis* type. The acetolysis followed by the hydrolysis of (II) gave *dl*-threo-1-phenyl-2-bromo-1,3-propanediol, m.p. 86~87°C. (II) is therefore, *dl*-threo isomer of (I). This formation is owing to the existence of *cis*- β -bromostyrene in the starting material, which cannot be removed completely by an ordinary procedure. The formation of (II) as a by-product of (I) is observed even when pure (as confirmed by the refractive index) *trans*- β -bromostyrene was used. This phenomenon is explained to be due to a side reaction, i.e., *trans* addition of formaldehyde to *trans*- β -bromostyrene.

Osaka Industrial Research Institute; Oyodo-ku, Osaka, Japan

Nippon Kagaku Zasshi, 81, 1470~1471 (1960)

Chemical Studies on Fragrant Components of Chrysanthemum Flowers. IV. On Chrysanthone

by Hiroaki CHIKAMATSU

It has been made clear that a monoterpene ketone, chrysanthone, isolated for the first time by Takahashi in 1933 from flowers of *Chrysanthemum boreale* (*Ch. lavandulaefolium*), is identical with α -thujone.

Institute of Organic Chemistry Osaka; Kita-ku, Osaka, Japan

Nippon Kagaku Zasshi, 81, 1472~1476 (1960)

Studies on the Intermolecular Hydrogen Bonding of Hydroxystearic Acids. I~II.

by Isokichi NAKAJIMA and Yoshiyuki TOYAMA

I. 10-Hydroxystearic Acid (pp. 1472~1474)

An infrared absorption band in the 3290~3380 cm^{-1} region has been observed of 10-hydroxystearic acid, and assigned to the OH-stretching vibration of hydroxyl group, which is involved in the intermolecular hydrogen bonding of a polymerlike association. Mixed samples of this acid and stearic acid were prepared by quenching of their molten mixtures of various proportions, and the amounts of the hydrogen-bonded OH groups in these samples were determined by the infrared absorption measurement. This was found to be proportional to the square of the concentration of 10-hydroxystearic acid. The X-ray diffractions from these mixed samples were observed. The results indicate that the 10-hydroxystearic acid has a crystal structure similar to that of stearic acid, and that the hydroxyl group at the middle part of carbon chain of each molecule forms a hydrogen bonding with the OH group of the adjacent molecule, resulting in a polymerlike long chain. The behavior of these mixed samples at their melting points indicated that these "mixtures" are solid solutions.

II. D-12-Hydroxystearic Acid (pp. 1474~1476)

The IR-absorption band, due to the OH-stretching vibration of D-12-hydroxystearic acid in its solid state has been observed at 3190 cm^{-1} , i.e. at much lower frequency than the OH-absorption band of the usual