Investigations of the Structure of $\text{SrNiZn}(\text{PO}_4)_2$ The Nickel Distribution within the Lattice of Related Compounds

B. EL BALI ⁽¹⁾, M. LACHKAR ⁽¹⁾, H. ALLOUCHI ⁽²⁾ And B. NARYMBETOV ⁽²⁾

⁽¹⁾ Laboratoire d'Analyses, d'Essais et d'Environnement (L.A.E.E.), Département de Chimie, Faculté des Sciences "Dhar Mehraz", Université Sidi Mohamed Ben Abdellah, 30000 Fès, Morocco

⁽²⁾ Université de Tours, Laboratoire de Chimie Physique - PIMIR E. A. 2098, Faculté de Pharmacie, 31, Avenue Monge 37200 Tours, France.

Abstract

$\text{SrNiZn}(\text{PO}_4)_2$ is isostructural to $\text{SrNi}_2(\text{PO}_4)_2$. The lattice parameters are: $a = 5.4560(10)$, $b = 6.7110(10)$, $c = 9.1820(10)$, $V = 110.600(10)$, $Z = 2$ for 1009 independent reflections, $R_1 = 6.98$, $wR_2 = 7.03$. The structure consists of sheets made of edge-sharing $[\text{NiO}_6]$ and $[\text{ZnO}_5]$ polyhedra. In the title compound, Ni ions are forming dimers $[\text{Ni}_2\text{O}_{10}]$ with short $d_{\text{Ni-Ni}}$ of 3.006 Å.

INTRODUCTION

Preparation and crystal structures of orthophosphates $\text{M}_3(\text{PO}_4)_2$ or $\text{T}_3(\text{PO}_4)_2$ (M = Alkaline-earth, T = 3d-transition divalent metal including Zn) have been studied for a long time in some detail (El Bali¹ and references therein). During the last decades mixed orthophosphates $\text{M}_{3-x}\text{T}_x(\text{PO}_4)_2$ have been reported in the literature: $\text{Ba}_2\text{T}(\text{PO}_4)_2$ [$\text{T} = \text{Ni}$ (El Bali²), Cu (Etheredge³)]; $\text{BaT}_2(\text{PO}_4)_2$ [$\text{T} = \text{Co}$ (Bircsak⁴), Ni (El Bali⁵), Cu (Moquine⁶), Zn (Schmidt⁷)]; $\text{Sr}_2\text{T}(\text{PO}_4)_2$ [$\text{T} = \text{Ni}$ (El Bali⁸)]; $\text{SrT}_2(\text{PO}_4)_2$ [$\text{T} = \text{Co}$ (El Bali⁹), Ni (El Bali¹⁰), Zn (Hemon¹¹)]. During our investigation of the "binary" system: $\text{Sr}_3(\text{PO}_4)_2$ - $\text{Ni}_3(\text{PO}_4)_2$ (El Bali¹²), we pointed out the evolution of the nickel-oxygen framework dimensionality in some of these mixed orthophosphates. Thus, analysis of the crystal structures of orthophosphates in this system shows a decrease of this dimensionality, from 3D in $\text{Ni}_3(\text{PO}_4)_2$ (Calvo¹³) and $\text{Sr}_2\text{Ni}(\text{PO}_4)_2$ (El Bali⁸) to 2D (Plane) in $\text{SrNi}_2(\text{PO}_4)_2$ (El Bali¹⁰). The linear link of Ni^{+2} , and even the isolated ones, characterise respectively the structures of $\text{SrNi}_3(\text{P}_2\text{O}_7)_2$ and SrNiP_2O_7 (El Bali¹). A similar decrease in the connectivity of nickel-oxygen coordination polyhedra is observed in quaternary diphosphates in the system $\text{Sr}_2\text{P}_2\text{O}_7$ - $\text{Ni}_2\text{P}_2\text{O}_7$. $\text{Ni}_2\text{P}_2\text{O}_7$ in its α -, β - and σ -form shows a 2D network (Lukaczewicz¹⁴, Pietraszko¹⁵, Masse¹⁶). The connectivity of the nickel-oxygen polyhedra is not affected by the "substitution" of Sr by Ba (El Bali¹⁷). It decreases however rapidly when substituting Ni by Zn. The present work deals with the crystal structure of the new Nickel-Zinc Orthophosphate $\text{SrNiZn}(\text{PO}_4)_2$, which is isostructural to $\text{SrNi}_2(\text{PO}_4)_2$.

EXPERIMENTAL

Stoichiometric amounts of SrCO_3 , NiO , ZnO and $(\text{NH}_4)_2\text{HPO}_4$, compatible with the chemical formula $\text{SrNiZn}(\text{PO}_4)_2$, were dissolved in dilute nitric acid. After evaporating water, the residue was dried on a heating-stirrer and heated, in a tubular furnace, at higher temperatures (6h at 873 K, 24h at 1173K). Finally, a yellowish single phase powder has been obtained. This powder has been melted at 1523 K and subsequently cooled down, at a rate of 10°/h, to 873K. From the solidified melt red crystals of $\text{SrNiZn}(\text{PO}_4)_2$ were isolated. Crystal data, experimental

conditions for X-ray diffraction, data collection and structure refinement results are reported in Table 1.

Table 1: Crystal data, experimental conditions for X-ray diffraction, data collection, structure refinement results

I-Crystal data		II- Intensities measurements	
Formula	SrNiZn(PO ₄) ₂	Temperature [K]	293(2)
Crystal system	Triclinic	λ [Mo(K α)]	0.71073 Å
S. G	P-1 (N° 2)	[θ] (°)	2.45 – 24.97
Parameters (Å, °)	a = 5.456 (1)	Abs. Correct.	empirical / psi-scan
	b = 6.711 (1)	n-zero reflexions	1009
	c = 9.182 (1)	observed	1114
	α = 110.60 (1)	$h_{\min}$ - $h_{\max}$	-6 – 6
	β = 101.10 (1)	$k_{\min}$ - $k_{\max}$	-7 – 7
	γ = 98.08 (1)	$l_{\min}$ - $l_{\max}$	-10 – 0
V(Å ³), Z	300.77(8), 2	III- Refinement	
d_{cal} (g/cm ³)	4.392	used programme	SHELX-97 package (Sheldrick ¹⁸)
Color	red	Indep. Parameters	119
F(000)	376	Agreement factors: R_1 , wR_2 (%)	6.98 / 7.03
		R_{all}	2.75

RESULTS AND DISCUSSION

The framework of SrNiZn(PO₄)₂ contains isolated [PO₄]³⁻ groups. Their average $\bar{d}$ (P-O) distance of 1.541(4) Å could be considered as identical to 1.542 Å in SrNi₂(PO₄)₂ (El Bali¹⁰). The cations Ni⁺² show sixfold coordination [NiO₆], with average $\bar{d}$ (Ni-O) of 2.078 Å, which is close to the value 2.072 Å in SrNi₂(PO₄)₂. In fact, in this later structure, Ni⁺² occupy two kind of Ni coordination: [Ni(1)O₆] and [Ni(2)O₅₊₁]. Comparing the two crystal structures, we conclude that Zn⁺² ion sites in the position of Ni(1) with a reduction of its coordination number to 5 which results in a small contraction: ($V_{\text{SrNiZn}}/V_{\text{SrNi}_2}$ = 1%). Average $d_{\text{Zn-O}}$, 2.090 Å, is shorter than 2.144 Å in this site in SrNi₂(PO₄)₂. Edge-sharing of [NiO₆] and [ZnO₅] leads to sheets [NiZnO₉]_{2∞} as shown of Figure 1, drawn according to the data reported in Tables 2 and 3. The structure shows big similarity with that of SrNi₂(PO₄)₂, however here Ni form dimers [Ni₂O₁₀] in which the short distance $d_{\text{Ni-Ni}}$ is equal to 3.006 Å, as in SrNi₂(PO₄)₂ (2.993 Å). Figure 2 shows the oxygen coordination polyhedra of Ni⁺² and Zn⁺² in SrNiZn(PO₄)₂. The 3D network extension in SrNiZn(PO₄)₂ is ensured by Sr-O interactions from Sr⁺² ions located in octacoordinated sites. The mean value of (Sr-O) = 2.643 Å, is comparable to the homologous bond in SrNi₂(PO₄)₂, which is equal to 2.641 Å. For the visualisation of the evolution of the Ni dimensionality in the systems Sr₃(PO₄)₂-Ni₃(PO₄)₂ and Sr₂P₂O₇-Ni₂P₂O₇, we report on figure 3a-d projections of the crystal structures of the isolated compounds in these systems, ie: Sr₂Ni(PO₄)₂, SrNi₂(PO₄)₂, SrNiP₂O₇ and SrNi₃(P₂O₇)₂.

Figure 1: Perspective view of the crystal structure of $\text{SrNiZn}(\text{PO}_4)_2$ [Diamond¹⁹, 1999]
Polyhedra: Yellow (PO_4), Green (NiO_6), Light-blue (ZnO_5); Black balls: Sr^{+2}

Figure 2: $\text{SrNiZn}(\text{PO}_4)_2$: View of the Ni and Zn coordination polyhedra. Displacement ellipsoids are at 60% level (Symmetry operators for generating equivalent atoms as in Table 3)

Figure 3: Ni distribution in four structures determined in the systems $\text{Sr}_3(\text{PO}_4)_2\text{-Ni}_3(\text{PO}_4)_2$ and $\text{Sr}_2\text{P}_2\text{O}_7\text{-Ni}_2\text{P}_2\text{O}_7$: $\text{Sr}_2\text{Ni}(\text{PO}_4)_2$ (a), $\text{SrNi}_2(\text{PO}_4)_2$ (b), SrNiP_2O_7 (c) and $\text{SrNi}_3(\text{P}_2\text{O}_7)_2$ (d)

Table 2: Atomic coordinates and isotropic displacement parameters for SrNiZn(PO₄)₂ (Esd's are given in parentheses)

Atom	x	y	z	U _{eq}
Sr	0.25316(9)	0.79867(7)	0.05416(5)	0.00612
Ni	0.36057(12)	1.14552(10)	0.44015(7)	0.0037
Zn	-0.00755(12)	0.40345(10)	-0.34850(8)	0.0084
P(1)	-0.1556(2)	1.0256(2)	0.30319(15)	0.0038
P(2)	0.3948(2)	0.42803(19)	0.23976(15)	0.0034
O(1)	-0.2525(7)	0.9992(6)	0.1310(4)	0.0081
O(2)	-0.3788(6)	0.9540(5)	0.3683(4)	0.0054
O(3)	0.0474(6)	0.8851(6)	0.3123(4)	0.0073
O(4)	-0.0043(7)	1.2636(6)	0.4180(4)	0.0080
O(5)	0.3461(7)	0.1970(5)	0.2367(4)	0.0061
O(6)	0.6537(7)	0.4840(6)	0.2043(4)	0.0073
O(7)	0.1712(7)	0.4520(6)	0.1211(5)	0.0113
O(8)	0.3795(6)	0.5933(5)	0.4041(4)	0.0062

a) $U_{eq} = (1/3) \sum_i \sum_j U_{ij} \mathbf{a}_i \cdot \mathbf{a}_j$

Table 3: SrNiZn(PO₄)₂, interatomic distances in Ni, P and Zn polyhedra

Ni- O(8) ^{vi} : 1.971(4)	Zn- O(6) ^{iv} : 1.988(4)
Ni- O(5) ⁱⁱⁱ : 2.005(3)	Zn- O(8) ⁱ : 2.000(3)
Ni- O(3): 2.073(4)	Zn- O(4) ^{viii} : 2.020(4)
Ni- O(2) ⁱⁱⁱ : 2.080(3)	Zn- O(3) ⁱ : 2.066(3)
Ni- O(2) ^v : 2.095(3)	Zn- O(7) ⁱ : 2.374(4)
Ni- O(4): 2.244(4)	<Ni-O> = ; <Zn-O> =
Sr- O(1) =	<Sr-O> =
P(1)- O(1): 1.505(4)	P(2)- O(5): 1.525(3)
P(1)- O(2): 1.546(3)	P(2)- O(6): 1.535(3)
P(1)- O(3): 1.561(3)	P(2)- O(7): 1.539(4)
P(1)- O(4): 1.566(4)	P(2)- O(8): 1.553(3)
<P-O>	

Symmetry codes:

- (i) -x, 1-y, -z; (ii) -x, 2-y, -z; (iii) x, 1+y, z; (iv) 1-x, 1-y, -z;
 (v) 1+x, y, z; (vi) 1-x, 2-y, 1-z; (vii) -x, 2-y, 1-z; (viii) x, -1+y, -1+z;
 (ix) -1+x, y, z; (x) x, 1+y, 1+z; (xi) x, -1+y, z.

Acknowledgements

B. El Bali would like to thank Prof. B. Elouadi (University La Rochelle, France) and Dr M. Dusek (Institute of Physics, Prag, Czech Republic) for their kind collaboration.

REFERENCES

1. B. El Bali, A. Boukhari, J. Aride, K. Maaß, D. Wald, R. Glaum, F. Abraham, *Solid State Science*, 3, 669 (2001).
2. B. El Bali, A. Boukhari, F. Abraham, J. Aride, M. Belaich, J. Darriet, *Eur. J. Solid State Inorg. Chem.*, 131, 61 (1994).
3. K. M. S. Etheredge, S.-J. Hwu, *Inorg. Chem.*, 35, 1474 (1996).
4. Z. Bircsak, W. T. A. Harrison, *Acta Cryst.*, C54, 1554 (1998).
5. B. El Bali, M. Bolte, A. Boukhari, J. Aride, M. Taibi, *Acta Cryst.*, C55, 701 (1999).
6. A. Moqine, A. Boukhari, J. Darriet, *J. Solid State Chem.*, 107, 362 (1993).
7. R. Schmidt, R. Kniep, *Z. Kristallogr.*, 196, 312 (1991).
8. B. El Bali, A. Boukhari, E. M. Holt, J. Aride, *Acta Cryst.*, C49, 1131 (1993).
9. B. El Bali, A. Boukhari, E.M. Holt, J. Aride, *J. of Crystallographic and Spectroscopic Res.*, 23, 1001 (1993).
10. B. El Bali, A. Boukhari, J. Aride, F. Abraham, *J. Solid State Chem.*, 104, 453 (1993).
11. A. Hemon, G. Courbion, *J. Solid State Chem.*, 85, 164 (1990).
12. B. El Bali, Thesis report (07.07.1994). University Mohammed V, Rabat Morocco.
13. C. Calvo, R. Faggiani, *Canad. J. Chem.*, 53, 1516 (1975).
14. K. Lukaczewicz, *Bull. Acad. Pol. Sci., Ser. Sci. Chimiques*, 15, 47 (1967).
15. A. Pietraszko, K. Lukaczewicz, *Bull. Acad. Pol. Sci., Ser. Sci. Chimiques*, 16, 183 (1968).
16. R. Masse, J. C. Guitel, A. Durif, *Mat. Res. Bull.*, 14, 337 (1979).
17. B. El Bali, R. Glaum, K. Maaß, unpublished results.
18. G. M. Sheldrick, SHELX97 (1997). Program for the Refinement of Crystal Structures. University of Göttingen, Germany.
19. M. Berndt, K. Brandenburg & H. Putz, DIAMOND (1999), version 2.1, Crystal Impact GbR, Bonn, Germany.