STRUCTURE AND REACTIVITY OF CARBON*

J. B. DONNET

Centre de Recherches Physico-Chimie des Surfaces Solides,
24, Av. du President Kennedy, 68200 Mulhouse

If we consider the considerable amount of work devoted to the physics of carbon, to their physical properties as well as to the understanding of their structure, and if we compare it to the work devoted to the chemistry and the chemical properties of carbon, we see that the later has been considerably less developed. The reasons are, among other, the small reactivity of the solid carbon, as compared to usual chemical reagents and also the peculiar difficulties of the chemistry of solid surfaces: heterogeneity and lack of reproducibility.

Our work on the physical chemical properties of carbons began in 1953 when we became interested in the surface properties of "water soluble" carbon blacks. These blacks were made industrially by treatment with sodium hypochlorite.

Rapidly, we were able to show that the blacks treated with sodium hypochlorite were electrically loaded in aqueous medium and that the electrical charge came from the dissociation of surface functions having a pK_a in the range of 10^{-4} to 10^{-5} . Moreover these surface groups behave like carboxylic groups in classical organic chemistry.

In 1954, we postulated for the first time (14) the concept of chemical surface groups which appeared to be very fruitful. This concept was also suggested by other authors, namely Boehm, at the same time and independently. It was also applied to other solides (65, 13). At the same time, we also observed that the treatment of carbon blacks with sodium hypochlorite was in fact a slight oxidation of the carbon surface and in a more general manner, that all oxidizing agents lead, more or less easily, to the same results. This treatment was the starting point of our work on carbon oxidation, the oxidized carbons having interesting properties such as ionic exchange, dispersability in polar solvents, etc. . .

This rapid historical survey leads one to the two main points of this paper:

— first, considerations about the chemical groups of

carbons and the grafting reactions of polymers on carbons.

— Secondly, I would like to demonstrate the relationship between carbon reactivity and carbon micro-structure by means of oxidation reactions.

I. — STUDY OF THE CHEMICAL SURFACE GROUPS AND OF THE GRAFTING REACTION

This work was mainly performed with carbon blacks.

Due to their method of preparation, carbon blacks are never formed of pure carbon, but always contain foreign elements. These are mainly, hydrogen from the original hydrocarbons, and oxygen from the fuel or from the atmosphere in which the different treatments took place.

The oxygen present in the carbon blacks is mainly held on the particle surface, and it was established that the oxygen was mostly a constituent of surface chemical radicals. The properties of these radicals have been studied by numerous authors; in particular Studebaker, Rivin, Boehm and our Laboratory showed on the following tables, the basis of the different methods of titration.

The treatment of a carbon black by an organo-magnesian compound or by lithium hydride has enabled the finding of labile hydrogen radicals, mainly carboxylic and hydroxylic, which can be methylated either by diazomethane or dimethylsulphate. Carboxylic groups were titrated by reaction with calcium acetate followed by a titration with a base, or by condensation of aniline with the acid chlorides followed by an elemental analysis of the fixed nitrogen (Table 1).

The hydroxyl radicals are readily acetylated and can then be titrated by a condensation reaction with 2,4-dinitrofluorobenzene or paradinitrobenzoyl chloride (Table 2).

One must also note the presence of lactonic radicals which are more difficult to determine (Table 3). Surface quinone radicals (Table 4) give condensation reactions with diazomethane, iso-octane, aniline, isobutyl nitrite; their reduction to hydroquinones can be effected by

* conference held by Professor J.B. DONNET at the Joined Meeting of CARBON SOCIETY OF JAPAN and CHEMICAL SOCIETY OF JAPAN, May 7th 1976, TOKYO.

Table 1 Carboxyl groups R-COOH

Identifying reactions	Authors
Organomagnesium compound $R - COOH + CH_3MgI \rightarrow RCOOMgI + \overset{\nearrow}{CH_4}$	D.S. VILLARS (1)
Diazomethane $R - COOH + CH_2N_2 \rightarrow RCOOCH_3 + \overset{\nearrow}{N_2}$	M.L. STUDEBAKER (2, 3)
Calcium acetate $2R - COOH + (CH_3COO)_2Ca \rightleftharpoons (RCOO)_2Ca + 2CH_3COOH$	J.B. DONNET and P. MARGUIER (4) F. HUEBER (5)
Decarboxylation $R - COOH \xrightarrow[600^\circ C]{\text{Heating above}} R - H + \overset{\nearrow}{CO_2}$	D. RIVIN (6)
Hydride of aluminium and lithium $4R - COOH + 3LiAlH_4 \rightarrow LiAl(OCH_2R)_4 + 2LiAlO_2 + 4\overset{\nearrow}{H_2}$ $LiAl(OCH_2R)_4 + 4H^+ \rightarrow Li^+ + Al^{+++} + 4RCH_2 - OH$	R.E. TEST and R.S. HANSEN (7) D. RIVIN (6)
Isotopic exchange $R - COOH + {}^3H \rightarrow R - COO^3H + H$	De BRUIN and Th. VAN DER PLAS (8)
Titration with alcalis (KOH, NaOH, Ba(OH) ₂ etc...) $R - COOH + KOH \rightarrow RCOOK + H_2O$	B.R. PURI (9) - D. RIVIN (6) R.E. TEST, R.S. HANSEN (7) - H.P. BOEHM (10, 11)
Titration with soda $2R - COOH + CO_3Na_2 \rightarrow 2R - COONa + \overset{\nearrow}{CO_2} + H_2O$	D. RIVIN (6)
Titration with sodium bicarbonate $R - COOH + CO_3HNa \rightarrow R - COONa + \overset{\nearrow}{CO_2} + H_2O$	D. RIVIN (6)
Titration with sodium acetate $R - COOH + CH_3COONa \rightarrow R - COONa + CH_3COOH$	H.P. BOEHM (10, 11)
Formation of an acid chloride $R - COOH + SOCl_2 \rightarrow R - COCl + \overset{\nearrow}{SO_2} + HCl$ $R - COOH + PCl_5 \rightarrow RCOCl + POCl_3 + HCl$ $(POCl_3)$	H.B. BOEHM (10, 11) J.B. DONNET and E. PAPIRER (12)
Characterization of the acid chloride, formation of anilide $R - COCl + \text{C}_6\text{H}_5 - NH_2 \rightarrow R - CO - NH - \text{C}_6\text{H}_5 + HCl$	H.P. BOEHM (10, 11)
Schmidt reaction (formation of urethan) $R - COCl + NaN_3 \rightarrow RCON_3 \xrightarrow{CH_3CH_2OH} R - NH - COOC_2H_5 + N_2$	H.P. BOEHM (13)
Dimethyl sulphate $2R - COOH + SO_2 \begin{matrix} \nearrow OCH_3 \\ \searrow OCH_3 \end{matrix} \rightarrow 2RCOOCH_3 + SO_4H_2$	J.B. DONNET and E. PAPIRER (14) H.P. BOEHM (13)

catalytic hydrogenation and the action of sodium borohydride. The simultaneous existence of quinonic and hydroquinonic radicals on the surface of carbon blacks was shown by Voet (19).

Finally one must note that carbon blacks are free radical acceptors, and also that the chemical studies of the properties of the carbon black surface were largely confirmed by physical methods, notably by heats of adsorption and infrared spectrometry.

More recently, we were able to confirm with the

E.S.C.A. technique, the nature of some chemical surface groups on carbon fibres (20). AC Carbon fibres treated with nitric acid exhibit a small C_{1s} peak near the neutral peak of carbon. This peak may be attributed to a carbonyl group (Figure 1a). On the other hand, AG graphite fibres having graphitic oxide layers on their surface (AG fibres treated with Hummer's reagent)[†] show a carbon peak corresponding to hydroxylic groups like in pure graphitic oxide (Figure 1b).

[†]Potassium permanganate in aqueous sulfuric acid.

Table 2 Hydroxyl function R-OH

Identifying reactions	Authors
<p>Organomagnesium compound</p> $R-OH + CH_3MgI \rightarrow R-O-MgI + \overset{\nearrow}{CH_4}$	D.S. VILLARS (1)
<p>Diazomethane</p> $R-OH + CH_2N_2 \rightarrow R-OCH_3 + \overset{\nearrow}{N_2}$	M.L. STUDEBAKER (2, 3)
<p>Hydride of aluminium and lithium</p> $4R-OH + LiAlH_4 \rightarrow LiAl(OH)_4 + 4H_2$	R.E. TEST and R.S. HANSEN (7) D. RIVEN (6)
<p>Acetylation</p> $R-OH + \begin{cases} CH_3COCl \\ CH_3COOH \\ 1/2 CH_3CO \begin{smallmatrix} O \\ // \\ O \end{smallmatrix} \end{cases} \rightarrow R-C-OCH_3 + \begin{cases} HCl \\ H_2O \end{cases}$	H.P. BOEHM (10, 11) J.B. DONNET (15) De BRUIN and VAN DER PLAS (8)
<p>2-4-dinitro-fluorobenzene</p> $R-OH + F-\text{C}_6H_3(NO_2)_2 \rightarrow R-O-\text{C}_6H_3(NO_2)_2 + F^- + H^+$	H.P. BOEHM (10, 11)
<p>Benzoyl p. nitro chloride</p> $R-OH + NO_2-\text{C}_6H_4-COCl \rightarrow R-O-\overset{O}{\underset{ }{C}}-\text{C}_6H_4-NO_2 + HCl$	H.P. BOEHM (10, 11)
<p>Dimethyl sulphate</p> $R-OH + SO_2 \begin{smallmatrix} \nearrow OCH_3 \\ \searrow OCH_3 \end{smallmatrix} \rightarrow R-OCH_3 + SO_2 \begin{smallmatrix} \nearrow OH \\ \searrow OCH_3 \end{smallmatrix}$	J.B. DONNET and E. PAPIRER (14) H.P. BOEHM (13)

Table 3 Lactone function

Identifying reactions	Authors
<p>Ammonia</p> $\begin{array}{c} O \\ \\ -C- \\ \\ -O- \end{array} + NH_3 \xrightarrow{\text{in methanol}} \begin{array}{c} O \\ \\ -C-NH_2 \\ \\ -OH \end{array}$	De BRUIN and VAN DER PLAS (8)
<p>Bromhydric acid</p> $\begin{array}{c} O \\ \\ -C- \\ \\ -O- \end{array} + HBr \rightarrow \begin{array}{c} O \\ \\ -C-OH \\ \\ -Br \end{array}$	De BRUIN and VAN DER PLAS (8)
<p>Hydride of aluminium and lithium</p> $\begin{array}{c} O \\ \\ -C- \\ \\ -O- \end{array} \xrightarrow{LiAlH_4} \begin{array}{c} O \\ \\ -C-OH \\ \\ -OH \end{array}$	D. RIVIN (6)

Table 4 1-4 Quinonic function

Identifying reactions	Authors
<p>Diazomethane</p> <p style="text-align: center;">Pyrazolinic cycle</p>	M.L. STUDEBAKER (2, 3)
<p>Catalytic hydrogenation</p>	M.L. STUDEBAKER (2, 3)
<p>Sodium borohydride</p>	M.L. STUDEBAKER (2, 3) J.B. DONNET and coll. (16)
<p>Condensation of the isooctane</p>	J.V. HALLUM and H.V. DRUSHEL (17)
<p>Condensation of the isobutyric nitrile</p> <p style="text-align: center;">black</p>	J.B. DONNET and G. HENRICH (18)
<p>Condensation of the aniline</p>	J.B. DONNET and G. HENRICH (18)
<p>Stannous fluoborate</p>	A. VOET and A.C. TETER (19)
<p>Ferric sulphate (hydroquinonic function)</p>	A. VOET and A.C. TETER (19)
<p>Lithium alumino-hydride</p>	R.E. TEST and R.S. HANSEN (7) D. RIVIN (6)
<p>Oxidation of Ti+++</p>	De BRUIN and Th. VAN DER PLAS (8)
<p>Hydroxylamine</p>	De BRUIN and Th. VAN DER PLAS (8)

Fig. 1 a: E.S.C.A. Spectra of carbon fibres.

Fig. 1 b: E.S.C.A. Spectra of graphite fibres.

One of the most important applications of carbon black results from its ability to improve the mechanical properties of the vulcanizates, such as tensile strength, modulus and abrasion resistance. This behaviour is referred to as reinforcement. (66)

As early as 1952, Braendle and Watson (21) pointed out that the formation of a carbon gel, that is an infinite network, is a necessity for reinforcement. The carbon filler then provides the crosslinks of the combined network. It is therefore not surprising that the funda-

mentals of reinforcement are directly related to the nature and properties of the carbon elastomer bonds.

Basically the interactions between carbon black and elastomer can be mechanical, physical, chemical or a combination of the three. A first important mode of interaction results from the carbon black structure and drove to the concept of elastomer occlusion in carbon black aggregates (22). A second important mode is physical adsorption. It must be noted that when rubber is adsorbed on carbon black from a poor solvent, only part of it can be removed by a good solvent for the rubber. This phenomenon has been explained on the basis of the multicontact adsorption theory. Obviously adsorption points to chemisorption as a capital process of interaction between elastomers and carbon black.

For a variety of solvents Sircar and Voet (23) determined the amount of elastomer unextractable from carbon black versus the extraction temperature. As shown on Figure 2 for butyl rubber and polyisobutylene, at successively higher temperature, elastomer is increasingly removed by exhaustive extraction with good solvents and the temperature T_m appears to be solvent independent. It represents the temperature theoretically required to eliminate all bonds between carbon black and elastomer and is therefore indicative of bond strength. These data led to the concept of chemisorption of the elastomer by carbon black that is supported by the lower value of T_m obtained with a chemically inert graphitized black.

In order to relate the reinforcing potential of a black to the presence of hydrogen on its surface, Voet, Papirer and Aboytes (24) studied the reinforcing ability of heat treated carbon blacks in SBR – polybutadiene formulations. As shown on Figure 3, they determined the relative loss of hydrogen between 1 000 and 2 500°C,

Fig. 2 Amount (mg/g) of elastomer unextractable by aromatic solvents as a function of the solvent extraction temperature.

Fig. 3 % strain energy retained vs. surface hydrogen content.

and they correlated it to the "stress strain energy" retained during stress-strain experiments. The carbon black treated at 1 000°C is chosen as reference.

We can observe the decrease of the retained strain energy simultaneously with the departure of hydrogen from the black. As a consequence, a chemisorptive phenomenon involving the hydrogen of carbon black seems highly probable and surface hydrogen plays a part in the reinforcement mechanism of SBR.

In order to check if the total amount of surface hydrogen or only a part of it enters the reaction, Papirer and coworker (25) have studied the kinetics of the tritium labelling reaction for a series of carbon blacks with different reinforcing properties. As shown in Table

5, four types of reactivities could be identified. For a given type of hydrogen, the labelling rate constants are of the same order of magnitude but differ significantly from one type to another. For example for Aro 1LS the most reactive type of hydrogen which represents only 2% of the total number of exchangeable hydrogen atoms is exchanged four times as fast as the least reactive type. The blacks being classified according to their reinforcing potentials, it appears clearly that a correlation can be drawn between reinforcing properties and the most reactive hydrogen form. We must conclude that since the content of active hydrogen is quite low (10% for the most reinforcing black) only a minor part of the carbon surface is reactive towards SBR.

By studying the kinetics of the labelling reaction at different temperatures and calculating the activation energies it would be possible to find how easily the reaction proceeds (26). This is shown in Table 6. It is particularly interesting to note that the relative proportions of a particular type of hydrogen remain almost constant irrespective to the temperature of reaction. This again gives a strong indication of the presence of four different types of hydrogen. The apparent activation energies deduced from the Arrhenius' plots are given in Table 7. The low value of the activation energy for type 1 reaction is in favour of an easy exchange reaction.

All these results have been confirmed by studying the substitution reaction by chlorine of the surface

Table 5 Rate constants (k') of tritium hydrogen exchange reaction at 25°C and relative hydrogen proportions (x)

	Aro 1LS	Aro 3LS	Aromex	Aro 100	Aro 150	Aro 175
$k'_1(\text{h}^{-1})$	0.090	0.097	0.080	0.106	0.101	0.105
$x_1(\%)$	2.0	2.7	5.3	7.9	9.3	10.2
$k'_2(\text{h}^{-1})$	0.055	0.051	0.040	0.065	0.062	0.064
$x_2(\%)$	13.4	24.9	9.9	8.8	22.9	17.5
$k'_3(\text{h}^{-1})$	0.028	0.025	0.020	0.030	0.026	0.026
$x_3(\%)$	40.6	31.7	25.3	29.5	24.6	37.9
$k'_4(\text{h}^{-1})$	0.021	0.021	0.018	0.026	0.025	0.025
$x_4(\%)$	44.0	40.7	59.5	53.8	43.8	32.6

Table 6 Kinetics of labelling of Vulcan 6: rate constants of exchange reactions and relative hydrogen proportions

$T(^{\circ}\text{C})$	k'_1	x_1	k'_2	x_2	k'_3	x_3	k'_4	x_4
0	0.034	9.8	0.015	18.6	0.013	31.6	0.013	39.9
26	0.045	9.5	0.031	18.3	0.019	32.7	0.017	39.5
36	0.052	10.3	0.038	18.2	0.032	31.7	0.031	39.9
46	0.086	10.1	0.068	18.6	0.047	31.5	0.043	39.9
56	0.134	10.1	0.123	19.2	0.103	31.2	0.088	39.5
76	0.770	10.0	0.472	19.5	0.341	31.0	0.201	39.5

Table 7 Apparent activation energies

Type of H exchange	E_a (kcal mol ⁻¹)
1	7.5
2	9.5
3	10.5
4	11.5

Fig. 4 Effect of temperature of the treatment by Cl₂ on the elimination of hydrogen.

hydrogen atoms of tritiated Vulcan 6 at different temperatures. Figure 4 shows that not only the elimination of tritium starts at room temperature but the surface hydrogen has completely reacted at 750°C. Moreover it is interesting to note that the elimination takes place in four steps, each one probably corresponding to a particular type of reactive hydrogen. In fact the first and second steps correspond to about 10 and 18% hydrogen loss respectively in good agreement with type 1 and 2 from the kinetics experiments.

In conclusion for this part of the paper we can say that a specific example of filler elastomer interaction has been shown where surface hydrogen of the black plays a significant role in reinforcement of SBR. However, the chemistry of carbon black opens larger domains of possible filler polymer interactions which we are going to discuss now. They are related to the grafting of polymers onto solid surfaces.

Grafting is generally obtained by reacting macromolecules bearing free radicals or ions with the active sites of the solid surface. We will class the grafting

reactions into two sets, namely the grafting onto where the reaction is obtained by termination of a growing polymer chain on the solid surface and grafting from in which a surface carrying promoting sites will allow the initiation of a polymeric chain either radical or ionic in nature. Under these conditions the chain will develop from the substrate.

Let us first have a look at grafting by deactivation of reactive chains onto a solid surface. We will refer to the nature of the active site, that is radical or ionic.

— **Radical process.** In 1956 Szwarc (27) established the fact that carbons could fix, under certain specific conditions, free radicals, by substitution or addition reactions on polyaromatic nuclei. Subsequently Donnet and coworkers, namely Henrich and Riess (28), showed the ability of carbon black to fix substances resulting from the thermolysis of free radical generators, such as lauroyl peroxide, and they proposed the reactions shown in Figure 5. This work was, by the way, confirmed by Studebaker (29) and Ohkita's studies (30) using benzoyl peroxide.

By analogy with these deactivation reactions one can admit the possibility of macromolecular grafting. As shown in Figure 6, the free radicals carried by the macromolecular backbone result generally either from a radical polymerization, corresponding in particular to the work of Kraus (31), Donnet (32), Ohkita (30), Suzuki (33) and their coworkers, or from hydrogen transfer (34). Here grafting takes place through the deactivation of the active species on the aroxylic or quinonic surface groups of the carbon black.

Grafting by hydrogen transfer is usually easy to set up requiring only a simple contact of the polymer in solution with the carbon black. As shown on Figure 7, the polymer having tertiary hydrogen atoms gives the best results. Confirmation of this abstraction of hydrogen was proved by kinetics (35) (V_g is the grafting

GRAFTING OF POLYSTYRENE ON CARBON BLACK

Fig. 5 Reactions occurring upon treatment of carbon black by Lauroyl peroxide.

Fig. 6 Grafting through a free radical process by termination of a reactive polymer chain on the solid surface.

$$V_g = k_{tr}[P][CB] e^{-2\tau[P]t}$$

P	ζ %
PVC	5,9
PP	7,0
PMM	3,0
ACRYLONITRILE ST.	8,0

Fig. 7 Grafting by transfer.

V_g = grafting rate, $[P]$ = polymer concentration,
 $[CB]$ = carbon black concentration,
 k_{tr} = transfer constant.

speed) and radiochemistry using polymers labelled with tritium. This radiochemical study is due mainly to Deviney (36).

Another example of grafting by radical reaction is given in Figure 8. This method was first developed by Henrich and Donnet in the 1960's (28). It was, in fact, known from studies of Kraus (31), Breitenbach (37), Donnet (38) and Suzuki (33), that carbon black was an efficient inhibitor of radical polymerization and these

Thermal polymerisation of styrene + CB

INIBITION

Formation of free radicals

Termination

$$\zeta = \frac{[\text{quinone}]}{\frac{dR_1^{\bullet}}{dt} + \frac{dR_2^{\bullet}}{dt}}$$

$$\frac{1}{\zeta} = A \frac{[M]^2}{[CB]} + B[M]$$

Fig. 8 Inhibition of thermal polymerization of styrene by carbon black.

[quinone] = quinone groups concentration,

[M] = monomer concentration,

[CB] = carbon black concentration,

ζ = inhibition period.

different authors attributed this to the quinonic groups present on the carbon black surface. This was proved by elimination of the quinonic groups by reduction and esterification. In these conditions inhibition was no longer observed. The kinetics of the inhibition process were proposed (32) as we see here. The importance of the inhibition period is, in fact, directly proportional to the number of free radicals formed. The free radicals, of course, either a growing species or result from hydrogen transfer.

We also see on Figure 9 that after the inhibition period, the reaction propagates at a rate superior to that obtained on thermal polymerization of styrene in the absence of carbon black. Donnet and coworkers, in particular Geldreich (39) and Peter (32), as well as Suzuki and Takakuwa (33) showed the dependence of this process on the quinonic and aroxylic surface groups.

On the Figure 9 we see the explanation given by Peter (32) of this catalytic effect. The macroradicals can grow either in solution or on the carbon black and differences in the value of the termination rate constants are sufficient to show an acceleration, for if the chains growing on the carbon black terminate more slowly.

ACCELERATION

Macroradicals on the C.B.

Grafting

Termination

Macroradicals in solution

Termination

$$\frac{v_p}{v_p^0} = \frac{1 + \frac{a}{[CB]}}{\left(\frac{a^2}{[CB]^2} + b \frac{a}{[CB]}\right)^{1/2}}$$

$$a = \frac{K_d}{K_a} \quad b = \frac{k'_t}{k_t}$$

Fig. 9 Thermal polymerization of styrene in presence of carbon black.

k_d = polymer desorption constant, k_a = polymer adsorption constant, k_t = termination reaction constant of a growing chain in solution, k'_t = termination reaction constant of a growing chain onto carbon black.

the polymerization propagates more rapidly. In this case, as well, theoretical expressions have been developed by Peter and Donnet and have been verified experimentally.

The graft ratio, that is, the quantity of polymer irreversibly fixed on the substrate surface, was found not to exceed 20 to 25% by weight for this grafting process by deactivation of radical species. Hence it would seem that there is a limit to the grafting process. We will examine this further on. For the moment let us look at grafting onto a surface by deactivation of ionic species.

— **Ionic process.** Examples of grafting of polymers carrying ionic sites, either anionic or cationic are shown in the Figure 10. For example an anionic polymer can react with ester groups previously introduced onto the carbon black (40), or, with siloxane bridges on a silica (41). We also see here grafting of cationic polymers. The cationic sites can arise from cationic polymerization of a monomer, such as living poly THF which will be deactivated on the hydroxyl functions existing on the

surface or created by the Lewis acid attack of a macromolecular backbone (42).

As we see in Figure 11, a Lewis acid can either be added onto a double bond or displace a hydride ion generating a carbonium ion which is generally fixed by a charge transfer mechanism.

The Figure 12 shows the reaction between an anionic polymer and a substance, carbon black, carrying ester groups (43). The polymer filler bond is assumed by an intermediary carbonyl group. The number of ester groups which, hence, represent grafting sites, can be easily determined by the Zeisel method. As for the number of polymer chains fixed, this can be evaluated by dividing the total mass of grafted macromolecules by the mass of single graft. The latter is determined with precision thanks to the narrow molecular weight distribution consequence of an anionic polymerization.

We can now measure a grafting efficiency. Some typical results are given in Table 8. We see that the

Fig. 10. Grafting through an ionic mechanism by termination of a reactive polymer chain on the solid surface.

Fig. 11 Grafting by deactivation of a carbonium ion on the hydroxylic groups of a solid surface.

Fig. 12 Grafting by reaction between an anionic polymer and an esterified carbon black.

efficiency diminishes with an increase in the molecular weight of the grafts. Hence the size of the macromolecule conditions the covering of the surface and therefore the grafting ratio.

Now that we have presented most of the grafting methods by deactivation of active polymers on solid surfaces, together with their interpretation, let us examine the grafting from a solid surface.

In the case of "grafting from", again we have the possibility of distinguishing between radical or ionic processes.

A grafting method perfected by Donnet et al (35, 44) consists in peroxidizing, with the help of lauroyl radicals, a carbon black following Henrich's methods. It was shown that these peroxidized blacks act as true radical polymerization initiators and interpreted the kinetics of the polymerization and the grafting. However, this particular type of promoter is much less efficient than pure lauroyl peroxide, the carbon black acting as a very good trap for radicals.

Following the work of Parrod and Beinert (45) who, as early as 1961, succeeded in triggering styrene

Fig. 13 Grafting efficiency and percentage of grafting vs. polymerization time for polymerization initiated by a metallated carbon black.

Fig. 14 Polymerization of styrene initiated by a Na or Li treated carbon black.

polymerization from alkaline metals inserted in graphite, Minoura and Katano (46), in 1969, introduced a metal atom into carbon by bringing a black into contact with an alkaline metal in THF. They then suggested the formation of a complex radical anion by electron transfer from the sodium to the carbon black. As shown in Figure 13, a large amount of homopolymer is formed alongside the grafted polymer, as the grafting efficiency expressed as the ratio of grafted polymer to total polymer formed, is only about 10%.

Table 8 % grafting efficiency

Carbon samples	Experiment number	Esters groups ($\times 10^{-6}/\text{g}$)	Number of polymer chains ($\times 10^{-6}/\text{g}$) fixed on the carbon	Grafting efficiency %	$\overline{\text{Mw}}$
Oxidized Vulcan 6 (methylated by $\text{CH}_3\text{OH} + \text{BF}_3$)	1	116	51.7	44.6	3,480
	2	116	6.6	5.7	18,900
	3	116	0.72	0.6	135,000
Initial Vulcan 6 (methylated by $\text{CH}_3\text{OH} + \text{BF}_3$)	4	34	30.3	89.2	5,280
	5	34	3.8	11.3	29,600

This work was continued by Rivin (47) and then Riess and Majowski (40) (Figure 14), who inserted a metal atoms into the black with the help of sodium amide or butyl lithium. They then used modified blacks to trigger the grafted polymerization of styrene. Again, the grafting ratio was not greater than 20%.

To conclude, the possible applications will be a direct consequence of the properties of the solid surface modified by grafting. We will illustrate these properties and applications by a few examples.

Pigments modified by polymers become hydrophobic and hence we can expect better dispersion of the filler in the polymer solvents. The electrical properties of carbon blacks having crosslinked structures have been studied by Ohkita and Fukushima (48) and have found applications in electronic industries.

The adsorbent characteristics of the grafted materials permits very interesting applications in the field of fight against pollution. We have elaborated elsewhere on this subject (67) which deserve, we feel, great attention.

II. — RELATIONSHIP BETWEEN MICROSTRUCTURE AND CHEMICAL REACTIVITY OF CARBONS

Carbons are polycrystalline solids whose microstruc-

ture and reactivity have been the object of much research for over a century. Moreover, the polymorphism of carbons gives us a good example for studying the reactivity of the solids as a functions of their crystalline organization. In fact, the carbon surface is generally heterogeneous with the crystalline arrangement perturbed by faults and dislocations. In particular, the border atoms of graphite layers can be favoured points of attack and hence, the centre of specific chemical reactivity.

In 1964, together with Bouland (49), we found that the oxidation of thermal blacks occurred at the expense of the badly organized areas (Figure 15). The well organized areas of particles seeming arranged concentrically. This subject has been extensively studied in the last ten years and will not be reviewed here.

But we then undertook a systematic study of the oxidation mechanisms of carbons and I will enlarge on the subject by selecting from oxidizing agents: dilute nitric acid and aqueous ozone which do not intercalate and Simon's and Hummer's reagent which may intercalate depending on the crystalline organization of the carbons.

Nitric acid oxidation

Nitric oxidation of a furnace black by nitric acid has

Fig. 15 Thermal black (Sterling MT) oxidized in air.

been the object of a detailed study by Hueber, Lahaye and Schultz (50, 52), who observed that nitric acid, like most oxidants used in aqueous solution, leads to the formation of carbon dioxide, the fixing of oxygenated functions on the particle surface, and the formation of polycarboxylic acids soluble in water which can be referred to as degradation products.

Lahaye showed, in particular, that nitric oxidation attacked preferentially the less crystallised regions of the particle. The badly organized carbon is then oxidized preferentially to carbon dioxide, the edge atoms of the crystallite being covered by carboxylic, hydroxylic and carbonyl functions. Apart from their covering of oxygenated functions, the crystallites react very slowly and the difference in reactivity of the badly organized parts and the crystallites leads to an important formation of microporosity.

Schultz, continuing the work of Lahaye, established the kinetics of the oxidation. He showed, in particular, that the transformation of carbon into CO_2 is limited. Figure 16 gives the rate of release of CO_2 as a function of the fraction of the remaining carbon. This shows that whatever the concentration of the nitric acid, the rates decrease linearly and tend towards zero when 20 to 25% of the carbon has been consumed. By comparing these

results with those of Lahaye, he concluded that nitric oxidation took place at the detriment to the least organized part of the particle, amorphous carbon and non-associated graphitic planes.

The observation, by electron microscopy, of the particle oxidized by nitric acid shows that hollow shells are formed with thermal blacks (Figure 17). These results confirm the observations of Bouland on blacks oxidized in air, and Schultz concludes that the internal particle layers, which are very sensitive to oxidizing agents, must be less well organized. Electron microscope

Fig. 16 Oxidation rate of Spheron 6 in nitric acid.

Fig. 17 Thermal black (Sterling FT) oxidized in nitric acid.

Fig. 18 Bright field and dark field micrography of oxidized and graphitized Sterling FT.

Fig. 19 Schematic microstructure of carbon black.

observation, with bright and dark field, of samples oxidized and treated at 2000°C shows that the graphitization takes place only on the external part of the particles, whereas it occurs throughout the mass for non oxidized blacks (Figure 18). Observations on a dark background confirm, besides, the tangential orientation of the crystallites on the particle surface. The model of the particle illustrated in the next figure (Figure 19) was proposed (Schultz model). We will see later how this model, which has been refined (68), may compare with

the sheet structure.

Oxidation mechanisms can be even more detailed by investigating, beside of the carbon dioxide release, the formation of the degradation products. In particular, their origin should be related to peculiar carbon structures. For analytical reasons, aqueous ozone is very suitable for such a study.

Oxidation with ozone

The oxidation of carbon black with ozone in aqueous solution has been studied by Ehrburger (53, 54). The oxidation mechanism shows two distinct and simultaneous reactions of the particle:

- an oxidizing reaction of carbon giving degradation products which are partially oxidized to carbon dioxide.
- and also a direct oxidation reaction of the carbon to carbon dioxide.

$$q_1 = \alpha t$$

$$q_3 = \beta t$$

$$\frac{q_1}{q_1 + q_3} = \frac{\alpha}{\alpha + \beta}$$

The fractions of carbon oxidized in these two reactions q_1 and q_3 are proportional to the time of reaction, α and β being two parameters depending upon the experimental conditions. The fraction of carbon transformed into degradation products, with respect to the total carbon consumption, is equal to $\alpha/(\alpha+\beta)$, and is characteristic of a given black, whatever the experimental conditions (temperature, concentration of ozone in the water) are (Table 9).

A study of the degradation products shows that the components have nearly identical chemical properties, no matter the black, (Table 10) (55). Figure 20 shows the infra-red spectrum of the oxidation products of Spheron 6. Spectroscopic analysis of chromatographic fractions indicates a similar constitution to that of humic acids.

It was possible to establish that the degradation products result from the oxidation of the disorganized areas of the particle, and especially from defects in the graphite planes. The amount of carbon transformed into degradation products is, in effect, related to the degree of crystalline order of the particle, and to a first approximation, the interplanar distance $c/2$ of the graphite layers (Figure 21).

These observations were confirmed by high resolution electron microscopy. This method permits the visualization of graphite layers and their arrangement within the particle. Channel and furnace blacks have, essentially, the same structure, which has already been seen with the ozone oxidation; with these blacks the graphite layers are arranged about several growth centres (Figure 22). Conversely, thermal blacks present a concentric structure of graphite layers (Figure 23), a structure we proposed with Bouland, as seen already, a few years ago. For graphitized blacks as well as high temperature treated blacks, there is a marked development of the organized areas (Figure 24).

Table 9 Oxidation conditions

Experimental condition	α 10^{-3} h^{-1}	β 10^{-3} h^{-1}	$\frac{\alpha}{\beta}$ %
$T = 20^\circ\text{C}$, $C = 13 \text{ mg O}_3/1$	1.93	3.4	36.2
$T = 20^\circ\text{C}$, $C = 30,6 \text{ mg O}_3/1$	3.82	6.9	35.6
$T = 50^\circ\text{C}$, $C = 13 \text{ mg O}_3/1$	4.04	8.2	33.0

Table 10 Degradation products properties

Origin	Elemental composition			Average mol. weight	COOH meg/g	OH meg/g
	% C	% O	% H			
Sterling FT	49.12	45.08	2.15	380	50	18.6
Vulcan 6	51.79	44.13	3.45	420	50	17.6
Spheron 6	50.02	46.13	3.25	435	51	18.7

Marsh, Voet et al. (56) measured the interplanar distances by high resolution electron microscopy and noted that the interplanar distances were distributed logarithmically for all blacks, with the exception of thermal blacks. The results obtained by microscopy are far superior to those by X-ray diffraction which only accounts for the most organized crystallites (that is, those which have the smallest $c/2$), whereas visualization of the carbon layers, to a larger extent, accounts for the whole of the graphite layers.

By plotting the amount of carbon oxidized, by ozone, to degradation products, as a function of $c/2$, determined by electron microscopy, we obtain a linear relationship permitting the classification of carbon

Fig. 20 Infra-red spectrum of degradation product.

Fig. 21 Degradation product formation versus $c/2$ measured by X-ray diffraction.

Fig. 22 Phase contrast micrograph of a furnace black.

Fig. 23 Phase contrast micrograph of a thermal black.

Fig. 24 Phase contrast micrograph of graphitized channel black (Graphon).

blacks with regard to their degree of crystalline organization as well as their reactivity (Figure 25).

We think now that the disorganization of the graphite layers in the particles of channel and furnace blacks gives rise to the high degree of degradation products formed with these two types of black, during the oxidative attack.

Oxidizing agents such as nitric acid and ozone are more favourable for the study of the reactivity of the poorly organized carbon. This corresponds in fact to hardly developed graphite layers containing numerous

defects (distortions, interstitial atoms, etc. . .).

Let us now examine the behaviour of carbons submitted to oxidizing agents which may intercalate between the graphitic layers, and at first the reactivity of blacks with Simon's reagent.

Oxidation with Simon's reagent

Silver dichromate in concentrated sulphuric acid solution is a distinctly different oxidizing agent. Simon (57) and then Blayden and Riley (58) and Platzter (59) showed that the rate of carbon oxidation increases when the percentage of graphitisation, that is, the crystallinity of the carbon, is greater. Oberlin and Mering (60), continuing this study, found the kinetic conditions, allowing a true structural analysis of the carbon. Schultz (61) showed that the oxidation reaction of carbon blacks was governed by a law of the type $A_t = e^{-kt}$ where A_t is the fraction of nonoxidized carbon at time t , and k a rate constant (Figure 26). It was established that carbon black acts as a homogeneous carbon with regard to Simon's reagent, in contrast to that observed with nitric acid, the oxidation being characterised by a single rate constant.

One knows, now, that for a reagent which proceeds by intercalation, as in this case, the rate of oxidation depends on the structure as well as on the texture. For carbons with high degree of crystallinity, mostly the

Fig. 25 Degradation product formation versus $c/2$ measured by electron microscopy.

Fig. 26 Oxidation kinetics of carbon blacks with Simon's reagent.

structure conditions the rate of reaction, whereas in the case of weakly organized carbons, such as carbon black, the surface area seems to be the determining factor. In fact, as indicated on Table 11, it appears that there is a good correlation between the rate constant k and the initial surface area of the black.

Intercalation reactions may also provide information on the reactivity of the well organized graphitic layers and we therefore also studied the formation of graphitic oxide.

It is well known that the conversion of graphite to graphitic oxide is accompanied by an oxidation to CO_2 and soluble acids of the peripheral carbon atoms. Furthermore there are important differences in the reactivity, with regard to intercalation, for different types of carbon, and the degree of structural organization is the determining factor in the formation of laminar composites.

Maire (62) showed that graphitizable carbons always gave graphitic oxides but non-graphitizable carbons are oxidized without formation of laminar compounds. On the other hand, the yield of graphitic oxide from carbon conversion is greater the more the structure approaches that of graphite.

Table 11 Values of the rate constant for some carbon blacks

Blacks	$k \cdot 10^2 \text{ mn}^{-1}$	$S \text{ m}^2/\text{g}$
Spheron 6	8.9	110
Regal R	2.29	43
Sterling FT	1.60	15.5
P 33	1.09	14
Sterling MT	0.96	6
Thermax	0.72	5.5

Hummer's reagent

Ehrburger (63) studied the kinetics of conversion of carbon into graphitic oxide by treating carbons with permanganate potassium in concentrated sulphuric acid (Hummer's reagent). The aim of this study was to specify the reactivity of graphite layers using the kinetics of the oxidation reaction.

Let us take a_t at time t as the initial mass fraction of carbon not oxidized to CO_2 , then a_t represents the amount of carbon remaining in the reaction medium either as carbon or as graphitic oxide.

The curves obtained for $\log a_t$ as a function of the oxidation time of a pitch coke treated at 3000°C have been determined (Figure 27): after a rapid fall in a_t at the beginning, we can see that the decrease becomes linear.

X-ray spectroscopy shows that the carbon is converted to graphitic oxide during the rapid fall in a_t . At the same time, the badly organized carbon, which does not give rise to a laminar oxide, is converted to CO_2 . The linear part of the curve corresponds to the production of CO_2 from the laminar oxides. Extrapolation of this part of the curve gives the same intercept 'A' for different temperatures. The value of A is a characteristic of each type of carbon and represents the amount of carbon convertible to graphitic oxide.

Table 12 gives the values of A for several carbons. Note that in the case of highly oriented pyrographite, the amount of carbon convertible to graphite oxide is

Fig. 27 Oxidation kinetics of pitch coke with Hummer's reagent.

Table 12 Amount of carbon convertible to graphitic oxide

CARBON	A (%)
Pyrographite	99.8
Natural graphite (Madagascar)	95.9
Coke G.F.E.C. n° 3	95.3
Sterling FT 3000 °C	90.6
Graphon	70.8

Fig. 28 Oxidation kinetics of heat treated anthracene coke with Hummer's reagent.

as expected nearly equal to 1.

The influence of the degree of graphitization on the formation of laminar oxides was studied using G.F.E.C. anthracene coke treated from 1300°C to 2600°C.

It can be seen on Figure 28 that the rate curves for the graphitized samples show the two steps described previously. A detailed examination of the kinetics shows that a_t is given by the following equation:

$$a_t = A e^{-k't} + (1-A) e^{-k''t}$$

where A is the amount of carbon converted to graphitic oxide,

$(1-A)$ is the amount of badly organized carbon,
 k is the rate constante for the oxidation of graphitic oxide to CO_2 ,

k' is the rate constant for the oxidation of badly organized carbon.

This relation is analogous to that for oxidation with Simon's reagent. However, one must note (Table 13)

Table 13 Anthracene coke

HTT °C	d_{002} Å	g	A %	k 10^2 h^{-1}	k' 10^2 h^{-1}
1300	3,44	0	24	13	78
1600	3,435	0,06	27	7,0	81
1800	3,428	0,14	36	5,6	76
2200	3,409	0,36	56	4,5	76
2350	3,383	0,67	79,3	2,5	80
2400	3,373	0,78	83,2	2,3	78
2600	3,362	0,90	95,5	1,3	69

that the rate constant k' for badly organized carbon is far superior to that for the conversion of well organized layers to graphitic oxide. Sample 1300, with no graphitization, is characterized by an amount of carbon transformable to graphitic oxide of about 20%. Hence, we have a known property of graphitizable carbons which give graphitic oxides whatever the degree of graphitization.

"A" tends towards 1 for increasing amounts of graphitization. " k " diminishes uniformly during graphitization and values obtained for well graphitized carbons are of the same order. This decrease in " k " shows the increasing resistance of the laminar oxides to oxidation and is connected to a rearrangement of the graphitic layers. In studying the reactivity of the carbon layers, we rediscover aspects of graphitization; an increase in the organized carbon, and rearrangement of the layers.

Contrarily, k' is independent of the amount of graphitization. It is probable that this structural form does not undergo any modification and that thermal treatment simply eliminate it progressively on the basis of all or nothing.

This "scavenging" of the layers, seen by Oberlin and Mering (64) agrees with our knowledge of structural defects eliminated during graphitization.

Finally, let us say in this case, that we can follow the reactivity of the graphite layers during graphitization from a knowledge of the kinetics and mechanisms of oxidation.

We have also examined the influence of structural defects on the formation of graphitic oxide. Samples of high purity artificial graphite were powdered under argon (Table 14). For all these samples the degree of graphitization was greater than 0.95. This powdering results in a diminution of A , either by increasing the number of edge atoms, or by the introduction of structural defects. Hence, the formation of graphitic oxide is very sensitive to the degree of perfection of the graphite layers.

Another important parameter in the oxidation mechanism is the mutual orientation of the graphite planes.

Table 14 Influence of grinding

Graphite	Specific area m ² /g	A %
Initial	< 1	93.3
Ground A	10	92.6
Ground B	60	89.6

Table 15 Graphitic oxide formation

Carbon	L_c nm	L_a nm	Observation
Fibre ex-PAN HTT 2500°C	7.5	7.0	Graphitic oxide
Glassy carbon HTT 2500°C	2.5	7.0	No graphitic oxide

This was shown using Hummer's reagent on two carbons having similar crystalline characteristics as measured by X-Rays diffraction (Table 15). Graphitized fibres rapidly give graphitic oxides whereas vitreous carbons, also treated at 2500 C, slowly oxidize to CO₂. This leads to the following explanation; the microstructure of graphitized fibres is characterized by extended layers more or less parallel to the fibre axis. One conceives, in this case, the easy penetration of the reagent. However the entanglement of the graphite layers in vitreous carbons is such that penetration is difficult if not impossible.

These few examples emphasize the complexity of the kinetics of oxidation which depend primarily on the oxidation mechanisms that is, the oxidizing agent as well as the carbon sample.

When the reaction mechanism proceeds by intercalation such as for Simon's and Hummer's reagent the phenomenon can be very complex. In effect, the whole oxidation mechanism can be altered by changing the oxidizing system.

If the formation of unstable intercalation compounds facilitates access of the reagent to the whole layer surface, the rate of attack is governed by the state of the structure *the better organized layers being the most oxidized*. However, when the intercalation compound is stable, for example graphitic oxide, there is competition between the oxidation rate of the laminar oxide layers and the badly organized carbon, both reactions proceeding by an attack on the border atoms. Finally, when the structure and orientation of the graphite layers are not too disorganized, oxidation of the peripheral atoms also takes place, and the texture becomes the predominant phenomenon such as shown by Simon's reagent on carbon black. Similarly, when oxidation proceeds without the formation of intermediary intercalation compounds, the kinetics are essentially a function of the effective surface accessible to the reagents,

and the structure of the superficial layers (that is the diameter of the surface graphite layers, and the number of border atoms).

I will conclude by saying that the study of carbon reactivity covers complex phenomena and it is not surprising that results obtained by different authors were sometimes (not to say often) divergent if not contradictory. The use of several techniques however, such as chemical reaction and electron microscopy has helped us to resolve some of these problems. Also, the study of different crystalline texture (glassy carbons blacks, fibers and pyrographite) has allowed us to better understand the close relationships between the reactivity and the structure of carbon, and there is very little doubt that the chemical study of the solid carbon has a future.

Acknowledgement – The author is very much indebted to Drs. P. Ehrburger, A. Vidal and E. Papirer for their great help in the manuscript preparation.

REFERENCES

- VILLARS D. S., J. Amer. Chem. Soc. 70, 3655 (1948)
- STUDEBAKER M. L., Rubber Age 77, 69 (1955)
- STUDEBAKER M. L., HUFFMANN E. W. D., WOLFE A. C. and NABORS L. G., Ind. Eng. Chem. 48, 162 (1956)
- DONNET J. B. and MARGUIER P., C. R. Acad. Sci. Paris 239, 1038 (1954); 242, 771 (1956)
- HUEBER F., étude physico-chimique de l'influence de l'oxydation sur la structure des noirs de carbone, Thesis, Strasbourg (France) (1961)
- RIVIN D., Rubber Chem. Technol. 36, 729 (1963)
- TEST R. E. and HANSEN R. S., M.S. Thesis, Iowa State University, Ames, Iowa, 56 pp. (I.S. 341 Report) (1961)
- BRUIN W. J. De and VAN DER PLAS TH., Rev. Gén. Caout. 41, 453 (1964)
- PURI B. R. and BANSAL R. C., Rev. Gén. Caout. 41, 444 (1964)
- BOEHM H. P., DIEHL E., HECK W. and SAPPOK R., Angew. Chem. 76, 742 (1964)
- BOEHM H. P., DIEHL E. and HECK W., Symp. Carbon, Tokyo, Preprints, VIII, 10 (1964)
- DONNET J. B., French Pat., No 1 164 786 (1. 7. 1958)
- BOEHM H. P., Advances in Catalysis 16, 198 (1966)
- DONNET J. B. and PAPIRER E., Rev. Gén. Caout. 42, 389 (1965)
- DONNET J. B., HUEBER F., REITZER C., ODDOUX J. and RIESS G., Bull. Soc. Chim. France 8-9, 1727 (1962)
- DONNET J. B., LAHAYE J. and SCHULTZ J., Bull. Soc. Chim. France 5, 1769 (1966)
- HALLUM J. V. and DRUSHEL H. V., J. Phys.

- Chem. 62, 110 (1958)
- 18) DONNET J. B. and HENRICH G., Bull. Soc. Chim. France 1609 (1960)
- 19) VOET A. and TETER A. C., Amer. Ink Maker 38, 44 (1960)
- 20) EHRBURGER P., DAUKSCH H., ESCARD J. and DONNET J. B., Silicates Industriels, 2, 55-59 (1975)
- 21) BRAENDLE H. A., Rubber Age Lond. 72, 205 (1952); WATSON W. F., Proc. 3rd Rubber Technol. Conf., 553 (1954)
- 22) MEDALIA A. I., J. Colloid Interface Sci. 32, 115 (1970)
- 23) SIRCAR A. K., VOET A., Rubber Chem. Tech. 43, 973 (1970)
- 24) VOET A., PAPIRER E., ABOYTES P., Paper presented before Div. Rubber Chem. Soc. Washington D.C., May 1970
- 25) PAPIRER E., DONNET J. B., HEINKELE J., J. Chim. Phys. 68, 581 (1961)
- 26) DONNET J. B., PAPIRER E., International Rubber Conf. Brighton 4, 18, 1972
- 27) SZWARC M., J. Polymer Sci. 19, 589 (1956)
- 28) DONNET J. B., HENRICH G., RIESS G., Rev. Gen. Caoutch. 38, 1803 (1961)
- 29) STUDEBAKER M. L., Rubber Chem. Tech., 30, 1400 (1957)
- 30) OHKITA K., KITAHARA N., YAMAZAKI H., J. Soc. Rubber Ind. 38, 13 (1965)
- 31) KRAUS G., GRUVES J. T., ROLLMANN K. W., J. Polymer Sci. 36, 564 (1959)
- 32) DONNET J. B., PETER G., RIESS G., J. Polymer Sci. 22, 645 (1969)
- 33) SUZUKI S., TAKAKUWA R., NIPPON KAGAKU ZASSHI 88, 1271 (1967)
- 34) VIDAL A., RIESS G., DONNET J. B., German Pat. 2130617, 12. 30. 1971; French Pat. 2094954, 01. 10. 1972; English Pat. 2130617, 12. 30. 1971
- 35) DONNET J. B., VIDAL A., RIESS G., J. Chim. Phys. 68, 1642 (1971)
- 36) DEVINEY M. L., WHITTINGTON L. E., Rubber Chem. Tech. 41, 382 (1968)
- 37) BREITENBACH J. W., PREUSSLER H., J. Polym. Sci. 4, 751 (1949)
- 38) DONNET J. B., HENRICH G., Bull. Soc. Chim. Fr., 1609 (1960)
- 39) DONNET J. B., L. GELDREICH, G. HENRICH, G. RIESS, Rev. Gén. Caout. 41, 519 (1964)
- 40) DONNET J. B., RIESS G., MAJOWSKI G., Eur. Polym. J. 7, 1065 (1971)
- 41) PAPIRER E., NGUYEN V. T., J. Polym. Sci. 10, 167 (1972)
- 42) PAPIRER E., MORAWSKI J. C., VIDAL A., Ang. Makromol. Chem. 42, 91 (1975)
- 43) PAPIRER E., DONNET J. B., NGUYEN V. T., RIESS G., J. Polym. Sci. 9, 195 (1971)
- 44) DONNET J. B., VIDAL A., RIESS G., GELDREICH L., Rev. Gén. Caout. Plast. 47, 1289 (1970)
- 45) PARROD J., BEINERT G., J. Polym. Sci. 53, 99 (1961)
- 46) MINOURA Y., KATANO M., J. Appl. Polym. Sci. 13, 2057 (1969)
- 47) RIVIN D., US Pat. 3472929, 11, 18, 1969
- 48) OHKITA K., FUKUSHIMA K., Jap. Plastics, p. 6 July 1969
- 49) DONNET J. B., BOULAND J. P., Rev. Gen. Caout. 41, 407 (1964)
- 50) DONNET J. B., LAHAYE J., Bull. Soc. Chim. Fr. 4, 1282 (1966)
- 51) DONNET J. B., LAHAYE J., SCHULTZ J., Bull. Soc. Chim. Fr. 5, 1769 (1966)
- 52) DONNET J. B., SCHULTZ J., J. Chim. Phys. 67, (6), 1070 (1970)
- 53) DONNET J. B., EHRBURGER P., Carbon 8, 697 (1970)
- 54) DONNET J. B., EHRBURGER P., VOET A., Carbon 10, 737 (1972)
- 55) DONNET J. B., EHRBURGER P., ILVOAS A. M., Bull. Soc. Chim. Fr. 6, 2239 (1972)
- 56) MARSH P. A., VOET A., MULLENS T. J., PRICE L. D., Carbon 9, 797 (1971)
- 57) SIMON L. J., C.R. Acad. Sci. Paris 176, 1409 (1923); 177, 122 (1923)
- 58) BLAYDEN H. E., RILEY H. L., J. Chim. Soc. Ind. 54, 159 (1935)
- 59) PLATZER N., Bull. Soc. Chim. Fr. 177, (1961)
- 60) OBERLIN M., MERING J., Carbon 4, 471 (1964)
- 61) DONNET J. B., SCHULTZ J., J. Chim. Phys. 63, 1139 (1966)
- 62) MAIRE J., C.R. Acad. Sci. Paris, 232, 151 (1951)
- 63) EHRBURGER P., DONNET J. B., Carbon 11, 309 (1973)
- 64) OBERLIN M., MERING J., Carbon 1, 471 (1964)
- 65) DONNET J. B., Carbon 6, 161-167 (1968)
DONNET J. B., Bull. Soc. Chim., No Spécial 3353-3366 (1970)
- 66) KRAUS G., Reinforcement of Elastomers. Interscience New York, 69, (1965)
DONNET J. B., VOET A., "Carbon Black", M. Dekker (1976)
- 67) DONNET J. B., PAPIRER E., Chimie Actualités, 44-45 (1973)
- 68) HECKMAN F. A., HARLING D. E., Rubber Chem. Technology, 39-1 (1966)

概 要

炭 素 の 構 造 と 反 応 性

炭素の化学と化学的性質は充分に明らかにされていない。それは炭素の界面化学の難しさ、すなわち不均質性と再現性の欠除、に原因している。我々は1953年以来、炭素の物理化学的性質の研究を続けてきた。ここでは、まず、カーボンの表面官能基とカーボン表面へのポリマーのグラフト反応について考察し、続いて、炭素の反応性と微細構造との関係を酸化反応について示す。

I. 表面官能基とグラフト反応の研究

カーボンブラック表面の官能基の性質が多くの人々によって研究されており、それらをTable 1~4にまとめて示した。これらの結果はカーボンブラックが遊離基のアクセプターであることを示しており、これらの化学的研究の結果がいずれも物理的手段、特に吸着熱および赤外吸収スペクトルの測定によって確かめられていることも記しておかなければならない。最近、我々はESCA法によって炭素繊維の表面官能基を確認しえた(Fig. 1)。

カーボンブラックの最も重要な応用の一つはゴムの機械的性質の改良(reinforcement)である。カーボンブラックとエラストマーの間の相互作用は、第1にカーボンブラック集合体の中にエラストマーが吸蔵されることで、それはカーボンブラックの“ストラクチャー”に由来するものである。第2はカーボンブラックによるエラストマーの吸着である。Fig. 2はカーボンブラックとエラストマーの間の結合を断ち切るには温度が必要であることを示しており、ブラックによるエラストマーの化学吸着を示唆している。また、改良能(reinforcement potential)と表面の水素とは密接な関係があり、このことがSBR-ポリブタジエンゴム中のカーボンブラックの水素量(言い換えれば加熱処理温度)とゴムの歪エネルギーの関係として示された(Fig. 3)。そして、この表面の水素は四つのタイプに分けられることが、トリチウムトレーサーを使った交換反応などから明らかとなった(Table 5~7, Fig. 4)。

これらのカーボンブラックの化学は、フィラーとポリマーの相互作用の大きな領域を解明し、それが固体表面へのポリマーのグラフティングへと発展した。我々はグラフティングを二つに分類する。すなわち、ポリマーの成長が固体表面で終結してグラフトされる場合と、固体表面がポリマー鎖の成長の発端となってグラフトされる場合であり、いずれの場合もラジカルプロセスとイオンックプロセスとを考える。まず、固体表面がポリマーの終結点となる場合について、ラジカルプロセスによ

ってカーボンブラック表面に多くのポリマーがグラフトされることが多くの研究によって示されている(Fig. 5~9)。また、イオンサイト(アニオンのおよびカチオンの)を持つポリマーのグラフティングの例がFig. 10~12に示されている。グラフティングの効率をTable 8に示した。固体表面からグラフティングの進む場合もラジカルとイオンックプロセスを区別しうが、その例をFig. 13と14に示した。

最後に、グラフティングによる固体表面の性質の改良の直接的結果として、新しい応用が開けていることを指摘しなければならない。ことえ、ポリマーで改良された顔料は疎水性となり高分子溶剤中への分散が良好となる、またカーボンブラックの電気的性質が電子工学での新しい応用を生んでいる。さらに、グラフトされた物質の吸着性能が公害防止の分野で新しい興味ある利用法を生んでいる。

II. カーボンの微細構造と化学反応性との関係

1964年にサーマルブラックの酸化が構造の乱れた部分から起こることを見出して(Fig. 15)以来、カーボンの酸化の機構に関する我々の系統的な研究がはじまった。酸化剤としては、黒鉛層間に挿入されることのない希硝酸とオゾン水溶液のみでなく、結晶性の良い部分には挿入されうるイオン種を含んでいるシモンおよびヒューマー試薬が用いられた。

硝酸による酸化 硝酸による酸化はより結晶性の悪い領域で選択的に起こり、酸化速度は酸化の進行(残留炭素量の減少)とともに直線的に減少し、20~25%の炭素が失われてほぼ零となる(Fig. 16)。これらの結果から硝酸酸化は粒子中の最も結晶性の悪い部分、無定形炭素と結晶性配列に組み入れられていない網平面、から起こると結論された。サーマルブラックからは酸化によって中空の殻が生成することが知られ(Fig. 17)、ブラック粒子の中心がより結晶性の悪いことが示された。また、黒鉛化が粒子の周辺で起こることが示され(Fig. 18)、カーボンブラックの微細構造のモデルが組み立てられた(Fig. 19)。

オゾンによる酸化 オゾンによる酸化は二つの同時反応によって進む。すなわち、粒子が酸化によって崩壊する反応(部分的にはCO₂まで酸化される)と、直接CO₂への反応である。崩壊生成物の量はカーボンブラックによって異なる(Table 9)が、その化学成分はほぼ同じである(Table 10, Fig. 20)。崩壊生成物が粒子

中の結晶性の悪い部分 (disorganized areas) の酸化によって生成するとすれば、粒子の結晶性の度合と関連づけられるはずであり、Fig. 21 に層間隔 $c/2$ の関数として示した。この考えはまた、高分解能電子顕微鏡観察によっても確かめられた (Fig. 22~24)。そして、高分解能電子顕微鏡下で決められた層間隔とオゾン酸化が密接な関係にあることがわかった (Fig. 25)。我々はチャネルおよびファーネスブラック粒子の乱れた構造 (Fig. 22, 24) が崩壊生成物の多い原因と考えている。

シモン試薬による酸化 シモン試薬 (重クロム酸銀の濃硫酸溶液) によるカーボンブラックの酸化反応は $A_t = e^{-kt}$ として表わされ、一つの速度定数 k で特性づけられた (Fig. 26)。そして、この k はカーボンブラック試料の表面積と密接に関係している (Table 11)。

ヒューマー試薬による酸化 ヒューマー試薬 (過マンガン酸カリの硫酸溶液) による酸化は Fig. 27 にピッチコークスについて示したように、最初 a_t (未酸化の炭素量) の急激な減少を示した後、直線的に減少する。X線回折から、最初の急激な減少が、カーボンの黒鉛酸への変換に対応していることが知られ、黒鉛酸となり得ない結晶性の悪い部分が CO_2 となる。直線部分は黒鉛酸から

の CO_2 の生成に対応し、その外挿点 A は酸化温度によらず一定で、試料の特性値である (Table 12)。また、黒鉛酸生成に対する黒鉛化度の影響が調べられた (Fig. 28, Table 13)。 A は黒鉛化とともに 1 に近づき、 k は減少する。この k の減少は酸化によって生じた黒鉛酸の酸化に対する抵抗が増加していることを示している。これに対して、 k' はほぼ一定である。黒鉛酸生成に対する構造欠陥の効果が調べられ (Table 14)、さらに網平面の選択的配向もまた酸化に対して影響を持つ (Table 15)。

カーボンの反応性の研究は非常に複雑な現象をカバーしており、多くの人々によって得られた結果が必ずしもまとまっていないことは驚くにあたらない。しかし、いくつかの手段、たとえば化学反応性と電子顕微鏡技術、の併用が、いくつかの問題を解明するのに役立ってきた。また、種々の組織を持つ試料についての研究が、反応性と構造の密接な関係をよりよく理解することを可能にしてくれる。固体炭素の化学的研究が高い将来性を持つことは疑うまでもない。

(名大工 稲垣道夫)